

Designation: D 6817 - 04

# Standard Specification for Rigid Cellular Polystyrene Geofoam<sup>1</sup>

This standard is issued under the fixed designation D 6817; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon  $(\epsilon)$  indicates an editorial change since the last revision or reapproval.

### 1. Scope

- 1.1 This specification covers the types, physical properties and dimensions of rigid cellular polystyrene intended for use as geofoam.
- 1.2 This specification does not cover the layout, placement and workmanship for proper installation and performance of rigid cellular polystyrene geofoam.
- 1.3 Rigid cellular polystyrene geofoam covered by this specification may need protection from certain chemicals, environmental exposure, and concentrated loads. Additional design considerations may include thermal conductivity and buoyancy. Guidelines regarding these end use considerations are included in Appendix X1.
- 1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.

## 2. Referenced Documents

- 2.1 ASTM Standards: <sup>2</sup>
- C 165 Test Method for Measuring Compressive Properties of Thermal Insulation
- C 203 Test Methods for Breaking Load and Flexural Properties of Block Type Thermal Insulation
- C 303 Test Method for Density of Preformed Block-Type Thermal Insulation
- C 390 Criteria for Sampling and Acceptance of Preformed Thermal Insulation Lots
- C 578 Specification for Rigid Cellular Polystyrene Insulation
- <sup>1</sup> This specification is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.03 on Permeability and Filtration.
- Current edition approved Dec. 1, 2004. Published January 2005. Originally approved in 2002. Last previous edition approved in 2002 as D 6817–02.
- <sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D 1621 Test Method for Compressive Properties of Rigid Cellular Plastics
- D 1622 Test Method for Apparent Density of Rigid Cellular Plastics
- D 2863 Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-like Combustion of Plastics (Oxygen Index)

#### 3. Terminology

- 3.1 Definitions:
- 3.1.1 Terms used in this specification are defined in Terminology D 4439.
- 3.1.2 *geofoam*—block or planar rigid cellular foam polymeric material used in geotechnical engineering applications.
  - 3.2 Definitions of Terms Specific to This Standard:
- 3.2.1 *EPS, XX*—number designation for expanded polystyrene geofoam Type(s) having a minimum density of XX kg/m<sup>3</sup> (lb/ft<sup>3</sup>).
- 3.2.2 XPS, XX—number designation for extruded polystyrene geofoam Type(s) having a minimum density of XX kg/m<sup>3</sup> (lb/ft<sup>3</sup>).
- 3.2.3 *RCPS*—letter designation for EPS and XPS rigid cellular polystyrene covered by this specification.

#### 4. Ordering Information

- 4.1 Acquisition documents shall specify the following:
- 4.1.1 Title, number and year of this specification.
- 4.1.2 Type, as per Table 1, or minimum density required.
- 4.1.3 Total product volume required of each Type, or minimum density.

#### 5. Materials and Manufacture

- 5.1 RCPS geofoam shall be formed by the expansion of polystyrene resin beads or granules in a molding process (EPS) or by the expansion of polystyrene base resin in an extrusion process (XPS). RCPS geofoam may be manufactured with reprocessed polystyrene foam (regrind).
- 5.2 RCPS geofoam shall be of uniform density and have essentially closed cells. RCPS geofoam is an organic material and is considered combustible. It should not be exposed to flames or other ignition sources.