
Lasersko varjeni posebej prilagojeni spoji - Tehnični dobavni pogoji

Laser welded tailored blanks - Technical delivery conditions

Laserstrahlgeschweißte Tailored Blanks aus Stahlfeinblech - Technische Lieferbedingungen

Flans raboutés laser - Conditions techniques de livraison

ITeH STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: EN 10359:2015

<https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015>

ICS:

25.160.40	Varjeni spoji in vari	Welded joints
77.140.50	Ploščati jekleni izdelki in polizdelki	Flat steel products and semi-products

SIST EN 10359:2015**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10359:2015

<https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 10359

July 2015

ICS 77.140.50

English Version

Laser welded tailored blanks - Technical delivery conditions

Flans raboutés laser - Conditions techniques de livraison

Laserstrahlgeschweißte Tailored Blanks aus Stahlfeinblech
- Technische Lieferbedingungen

This European Standard was approved by CEN on 20 June 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

SIST EN 10359:2015

<https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Requirements	4
5 Tolerances on dimensions and shape	4
6 Destructive testing of weld joints	5
6.1 Cup test.....	5
6.2 Cross section	5
Bibliography	14

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 10359:2015](https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015)

<https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015>

European foreword

This document (EN 10359:2015) has been prepared by Technical Committee ECISS/TC 109 “Coated and uncoated flat products to be used for cold forming”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2016 and conflicting national standards shall be withdrawn at the latest by January 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 10359:2015](https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015)

<https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015>

EN 10359:2015 (E)

1 Scope

This European Standard describes the requirements for laser welded tailored blanks made of alloyed and unalloyed steels, of uniform or different steel grades and with or without metallic and/or organic coatings, having uniform or different sheet thickness. It applies only to the (Tailored Blanks) as-supplied condition of tailored blanks.

After the welding process, tailored blanks are further processed to pressed parts by forming operations under the responsibility of the processor. In the design of the component due consideration should be given to the fact that the weld seam is less formable in comparison to the base material.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10131, *Cold rolled uncoated and zinc or zinc-nickel electrolytically coated low carbon and high yield strength steel flat products for cold forming — Tolerances on dimensions and shape*

EN 10143, *Continuously hot-dip coated steel sheet and strip — Tolerances on dimensions and shape*

ISO 2768-1, *General tolerances — Part 1: Tolerances for linear and angular dimensions without individual tolerance indications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3 Terms and definitions

For the purposes of this document, the following term and definition applies.

[SIST EN 10359:2015](https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015)

3.1

tailored blanks

laser welded metal sheets of uniform and/or different thickness and/or uniform or different steel grades, both with and without surface coating

<https://standards.iteh.ai/catalog/standards/sist/807f4f84-c11c-4413-967d-aad68c76c488/sist-en-10359-2015>

4 Requirements

As far as the properties of the components are concerned, the general rules of engineering apply. The suitability of tailored blanks for the processes of the customer is guaranteed in case of appropriate execution of the welding seam, suitable positioning of weld seam in the part to be formed and appropriate lay out of sheet thicknesses and steel grades under taking into consideration the requirements of known further processing steps. The criteria laid down in Table 1 have proved to be a practical basis for ordering. Additional specific deviations are admissible and have to be agreed upon at the time of ordering.

5 Tolerances on dimensions and shape

Regarding tolerances on dimensions and shape the agreements of EN 10131 and EN 10143 shall apply for cold rolled and surface coated wide coils, cut to length sheets and slit coils, which are used for the manufacturing tailored blanks.

The relevant tolerance classes for width, flatness and thickness have to be agreed upon between producer of tailored blank and steel producer.

For the general tolerances regarding lengths, angles, coaxiality and symmetry, the precision class c according to ISO 2768-1 shall apply.

If not all edges of the blank were cut, the definition of the dimension has to be according to EN 10143 and EN 10131 also.

Specific requirement and other beyond that valid special customer agreement have to be agreed upon between producer of tailored blank / steel producer and customer.

6 Destructive testing of weld joints

6.1 Cup test

Destructive testing of weld joints with cup test is considered as best practice procedure.

The evaluation of weld quality is done according to the pictures in Table 2.

Frequency of the cup test is minimum once a run.

6.2 Cross section

Samples shall be taken minimum 5 mm from both ends of welds. For measurements, Table 3 applies.

Table 1 — Requirements

Dimensions, surface			
Criterion	Figures	Assessment	Frequency
Shape inspection (Tolerance)	—	Tolerances for linear and angular dimensions without individual tolerance indications according ISO 2768-1, class c, EN 10143, EN 10131 or customer specification	
Shape inspection (Method of measurement)	—	Master sample (Initial sample): Reference points have to be agreed with the customer. Production: measuring of the influential dimensions.	Initial parts or master sample for PSW ^a Production sample each run
Flatness of the entire blank	Figure 1	Deviation h guaranteed acc. to EN 10131 and EN 10143. Furthermore, the “process ability” criterion shall apply. Tighter specification should be agreed between customer and supplier.	Initial parts or master sample for PSW ^a . Production samples each run. Visual.
Burr of the entire laser welded blank	—	Customer specification.	Production samples each run. Visual.
Surface quality of laser welded blanks	—	According to relevant technical delivery conditions for flat products.	Production samples each run. Visual.
Oiling of tailored blanks	—	The entire blank shall be free from corrosion products. Oil type and amount of oil at time of steel strip production acc. to customer specification. More than 1,5 g/m ² is not state of the art due to process ability	Initial parts or master sample for PSW ^a . Visual each run.

EN 10359:2015 (E)

Offset of sheets	Figure 13	maximal Offset $\pm 1,5$ mm	Initial parts or master sample for PSW ^a . Production sample one each run.
Requirements on weld seam			
Criterion	Figures	Assessment	Frequency
Cracks / Pores / Inclusions / Craters / Lack of fusion	–	Pores, Inclusions: Maximum size of imperfection $\leq 0,3 \times t_2$ Pore nests: $f \leq 0,7$ %. No cracks, craters or lack of fusion are allowed. f = surface of pores measured over a length of 100 mm along the weld (parallel cross section)	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Hardness in the area of the weld and HAZ	–	Hardness depends on the defined steel grades.	Initial parts or master sample for PSW (If required).
Spatter	–	Scale and smoke residues as well as welding spatter shall not negatively affect the processability nor the downstream processes	Initial parts or master sample for PSW. Production samples each run.
Burning of zinc coating (total)		The maximum width of the entire zinc-free zone is 3 mm for $t_1 \leq 2$ mm, and $1 + t_1$ for $t_1 > 2$ mm	Customer specification
Undercut (Definition: un-fused edge that reduces the carrying cross section)	Figure 2	$t_2 \leq 1$ mm: $h \leq 0,1$ mm; $t_2 > 1$ mm: $h \leq 0,1 \times t_2$	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Excess weld metal	Figure 3	$t_2 \leq 1$ mm: $h \leq 0,1$ mm; $t_2 > 1$ mm: $h \leq 0,1 \times t_2$	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Excessive root penetration	Figure 4	$t_2 \leq 1$ mm: $h \leq 0,1$ mm, $t_2 > 1$ mm: $h \leq 0,1 \times t_2$	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Upper weld concavity	Figure 5	$t_2 \leq 1$ mm: $h \leq 0,1$ mm, $t_2 > 1$ mm: $h \leq 0,1 \times t_2$	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Root concavity	Figure 6	$t_2 \leq 1$ mm: $h \leq 0,1$ mm, $t_2 > 1$ mm: $h \leq 0,1 \times t_2$	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Weld sagging	Figure 7	$t_2 \leq 1$ mm: $h \leq 0,1$ mm, $t_2 > 1$ mm: $h \leq 0,1 \times t_2$	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.

Mismatch	Figure 8 and 9	negative mismatch: $t_2 \leq 1 \text{ mm}: h \leq 0,1 \text{ mm}$, $t_2 > 1 \text{ mm}: h \leq 0,1 \times t_2$ positive mismatch: $t_2 \leq 1 \text{ mm}: h \leq 0,2 \text{ mm}$, $t_2 > 1 \text{ mm}: h \leq 0,2 \times t_2$ Furthermore, the processability criterion shall apply.	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Weld cross section	Figure 10	The remaining cross section due to weld defects (Undercut, Root concavity, Upper weld concavity, negative mismatch) should not be smaller than: $t_2 \leq 1 \text{ mm}: g \geq 0,80 \times t_2$ $t_2 > 1 \text{ mm}: g \geq 0,80 \times t_2$	
Beginning/end of weld	Figure 12	At the beginning and end of the weld areas with a max. length of 2 mm each may occur where the laser beam is without effect. Furthermore the "processability" criterion shall apply.	Production sample each run. Visual
Lack of penetration	Figure 11	Lack of penetration is not allowed	Checked by online-systems. Additional minimum one destructive test (cross section) once a year.
Testing			
Criterion	Figures	Assessment	Frequency
Testing of weld seam (non- destructive)	Figure 12	Each tailored blank is tested with appropriate and ensured test procedures (online). Additional visual inspection is possible. Up to max. 5 mm at the beginning and end of the weld cannot be monitored by state-of-the-art online test procedures.	100 % by online- system
Weld seam testing (mechanical and technological) for the series delivery	Table 2	Using ensured test procedures with appropriate testing frequency (offline), e.g. the cup test according to EN ISO 20482 or other appropriate standards	Once per run
Process assurance by traceability		Traceability from stack label back to the batch number of steel sheet or coil.	
Packaging			
Criterion	Figures	Assessment	Frequency
Packaging		As specified by the customer and complying with "stacking deviation" and "stacking height deflection" as defined below.	Each stack Visual
Stack deviation	Figure 14	$h \leq 5,0 \text{ mm}$ provided that the palette has been designed adequately	Each stack