



Designation: F180 – 94 (Reapproved 2005)

Standard Test Method for Density of Fine Wire and Ribbon Wire for Electronic Devices¹

This standard is issued under the fixed designation F180; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of, to an accuracy of 1.0 %, the density of fine wires ranging from 0.25 to 0.02 mm (0.010 to 0.001 in.) in diameter, or ribbons of similar thicknesses, for electronic devices.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Section 4.

2. Terminology

2.1 Definition:

2.1.1 *density*—the weight per unit volume, expressed in grams per cubic centimetre, in accordance with the following equation:

$$\Delta = W/V$$

where:

Δ = density of the specimen

W = weight of the specimen, g, and

V = volume of the specimen, cm^3 .

3. Apparatus

3.1 *Balance*—A suitable chemical balance capable of being read to 0.1 mg.

3.2 *Micrometer*, capable of being read to 0.002 mm (0.0001 in.)

3.3 *Standard Volume Cylinder*—A cylinder of standard volume made from corrosion-resistant material such as nickel, cylindrical in shape to within 0.0025 mm (0.0001 in.) and of uniform diameter and length. The length of the cylinder shall be approximately the same as the diameter and about 12.7 to 25.4 mm ($\frac{1}{2}$ to 1 in.). The surface of the cylinder shall be smooth and free from defects, pits, or cracks. The corners of the cylinder shall not be rounded.

3.4 *Thermometer*, capable of being read to 0.2°C within the range from 10 to 35°C.

3.5 *Vacuum Pump and Desiccator*—A vacuum pump capable of producing a vacuum of 0.1 mm Hg and a vacuum desiccator.

3.6 *Hook* suspended by a fine wire about 0.08 mm (0.003 in.) in diameter, both made of corrosion-resistant material, for supporting the test specimen while weighing it in the liquid.

3.7 *Cradle* suspended by a fine wire about 0.08 mm (0.003 in.) in diameter, both made of corrosion-resistant material, for supporting the standard volume cylinder while weighing it in the test liquid.

4. Test Liquid

4.1 The test liquid in which the test specimen and standard volume cylinder are to be immersed while being weighed shall be pure, stable, and shall have a low viscosity, low surface tension, low vapor pressure and a density of not less than 2 g/cm^3 . Tetrabromoethane and tribromomethane have been found satisfactory for this purpose.

4.2 **Precaution**²—These liquids are moderately toxic and should only be used by those familiar with the hazards involved.

4.2.1 Tests should be carried out under a fume hood. The fluids used should be considered potentially dangerous.

4.2.2 *Hazard*—When treated, highly toxic fumes are given off. Prolonged inhalation can cause unconsciousness.

4.2.3 *Treatment*—Fresh air; artificial respiration if unconscious; oxygen if required.

¹ This test method is under the jurisdiction of ASTM Committee F01 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials.

Current edition approved Jan. 1, 2005. Published January 2005. Originally approved in 1943 as B180–43 T. Last previous edition approved in 1999 as F180–94 (1999). DOI: 10.1520/F0180-94R05.

² See Sax, N. I., *Handbook of Dangerous Materials*, 1951.