

SLOVENSKI STANDARD SIST-TS CEN/TS 15963:2014

01-julij-2014

Nadomešča: SIST-TS CEN/TS 15963:2010

Bitumen in bitumenska veziva - Določanje temperature lomne žilavosti s tritočkovnim upogibnim preskusom na zarezanem vzorcu

Bitumen and bituminous binders - Determination of the fracture toughness temperature by a three point bending test on a notched specimen

Bitumen und bitumenhaltige Bindemittel Bestimmung der Bruchwiderstandstemperatur mittels eines Drei-Punkt-Biegeversuches an einem gekerbten Probekörper

Bitumes et liants bitumineux - Détermination de la température de résistance à la fissuration par un essai de flexion 3 points sur dun barreau entaillé 5-85de-983e020e6cfl/sist-ts-cen-ts-15963-2014

Ta slovenski standard je istoveten z: CEN/TS 15963:2014

ICS:

75.140	Voski, bitumni in drugi naftni proizvodi	Waxes, bituminous materials and other petroleum products
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

SIST-TS CEN/TS 15963:2014 en,fr,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TS CEN/TS 15963:2014 https://standards.iteh.ai/catalog/standards/sist/0329d150-75d7-4da5-85de-983e020e6cf1/sist-ts-cen-ts-15963-2014

SIST-TS CEN/TS 15963:2014

TECHNICAL SPECIFICATION SPÉCIFICATION TECHNIQUE TECHNISCHE SPEZIFIKATION

CEN/TS 15963

April 2014

ICS 91.100.50

Supersedes CEN/TS 15963:2010

English Version

Bitumen and bituminous binders - Determination of the fracture toughness temperature by a three point bending test on a notched specimen

Bitumes et liants bitumineux - Détermination de la température de résistance à la fissuration par un essai de flexion 3 points sur un barreau entaillé Bitumen und bitumenhaltige Bindemittel - Bestimmung der Bruchwiderstandstemperatur mittels eines Drei-Punkt-Biegeversuches an einem gekerbten Probekörper

This Technical Specification (CEN/TS) was approved by CEN on 16 December 2013 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form./It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

https://standards.iteh.ai/catalog/standards/sist/0329d150-75d7-4da5-85de-983e020e6cf1/sist-ts-cen-ts-15963-2014



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Ref. No. CEN/TS 15963:2014 E

SIST-TS CEN/TS 15963:2014

CEN/TS 15963:2014 (E)

Contents

Foreword					
1	Scope	.4			
2	Normative references	.4			
3	Terms and definitions	.4			
4	Principle	.6			
5 5.1 5.2	Apparatus Testing apparatus Test specimen	.6 .6 .8			
6 6.1 6.2 6.3	Preparation of test samples Preparation of test samples Preparation of moulds Preparation of test specimen	.9 .9 .9 11			
7 7.1 7.2 7.3 7.4 7.5	Procedure to determine the Fracture Toughness temperature T_{FT}	2 2 2 2 2			
8 8.1 8.2 8.3	SIST-TS CEN/TS 15963:2014 Test sample https://standards.iteh.ai/catalog/standards/sist/0329d150-75d7-4da5-85de- 983e020e6cf1/sist-ts-cen-ts-15963-2014 Fracture Toughness temperature, T _{FT}	2 2 3 3			
9 9.1 9.2	Expression of results Fracture Toughness temperature, <i>T_{FT}</i> Other properties	4 4 4			
10 10.1 10.2	Precision Repeatability Reproducibility	4 4 4			
11	Test report 1	15			
Annex	A (informative) Calculation of Critical Stress Intensity factor 1	6			
A.1	General1	6			
A.2	Terms and definitions 1	6			
A.3	Calculations1	6			
Bibliog	jraphy1	Bibliography			

Foreword

This document (CEN/TS 15963:2014) has been prepared by Technical Committee CEN/TC 336 "Bituminous binders", the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 15963:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TS CEN/TS 15963:2014 https://standards.iteh.ai/catalog/standards/sist/0329d150-75d7-4da5-85de-983e020e6cf1/sist-ts-cen-ts-15963-2014

1 Scope

This Technical Specification specifies a method for the determination of the Fracture Toughness temperature, T_{FT} , of bituminous binders by means of a three point bending test on a notched binder sample.

WARNING — The use of this Technical Specification can involve hazardous materials, operations and equipment. This Technical Specification does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this Technical Specification to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use. For environmental reasons, it is recommended to limit the use of products, solvents and energy to minimum in order to reduce the emissions to air, water and soil.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, Bitumen and bituminous binders - Sampling bituminous binders

EN 12594, Bitumen and bituminous binders - Preparation of test samples

iTeh STANDARD PREVIEW (standards.iteh.ai)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

SIST-TS CEN/TS 15963:2014

3.1

https://standards.iteh.ai/catalog/standards/sist/0329d150-75d7-4da5-85de-983e020e6cf1/sist-ts-cen-ts-15963-2014

maximum force

highest force measured during the bending test

Note 1 to entry: The test is done in the brittle state or close to that, so that the maximum force is considered as the onset of the crack propagation.

Note 2 to entry: Force is expressed in newtons (N).

3.2

displacement at maximum force

D

bending of the test beam from the beginning of the test (from the zero point) to the break point

Note 1 to entry: Displacement is expressed in millimetres (mm).

3.3

work

W

area under the force-displacement curve from the beginning of the test to the break of the sample, i.e. at the maximum force

Note 1 to entry: Work is expressed in newtons-metres (N·m) or in Joules (J).

3.4 Fracture Toughness temperature

Т_{FT}

temperature at which the displacement at the maximum force is 0,3 mm (from the zero point)

Note 1 to entry: Fracture Toughness temperature is expressed in degrees Celsius (°C).

3.5

initial stiffness S

value calculated as the slope of the tangent of the force-displacement curve at the inflection point

Note 1 to entry: See Figure 1.

Note 2 to entry: Stiffness is expressed in newtons per millimetre (N/mm).

3.6

zero point

intersection of the x-axis and the tangent of the force-displacement curve at the inflection point expressed in millimetres (mm)

Figure 1 presents an example of the force versus displacement curve at a temperature T close to T_{FT} .



Key

- X displacement, in millimetres (mm)
- Y force, in newtons (N)

- A maximum force (defined as F)
- B X point at maximum force
- C tangent at the inflection point
- D displacement at maximum force, (D = B E)
- E zero point
- W work as defined in 3.3
- I inflection point of *F* versus displacement

Figure 1 — Example of a Force versus displacement curve at temperature T (close to T_{FT})

4 Principle

The notched three point bending test is used to measure cracking performance of unmodified and modified bituminous binder samples. The test sample is a beam with a notch in the middle of one side of the beam. The sample is conditioned in a temperature controlled bath. The beam is placed on two supports with the notch facing downwards and a vertical downward force is applied on the middle of the upper face of the sample. The beam is loaded until failure with a specified displacement rate, whereby force is recorded versus displacement.

NOTE 1 The fracture properties of bituminous binders are strongly dependent on test temperature, loading rate and sample preparation method.

NOTE 2 This test is based on the work done by S. Hesp for the Ministry of Transportation in Ontario, Canada [1].

5 Apparatus

5.1 Testing apparatus

5.1.1 Tension-compression device

A universal tension-compression device, which is capable of sustaining a constant, predetermined displacement rate.

5.1.2 Bending rig **iTeh STANDARD PREVIEW**

A bending rig consisting of two cylindrical specimen supports, a cylindrical-nosed shaft to apply the load to the mid-point of the test specimen and a load cell mounted in line with the loading shaft.

SIST-TS CEN/TS 15963:2014

983e020e6cfl/sist-ts-cen-ts-15963-2014

The dimensions and tolerances of the loading frame are given in Table 150-75d7-4da5-85de-

5.1.3 Loading system

A loading system, which is capable of applying a rate of displacement of 0,01 mm/s. The specified displacement rate shall fluctuate by no more than \pm 10 % over time. The maximum stroke of the instrument shall be at least 20 mm for this test.

5.1.4 Loading shaft

A loading shaft, which is continuous and in line with the load cell and deflection measuring transducer. The T-shape shaft shall have a cylindrical-shaped loading pin in the end. The diameter of the pin shall be $(10,0 \pm 0,1)$ mm.

5.1.5 Load cell

A load cell having a minimum capacity of no less than 500 N and an accuracy of ± 1 % above 5 N with a minimum resolution of at least 100 m·N is required. The load cell shall allow the measurement of the force at any time during the test.

5.1.6 LVD-transducer

An LVD transducer or other suitable device to measure the deflection of the sample is necessary. It shall have a linear range of at least 5 mm with an accuracy of 2 μ m. The deflection may be measured using this separate transducer or by measuring the vertical movement of the tension/compression device.

5.1.7 Specimen supports

Specimen supports which shall consist of two non-corrosive metal half-rounds or cylinders with a diameter of $(10,0 \pm 0,1)$ mm that are spaced (100 ± 1) mm apart (cylinder centre point to cylinder centre point). The specimen shall be placed perpendicular to the supports and the loading pin. To facilitate that, two vertical alignment pins of 2 mm to 4 mm in diameter can be provided at the back of each support. A schematic diagram of the sample supports is shown in Figure 2.

5.1.8 Ventilated oven, capable of maintaining a temperature up to 200 °C, with an accuracy of ± 1 °C.

The specified temperature shall only be assessed in the surroundings of the sample (see 6.3).

Dimensions in millimetres



3 specimen supports

Key

1

2

Figure 2 — Bending rig

Dimension	Size, mm	Tolerance, mm
Loading shaft pin length	25	±2
Loading shaft diameter	10,0	±0,1
Specimen support length	25	±2
Specimen support diameter	10,0	±0,1
Specimen support span	100	±1

Table 1 — Measurement and tolerances of the rig

5.1.9 Temperature measurement device

A calibrated temperature transducer capable of measuring the temperature with the accuracy of $\pm 0,1$ °C over the range of - 40,0 °C to 0,0 °C. The temperature measuring head shall be mounted in the near vicinity of the specimen, at a distance of not more than 25 mm from the middle of the specimen.

5.1.10 Liquid bath

A liquid bath shall be capable of maintaining the required test temperature near the test specimen within ± 0.2 °C during the isothermal conditioning and the test procedure, enabling to reach the lower temperature required for testing the specimen.

Bath liquid shall not affect the properties of the bituminous binder being tested.

NOTE 95 % volume ethanol or a 40 % to 50 % mass potassium acetate-water solution has been found to be suitable as a bath liquid.

5.1.11 Data acquisition

The data acquisition system shall resolve loads to the nearest 100 mN, record specimen deflection to the nearest 0,5 μ m, record time to the nearest 0,1 s and temperature around the sample to the nearest 0,1 °C. The software shall control the measuring system and record time, load, deflection and temperature during the test. Sampling rate of force and displacement should be at least 0,1 s⁻¹ (10 Hz).

5.2 Test specimen

A test specimen as shown on Figure 3 is used. The sample is moulded from the bituminous binder to be assessed. Two aluminium inserts are installed at the ends of the mould. The notch is made by installing two sheets of silicone paper into the pre-notched mould frame.



Figure 3 — Specimen geometry

Dimension	Size, mm	Tolerance ^a , mm		
Beam length, L _{Be}	120,0	±0,3		
Insert length, L _{in}	40,0	±0,1		
Specimen length, L	40,0	±0,2		
Specimen height, H	25,0	±0,5		
Specimen thickness, <i>B</i>	12,5	±0,3		
Notch depth, <i>a</i>	5,0	±0,1		
Notch thickness, b	2 × 25 µm	-		
^a Tolerance is related to the mould.				

6 Preparation of test samples

6.1 Preparation of test samples

The laboratory sample shall be taken in accordance with EN 58 and the test samples shall be prepared in accordance with EN 12594. en STANDARD PREVIEW

6.2 Preparation of moulds

(standards.iteh.ai)

The moulds for making the samples shall be assembled from aluminium side spacers. On the side spacers and on the bottom alplastic film is glued with an anti-sticking agent to prevent sticking of the bitumen binder to the mould. Two aluminium inserts are installed in the ends of the mould. The surfaces of the aluminium inserts that are in contact with bitumen should be roughened to ensure good adhesion. A series of such assemblies may be clamped together to make more than one specimen at a time. Figure 4 shows the different parts of the mould. Figure 5 shows a picture of such an example assembly and its parts.