

SLOVENSKI STANDARD

SIST EN 2267-009:2013

01-maj-2013

Nadomešča:

SIST EN 2267-009:2006

Aeronavtika - Električni kabli za splošno uporabo - Delovne temperature med -55 °C in 260 °C - 009. del: Družina DRA, snop enožilnih in večžilnih kablov - Standard za izdelek

Aerospace series - Cables, electrical, for general purpose - Operating temperatures between - 55 °C and 260 °C - Part 009: DRA family, single and multicore assembly - Product standard

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Luft- und Raumfahrt - Leitungen, elektrisch, für allgemeine Verwendung - Betriebstemperaturen zwischen - 55 °C und 260 °C - Teil 009: DRA-Familie Ein- und mehradrige Leitungen - Produktnorm

SIST EN 2267-009:2013

[https://standards.iteh.ai/catalog/standards/sist/0c34549b-7b22-4741-b53f-](https://standards.iteh.ai/catalog/standards/sist/0c34549b-7b22-4741-b53f-7672816f7846/sist-en-2267-009-2013)

7672816f7846/sist-en-2267-009-2013

Série aérospatiale - Câbles, électriques, d'usage général - Températures de fonctionnement comprises entre - 55 °C et 260 °C - Partie 009: Famille DRA, fil simple et éléments assemblés - Norme de produit

Ta slovenski standard je istoveten z: EN 2267-009:2013

ICS:

49.060

Letalska in vesoljska
električna oprema in sistemi

Aerospace electric
equipment and systems

SIST EN 2267-009:2013

en,fr

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 2267-009:2013](https://standards.iteh.ai/catalog/standards/sist/0c34549b-7b22-4741-b53f-7672816f7846/sist-en-2267-009-2013)

<https://standards.iteh.ai/catalog/standards/sist/0c34549b-7b22-4741-b53f-7672816f7846/sist-en-2267-009-2013>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 2267-009

January 2013

ICS 49.060

Supersedes EN 2267-009:2005

English Version

**Aerospace series - Cables, electrical, for general purpose -
Operating temperatures between - 55 °C and 260 °C - Part 009:
DRA family, single and multicore assembly - Product standard**

Série aérospatiale - Câbles, électriques, d'usage général -
Températures de fonctionnement comprises entre - 55 °C
et 260 °C - Partie 009 : Famille DRA, fil simple et éléments
assemblés - Norme de produit

Luft- und Raumfahrt - Leitungen, elektrisch, für allgemeine
Verwendung - Betriebstemperaturen zwischen - 55 °C und
260 °C - Teil 009: DRA-Familie Ein- und mehradrige
Leitungen - Produktnorm

This European Standard was approved by CEN on 27 October 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms, definitions and symbols	4
4 Materials and construction	4
5 Required characteristics.....	5
6 Quality assurance	9
7 Designation	9
8 Identification and marking	10
9 Packaging, labelling and delivery lengths	10
10 Technical specification	10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 2267-009:2013](https://standards.iteh.ai/catalog/standards/sist/0c34549b-7b22-4741-b53f-7672816f7846/sist-en-2267-009-2013)

<https://standards.iteh.ai/catalog/standards/sist/0c34549b-7b22-4741-b53f-7672816f7846/sist-en-2267-009-2013>

Foreword

This document (EN 2267-009:2013) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2013, and conflicting national standards shall be withdrawn at the latest by July 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 2267-009:2005.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SIST EN 2267-009:2013

<https://standards.iteh.ai/catalog/standards/sist/0c34549b-7b22-4741-b53f-7672816f7846/sist-en-2267-009-2013>

EN 2267-009:2013 (E)

1 Scope

This European Standard specifies the characteristics of electrical lightweight wires DRA family for use in the on-board 115 V (phase to neutral) or 200 V (phase to phase) electrical systems of aircraft at operating temperatures between – 65 °C and 260 °C. These cables are demonstrated to be arc resistant in sizes 001 to 020 (26 AWG to 14 AWG).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2083, *Aerospace series — Copper or copper alloy conductors for electrical cables — Product standard*

EN 2084, *Aerospace series — Cables, electric, single-core, general purpose, with conductors in copper or copper alloy — Technical specification*

EN 2235, *Aerospace series — Single and multicore electrical cables, screened and jacketed*

EN 2267-002, *Aerospace series — Cables, electrical, for general purpose — Operating temperatures between – 55 °C and 260 °C — Part 002: General*

EN 3475-100:2010, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 100: General*

EN 4434, *Aerospace series — Copper or copper alloy lightweight conductors for electrical cables — Product standard (Normal and tight tolerances)*

EN 9133, *Aerospace series — Quality management systems — Qualification procedure for aerospace standard parts*

3 Terms, definitions and symbols

For the purposes of this document, the terms, definitions and symbols given in EN 3475-100:2010 apply.

4 Materials and construction

4.1 Materials

Conductor:

These cable conductors shall be made of copper or copper alloy and nickel plated (code D) according to EN 4434 Table 2 (tight tolerances) for 001 to 140 section codes and to EN 2083 for 220 to 340 section codes.

Insulation:

All conductor size codes shall be defined to satisfy all required characteristics of Clause 5.

4.2 Construction

See EN 4434, EN 2083 and Table 1.

Table 1

Code for nominal section	Nominal section mm ²	AWG ^a	Linear resistance at 20 °C Ω/km max.	External diameter		Mass kg/km max.
				mm min.	mm max.	
001	0,15	26	160,0	0,75	0,84	2,08
002	0,25	24	114,0	0,85	0,96	2,72
004	0,4	22	60,0	1,00	1,10	4,14
006	0,6	20	33,2	1,22	1,34	6,85
010	1	18	21,1	1,46	1,61	10,43
012	1,2	16	14,5	1,76	1,92	14,61
020	2	14	10,9	2,04	2,24	19,78
030	3	12	6,8	2,50	2,70	31,33
051	5	10	4,1	3,13	3,33	49,85
090	9	8	2,3	4,10	4,40	90,00
140	14	6	1,58	5,30	5,70	135,0
220	22	4	0,97	6,71	7,41	222,0
340	34	2	0,61	8,28	9,16	347,0

^a AWG = closest American Wire Gauge.

4.3 Multiple core cables

See EN 2267-002.

See EN 2235, 4.3.2 for cabling.

4.4 Colour coding of cores

See EN 2267-002.

5 Required characteristics

According to EN 2084 and EN 3475-100.

See Table 2.

Table 2 (1 of 4)

EN 3475-	Test	Details
201	Visual examination	Applicable
202	Mass	Applicable; see Table 1.
203	Dimensions	Applicable; see Table 1.
301	Ohmic resistance per unit length	Applicable; see Table 1.
302	Voltage proof test	Applicable
303	Insulation resistance	Applicable
304	Surface resistance	Applicable
305	Overload resistance	Applicable $T_1 = (310 \pm 5) ^\circ\text{C}$; $T_2 = (450 \pm 5) ^\circ\text{C}$.
306	Continuity of conductors	Applicable
307	Corona extinction voltage	Not applicable
401	Accelerated ageing	Applicable Temperature $(310 \pm 5) ^\circ\text{C}$
402	Shrinkage and delamination	Applicable Temperature $(290 \pm 5) ^\circ\text{C}$ Maximum shrinkage at each end of cable: — $0,15 \text{ mm}^2$ to $0,60 \text{ mm}^2$: 0,80 mm; — $1,00 \text{ mm}^2$ to $1,20 \text{ mm}^2$: 1,00 mm; — $2,00 \text{ mm}^2$ to $5,00 \text{ mm}^2$: 1,20 mm; — 9 mm^2 : 1,5 mm; — 14 mm^2 to 34 mm^2 : 2,0 mm.
403	Delamination and blocking	Applicable temperature $(310 \pm 5) ^\circ\text{C}$
404	Thermal shock	Applicable but $(- 65 \pm 2) ^\circ\text{C}$ instead of $(55 \pm 2) ^\circ\text{C}$ Temperature $(260 \pm 5) ^\circ\text{C}$ Maximum shrinkage at each end of cable: — $0,15 \text{ mm}^2$ to $0,60 \text{ mm}^2$: 0,80 mm; — $1,00 \text{ mm}^2$ to $1,20 \text{ mm}^2$: 1,00 mm; — $2,00 \text{ mm}^2$ to $5,00 \text{ mm}^2$: 1,20 mm; — 9 mm^2 : 1,5 mm; — 14 mm^2 to 34 mm^2 : 2,0 mm.
405	Bending at ambient temperature	Applicable

Table 2 (2 of 4)

EN 3475-	Test	Details																																						
406	Cold bend test	Applicable Temperature (-65 ± 2) °C																																						
407	Flammability	Applicable (method 1) Extinguishing time: 3 s max.																																						
408	Fire resistance	Not applicable																																						
409	Air excluded ageing	Not applicable																																						
410	Thermal endurance	Applicable 10 000 h at 260 °C with curve extrapolation 100 000 h at 200 °C with curve reading																																						
411	Resistance to fluids	Applicable																																						
412	Humidity resistance	Applicable Method B – Temperature (95 ± 5) °C Duration 360 h																																						
413	Wrap back test	Applicable																																						
414	Differential scanning calorimeter (DSC test)	Applicable (only if PTFE in the construction)																																						
415	Rapid change of temperature	Not applicable																																						
416	Thermal stability	Not applicable																																						
501	Dynamic cut-through	Applicable for sections up to 14 mm ² Temperatures (20 ± 3) °C and (260 ± 5) °C <table border="1"> <thead> <tr> <th rowspan="2">Nominal section mm²</th><th colspan="2">Cut-through force</th></tr> <tr> <th>20 °C N</th><th>260 °C N</th></tr> </thead> <tbody> <tr><td>0,15</td><td>70</td><td>15</td></tr> <tr><td>0,25</td><td>85</td><td>30</td></tr> <tr><td>0,40</td><td>110</td><td>45</td></tr> <tr><td>0,60</td><td>140</td><td>55</td></tr> <tr><td>1,00</td><td>140</td><td>70</td></tr> <tr><td>1,20</td><td>150</td><td>85</td></tr> <tr><td>2,00</td><td>150</td><td>95</td></tr> <tr><td>3,00</td><td>165</td><td>105</td></tr> <tr><td>5,00</td><td>180</td><td>120</td></tr> <tr><td>9,00</td><td>195</td><td>135</td></tr> <tr><td>14,00</td><td>210</td><td>150</td></tr> </tbody> </table>	Nominal section mm ²	Cut-through force		20 °C N	260 °C N	0,15	70	15	0,25	85	30	0,40	110	45	0,60	140	55	1,00	140	70	1,20	150	85	2,00	150	95	3,00	165	105	5,00	180	120	9,00	195	135	14,00	210	150
Nominal section mm ²	Cut-through force																																							
	20 °C N	260 °C N																																						
0,15	70	15																																						
0,25	85	30																																						
0,40	110	45																																						
0,60	140	55																																						
1,00	140	70																																						
1,20	150	85																																						
2,00	150	95																																						
3,00	165	105																																						
5,00	180	120																																						
9,00	195	135																																						
14,00	210	150																																						