



SLOVENSKI STANDARD

SIST EN 941:2014

01-julij-2014

Nadomešča:
SIST EN 941:1998

Aluminij in aluminijeve zlitine - Rondele in polizdelki za splošno uporabo - Specifikacije

Aluminium and aluminium alloys - Circle and circle stock for general application -
Specifications

Aluminium und Aluminiumlegierungen - Ronden und Rondenvormaterial für allgemeine
Anwendungen - Spezifikationen

Aluminium et alliages d'aluminium - Disques et ébauches pour disques pour applications
générales - Spécifications

Ta slovenski standard je istoveten z: EN 941:2014

ICS:

77.150.10 Alumijski izdelki Aluminium products

SIST EN 941:2014

en,fr,de

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

SIST EN 941:2014

<https://standards.iteh.ai/catalog/standards/sist/fe9290af-5d66-4a18-b0b2-12d3aa4bb279/sist-en-941-2014>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 941

April 2014

ICS 77.150.10

Supersedes EN 941:1995

English Version

Aluminium and aluminium alloys - Circle and circle stock for the
production of general applications - Specifications

Aluminium et alliages d'aluminium - Disques et ébauches
pour disques pour applications générales - Spécifications

Aluminium und Aluminiumlegierungen - Ronden und
Rondenvormaterial für allgemeine Anwendungen -
Spezifikationen

This European Standard was approved by CEN on 13 March 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 941:2014](https://standards.iteh.ai/catalog/standards/sist/fe9290af-5d66-4a18-b0b2-12d3aa4bb279/sist-en-941-2014)

<https://standards.iteh.ai/catalog/standards/sist/fe9290af-5d66-4a18-b0b2-12d3aa4bb279/sist-en-941-2014>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Technical conditions for inspection and delivery	5
4.1 General.....	5
4.2 Orders or tenders.....	5
5 Mechanical properties	6
6 Tolerances on dimensions and form	6
6.1 General.....	6
6.2 Diameter.....	6
6.3 Thickness	6
6.4 Tolerances on flatness for circles.....	6

ITeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 941:2014

<https://standards.iteh.ai/catalog/standards/sist/fe9290af-5d66-4a18-b0b2-12d3aa4bb279/sist-en-941-2014>

Foreword

This document (EN 941:2014) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2014 and conflicting national standards shall be withdrawn at the latest by October 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 941:1995.

With regard the previous version, Clause 2 Normative references was updated; no new alloys were added.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 941:2014

<https://standards.iteh.ai/catalog/standards/sist/fe9290af-5d66-4a18-b0b2-12d3aa4bb279/sist-en-941-2014>

EN 941:2014 (E)

1 Scope

This European Standard specifies the particular requirements for wrought aluminium and aluminium alloys in the form of circle or circle stock for general applications.

It applies to:

- Circles made out of hot or cold rolled circles stock by:
 - Blanking: thickness 0,2 mm up to including 12 mm and with a diameter up to 1 000 mm;
 - Sawing or shearing: thickness 0,2 mm up to and including 200 mm with a diameter up to 3 500 mm;
- Hot or cold rolled circle stock with a thickness from 0,2 mm up to and including 200 mm and with a width up to 3 500 mm.

It does not apply to slugs for impact extrusions or to circle and circle stock for culinary utensils applications which are dealt with in other European Standards.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 485-1:2008+A1:2009, *Aluminium and aluminium alloys - Sheet, strip, and plate - Part 1: Technical conditions for inspection and delivery*

[SIST EN 941:2014](https://standards.iteh.ai/catalog/standards/sist/fe9290af-5d66-4a18-b0b2-12d3aa486279/sist-en-941-2014)

EN 485-2, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 2: Mechanical properties*

EN 485-3:2003, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 3: Tolerances on dimensions and form for hot-rolled products*

EN 485-4:1993, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 4: Tolerances on shape and dimensions for cold-rolled products*

EN 515, *Aluminium and aluminium alloys - Wrought products - Temper designations*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

circle

circular flat product obtained by circular sawing or shearing, or by blanking of a flat rolled product with a uniform thickness over 0,20 mm

3.2**circle stock**

flat rolled product of rectangular cross-section with uniform thickness over 0,20 mm, supplied in coils, sheets, or plates, usually with sheared or sawn edges, and intended to be sawn, sheared or blanked into flat shapes to be subsequently formed, drawn, etc.

Note 1 to entry: The thickness does not exceed one tenth of the width.

3.3**hot rolled circle and circle stock**

circle or circle stock whose final thickness is obtained by hot rolling

3.4**cold rolled circle and circle stock**

circle or circle stock whose final thickness is obtained by cold rolling

4 Technical conditions for inspection and delivery**4.1 General**

All the provisions of EN 485-1 shall apply, except Clause 4 (orders and tenders) which is modified as follows:

4.2 Orders or tenders

The order or tender shall define the product required and shall contain the following information:

- a) the form and the type of product:
 - 1) the form of the product (circle and circle stock);
 - 2) the designation of the aluminium or aluminium alloy;
 - 3) the customer application,
- b) the metallurgical temper of the material for delivery according to EN 515 (degree of hardness or heat treatment condition) and, if different, the metallurgical temper for use;
- c) the number of this European Standard or Specification number, or where none exists, the properties agreed between purchaser and supplier;
- d) the dimensions and shape of the product as applicable:
 - 1) thickness;
 - 2) diameter of the circle;
 - 3) width of the strip, sheet, or plate;
 - 4) length of the sheet or plate;
 - 5) internal and external diameters of the coil;
- e) whether hot rolled or cold rolled tolerances apply;
- f) quantity:

EN 941:2014 (E)

- 1) mass or number of pieces;
- 2) tolerances on quantity if required;
- g) any requirements for certificates of conformity, test and/or analysis reports or inspection certificates;
- h) any special requirements agreed between purchaser and supplier :
 - 1) marking of products;
 - 2) references to drawings, etc.

5 Mechanical properties

The mechanical properties shall conform to the requirements specified in EN 485-2.

6 Tolerances on dimensions and form**6.1 General**

All provisions of EN 485-3 and EN 485-4 shall apply with the following amendments and additions.

6.2 Diameter

Tolerances on diameters for circle shall conform to Table 1. These tolerances include the tolerances on roundness.

NOTE For circle obtained by blanking the recommended standard diameters are:

- From 100 mm up to 500 mm nominal diameter: every multiple of 5;
- Over 500 mm up to 1 000 mm nominal diameter: every multiple of 10.

6.3 Thickness

Tolerances on thickness for hot rolled circle and circle stock shall conform to Table 2. They are identical to those specified in Table 1 of EN 485-3:2003 and are reproduced here for convenience.

The tolerances on thickness for cold rolled circle and circle stock shall conform to Table 3. They are identical to those specified in Table 1 of EN 485-4:1993 and are reproduced here for convenience. The partition into group I and group II of most common materials which may be used for the present application shall be as shown in Table 4.

6.4 Tolerances on flatness for circles

Tolerances on flatness for circles, expressed as a percentage of the diameter D and/or the measured chord length L , shall conform to Table 5.

Deviation from flatness d , resulting from arching or buckling, shall be measured as shown in Figures 1 and 2, using a lightweight straightedge and a feeler gauge, dial gauge or scale, while the circle is resting on a horizontal base plate, concave side upwards.

Two measurements shall be carried out with the straight edge respectively parallel and perpendicular to the rolling direction.

These tolerances do not apply to circles supplied in O or F tempers except for special agreement between supplier and purchaser.

Table 1 — Tolerances on diameter

Dimensions in millimetres

Specified thickness		Method of production	Diameter tolerances for specified diameter ^a				
over	up to		up to 600	over 600 up to 1 000	over 1 000 up to 1 600	over 1 600 up to 3 000	over 3 000 up to 3 500
0,2	4	Blanking	± 0,5	± 0,5	-	-	-
		circular sawing or shearing	+ 3 0	+ 4 0	+ 7 0	+ 9 0	+ 11 0
4	6	Blanking	± 0,7	± 0,7	-	-	-
		circular sawing or shearing	+ 4 0	+ 5 0	+ 8 0	+ 9 0	+ 11 0
6	12	Blanking	± 1	± 1	-	-	-
		circular sawing or shearing	+ 4 0	+ 5 0	+ 8 0	+ 10 0	+ 12 0
12	50	circular sawing or shearing	+ 7 0	+ 7 0	+ 9 0	+ 12 0	+ 14 0
		circular sawing or shearing	+ 10 0	+ 10 0	+ 12 0	+ 14 0	+ 16 0

^a These tolerances include the tolerances on roundness.