



SLOVENSKI STANDARD
oSIST prEN 1396:2014
01-januar-2014

Aluminij in aluminijeve zlitine - Prevlečena ali premazana pločevina in trakovi za splošno uporabo - Specifikacije

Aluminium and aluminium alloys - Coil coated sheet and strip for general applications - Specifications

Aluminium und Aluminiumlegierungen - Bandbeschichtete Bleche und Bänder für allgemeine Anwendungen - Spezifikationen

Aluminium et alliages d'aluminium - Tôles et bandes revêtues en bobine pour applications générales - Spécifications

Ta slovenski standard je istoveten z: prEN 1396

ICS:

77.150.10 Alumijski izdelki Aluminium products

oSIST prEN 1396:2014

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 1396

September 2013

ICS 77.150.10

Will supersede EN 1396:2007

English Version

Aluminium and aluminium alloys - Coil coated sheet and strip for general applications - Specifications

Aluminium et alliages d'aluminium - Tôles et bandes
revêtues en bobine pour applications générales -
Spécifications

Aluminium und Aluminiumlegierungen - Bandbeschichtete
Bleche und Bänder für allgemeine Anwendungen -
Spezifikationen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 132.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Technical conditions for inspection and delivery	9
4.1 Ordering information	9
4.2 Requirements	11
4.2.1 Production and manufacturing processes	11
4.2.2 Quality control	11
4.2.3 Freedom from defects.....	12
4.2.4 Chemical composition	12
4.2.5 Mechanical properties.....	12
4.2.6 Tolerances on shape and dimensions	12
4.2.7 Coating properties.....	12
4.3 Test procedures.....	12
4.3.1 Chemical composition	12
4.3.2 Tensile test	13
4.3.3 Coating tests	13
4.3.4 Retests	13
5 Mechanical properties	13
6 Organic coating properties	16
6.1 Tolerances on thickness	16
6.2 Tolerances on gloss	16
6.3 Tolerances on colour.....	17
7 Inspection documents.....	17
8 Marking	17
9 Packing	17
10 Arbitration tests	18
Annex A (normative) Rules for rounding	19
A.1	19
A.2	19
Annex B (informative) Examples of coating systems	20
Annex C (informative) Guidelines for organic coatings.....	22
C.1 General.....	22
C.2 Colour	22
C.3 Flexibility	22
C.4 Adhesion.....	23
C.5 Pencil hardness	24
C.6 Durability of the organic coating.....	24
C.6.1 General	24
C.6.2 Corrosion resistance (outdoor exposure).....	26
C.6.3 UV resistance.....	26
C.6.4 Humidity resistance (accelerated test)	28
C.6.5 Acetic acid salt spray fog resistance (accelerated corrosion test)	28

C.6.6	Filiform corrosion test, FFC (accelerated corrosion test).....	28
Annex D (informative) Guidelines for storage and subsequent processing		30
D.1	Storage	30
D.2	General instructions for processing.....	30
D.3	Forming	30
D.4	Cutting	30
D.5	Joining	31
D.6	Cleaning.....	31
D.7	Temporary protective films	31
Annex E (normative) Chemical composition of aluminium alloys EN AW-5006 and EN AW-6025.....		32
Bibliography.....		33

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 1396:2015

<https://standards.iteh.ai/catalog/standards/sist/1d409745-90b3-4557-a700-f82f018f5f9a/sist-en-1396-2015>

Foreword

This document (prEN 1396:2013) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 1396:2007.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1396:2015

<https://standards.iteh.ai/catalog/standards/sist/1d409745-90b3-4557-a700-f82f018f5f9a/sist-en-1396-2015>

Introduction

Organic coated aluminium and aluminium alloy strip and sheet products can be used to advantage in cases where corrosion resistance and decorative appearance are of primary importance. They have applications throughout the flat products processing industry e.g. in the building, automotive, caravans, appliances, fabricating and pack-aging industries.

Organic coated aluminium and aluminium alloy flat products can be delivered in numerous types and grades, depending on the base material used (various grades of aluminium), on the coating material and types of coating and on the requirements for the surface appearance and the formability.

The properties of the products can vary within greater or smaller limits depending on the choice and combination of properties required. It is therefore not practicable to specify in detail minimum requirements for all properties for all types of products.

As a general rule, material specifications shall be agreed between manufacturer and user/purchaser using, when appropriate, the guidelines from Annex C.

Guidelines for proper storage and subsequent processing of organic coated aluminium flat products are given in Annex D.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1396:2015

<https://standards.iteh.ai/catalog/standards/sist/1d409745-90b3-4557-a700-f82f018f5f9a/sist-en-1396-2015>

prEN 1396:2013 (E)**1 Scope**

This European Standard specifies the particular requirements for wrought aluminium and wrought aluminium alloys in the form of coil coated sheet and strip for general applications. This product is generally supplied in thicknesses up to 3,0 mm.

It applies to cold-rolled aluminium and aluminium alloy strip coated by the coil coating process both with liquid as well as with powder paints, either in the final width or slit afterwards, and to sheet obtained from such strip.

It does not apply to coil coated sheet and strip used for special applications such as cans, closures and lids which are dealt with in separate EN 541.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 485-1, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 1: Technical conditions for inspection and delivery*

EN 485-4, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 4: Tolerances on shape and dimensions for cold-rolled products*

EN 515, *Aluminium and aluminium alloys — Wrought products — Temper designations*

EN 573-3, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 3: Chemical composition*

EN 12258-1:1998, *Aluminium and aluminium alloys — Terms and definitions — Part 1: General terms*

EN 13523-1, *Coil coated metals — Test methods — Part 1: Coating thickness*

EN 13523-2, *Coil coated metals — Test methods — Part 2: Specular gloss*

EN 13523-3, *Coil coated metals — Test methods — Part 3: Colour difference — Instrumental comparison*

EN 13523-4, *Coil coated metals - Test methods — Part 4: Pencil hardness*

EN 13523-6, *Coil coated metals – Test methods – Part 6: Adhesion after indentation (cupping test)*

EN 13523-7, *Coil coated metals – Test methods – Part 7: Resistance to cracking on bending (T-Bend test)*

EN 13523-8, *Coil coated metals – Test methods – Part 8: Resistance to salt spray (fog)*

EN 13523-10, *Coil coated metals – Test methods – Part 10: Resistance to fluorescent UV light and water condensation*

EN 13523-19, *Coil coated metals — Test methods — Part 19: Panel design and method of atmospheric exposure testing*

EN 13523-21, *Coil coated metals — Test methods — Part 21: Evaluation of outdoor exposed panels*

EN 13523-22, *Coil coated metals — Test methods — Part 22: Colour difference — Visual comparison*

EN ISO 1520, *Paints and varnishes — Cupping test*

EN ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*

EN ISO 6270-1, *Paints and varnishes — Determination of resistance to humidity — Part 1: Continuous condensation*

EN ISO 6272-1, *Paints and varnishes — Rapid-deformation (impact resistance) tests — Part 1: Falling-weight test, large-area indenter*

EN ISO 6272-2, *Paints and varnishes — Rapid-deformation (impact resistance) tests — Part 2: Falling-weight test, small-area indenter*

EN ISO 6892-1:2009, *Metallic materials — Tensile testing – Part 1: Method of test at room temperature*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12258-1:1998 and the following apply.

3.1

aluminium

metal with a minimum content of 99,0 % by mass of aluminium and with content by mass of any other element within the following limits:

- a total content of iron and silicon not greater than 1,0% ;
- a content of any other element not greater than 0,10 % except for copper which can have a content of up to 0,20 % provided that neither the chromium nor the manganese content exceeds 0,05 %

Note 1 to entry: Aluminium in the liquid state or in the form of ingots for remelting is often called “unalloyed aluminium”.

[SOURCE: EN 12258-1:1998]

3.2

aluminium alloy

alloy in which aluminium predominates by mass over each of the other elements, provided that it does not conform to the definition of aluminium

[SOURCE: EN 12258-1:1998]

3.3

metal substrate

base material from cold rolled aluminium or aluminium alloy strip

3.4

coating material

material comprising organic polymers e.g. synthetic resins or plastics, to which pigments, additives and solvents (if required) have generally been added, suitable for coil coating. These can be paints (liquid or powder) or plastic films

prEN 1396:2013 (E)

3.5
coil coating
method in which a coating material is applied in a continuous process on a cold rolled metal strip. This process includes cleaning and chemical pre-treatment of the surface and either:

- one-side or two-side, single or multiple application of liquid or powder coating materials which are subsequently cured, or
- laminating with plastic films

3.6
organic coating
dry paint film of the coated product or the organic film of the organic film/metal laminate

[SOURCE: EN 12258-1:1998]

3.7
top side
side of the strip with the highest decorative demand and which, in normal production, is uppermost.

For strip supplied in coil form, the top side is normally the outside of the coil. For sheet supplied in stacks or bundles the top side is normally uppermost

3.8
reverse side
underside of the strip, generally coated with a backing coat (see 3.12), but possibly pre-treated only or coated with one of the other systems described in 3.10, 3.11 and 3.13, to fulfil special requirements such as foam or glue adhesion, specially defined friction, etc.

3.9
coating system
combination of coatings either on the top side or on the reverse side of the metal substrate

The name of the coating system derives from the top coat coating material (see examples in Annex B).

3.10
single layer coating
single coating either with requirements on appearance, formability, corrosion protection, subsequent painting etc., or as a primer with special properties regarding adhesion and corrosion protection for post-painting applications

3.11
multilayer coating
system comprising a primer or a base coat, possibly intermediate coat(s), and a top coat with particular requirements on appearance, formability, corrosion protection etc.

3.12
backing coat
single coating of any type with no particular requirements for appearance, formability, corrosion protection etc., usually on the reverse side of the coated product

3.13
film coating
organic film applied to a substrate to which an adhesive and, if appropriate, a primer has been applied before-hand

[SOURCE: EN 12258-1:1998]

3.14**master coil / mother coil**

coil-coated in coil from which products (coil or sheet) are obtained

3.15**order document**

document or set of documents agreed between supplier and purchaser at the time of ordering

Note 1 to entry: An order document can be an order of the purchaser confirmed by the supplier or a quotation of the supplier confirmed by the purchaser.

4 Technical conditions for inspection and delivery**4.1 Ordering information**

The order document shall define the product required and shall contain the following information:

- a) the form and type of product:
 - the form of the product (organic coated coil, sheet or strip);
 - the designation of the aluminium or aluminium alloy, in accordance with EN 573-3;
 - b) the temper of the material for delivery (degree of hardness or heat treatment condition) in accordance with EN 515 and EN ISO 6892-1:2009;
 - c) the dimensions and shape of the product:
 - thickness (of the metal substrate);
 - width;
 - length of sheet (in the rolling direction);
 - internal and external diameters of the coil;
 - core size and type.
- NOTE Unless otherwise agreed, the length is the largest dimension;.
- d) the quantity:
 - mass or number of pieces;

prEN 1396:2013 (E)

e) the coating system (see examples in Annex B):

1) for the top side:

- colour designation (international and/or company code);
- nominal gloss value;
- protective strippable film when required ¹⁾

2) for the reverse side:

- whether it is a backing coat or not;
- colour designation (international and/or company code);
- nominal gloss value;

f) the type and the design of embossing, when required;

g) any requirements for inspection documents;

h) any special requirements for packing:

- mass per coil and per packing unit;
- number of sheets per stack;
- position of coil axis (vertical or horizontal);
- design of pallet;
- direction of winding;

STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1396:2015

<https://standards.iteh.ai/catalog/standards/sist/1d409745-90b3-4557-a700-f82f018f5f9a/sist-en-1396-2015>

Optional information to be mentioned in the order:

i) the form and type of product:

- the purchaser application;

j) the number of this European Standard, i.e. EN 1396, or a specification number, or, where none exists, the properties agreed between manufacturer and purchaser;

- the quantity

k) quantity tolerances if required;

1) If the surface is likely to be damaged during transportation, storage, processing or erection, the coil coated material may, on agreement, be supplied with the additional protection of a temporary strippable film. Type, thickness, adhesion properties, formability, tear strength and light fastness are to be taken into consideration when choosing protective films. Only certain protective films can be exposed to outdoor weathering, and these only for a limited period.