
**Aeronavtika - Kislinsko luženje aluminija in aluminijske zlitine brez
heksavalentnega kroma**

Aerospace series - Acid pickling of aluminum and aluminum alloy without hexavalent chromium

Luft- und Raumfahrt - Beizen von Aluminium und Aluminiumlegierungen ohne sechswertiges Chrom

Série aérospatiale - Décapage acid de l'aluminium et des alliages d'aluminium sans chrome hexavalent

<https://standards.iteh.ai/catalog/standards/sist/c24e5714-75d2-4244-bf44-35a9bdc7111c/sist-en-4707-2014>

Ta slovenski standard je istoveten z: EN 4707:2014

ICS:

25.220.20	Površinska obdelava	Surface treatment
49.025.20	Aluminij	Aluminium

SIST EN 4707:2014**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4707:2014

<https://standards.iteh.ai/catalog/standards/sist/c24e5714-75d2-4244-bf44-35a9bdc7111c/sist-en-4707-2014>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 4707

April 2014

ICS 25.220.20; 49.025.20

English Version

Aerospace series - Acid pickling of aluminum and aluminum alloy without hexavalent chromium

Série aérospatiale - Décapage acid de l'aluminium et des alliages d'aluminium sans chrome hexavalent

Luft- und Raumfahrt - Beizen von Aluminium und Aluminiumlegierungen ohne sechswertiges Chrom

This European Standard was approved by CEN on 27 December 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

SIST EN 4707:2014

<https://standards.iteh.ai/catalog/standards/sist/c24e5714-75d2-4244-bf44-35a9bdc7111c/sist-en-4707-2014>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Purpose of process	4
3 Normative references	4
4 Information for the processor	4
5 Condition of parts prior to processing.....	5
6 Process schedule	5
7 Pre-treatments.....	6
8 Treatment.....	6
9 Rinsing.....	7
10 Drying.....	7
11 Required characteristics and inspection	7
11.1 Parts	7
11.1.1 Inspection before treatment	7
11.1.2 Cleanliness	7
11.1.3 Inspection after treatment	7
11.2 Process	7
12 Quality assurance	8
12.1 Approval of the processor	8
12.2 Process approval	8
12.3 Acceptance	8
13 Health, safety and environmental aspects	8
Annex A (normative) Pickling bath.....	9

Foreword

This document (EN 4707:2014) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2014, and conflicting national standards shall be withdrawn at the latest by October 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4707:2014

<https://standards.iteh.ai/catalog/standards/sist/c24e5714-75d2-4244-bf44-35a9bdc7111c/sist-en-4707-2014>

EN 4707:2014 (E)**1 Scope**

This standard specifies the acid pickling of aluminium and aluminium alloys.

It is applicable whenever referenced.

2 Purpose of process

- 2.1** Pre-treatment before penetrant testing/penetrant inspection.
- 2.2** Pre-treatment before anodizing.
- 2.3** Final treatment for parts prior to adhesive bonding application.
- 2.4** Final treatment before welding or brazing.
- 2.5** Pre-treatment before chemical milling.
- 2.6** Final treatment for parts prior to painting application.
- 2.7** Pre-treatment for parts prior to surface conversion coatings.
- 2.8** Desmutting (Blanchiment), after alkaline etching or acid pickling.

3 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

<https://standards.iteh.ai/catalog/standards/sist/c24e5714-75d2-4244-bf44-35c9bde7111b/sist-en-4707-2014>

EN 9100, *Quality Management Systems - Requirements for Aviation, Space and Defense Organizations*

4 Information for the processor

- Designation;
- Number of the material standard and metallurgical condition of the latter;
- Sequence of operations;
- Areas to be processed;
- Treatment.

5 Condition of parts prior to processing

Fabrication of the parts shall have been completed before pickling.

Toolings:

Toolings, fixturings, and metal tooling masking must be protected from the corrosion and/or free from corrosion or another deterioration prejudicial to the treatment during their use.

Design of the toolings and racking must be achieved in order to:

- avoid any retention of air or solution on the parts,

- allow the neutralisation and the suppression of the solutions during rinsing operations,
- avoid any accidental contact during treatment between parts and tank equipments, and between various parts.

Tanks and rackings:

Materials used must be resistant to temperature and chemically compatible with the products involved in the sequence of operations.

6 Process schedule

The pickling process shall be performed according to Table 1.

Table 1

Process schedule		Post Pickling processes							
		Penetrant testing/ penetrant inspection	Anodizing	Adhesive bonding application	Welding Or brazing	Preparation before masking for chemical milling	Painting application	Surface conversion coatings	Desmutting , after etching or pickling
Pre-treatments – Clause 7		Applicable	Applicable	Applicable	Applicable	Not applicable	Applicable	Applicable	Applicable
Pickling – Clause 8		Applicable	Applicable	Applicable	Applicable	Applicable	Applicable	Applicable	Applicable
Post-treatments	Rinsing	Applicable	Applicable	Applicable	Applicable	Applicable	Applicable	Applicable	Applicable
	Drying	Applicable	Not applicable	Applicable	Applicable	Applicable	Applicable	Not applicable	Not applicable
Post pickling maximum lead-time		< 16 h ^a	Immediately in process	< 8 h	< 8 h ^a	< 8 h ^a or Immediately in process	< 16 h ^a	Immediately in process	Immediately in process
^a Recommended (in case of over lead time an appropriate storage and visual inspection (according 11.1) should be carried out before and after the post pickling process).									

7 Pre-treatments

Heavily soiled/Polluted parts shall be emulsion cleaned, vapour degreased or solvent cleaned.

If there is a significant natural oxide film (ex.: laminated parts or oxidized parts), carry out abrasive blasting or chemical deoxidizing.

Sequence of operations

1) Pre-degreasing:

- alkaline degreasing (with rinsings);
- or solvent;
- or vapour solvent.

EN 4707:2014 (E)

NOTE If necessary (laminated parts / oxidized parts), do a chemical deoxidizing (with rinsings) or abrasive blasting after pre-degreasing.

2) A second alkaline degreasing shall be performed after pre-degreasing, if necessary.

The alkaline degreasing shall be:

- corrosion inhibited;
- preferably of a non-silicated type (especially for dye penetrant inspection).

Generally alkaline solutions with pH between 9 and 11 are considered as a degreasing-etching solutions, whereas those with pH between 7 and 9, are considered only as a degreasing solution.

For the parts to be bonded, a non-silicated alkaline solution is mandatory.

3) After alkaline degreasing/cleaning, the parts shall be thoroughly water rinsed and inspected for water break. Cleaning shall be repeated if break occurs.

8 Treatment

Immediately after pre-treatments, the parts shall be pickled in one of the solutions specified below.

To ensure a well pickled surface, excessive bath loading and shielding of parts by each other shall be avoided:

Type of substances that can be used in pickling:

- Nitric or sulfonitric;
- Phosphosulfonitric;
- Sulfonitro-ferric fluoride free;
- Sulfonitro-ferric with fluoride.

9 Rinsing

After each treatment bath, water rinsing is mandatory. This operation has to be composed by at least one recycled rinsing. Recycled rinsing is generally completed by non-recycled or low-flow rate rinsing. Several quality of rinsing water can be used but the water used before surface treatment (see Table 1) rinsing shall have a conductivity not more than 70 $\mu\text{S}/\text{cm}$.

Rinsing shall be carried out consecutively to the pickling step in running water with a temperature not exceeding 40 °C.

10 Drying

The parts shall be dried except for those submitted for subsequent chemical treatment, anodic treatment or desmutting/chemical conversion ...

The temperature shall not exceed 80 °C.

After drying, parts shall be protected against contamination.

In case of bonding and paint applications, parts shall be stored under clean, dry conditions.

11 Required characteristics and inspection

11.1 Parts

11.1.1 Inspection before treatment

By visual inspection, make sure that the parts to be protected/treated are free from defects such as: scratches, corrosion pits, cracks ... prejudicial to the aspect or the effectiveness of protection. Adherent chips and metal particles must be removed beforehand using a clean cloth.

11.1.2 Cleanliness

During the degreasing phases, each rinsing operation must be followed by a water break test in order to evaluate the wettability (and the cleanliness) of the surfaces.

This test consists of covering the parts with a uniform water film. This water film must cover the parts for at least 30 s without any discontinuity in the film. Otherwise, degreasing phases have to be repeated.

11.1.3 Inspection after treatment

When subjected to visual inspection, the pickled surfaces shall be of a homogeneous appearance and free from pitting, stains and contamination.

11.2 Process

11.2.1 Air used for drying or other operations shall be substantially dry and free from oil.

11.2.2 Chemical analysis of the pickling solutions (and different baths involved in the sequence of operations) shall be carried out at regular intervals to determine the content of heavy metal, chloride, iron copper etc., when requested.

<https://standards.iteh.ai/catalog/standards/sist/c24e5714-75d2-4244-bf44-35a9bdc71111/sist-en-4707-2014>

11.2.3 The bath shall be discarded when pitting of parts occurs or when solid material starts to precipitate on cooling the solution to ambient temperature. The process must be managed by monitoring the significant parameters as aluminium and pollutant contents.

11.2.4 The purity of the rinsing water shall be determined by conductivity/resistivity measurements.

11.2.5 When required for adhesive bonding, the test to the relevant bonding standard shall be carried out to ensure that the process has been correctly applied.

11.2.6 Each pickling process must be characterized by its specific etching rate range. All pickling process must not lead to localized attack.

11.2.7 The etching rate of the complete sequence of operations must be periodically measured to ensure the control of the process.

NOTE The etching rate and maximum dipping time cannot be generally specified but has to be specified according to final customer requirements.

12 Quality assurance

12.1 Approval of the processor

See EN 9100.