



Standard Specification for High-Yield-Strength, Quenched and Tempered Alloy Steel Plate, Suitable for Welding¹

This standard is issued under the fixed designation A 514/A514M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers quenched and tempered alloy steel plates of structural quality in thicknesses of 6 in. [150 mm] and under intended primarily for use in welded bridges and other structures.

NOTE 1—All grades are not available in a maximum thickness of 6 in. [150 mm]. See Table 1 for thicknesses available in each grade.

1.2 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X 3 of Specification A 6A 6/A/A 6M for information on weldability.

1.3 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

2. Referenced Documents

2.1 *ASTM Standards:*

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling²

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products³

E 112 Test Methods for Determining the Average Grain Size⁴

3. General Requirements for Delivery

3.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, and Ships.

Current edition approved Sept. 10, 2000. Published November 2000. Originally published as A 514 – 64. Last previous edition A 514/A 514M – 00.

² Annual Book of ASTM Standards, Vol 01.04.

³ Annual Book of ASTM Standards, Vol 01.03.

⁴ Annual Book of ASTM Standards, Vol 03.01.

A 6/A 6MA 6/A, for the ordered material, unless a conflict exists in which case this specification shall prevail.

4. Materials and Manufacture

4.1 The requirements for fine austenitic grain size in Specification A 6/A 6MA 6/A shall be met.

5. Heat Treatment

5.1 The material shall be heat treated by the manufacturer to conform to the tensile and hardness requirements of Table 2 by heating to not less than 1650°F [900°C], quenching in water or oil and tempering at not less than 1150°F [620°C]. The heat-treating temperatures shall be reported on the test certificates.

6. Chemical Composition

6.1 The heat analysis shall conform to the requirements prescribed in Table 1.

6.2 The steel shall conform on product analysis to the requirements as prescribed in Table 1, subject to the product analysis tolerances in Specification A 6A 6/A/A 6M.

7. Mechanical Properties

7.1 *Tension Test*—The material as represented by the tension test specimens shall conform to the tensile properties prescribed in Table 2.

7.2 *Hardness Test*—For plates $\frac{3}{8}$ in. [10 mm] and under in thickness, a Brinell hardness test may be used instead of tension testing each plate, in which case a tension test shall be made from a corner of each of two plates per lot. A lot shall consist of plates from the same heat and thickness, same prior condition and scheduled heat treatment and shall not exceed 15 tons [15 Mg] in weight [mass]. A Brinell hardness test shall be made on each plate not tension tested and shall meet the requirements shown in Table 2.

8. Number of Tests

8.1 Except as described in 7.2, one tension test shall be taken from a corner of each plate as heat treated. Plates wider than 24 in. [600 mm] shall be tested in the transverse direction