



Designation: C1589 – 05

# Standard Practice for Outdoor Weathering of Construction Seals and Sealants<sup>1</sup>

This standard is issued under the fixed designation C1589; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope

1.1 This practice describes outdoor exposure procedures to be used as part of a test designed to determine the weathering durability of building construction, seals and sealants.

NOTE 1—See Practice G24 for Exposures to Daylight Filtered Through Glass.

1.2 This practice is limited to the method by which the construction seals or sealants are exposed to outdoor weathering as part of a test program. It does not describe the test methods to be performed following the outdoor exposure. It is intended for specimens of any size and shape to be used in static or dynamic tests.

1.3 Means of evaluation of the effects of weathering will depend on the intended use for the test material.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

C717 Terminology of Building Seals and Sealants

E772 Terminology of Solar Energy Conversion

G7 Practice for Atmospheric Environmental Exposure Testing of Nonmetallic Materials

G24 Practice for Conducting Exposures to Daylight Filtered Through Glass

G84 Practice for Measurement of Time-of-Wetness on Surfaces Exposed to Wetting Conditions as in Atmospheric Corrosion Testing

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.40 on Weathering.

Current edition approved Jan. 1, 2005. Published January 2005. Originally approved in 2004. Last previous edition approved in 2004 as C1589-04. DOI: 10.1520/C1589-05.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

G113 Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials

G147 Practice for Conditioning and Handling of Nonmetallic Materials for Natural and Artificial Weathering Tests

G178 Practice for Determining the Activation Spectrum of a Material (Wavelength Sensitivity to an Exposure Source) Using the Sharp Cut-On Filter or Spectrographic Technique

## 3. Terminology

3.1 *Definitions*—Definitions are found in Terminologies C717, G113, and E772.

## 4. Significance and Use

4.1 Tests conducted in accordance with this practice are used to evaluate the stability of construction seals and sealant materials when they are exposed to outdoor weather conditions. The durability of seals and sealants in actual outdoor use can be very different depending on the location, because of differences in solar radiation, moisture, temperature, pollutants, and other factors. Sealant color may also affect durability.

4.2 The type, frequency and amount of movement of sealants varies with location and may affect durability. It cannot be assumed, therefore, that results from one exposure in a single location will be useful for determining durability in a different location. Exposures in several locations with different climates (for example, solar radiation, moisture, temperature, pollutants, biological and other factors) that represent a broad range of anticipated service conditions are recommended.

4.3 It is strongly recommended that control materials with known durability should be included with each exposure test. Control materials should be exposed along with the test specimens for the purpose of comparing the performance of test materials to the controls. It is preferable to use two control materials of similar composition and construction to the test specimens, one with relatively good durability and one with relatively poor durability. Unless otherwise specified, use at least three replicate specimens of each test and control material.

4.4 The results of short-term exposure tests can provide an indication of relative outdoor performance, but they shall not be used to predict the absolute long-term performance of a seal

or sealant material. The results of tests conducted for less than 12 months will depend on the particular season of the year in which they begin.

4.5 Because of year-to-year climatological variations, results from a single exposure test cannot be used to predict the absolute rate at which a seal or sealant degrades. Several years of repeat exposures are needed to get an average test result for a given location.

4.6 Climatic and construction factors can impose movement upon sealed joints in use. This movement can impact the effects of outdoor weathering. Consideration shall be given to the effect of movement when analyzing exposure results obtained on static specimens.

4.7 When combined with proper provision for natural or forced cyclic movement, this outdoor weathering procedure can also be used as an indicator of the ability of a seal or sealant to withstand climate influences and the stresses of cyclic movement.

## 5. Apparatus

5.1 The test site shall conform to the requirements of Practice G7. Unless otherwise specified, position exposure racks 45° relative to horizontal, facing the equator. The angle of exposure rack, and the orientation relative to the equator can vary depending upon the application and performance criteria that are being evaluated. Consult Practice G7 for information on other exposure rack angles.

### 5.2 Specimen Holders:

5.2.1 The specimens for most static tests under test will not be of an exact size for mounting directly onto the frame. Specimen holders shall be used to support the many sizes of specimens involved in this testing. In no case shall the specimen holder constitute a backing for that portion of the material to be evaluated.

5.2.2 The specimen holders shall be constructed of a material agreed upon by the mutual parties. Aluminum panels, glass, and marble shapes have been found suitable for static exposures.

5.2.3 The design of the specimen holders intended to induce or allow for cyclic movement (for example, testing rigs, manually adjusted vices, and fully automatic mechanical devices) shall be agreed upon by the mutual parties.

5.3 *Materials and Manner of Construction*—Test racks and hardware shall conform to the requirements of Practice G7 and shall provide for the attachment of specimens or holders of any convenient width and length. The structural members of the test racks shall not constitute a backing to the specimens under test. Fasteners used to attach specimens to the test rack shall provide for secure attachment but allow specimens to expand or contract with thermal changes, moisture absorption or desorption, or plasticizer loss.

### 5.4 Instruments for Measuring Climatological Data:

5.4.1 *Instruments Used to Measure Ambient Temperature and Relative Humidity*—Instrument and procedures used for measurement of ambient temperature and relative humidity shall be in accordance with Practice G7.

5.4.2 *Instruments Used to Measure Solar Radiation*—Instrument and calibration procedures used for measurement of total solar radiation, total solar ultraviolet radiation, or narrow band solar ultraviolet radiation shall be in accordance with Practice G7.

## 6. Preparation of Samples

6.1 Follow the manufacturer's instructions for mixing and/or preparing materials to be tested.

6.2 It is strongly recommended that control materials and test materials be of the same dimensions.

## 7. Test Specimen

7.1 Exposure test specimens may be of any size or shape that can be mounted in a fixture, a holder or applied directly to the racks. They may be specimens suited to the means of evaluating the effects of weathering on specific properties, or they may be larger specimens from which smaller specimens for evaluation may be cut. The exposure test specimens shall be large enough that mounting edges may be removed where evaluation test results would be otherwise affected.

7.2 As far as practical, exposure test specimens shall simulate those used in service conditions of an end-use application. When conditions of use are known, the specimen exposed will consist of seal or sealant material being evaluated plus suitable substrate or installation materials to conform to the projected practice. The effect of substrate or installation materials is highly significant and contributes to the degradation due to reflectance, heat absorption, moisture retention, etc.

7.3 The use of replicates of each experimental material being evaluated is required in order to allow for variability.

7.4 The total number of specimens will be determined by the removal schedule and number of replicates plus file specimens. These unexposed file specimens shall be retained at conditions of  $23.0 \pm 2^\circ\text{C}$  and  $50 \pm 20\%$  relative humidity. They shall be covered with inert opaque wrapping to exclude light during the storage period. Refer to Practice G147 for more information on specimen handling and conditioning.

## 8. Test Sites

8.1 Weathering racks shall be located in cleared areas, preferably at a suitable number of climatologically different sites representing the variable conditions under which the construction seal or sealant will be used. Climatological variations within these areas may include those represented by desert, seashore (salt air), industrial locations, tropical, and subtropical regions, plus areas exhibiting a wide range of in solar radiant energy. The area beneath and in the vicinity of the weathering racks shall be typical of the ground cover in that climatological area. In desert areas in which sand is the prevailing ground cover, coarse gravel is required to prevent abrasion and significant dust accretion due to wind-blown sand (Note 2). The ground cover shall be low-cut grass in most temperate, tropical, and subtropical areas.

NOTE 2—Sand as a ground cover may be desirable where the abrasive effects of exposure to wind-blown sand is a part of the desired exposure.