



Designation: C 1250 – 93 (Reapproved 2005)

Standard Test Method for Nonvolatile Content of Cold Liquid-Applied Elastomeric Waterproofing Membranes¹

This standard is issued under the fixed designation C 1250; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes a laboratory procedure for determining the average nonvolatile content for one- or two-component cold liquid-applied elastomeric waterproofing membranes.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards*:²
C 717 Terminology of Building Seals and Sealants

3. Terminology

3.1 *Definitions*—Refer to Terminology **C 717** for definitions of compound, elastomeric, and waterproofing, used in this test method.

4. Summary of Test Method

4.1 This test method consists of preparing duplicate samples, each of known mass, and aging these samples for 72 h at $70 \pm 2^\circ\text{C}$ ($158 \pm 3.6^\circ\text{F}$) in an air-circulating oven.

5. Significance and Use

5.1 This test method is used to determine the nonvolatile content of cold liquid-applied elastomeric waterproofing membranes and can be useful in determining application coverage rates.

6. Apparatus

- 6.1 *Forced-draft Oven*, controlled to $70 \pm 2^\circ\text{C}$ ($158 \pm 3.6^\circ\text{F}$).
6.2 *Balance*, sensitive to 0.01 g.
6.3 *Two Aluminum Weighing Dishes*, 57 by 18 mm.

7. Conditioning/Mixing

7.1 Unless otherwise specified by those authorizing the tests, standard conditions for all tests are $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 5\%$ relative humidity.

7.2 Store all membrane materials to be tested in an unopened container at standard conditions for at least 24 h before any test specimens are prepared.

7.3 Follow the manufacturer's instructions for mixing and preparing membrane materials for testing. Thoroughly mix one-component materials before using. Mix two-component compounds in the ratio recommended by the manufacturer.

8. Procedure

8.1 For each test sample, prepare two test specimens as follows:

8.1.1 Mark each aluminum weighing dish for identification. Accurately weigh each aluminum weighing dish to the nearest 0.01 g. Record each mass.

8.1.2 Place an aluminum weighing dish on the balance and tare. Add 5.0 ± 0.2 g of compound and spread evenly over the interior surface area of the dish.

8.1.3 Reweigh the test specimen, combination membrane, and dish, and record the mass.

8.1.4 Repeat 8.1.2 and 8.1.3 for duplicate specimens.

8.1.5 Immediately place the dishes in a forced-draft oven for 72 h at $70 \pm 2^\circ\text{C}$ ($158 \pm 3.6^\circ\text{F}$).

8.1.6 Remove the specimens and allow them to cool at standard conditions for 30 min. Weigh the specimens and calculate the percent nonvolatile as follows:

$$\text{nonvolatile, \%} = [(W_3 - W_1)/(W_2 - W_1)] \times 100 \quad (1)$$

where:

- W_1 = mass of aluminum weighing dish,
 W_2 = mass of aluminum dish with fresh compound, and
 W_3 = mass of heat-aged dish and compound.

¹ This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.80 on Building Deck Waterproofing Systems.

Current edition approved Jan. 1, 2005. Published January 2005. Originally approved in 1993. Last previous edition approved in 1998 as C 1250-93(1998).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.