



**SLOVENSKI STANDARD**  
**SIST EN 4492:2014**

**01-februar-2014**

---

**Aeronavtika - Nekovinski materiali - Anaerobne polimerizirajoče zmesi -  
Zavarovanje vijakov - Navorna trdnost 19 Nm**

Aerospace series - Non-metallic materials - Anaerobic polymerisable compounds -  
Threadlocking - Torque strength 19 Nm

Luft- und Raumfahrt - Nichtmetallische Werkstoffe - Anaerobe polymerisierbare  
Klebstoffe - Schraubensicherung - Torsionsfestigkeit 19 Nm

Série aérospatiale - Matériaux non-métalliques - Composé polymérisable anaérobie -  
Agent de freinage - Résistance au couple de torsion 19 Nm

[https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-](https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-d7578d41b21f/sist-en-4492-2014)

**Ta slovenski standard je istoveten z: EN 4492:2013**

---

**ICS:**

49.025.50      Lepila

Adhesives

**SIST EN 4492:2014**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 4492:2014

<https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-d7578d41b21f/sist-en-4492-2014>

EUROPEAN STANDARD

EN 4492

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2013

ICS 49.025.50

English Version

## Aerospace series - Non-metallic materials - Anaerobic polymerisable compounds - Threadlocking - Torque strength 19 Nm

Série aérospatiale - Matériaux non-métalliques - Composé polymérisable anaérobie - Agent de freinage - Résistance au couple de torsion 19 Nm

Luft- und Raumfahrt - Nichtmetallische Werkstoffe - Anaerobe polymerisierbare Klebstoffe - Schraubensicherung - Torsionsfestigkeit 19 Nm

This European Standard was approved by CEN on 10 November 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

**Contents**

Page

Foreword.....	3
Introduction .....	4
1 <b>Scope</b> .....	5
2 <b>Normative references</b> .....	5
3 <b>Terms, definitions, symbols and abbreviations</b> .....	5
4 <b>Requirements</b> .....	6

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 4492:2014

<https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-d7578d41b21f/sist-en-4492-2014>

## Foreword

This document (EN 4492:2013) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2013, and conflicting national standards shall be withdrawn at the latest by July 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 4492:2014

<https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-d7578d41b21f/sist-en-4492-2014>

## Introduction

This standard is part of a series of EN non-metallic materials standards for aerospace applications. The general organisation of this series is described in EN 4385. This standard is a level 3 document as defined in EN 4385. It has been prepared in accordance with TR 7000-7.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 4492:2014](https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-d7578d41b21f/sist-en-4492-2014)

<https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-d7578d41b21f/sist-en-4492-2014>

## 1 Scope

This European Standard specifies the requirements relating to anaerobic polymerisable threadlocking compounds having a torque strength of 19 Nm for aerospace applications.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 3792, *Aerospace series — Anaerobic polymerisable compounds — Technical specification* <sup>1)</sup>

EN 4385, *Aerospace series — Non-metallic materials — General organisation of standardisation — Links between types of standards* <sup>1)</sup>

TR 7000-7, *Aerospace series — Non-metallic materials — Rules for drafting and presentation of material standards — Part 7: Anaerobic polymerisable compounds* <sup>2)</sup>

## 3 Terms, definitions, symbols and abbreviations

### 3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1.1 Definition of subcase numbering

<https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-47578411b216/sist-en-4492-2014>

In the column “requirement” at the left hand side a subcase number is given. The definition of these subcase numbers is as follows:

Subcase number	Definition
–	Technical specification
1	Test method
2	Frequency of testing
3	Sample type
4	Test piece definition
5	Condition of test piece
6	Testing condition
7	Acceptance criteria

Note 1 to entry: The absence of a subcase indicates that the necessary information is given in Table 1 of this standard, e.g. in the reference to the technical standard (characteristic 1.004).

1) Published as ASD-STAN Prestandard at the date of publication of this standard ([www.asd-stan.org](http://www.asd-stan.org)).

2) Published as ASD-STAN Technical Report at the date of publication of this standard ([www.asd-stan.org](http://www.asd-stan.org)).

**EN 4492:2013 (E)**

All the necessary information which does not appear is to be found in the referenced technical specification or the relevant test method.

Note 2 to entry: In this material standard, batch acceptance test titles and subcases 7 acceptance criteria are highlighted in the form of a bold frame and bold characters to show that they are mandatory for routine acceptance of the material.

**3.1.2 Other definitions**

See EN 3792.

**3.2 Symbols and abbreviations**

See EN 3792.

**4 Requirements**

The required characteristics are given in:

- Table 1 — General requirements
- Table 2 — Requirements in the delivery condition
- Table 3 — Requirements as processed to characteristic number 1.013
- Table 4 — Environmental testing requirements as processed to characteristic number 1.013

**Table 1 — General requirements**

Characteristic number	Characteristic	Requirements
1.001	Material description	One part, threadlocking, anaerobic polymerisable compound
1.002	Formulation	Acrylic ester of a polyhydroxy compound
1.003	Form and method of production	Liquid
1.004	Technical specification	See EN 3792.
1.005	Grade	– 01      – 02      – 03      – 04
1.007	Colour	<sup>a</sup>
1.010	Storage	Temperature < 25 °C, out of direct sunlight and in the presence of oxygen
1.011	Shelf life	Not less than 12 m under storage conditions
1.013	Processing condition	At least 24 h at (23 ± 2) °C
1.093	Quality assurance	See EN 3792.
1.094	Designation	See EN 4492 plus Grade.
1.097	Flashpoint	> 100 °C
1.098	Health and safety	See EN 3792.
1.999	Notes	<sup>a</sup> Colour to be agreed between purchaser and supplier.



Table 2 — Requirements in the delivery condition

Characteristic number	Characteristic		Requirements				
2.007	Visual inspection	7	Correct colour (see Table 1)				
2.106	Cure rate	7	> 4 min				
2.106	Reactivity in contact with zinc	7	< 30 min				
2.106	Gel time – stability at 100 °C	7	> 10 min				
2.107	Viscosity	7	Grade	– 01	– 02	– 03	
			mm <sup>2</sup> s <sup>-1</sup>	< 50	125 ± 25	500 ± 250	
	Viscosity	7	Grade				– 04
			mPa.s at 20 rpm				8 ± 3
			mPa.s at 2 rpm				70 ± 15
Thixotropic index	7	Grade				– 04	
						8 ± 2	
2.111	Fluorescence	7	Shall fluoresce				

SIST EN 4492:2014

<https://standards.iteh.ai/catalog/standards/sist/a7353964-6b60-4889-95c4-d7578d41b211/sist-en-4492-2014>  
 Table 3 — Requirements as processed to characteristic number 1.013

Characteristic number	Characteristic		Requirements	
3.310	Static shear strength	7	MPa	> 17
3.315	Torque strength	7	Nm	> 19