



SLOVENSKI STANDARD

SIST EN 13108-6:2016

01-november-2016

Nadomešča:

SIST EN 13108-6:2006

SIST EN 13108-6:2006/AC:2008

Bitumenske zmesi - Specifikacije materialov - 6. del: Liti asfalt

Bituminous mixtures - Material specifications - Part 6: Mastic Asphalt

Asphaltmischgut - Mischgutanforderungen - Teil 6: Gussasphalt

Mélanges bitumineux - Spécifications des matériaux - Partie 6: Asphalt coulé routier

Ta slovenski standard je istoveten z: EN 13108-6:2016

[SIST EN 13108-6:2016](https://standards.iteh.ai/catalog/standards/sist/en-13108-6-2016)

<https://standards.iteh.ai/catalog/standards/sist/en-13108-6-2016>

ICS:

93.080.20 Materiali za gradnjo cest Road construction materials

SIST EN 13108-6:2016

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13108-6:2016

<https://standards.iteh.ai/catalog/standards/sist/67da9c53-5d32-43b7-bae6-ad738bcbafaf/sist-en-13108-6-2016>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13108-6

June 2016

ICS 93.080.20

Supersedes EN 13108-6:2006

English Version

**Bituminous mixtures - Material specifications - Part 6:
Mastic Asphalt**

Mélanges bitumineux - Spécifications pour le matériau
- Partie 6: Asphaltes coulés routiers

Asphaltnischgut - Mischgutanforderungen - Teil 6:
Gussasphalt

This European Standard was approved by CEN on 27 February 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/67da9c53-5d32-43b7-bae6-ad738bcbafaf/sist-en-13108-6-2016>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

| | Page |
|---------------------------------------------------------------------------------------------------------------------------------------------------|-----------|
| European foreword..... | 4 |
| Introduction | 6 |
| 1 Scope | 7 |
| 2 Normative references | 7 |
| 3 Terms and definitions, symbols and abbreviations | 8 |
| 3.1 Terms and definitions | 8 |
| 3.2 Symbols and abbreviations | 10 |
| 4 Requirements for constituent materials | 10 |
| 4.1 General..... | 10 |
| 4.2 Binder..... | 11 |
| 4.2.1 General..... | 11 |
| 4.2.2 Selection of Binder..... | 11 |
| 4.2.3 Mixes with reclaimed asphalt..... | 11 |
| 4.3 Aggregates | 12 |
| 4.3.1 Coarse aggregate | 12 |
| 4.3.2 Fine aggregate | 12 |
| 4.3.3 All-in aggregates..... | 12 |
| 4.3.4 Added filler..... | 12 |
| 4.4 Reclaimed asphalt..... | 12 |
| 4.5 Additives..... | 12 |
| 5 Requirements for the mixture..... | 13 |
| 5.1 General..... | 13 |
| 5.2 Composition, grading, binder content..... | 13 |
| 5.2.1 Composition | 13 |
| 5.2.2 Grading..... | 13 |
| 5.2.3 Minimum binder content | 15 |
| 5.3 Properties | 16 |
| 5.3.1 Specimens | 16 |
| 5.3.2 Indentation and resistance to permanent deformation | 16 |
| 5.3.3 Low temperature properties | 19 |
| 5.3.4 Coating and homogeneity..... | 20 |
| 5.3.5 Reaction to fire..... | 20 |
| 5.3.6 Resistance to fuel for application on airfields | 20 |
| 5.3.7 Resistance to de-icing fluid for application on airfields | 21 |
| 5.4 Temperature of the mixture | 21 |
| 5.5 Regulated dangerous substances | 22 |
| 6 Assessment and verification of constancy of performance — AVCP | 22 |
| 7 Identification | 22 |
| Annex A (normative) Calculations of the penetration or the softening point of the binder of a mixture when reclaimed asphalt is used | 24 |
| A.1 General..... | 24 |
| A.2 Calculation of the penetration of the binder of a mixture..... | 24 |

| | | |
|-------------------------------------------------------------------------------------------|---------------------------------------------------------------------------|-----------|
| A.3 | Calculation of the softening point of the binder of a mixture..... | 24 |
| Annex ZA (informative) Relationship of this European Standard with Regulation (EU) | | |
| | No. 305/2011 | 26 |
| ZA.1 | Scope and relevant characteristics | 26 |
| ZA.2 | Procedure for AVCP of Mastic Asphalt | 28 |
| ZA.3 | Assignment of AVCP tasks | 28 |
| | Bibliography | 32 |

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

SIST EN 13108-6:2016

<https://standards.iteh.ai/catalog/standards/sist/67da9c53-5d32-43b7-bae6-ad738bcbaaf/sist-en-13108-6-2016>

EN 13108-6:2016 (E)**European foreword**

This document (EN 13108-6:2016) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2016, and conflicting national standards shall be withdrawn at the latest by March 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13108-6:2006.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) No 305/2011 for construction products (CPR).

For relationship with Regulation (EU) No 305/2011 see informative Annex ZA which is an integral part of this European Standard.

Compared with EN 13108-6:2006, the following changes have been made:

- STANDARD PREVIEW**
(standards.iteh.ai)
- SIST EN 13108-6:2016
<https://standards.iteh.ai/catalog/standards/sist/67da9c95-5d32-43b7-bac6-ad738bcbafaf/sist-en-13108-6-2016>
- a) new property introduced (low temperature properties);
 - b) additional optional sieves for the characterization of the grading;
 - c) for several properties additional categories are introduced;
 - d) possibility to define specific conditions in documents related to the application of the product;
 - e) CPR reference and new Annex ZA according to CPR rules.

This European Standard is one of a series as listed below:

- EN 13108-1, *Bituminous mixtures — Material specifications — Part 1: Asphalt Concrete*
- EN 13108-2, *Bituminous mixtures — Material specifications — Part 2: Asphalt Concrete for Very Thin Layers (BBTM)*
- EN 13108-3, *Bituminous mixtures — Material specifications — Part 3: Soft Asphalt*
- EN 13108-4, *Bituminous mixtures — Material specifications — Part 4: Hot Rolled Asphalt*
- EN 13108-5, *Bituminous mixtures — Material specifications — Part 5: Stone Mastic Asphalt*
- EN 13108-6, *Bituminous mixtures — Material specifications — Part 6: Mastic Asphalt*
- EN 13108-7, *Bituminous mixtures — Material specifications — Part 7: Porous Asphalt*
- EN 13108-8, *Bituminous mixtures — Material specifications — Part 8: Reclaimed Asphalt*

- EN 13108-9, *Bituminous mixtures — Material specifications — Part 9: Asphalt for Ultra-Thin Layer (AUTL)*
- EN 13108-20, *Bituminous mixtures — Material specifications — Part 20: Type Testing*
- EN 13108-21, *Bituminous mixtures — Material specifications — Part 21: Factory Production Control*

Annex A (normative) details the calculation of the penetration or the softening point in mixtures containing reclaimed asphalt from the penetrations or softening points of the added binder and the recovered binder from the reclaimed asphalt.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13108-6:2016](https://standards.iteh.ai/catalog/standards/sist/67da9c53-5d32-43b7-bae6-ad738bcbaaf/sist-en-13108-6-2016)

<https://standards.iteh.ai/catalog/standards/sist/67da9c53-5d32-43b7-bae6-ad738bcbaaf/sist-en-13108-6-2016>

Introduction

The aim of this European Standard is to enable specification of Mastic Asphalt mixtures on a performance basis. In general, however, there are currently more empirical tests available to describe the mixtures. The standard for Mastic Asphalt has only empirical requirements.

This European Standard covers a large variety of materials for different applications, traffic and climate conditions. EN 13108-6 gives properties and listings of possible categories. It has to accommodate the road industry for all of Europe. For this reason the menu approach for properties has been chosen. The tables represent categories that are required all over Europe. For this reason numerical values in tables do not always obey statistical rules. Based on conditions of use specific properties and categories may be defined in documents related to the application of the product. The categories defined in those documents need to take into account the reproducibility of the test when this is given in the appropriate test method.

Care should be taken to only select those tests which are relevant to the application of the asphalt and the use of the pavement and to avoid a combination of potentially conflicting requirements.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 13108-6:2016

<https://standards.iteh.ai/catalog/standards/sist/67da9c53-5d32-43b7-bae6-ad738bcbafaf/sist-en-13108-6-2016>

1 Scope

This European Standard specifies requirements for mixtures of the mix group Mastic Asphalt for use on roads, airfields and other trafficked areas. Mastic Asphalt is used for surface courses, binder courses, protection layers and inter-layers for bridges, tunnels and troughs.

The mixtures of the mix group Mastic Asphalt are produced on the basis of hot bitumen. Mixtures utilizing bitumen emulsion and bituminous materials based on *in situ* recycling are not covered by this standard.

This European Standard includes requirements for the selection of the constituent materials. It is designed to be read in conjunction with EN 13108-20 and EN 13108-21.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1097-6:2013, *Tests for mechanical and physical properties of aggregates — Part 6: Determination of particle density and water absorption*

EN 1426, *Bitumen and bituminous binders — Determination of needle penetration*

EN 1427, *Bitumen and bituminous binders — Determination of the softening point — Ring and Ball method*

EN 12591, *Bitumen and bituminous binders — Specifications for paving grade bitumens*

EN 12697-3, *Bituminous mixtures — Test methods for hot mix asphalt — Part 3: Bitumen recovery: Rotary evaporator*

EN 12697-13, *Bituminous mixtures — Test methods for hot mix asphalt — Part 13: Temperature measurement*

EN 12697-20, *Bituminous mixtures — Test methods for hot mix asphalt — Part 20: Indentation using cube or cylindrical specimens (CY)*

EN 12697-21, *Bituminous mixtures — Test methods for hot mix asphalt — Part 21: Indentation using plate specimens*

EN 12697-25, *Bituminous mixtures — Test methods for hot mix asphalt — Part 25: Cyclic compression test*

EN 12697-41, *Bituminous mixtures — Test methods for hot mix asphalt — Part 41: Resistance to de-icing fluids*

EN 12697-43, *Bituminous mixtures — Test methods for hot mix asphalt — Part 43: Resistance to fuel*

EN 12697-46, *Bituminous mixtures — Test methods for hot mix asphalt — Part 46: Low temperature cracking and properties by uniaxial tension tests*

EN 13043, *Aggregates for bituminous mixtures and surface treatments for roads, airfields and other trafficked areas*

EN 13108-6:2016 (E)

EN 13108-4:2016, *Bituminous mixtures — Material specifications — Part 4: Hot Rolled Asphalt*

EN 13108-8, *Bituminous mixtures — Material specifications — Part 8: Reclaimed asphalt*

EN 13108-20:2016, *Bituminous mixtures — Material specifications — Part 20: Type Testing*

EN 13108-21, *Bituminous mixtures — Material specifications — Part 21: Factory Production Control*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13924-1, *Bitumen and bituminous binders — Specification framework for special paving grade bitumen — Part 1: Hard paving grade bitumens*

EN 14023, *Bitumen and bituminous binders — Specification framework for polymer modified bitumens*

EN ISO 11925-2, *Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2)*

3 Terms and definitions, symbols and abbreviations

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

pavement

structure, composed of one or more courses, to assist the passage of traffic over terrain

3.1.2

layer

element of a pavement laid in a single operation

3.1.3

course

element of a pavement constructed with a single material

Note 1 to entry: A course can be laid in one or more layers.

3.1.4

surface course

upper course of a pavement, which is in contact with the traffic

3.1.5

binder course

structural course of a pavement between the surface course and the base

3.1.6

regulating course

course of variable thickness applied to an existing course to provide the necessary profile for a further course of consistent thickness

3.1.7**base**

main structural element of a pavement

Note 1 to entry: The base can be laid in one or more courses, described as “upper“ base, “lower“ base

3.1.8**asphalt**

homogenous mixture of coarse and fine aggregates, filler aggregate and bituminous binder which is used in the construction of a pavement

Note 1 to entry: Asphalt can include one or more additives to enhance the laying characteristics, performance or appearance of the mixture.

3.1.9**natural asphalt**

naturally occurring mixture of bitumen and finely divided mineral matter which is found in well-defined surface deposits and which is processed to remove unwanted components such as water and vegetable matter

Note 1 to entry: Natural asphalt is described in EN 13108-4.

3.1.10**Mastic Asphalt**

voidless asphalt mixtures with bitumen as a binder in which the volume of filler and binder fills the volume of the remaining voids in the mix

3.1.11**mix formulation**

composition of a single mixture expressed as a target composition

Note 1 to entry: A target composition is expressed in one of two ways (see 3.1.12 and 3.1.13).

3.1.12**input target composition**

expression of a mix formulation in terms of the constituent materials, the grading curve and the percentage of binder added to the mixture

Note 1 to entry: This will usually be the result of a laboratory mix design and validation.

3.1.13**output target composition**

expression of a mix formulation in terms of the constituent materials and the mid point grading and soluble binder content to be found on analysis

Note 1 to entry: This will usually be the result of a production validation.

3.1.14**additive**

constituent material that can be added in small quantities to influence specific properties of the mixture

Note 1 to entry: For example additives are used to influence the affinity of binder to aggregate, and the mechanical properties when using inorganic and organic fibres and polymers. They are also used to influence the colour of the mixture.

EN 13108-6:2016 (E)**3.1.15****conflicting requirements**

combination of requirements or properties which are impracticable to fulfil in their entirety

Note 1 to entry: This can occur by combining specific requirements for the composition and constituent materials together with more performance related tests. These are also relevant when two or more performance or test parameters are selected which measure similar properties using conflicting test methods resulting in a lack of clarity and consistency in the characteristics of the mixture.

3.1.16**premixed binder**

bitumen which is blended on the site of the asphalt mixing plant, with an additive before or during the addition of the binder to the plant mixer, which in the case of a continuous plant, will be before or during the delivery of the binder to the mixing zone of the drier drum

3.1.17**category**

defined level of a property of an asphalt mixture

Note 1 to entry: The designation of a category is expressed with a symbol and a numerical value representing the level.

EXAMPLE $B_{\min} 7,0$ means that the minimum binder content shall be 7,0 %.

Note 2 to entry: Defined categories for each property are listed in EN 13108-6.

3.1.18**class**

range of levels delimited by a minimum and a maximum value

3.2 Symbols and abbreviations

MA general designation of Mastic Asphalt

MA *D* designation of Mastic Asphalt followed by an indication of *D*, the upper sieve size of the aggregate in the mixture, in millimetres (mm)

EXAMPLE MA 11 Mastic Asphalt with an upper sieve size of the aggregate of 11 mm.

4 Requirements for constituent materials**4.1 General**

Only constituent materials with established suitability shall be used. For all constituent materials the properties relevant to the performance of the mixture shall be made available.

The establishment of suitability shall result from one or more of the following:

- European Standard;
- European Technical Assessment;