

**SLOVENSKI STANDARD**  
**kSIST-TS FprCEN/TS 17195:2018**  
**01-januar-2018**

---

**Gradbeni proizvodi - Ocenjevanje sproščanja nevarnih snovi - Analiza anorganskih snovi v izlužkih**

Construction Products - Assessment of release of dangerous substances - Analysis of inorganic substances in eluates

Bauprodukte - Bewertung der Freisetzung von gefährlichen Stoffen - Analyse von anorganischen Stoffen in Eluaten

Produits de construction □ Evaluation de l'émission de substances dangereuses □  
Analyse des substances inorganiques dans les éluats

**Ta slovenski standard je istoveten z: FprCEN/TS 17195**

SIST-TS CEN/TS 17195:2019

<https://standards.iteh.ai/catalog/standards/sist/89f30ce2-d892-467c-a960-893cf4021a39/sist-ts-cen-ts-17195-2019>

**ICS:**

13.020.99	Drugi standardi v zvezi z varstvom okolja	Other standards related to environmental protection
91.100.01	Gradbeni materiali na splošno	Construction materials in general

**kSIST-TS FprCEN/TS 17195:2018**

**en,fr,de**



TECHNICAL SPECIFICATION  
SPÉCIFICATION TECHNIQUE  
TECHNISCHE SPEZIFIKATION

**FINAL DRAFT**  
**FprCEN/TS 17195**

November 2017

ICS 91.100.01

English Version

**Construction products: Assessment of release of  
dangerous substances - Analysis of inorganic substances in  
eluates**

Produits de construction - Evaluation de l'émission de  
substances dangereuses - Analyse des substances  
inorganiques dans les éluats

Bauprodukte - Bewertung der Freisetzung von  
gefährlichen Stoffen - Analyse von anorganischen  
Stoffen in Extrakten und Eluaten

This draft Technical Specification is submitted to CEN members for Vote. It has been drawn up by the Technical Committee CEN/TC 351.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning :** This document is not a Technical Specification. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a Technical Specification.

SIST-TS CEN/TS 17195:2019

<https://standards.iteh.ai/catalog/standards/sist/89f30ce2-d892-467c-a960-893cf4021a39/sist-ts-cen-ts-17195-2019>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

European foreword.....	3
Introduction .....	4
1 Scope .....	5
2 Normative references .....	5
3 Terms and definitions .....	6
4 Abbreviations .....	8
5 Sample pre-treatment .....	8
6 Selection of suitable analytical test method.....	9
6.1 Table of test methods .....	9
6.2 General validation information .....	9
7 Method performance .....	11
8 Expression of results.....	11
9 Test report.....	11
10 Test performance.....	12
Annex A (informative) Validation of analytical methods for eluates of waste .....	13
A.1 General.....	13
A.2 Interlaboratory study.....	13
Annex B (informative) Additional validation data for Ba, Cd, Cr, Mo, Sb and Se in eluates using hydride generation.....	19
B.1 General.....	19
B.2 Round robin samples.....	19
B.3 Results of the round robin test.....	20
B.4 Conclusion from the round robin test .....	24
Bibliography.....	25

## European foreword

This document (FprCEN/TS 17195:2017) has been prepared by Technical Committee CEN/TC 351 “Construction products: Assessment of release of dangerous substances”, the secretariat of which is held by NEN.

This document is currently submitted to the Vote on TS.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

A similar standard has been developed for eluates from different types of waste, see Annex A.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[SIST-TS CEN/TS 17195:2019](https://standards.iteh.ai/catalog/standards/sist/89f30ce2-d892-467c-a960-893cf4021a39/sist-ts-cen-ts-17195-2019)

<https://standards.iteh.ai/catalog/standards/sist/89f30ce2-d892-467c-a960-893cf4021a39/sist-ts-cen-ts-17195-2019>

## Introduction

Following an extended evaluation of available methods for content analysis in construction products (CEN/TR 16045, [1]) it was concluded that eluate analysis methods are very similar to analytical methods used to determine content after digestion of a solid matrix.

This document has been adopted from the work carried out in the context of CEN/TC 292 and is very similar to EN 16192 *Characterization of waste – Analysis of waste eluates* [2].

This Technical Specification is part of a modular horizontal approach which was adopted in CEN/TC 351. 'Horizontal' means that the methods can be used for a wide range of materials and products with certain properties. 'Modular' means that a test standard developed in this approach concerns a specific step in assessing a property and not the whole chain of measurement (from sampling to analyses). Beneficial features of this approach are that modules can be replaced by better ones without jeopardizing the standard chain and duplication of work of in different Technical Committees for Products can be avoided as far as possible.

The modules that relate to the standards developed in CEN/TC 351 are specified in CEN/TR 16220 [3], which distinguishes between the modules. This Technical Specification belongs to the analytical step.

The use of modular horizontal standards implies the drawing of test schemes as well. Before executing a test on a certain construction product to determine certain characteristics it is necessary to draw up a protocol in which the adequate modules are selected and together form the basis for the entire test procedure.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[SIST-TS CEN/TS 17195:2019](https://standards.iteh.ai/catalog/standards/sist/89f30ce2-d892-467c-a960-893cf4021a39/sist-ts-cen-ts-17195-2019)

<https://standards.iteh.ai/catalog/standards/sist/89f30ce2-d892-467c-a960-893cf4021a39/sist-ts-cen-ts-17195-2019>

## 1 Scope

This Technical Specification specifies analytical methods for the determination of major, minor and trace elements and of anions in aqueous eluates from construction products. It refers to the following 67 elements:

Aluminium (Al), antimony (Sb), arsenic (As), barium (Ba), beryllium (Be), bismuth (Bi), boron (B), cadmium (Cd), calcium (Ca), cerium (Ce), cesium (Cs), chromium (Cr), cobalt (Co), copper (Cu), dysprosium (Dy), erbium (Er), europium (Eu), gadolinium (Gd), gallium (Ga), germanium (Ge), gold (Au), hafnium (Hf), holmium (Ho), indium (In), iridium (Ir), iron (Fe), lanthanum (La), lead (Pb), lithium (Li), lutetium (Lu), magnesium (Mg), manganese (Mn), mercury (Hg), molybdenum (Mo), neodymium (Nd), nickel (Ni), palladium (Pd), phosphorus (P), platinum (Pt), potassium (K), praseodymium (Pr), rubidium (Rb), rhenium (Re), rhodium (Rh), ruthenium (Ru), samarium (Sm), scandium (Sc), selenium (Se), silicon (Si), silver (Ag), sodium (Na), strontium (Sr), sulphur (S), tellurium (Te), terbium (Tb), thallium (Tl), thorium (Th), thulium (Tm), tin (Sn), titanium (Ti), tungsten (W), uranium (U), vanadium (V), ytterbium (Yb), yttrium (Y), zinc (Zn), and zirconium (Zr) and to the following four anions: Cl<sup>-</sup>, Br<sup>-</sup>, F<sup>-</sup>, SO<sub>4</sub><sup>2-</sup>.

The Technical Specification also describes how to measure general parameters like pH, electrical conductivity, DOC/TOC.

The methods in this Technical Specification are applicable to construction products.

**NOTE** Construction products include e.g. mineral-based products (S); bituminous products (B); metals (M); wood-based products (W); plastics and rubbers (P); sealants and adhesives (A); paints and coatings (C), see also CEN/TR 16045.

The selection of analytical methods to be applied is based on the required sensitivity of the method, which is provided for all substance - analytical procedure combinations.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

FprCEN/TS 17197:2017<sup>1</sup>, *Construction products: Assessment of release of dangerous substances – Analysis of major, minor and trace elements in digests and eluates by Inductively Coupled Plasma – Optical Emission Spectrometry (ICP-OES)*

FprCEN/TS 17200:2017<sup>2</sup>, *Construction products: Assessment of release of dangerous substances – Analysis of major, minor and trace elements in digests and eluates by Inductively Coupled Plasma – Mass Spectrometry (ICP-MS)*

EN 1484, *Water analysis - Guidelines for the determination of total organic carbon (TOC) and dissolved organic carbon (DOC)*

EN 27888, *Water quality - Determination of electrical conductivity (ISO 7888:1985)*

---

<sup>1</sup> Under development.

<sup>2</sup> Under development.

**FprCEN/TS 17195:2017 (E)**

EN ISO 5667-3, *Water quality - Sampling - Part 3: Preservation and handling of water samples (ISO 5667-3)*

EN ISO 10304-1, *Water quality - Determination of dissolved anions by liquid chromatography of ions - Part 1: Determination of bromide, chloride, fluoride, nitrate, nitrite, phosphate and sulfate (ISO 10304-1)*

EN ISO 10523, *Water quality - Determination of pH (ISO 10523)*

EN ISO 12846, *Water quality - Determination of mercury - Method using atomic absorption spectrometry (AAS) with and without enrichment (ISO 12846)*

EN ISO 15586, *Water quality - Determination of trace elements using atomic absorption spectrometry with graphite furnace (ISO 15586)*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025)*

EN ISO 17852, *Water quality - Determination of mercury - Method using atomic fluorescence spectrometry (ISO 17852)*

ISO 10359-1, *Water quality — Determination of fluoride — Part 1: Electrochemical probe method for potable and lightly polluted water*

ISO 17378-1, *Water quality — Determination of arsenic and antimony — Part 1: Method using hydride generation atomic fluorescence spectrometry (HG-AFS)*

ISO 17378-2, *Water quality — Determination of arsenic and antimony — Part 2: Method using hydride generation atomic absorption spectrometry (HG-AAS)*

ISO/TS 13530, *Water quality — Guidance on analytical quality control for chemical and physicochemical water analysis*

ISO/TS 17379-1, *Water quality — Determination of selenium — Part 1: Method using hydride generation atomic fluorescence spectrometry (HG-AFS)*

ISO/TS 17379-2, *Water quality — Determination of selenium — Part 2: Method using hydride generation atomic absorption spectrometry (HG-AAS)*

### **3 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### **3.1 eluate**

solution obtained from a leaching test

[SOURCE: EN 12457-1:2002 [4], 3.3, modified – “recovered” replaced by “obtained”]



**3.2****leachant**

liquid that is brought into contact with the test portion in the leaching procedure

Note 1 to entry: Usually demineralized water is used as leachant for laboratory leaching tests.

[SOURCE: EN 16687:2015 [5]]

**3.3****leaching test**

laboratory test for the determination of the release of substances from a construction product into a leachant

**3.4****sample**

portion of material selected from a larger quantity of material

[SOURCE: ISO 11074:2005 [6], 4.1.16; modified – “soil deleted”, Note deleted]

Note 1 to entry: The term “sample” is often accompanied by a prefix (e.g. laboratory sample, test sample) specifying the type of sample and/or the specific step in the sampling process to which the obtained material relates.

[SOURCE of note: EN 16687:2015 [5], 3.2.1]

**3.5****laboratory sample**

sample or subsample(s) sent to or received by the laboratory

Note 1 to entry: When the laboratory sample is further prepared by subdividing, mixing, diluting, etc. or by combinations of these operations, the result is the test sample. When no preparation of the laboratory sample is required, the laboratory sample is the test sample. A test portion is removed from the test sample for the performance of the test/ analysis.

SIST-TS CEN/TS 17195:2019

<https://standards.iteh.ai/> [SOURCE: IUPAC 2014 [7], modified – abridged and specified] 960-893cf4021a39/sist-ts-cen-ts-17195-2019

**3.6****test sample****analytical sample**

sample, prepared from the laboratory sample, from which test portions are removed for testing or for analysis

[SOURCE: IUPAC 2014 [7]]

**3.7****test portion****analytical portion**

amount of the test sample taken for testing/analysis, usually of known weight or volume

[SOURCE: IUPAC 2014 [7], modified – first “or volume” deleted, “testing” added]

## FprCEN/TS 17195:2017 (E)

### 3.8 method detection limit MDL

smallest analyte concentration that can be detected with a specified analytical method including sample preparation with a defined statistical probability

[SOURCE: ISO 17294-1:2004 [8], 3.12, modified – “including sample preparation” added, symbol replaced by abbreviation]

## 4 Abbreviations

For the purposes of this document, the following abbreviations apply.

CV-AAS	Cold vapour atomic absorption spectrometry
CV-AFS	Cold vapour atomic fluorescence spectrometry
DOC	Dissolved organic carbon
GF-AAS	Graphite furnace atomic absorption spectrometry
HG-AAS	Hydride generation atomic absorption spectrometry
IC	Ion chromatography
ICP	Inductively coupled plasma
ISE	Ion selective electrode
MDL	Method detection limit (limit of detection)
MS	Mass spectrometry
OES	Optical emission spectrometry
TOC	Total organic carbon

## 5 Sample pre-treatment

The eluate shall be analysed for the total content of the elements and anions of interest. If precipitation occurs between the preparation of the eluate and the analysis it is necessary to ensure by appropriate methods (e.g. redissolution, separate analysis of solution and precipitate) that the total content of the substances of interest is determined. If the eluate results from a procedure including 0,45 µm membrane filtration, analytical results refer to the content obtained from the leaching process.

Eluates are susceptible to be changed to different extents as a result of physical, chemical or biological reactions which may take place between the time of leaching and the analysis. pH shall be determined as soon as possible after preparation of the eluates and prior to sample pretreatment. In case of collection of eluates over periods of days, the time between completing eluate collection and pH measurement shall not exceed 18 hrs (overnight).

NOTE As noted in CEN/TS 16637-2 [9] and CEN/TS 16637-3 [10] measures can be taken to avoid eluate deterioration by carbonation through CO<sub>2</sub> uptake in alkaline eluates.

Split the eluate (the laboratory sample) into an adequate number of test samples for different chemical analyses. Take the necessary precautions and make preservations according to the requirements in the analytical standards (EN ISO 5667-3).

One specific test sample may be an untreated aliquot of the laboratory sample for the analysis of anions such as chloride, bromide, fluoride and sulfate, as well as for the determination of electrical conductivity.