

SLOVENSKI STANDARD
kSIST-TS FprCEN/TS 17196:2018
01-januar-2018

**Gradbeni proizvodi - Ocenjevanje sproščanja nevarnih snovi - Razklop z
zlatotopko za analizo anorganskih snovi**

Construction products: Assessment of release of dangerous substances - Digestion by
aqua regia for subsequent analysis of inorganic substances

Bauprodukte - Beurteilung der Freisetzung von gefährlichen Stoffen - Königswasser-
Aufschluss von Bauprodukten

Produits de construction - Évaluation des émissions de substances dangereuses -
Digestion à l'eau régale des produits de construction

Ta slovenski standard je istoveten z: FprCEN/TS 17196

[SIST-TS CEN/TS 17196:2019](https://standards.iteh.ai/catalog/standards/sist/0c1a2f23-0cf9-468d-b7c9-f388e82f848c/sist-ts-cen-ts-17196-2019)

<https://standards.iteh.ai/catalog/standards/sist/0c1a2f23-0cf9-468d-b7c9-f388e82f848c/sist-ts-cen-ts-17196-2019>

ICS:

13.020.99	Drugi standardi v zvezi z varstvom okolja	Other standards related to environmental protection
91.100.01	Gradbeni materiali na splošno	Construction materials in general

kSIST-TS FprCEN/TS 17196:2018

en,fr,de

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

FINAL DRAFT
FprCEN/TS 17196

November 2017

ICS 91.100.01

English Version

**Construction products: Assessment of release of
dangerous substances - Digestion by aqua regia for
subsequent analysis of inorganic substances**

Produits de construction - Évaluation des émissions de
substances dangereuses - Digestion à l'eau régale des
produits de construction

Bauprodukte - Beurteilung der Freisetzung von
gefährlichen Stoffen - Königswasser-Aufschluss von
Bauprodukten

This draft Technical Specification is submitted to CEN members for Vote. It has been drawn up by the Technical Committee CEN/TC 351.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a Technical Specification. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a Technical Specification.

SIST-TS CEN/TS 17196:2019

<https://standards.iteh.ai/catalog/standards/sist/0c1a2f23-0cf9-468d-b2c9-f388e82f848c/sist-ts-cen-ts-17196-2019>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Symbols and abbreviations	7
5 Principle	8
6 Interferences and sources of errors	8
7 Reagents	8
8 Apparatus.....	8
9 Procedure.....	10
9.1 Sample pre-treatment	10
9.2 Blank test	10
9.3 Method A: Thermal heating under reflux conditions.....	10
9.4 Method B: Microwave heating with temperature control at 170 °C – 180 °C	11
10 Precision data.....	12
11 Test report.....	13
Annex A (informative) Repeatability and reproducibility data for other matrices.....	14
A.1 General.....	14
A.2 Interlaboratory studies.....	14
A.2.1 Background information in the interlaboratory study for EN 13657	14
A.2.2 Background information in the interlaboratory study for EN 16174.....	14
A.2.3 Interlaboratory comparison results	15
Bibliography.....	19

European foreword

This document (FprCEN/TS 17196:2017) has been prepared by Technical Committee CEN/TC 351 “Construction Products: Assessment of release of dangerous substances”, the secretariat of which is held by NEN.

This document is currently submitted to the Vote on TS.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

A similar standard has been developed for soil, sludge and biowaste, see Annex A.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST-TS CEN/TS 17196:2019](https://standards.iteh.ai/catalog/standards/sist/0c1a2f23-0cf9-468d-b2c9-f388e82f848c/sist-ts-cen-ts-17196-2019)

<https://standards.iteh.ai/catalog/standards/sist/0c1a2f23-0cf9-468d-b2c9-f388e82f848c/sist-ts-cen-ts-17196-2019>

Introduction

Following an extended evaluation of available methods for content analysis in construction products (CEN/TR 16045) it was concluded that multi matrix and multi-element digestion methods have preference over methods developed for single matrices or small groups of matrices. This implies that for inorganic substances aqua regia digestion is preferred for the digestion of construction products for content analysis.

This document has been adopted from the work carried out in the context of CEN/TC 292 and CEN/TC 400 and is very similar to EN 13657 *Characterization of waste – Digestion for subsequent determination of aqua regia soluble portion of elements* [1] and EN 16174 *Sludge, treated biowaste and soil – Digestion of aqua regia soluble fractions of elements* [2].

This Technical Specification is part of a modular horizontal approach which was adopted in CEN/TC 351. 'Horizontal' means that the methods can be used for a wide range of materials and products with certain properties. 'Modular' means that a test standard developed in this approach concerns a specific step in assessing a property and not the whole chain of measurement (from sampling to analyses). Beneficial features of this approach are that modules can be replaced by better ones without jeopardizing the standard chain and duplication of work of in different Technical Committees for Products can be avoided as far as possible.

The modules that relate to the standards developed in CEN/TC 351 are specified in CEN/TR 16220 [3], which distinguishes between the modules. This Technical Specification belongs to the analytical step.

The use of modular horizontal standards implies the drawing of test schemes as well. Before executing a test on a certain construction product to determine certain characteristics it is necessary to draw up a protocol in which the adequate modules are selected and together form the basis for the entire test procedure.

WARNING — Persons using this Technical Specification should be familiar with usual laboratory practice. The reagents used in this Technical Specification are strongly corrosive and partly very toxic. Safety precautions are absolutely necessary, not only due to the strong corrosive reagents, but also to high temperature and high pressure.

The use of laboratory-grade microwave equipment with isolated and corrosion resistant safety devices is required. Domestic (kitchen) type microwave ovens should not be used, as corrosion by acid vapours may compromise the function of the safety devices and prevent the microwave magnetron from shutting off when the door is open, which could result in operator exposure to microwave energy.

All procedures should be performed in a fume hood or in closed force-ventilated equipment. By the use of strong oxidising reagents, the formation of explosive organic intermediates is possible, especially when dealing with samples with a high organic content. Do not open pressurized vessels before they have cooled down. Avoid contact with the chemicals and the gaseous reaction products.

IMPORTANT — It is absolutely essential that tests conducted according to this Technical Specification be carried out by suitably trained staff.

1 Scope

This Technical Specification specifies methods for obtaining the aqua regia digestible content of construction products. Solutions produced by this method for analysis by inductively coupled plasma mass spectrometry (ICP-MS) and inductively coupled spectrometry (ICP-OES) for the following 67 elements:

Aluminium (Al), antimony (Sb), arsenic (As), barium (Ba), beryllium (Be), bismuth (Bi), boron (B), cadmium (Cd), calcium (Ca), cerium (Ce), cesium (Cs), chromium (Cr), cobalt (Co), copper (Cu), dysprosium (Dy), erbium (Er), europium (Eu), gadolinium (Gd), gallium (Ga), germanium (Ge), gold (Au), hafnium (Hf), holmium (Ho), indium (In), iridium (Ir), iron (Fe), lanthanum (La), lead (Pb), lithium (Li), lutetium (Lu), magnesium (Mg), manganese (Mn), mercury (Hg), molybdenum (Mo), neodymium (Nd), nickel (Ni), palladium (Pd), phosphorus (P), platinum (Pt), potassium (K), praseodymium (Pr), rubidium (Rb), rhenium (Re), rhodium (Rh), ruthenium (Ru), samarium (Sm), scandium (Sc), selenium (Se), silicon (Si), silver (Ag), sodium (Na), strontium (Sr), sulphur (S), tellurium (Te), terbium (Tb), thallium (Tl), thorium (Th), thulium (Tm), tin (Sn), titanium (Ti), tungsten (W), uranium (U), vanadium (V), ytterbium (Yb), yttrium (Y), zinc (Zn), and zirconium (Zr).

Solutions produced by the methods are suitable for analysis by cold vapour atomic absorption or fluorescent spectrometry (CV-AAS, CV-AFS), for mercury (Hg).

The method in this Technical Specification is applicable to construction products.

Digestion with aqua regia will not necessarily accomplish total decomposition of the sample. The extracted analyte concentrations may not necessarily reflect the total content in the sample.

NOTE Construction products include e.g. mineral-based products (S); bituminous products (B); metals (M); wood-based products (W); plastics and rubbers (P); sealants and adhesives (A); paints and coatings (C), see also CEN/TR 16045.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 15936, *Sludge, treated biowaste, soil and waste - Determination of total organic carbon (TOC) by dry combustion*

prEN 17087:2017, Construction products: Assessment of release of dangerous substances – Preparation of test portions from the laboratory sample for testing of release and analysis of content (*under development*)

EN ISO 3696:1995, *Water for analytical laboratory use - Specification and test methods (ISO 3696:1987)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply

NOTE The terms and definitions, where relevant, were taken from EN 16687:2015.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

FprCEN/TS 17196:2017 (E)**3.1****analyte
determinand**

element, ion or substance to be determined by an analytical method

[SOURCE: EN 16687:2015, 4.1.11]

3.2**aqua regia**

digestion solution obtained by mixing one volume of concentrated nitric acid and three volumes of concentrated hydrochloric acid

3.3**digestion**

mineralization of the organic matter of a sample and dissolution of its mineral part (as completely as possible) when reacted with a reagent mixture

Note 1 to entry: Usually done with a strong, concentrated acid like aqua regia or nitric acid to dissolve inorganic substances for chemical analysis.

[SOURCE: CEN/TR 16045:2010, 2.2.2]

3.4**digestion vessel**

flask where the test portion and the acid solution are mixed together and the digestion is carried out

3.5**digest**

solution resulting from acid digestion of a sample

[SOURCE: CEN/TR 16045:2010, 2.2.1]

3.6**dry matter**

mass fraction of a sample excluding water expressed as mass fraction calculated by determination of dry residue or water content

[SOURCE: EN 15934:2012, 3.3]

3.7**microwave unit**

microwave digestion system (oven and associated equipment)

3.8**sample**

portion of material selected from a larger quantity of material

Note 1 to entry: The manner of selection of the sample should be prescribed in a sampling plan.

Note 2 to entry: The term “sample” is often accompanied by a prefix (e.g. laboratory sample, test sample) specifying the type of sample and/or the specific step in the sampling process to which the obtained material relates.

[SOURCE: EN 16687:2015, 3.1.5]

3.9**laboratory sample**

sample or sub-sample(s) sent to or received by the laboratory

Note 1 to entry: When the laboratory sample is further prepared by subdividing, cutting, sawing, coring, mixing, drying, grinding, and curing or by combinations of these operations, the result is the test sample. When no preparation of the laboratory sample is required, the laboratory sample is the test sample. A test portion is removed from the test sample for the performance of the test/ analysis or for the preparation of a test specimen.

Note 2 to entry: The laboratory sample is the final sample from the point of view of sample collection but it is the initial sample from the point of view of the laboratory.

[SOURCE: EN 16687:2015, 3.2.1]

3.10**test sample****analytical sample**

sample, prepared from the laboratory sample, from which test portions are removed for testing or for analysis

[SOURCE: EN 16687:2015, 3.2.2]

3.11**test portion****analytical portion**

amount of the test sample taken for testing/ analysis, usually of known weight or volume

EXAMPLE 1 A bag of aggregates is delivered to the laboratory (the laboratory sample). For test purposes a certain amount of the aggregate is dried, the result is the test sample. Afterwards the column for a percolation test is filled with a test portion of dried aggregate

EXAMPLE 2 A piece of flooring is delivered to the laboratory (the laboratory sample). For the purpose of digestion a certain amount is size reduced, the result is the test sample. From the size-reduced test sample a test portion is taken to execute the digestion. If the digest is to be analysed afterwards e.g. by ICP-MS, the whole amount of the digest is the laboratory sample again (and without any further treatment also the test sample), the amount taken for the analytical procedure the test portion.

[SOURCE: EN 16687:2015, 3.2.3]

4 Symbols and abbreviations

For the purposes of this document, the following abbreviations apply.

CAS	Chemical Abstracts Service
CASRN	CAS Registry Number
CV-AAS	Cold vapour atomic absorption spectrometry
CV-AFS	Cold vapour atomic fluorescence spectrometry
ICP	Inductively coupled plasma
MS	Mass spectrometry
OES	Optical emission spectrometry
PFA	Perfluoroalkoxylalkane

FprCEN/TS 17196:2017 (E)

PTFE	Polytetrafluoroethene
SRM	Standard reference material

5 Principle

A test portion is digested with *aqua regia* according to one of the following heating procedures:

- Method A: boiling under reflux for 2 h, followed by filtration if necessary and by adjusting the volume in a volumetric flask;
- Method B: microwave digestion at $(175 \pm 5) ^\circ\text{C}$ for (10 ± 1) min in a closed vessel followed by filtration if necessary and adjusting the volume in a volumetric flask.

NOTE In the validation testing for other materials (sludge, compost, soil) no significant difference between the reflux and the microwave method was found. So there seems to be no need to prescribe a particular extraction method for construction products.

6 Interferences and sources of errors

Due to the volatility of some compounds care shall be taken, that the sample is not heated before the digestion and that any volatile reaction products formed during the digestion do not escape.

High acid and solute concentrations in the digest may cause interferences at determination.

Contamination shall be avoided. Glass containing e.g. B, Na, K, Al can contaminate samples.

Ensure that all of the test portion is thoroughly mixed with the acid mixture in the digestion vessel.

Some elements of interest can be lost due to precipitation with ions present in the digest solution, e.g. low soluble chlorides, fluorides and sulfates.

7 Reagents

Use only acids and reagents of recognized analytical grade to avoid high blank values for subsequent analytical measurements.

7.1 Water, quality 2 according to EN ISO 3696:1995 or better.

7.2 Hydrochloric acid, $c(\text{HCl}) = 12 \text{ mol/l}$; $\rho = 1,18 \text{ kg/l}$.

Other grade may be used provided it is ascertained that the reagent is of sufficient purity to permit its use without decreasing the accuracy of the subsequent analysis.

7.3 Nitric acid, $c(\text{HNO}_3) = 16 \text{ mol/l}$, $\rho = 1,4 \text{ kg/l}$.

7.4 Nitric acid, $c(\text{HNO}_3) = 0,5 \text{ mol/l}$, $\rho = 1,0 \text{ kg/l}$.

Dilute 35 ml nitric acid (7.3) to 1 l with water (7.1).

7.5 Antifoaming agent, e.g. n-dodecane ($\text{C}_{12}\text{H}_{26}$) or Octanol ($\text{C}_8\text{H}_{18}\text{O}$) are suitable.

8 Apparatus

All glassware and plastic ware shall be adequately cleaned and stored in order to avoid any contamination.