

SLOVENSKI STANDARD

SIST-TS CEN/TS 17200:2019

01-januar-2019

Gradbeni proizvodi - Ocenjevanje sproščanja nevarnih snovi - Analiza anorganskih snovi po razklopu in v izlužkih - Analiza z masno spektrometrijo z induktivno sklopljeno plazmo (ICP/MS)

Construction products - Assessment of release of dangerous substances - Analysis of inorganic substances in digests and eluates - Analysis by Inductively Coupled Plasma - Mass Spectrometry (ICP-MS)

Bauprodukte - Beurteilung der Freisetzung von gefährlichen Stoffen - Analyse von anorganischen Stoffen in Aufschluslösungen und Eluaten - Analyse mit induktiv gekoppeltem Plasma - Massenspektrometrie (ICP-MS)

Produits de construction - Évaluation des émissions de substances dangereuses - Analyse des substances inorganiques dans les digestats et les éluats - Analyse par spectrométrie de masse avec plasma à couplage inductif

Ta slovenski standard je istoveten z: CEN/TS 17200:2018

ICS:

13.020.99	Drugi standardi v zvezi z varstvom okolja	Other standards related to environmental protection
91.100.01	Gradbeni materiali na splošno	Construction materials in general

SIST-TS CEN/TS 17200:2019

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST-TS CEN/TS 17200:2019

<https://standards.iteh.ai/catalog/standards/sist/6065a4a8-80fe-404d-90c3-da0685751d88/sist-ts-cen-ts-17200-2019>

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

CEN/TS 17200

July 2018

ICS 91.100.01

English Version

**Construction products: Assessment of release of
dangerous substances - Analysis of inorganic substances in
digests and eluates - Analysis by Inductively Coupled
Plasma - Mass Spectrometry (ICP-MS)**

Produits de construction: Évaluation des émissions de
substances dangereuses - Analyse des substances
inorganiques dans les digestats et les éluats - Analyse
par spectrométrie de masse avec plasma à couplage
inductif

Bauprodukte: Beurteilung der Freisetzung von
gefährlichen Stoffen - Analyse von anorganischen
Stoffen in Aufschlusslösungen und Eluaten - Analyse
mit induktiv gekoppeltem Plasma -
Massenspektrometrie (ICP-MS)

This Technical Specification (CEN/TS) was approved by CEN on 2 April 2018 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Symbols and abbreviations	9
5 Principle	9
6 Interferences	9
6.1 General	9
6.2 Spectral interferences	9
6.2.1 Isobaric elemental interferences	9
6.2.2 Isobaric molecular and doubly charged ion interferences	10
6.3 Non spectral interferences	10
7 Reagents	10
8 Apparatus	13
9 Procedure.....	14
9.1 Test sample	14
9.2 Test portion	14
9.3 Instrument set up	14
9.4 Calibration	15
9.4.1 Calibration function	15
9.4.2 Standard addition calibration	15
9.4.3 Determination of correction factors	16
9.4.4 Variable isotope ratio	16
9.5 Sample measurement	16
10 Calculation	16
10.1 Calculation for digests of construction products	16
10.2 Calculation for eluates of construction products	17
11 Expression of results	17
12 Performance characteristics	17
12.1 General	17
12.2 Blank	17
12.3 Calibration check	17
12.4 Internal standard response	17
12.5 Interference	17
12.6 Recovery	17
12.7 Precision	17
13 Test report	18

Annex A (informative) Method detection limit (MDL) and precision data for soil, sludge and biowaste	20
Annex B (informative) Validation results for construction products.....	28
B.1 Introduction.....	28
B.2 Performance data	28
Bibliography	29

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TS CEN/TS 17200:2019

<https://standards.iteh.ai/catalog/standards/sist/6065a4a8-80fe-404d-90c3-da0685751d88/sist-ts-cen-ts-17200-2019>

CEN/TS 17200:2018 (E)**European foreword**

This document (CEN/TS 17200:2018) has been prepared by Technical Committee CEN/TC 351 “Construction products - Assessment of release of dangerous substances”, the secretariat of which is held by NEN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

A similar document has been developed for drinking water, surface water and waste water and different types of waste respectively, see Annex A.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

(standards.iteh.ai)

SIST-TS CEN/TS 17200:2019

<https://standards.iteh.ai/catalog/standards/sist/6065a4a8-80fe-404d-90c3-da0685751d88/sist-ts-cen-ts-17200-2019>

Introduction

Following an extended evaluation of available methods for content and eluate analysis in construction products (CEN/TR 16045; [1]) it was concluded that multi element analysis methods have preference over methods developed for single elements or small groups of elements. This implies that for inorganic substances ICP methods are preferred for the analysis of extracts obtained from digestion or eluates obtained from leaching.

This standard has been adopted from the work carried out in the context of CEN/TC 400 (project HORIZONTAL) and is very similar to EN 16171, *Sludge, treated biowaste and soil - Determination of elements using inductively coupled plasma mass spectrometry (ICP-MS)* [2].

This Technical Specification is part of a modular horizontal approach which was adopted in CEN/TC 351. 'Horizontal' means that the methods can be used for a wide range of materials and products with certain properties. 'Modular' means that a test standard developed in this approach concerns a specific step in assessing a property and not the whole chain of measurement (from sampling to analyses). Beneficial features of this approach are that modules can be replaced by better ones without jeopardizing the standard chain and duplication of work of in different Technical Committees for Products can be avoided as far as possible.

The modules that relate to the standards developed in CEN/TC 351 are specified in CEN/TR 16220, *Construction products: Assessment of release of dangerous substances – Complement to sampling* [3] which distinguishes between the modules. This Technical Specification belongs to the analytical step.

The use of modular horizontal standards implies the drawing of test schemes as well. Before executing a test on a certain construction product to determine certain characteristics it is necessary to draw up a protocol in which the adequate modules are selected and together form the basis for the entire test procedure.

[SIST-TS CEN/TS 17200:2019](https://standards.iteh.ai/catalog/standards/sist/6065a4a8-80fe-404d-90c3-da0685751d88/sist-ts-cen-ts-17200-2019)

<https://standards.iteh.ai/catalog/standards/sist/6065a4a8-80fe-404d-90c3-da0685751d88/sist-ts-cen-ts-17200-2019>

CEN/TS 17200:2018 (E)

1 Scope

This Technical Specification specifies the method for the determination of major, minor and trace elements in aqua regia and nitric acid digests and in eluates of construction products by Inductively Coupled Plasma - Mass Spectrometry (ICP-MS). It refers to the following 67 elements: Aluminium (Al), antimony (Sb), arsenic (As), barium (Ba), beryllium (Be), bismuth (Bi), boron (B), cadmium (Cd), calcium (Ca), cerium (Ce), cesium (Cs), chromium (Cr), cobalt (Co), copper (Cu), dysprosium (Dy), erbium (Er), europium (Eu), gadolinium (Gd), gallium (Ga), germanium (Ge), gold (Au), hafnium (Hf), holmium (Ho), indium (In), iridium (Ir), iron (Fe), lanthanum (La), lead (Pb), lithium (Li), lutetium (Lu), magnesium (Mg), manganese (Mn), mercury (Hg), molybdenum (Mo), neodymium (Nd), nickel (Ni), palladium (Pd), phosphorus (P), platinum (Pt), potassium (K), praseodymium (Pr), rubidium (Rb), rhenium (Re), rhodium (Rh), ruthenium (Ru), samarium (Sm), scandium (Sc), selenium (Se), silicon (Si), silver (Ag), sodium (Na), strontium (Sr), sulphur (S), tellurium (Te), terbium (Tb), thallium (Tl), thorium (Th), thulium (Tm), tin (Sn), titanium (Ti), tungsten (W), uranium (U), vanadium (V), ytterbium (Yb), yttrium (Y), zinc (Zn), and zirconium (Zr).

NOTE 1 Construction products include e.g. mineral-based products (S); bituminous products (B); metals (M); wood-based products (W); plastics and rubbers (P); sealants and adhesives (A); paints and coatings (C), see also CEN/TR 16045 [1].

The working range depends on the matrix and the interferences encountered.

NOTE 2 The limit of detection of most elements will be affected by their natural abundance, ionization behaviour, on abundance of isotope(s) free from isobaric interferences and by contamination (e.g. handling and airborne). Handling contaminations are in many cases more important than airborne ones.

The limit of detection will be higher in cases where the determination is likely to be interfered (see Clause 4) or in case of memory effects (see e.g. EN ISO 17294-1:2006, 8.2).

The method in this Technical Specification is applicable to construction products and validated for the product types listed in Annex B.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

CEN/TS 16637-2, *Construction products — Assessment of release of dangerous substances — Part 2: Horizontal dynamic surface leaching test*

CEN/TS 16637-3, *Construction products — Assessment of release of dangerous substances — Part 3: Horizontal up-flow percolation test*

CEN/TS 17196, *Construction products: Assessment of release of dangerous substances — Digestion by aqua regia for subsequent analysis of the major, minor and trace elements*

EN ISO 3696:1995, *Water for analytical laboratory use — Specification and test methods (ISO 3696:1987)*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025)*

EN ISO 17294-1:2006, *Water quality — Application of inductively coupled plasma mass spectrometry (ICP-MS) — Part 1: General guidelines (ISO 17294-1:2004)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

digest

solution resulting from acid digestion of a sample

[SOURCE: EN 16687:2015, 3.2.8]

3.2

eluate

solution obtained from a leaching test

[SOURCE: EN 16687:2015, 4.2.7]

3.3

analyte

determinand

element, ion or substance to be determined by an analytical method

[SOURCE: EN 16687:2015, 4.1.11]

3.4

sample

portion of material selected from a larger quantity of material

Note 1 to entry: The manner of selection of the sample should be prescribed in a sampling plan.

Note 2 to entry: The term “sample” is often accompanied by a prefix (e.g. laboratory sample, test sample) specifying the type of sample and/or the specific step in the sampling process to which the obtained material relates.

[SOURCE: EN 16687:2015, 3.1.5]

3.5

laboratory sample

sample or subsample(s) sent to or received by the laboratory

Note 1 to entry: When the laboratory sample is further prepared by subdividing, cutting, sawing, coring, mixing, drying, grinding, and curing or by combinations of these operations, the result is the test sample. When no preparation of the laboratory sample is required, the laboratory sample is the test sample. A test portion is removed from the test sample for the performance of the test/analysis or for the preparation of a test specimen.

Note 2 to entry: The laboratory sample is the final sample from the point of view of sample collection but it is the initial sample from the point of view of the laboratory.

[SOURCE: EN 16687:2015, 3.2.1]

CEN/TS 17200:2018 (E)

3.6

test sample**analytical sample**

sample, prepared from the laboratory sample, from which test portions are removed for testing or for analysis

[SOURCE: EN 16687:2015, 3.2.2]

3.7

test portion**analytical portion**

amount of the test sample taken for testing/ analysis, usually of known weight or volume

EXAMPLE 1 A bag of aggregates is delivered to the laboratory (the laboratory sample). For test purposes a certain amount of the aggregate is dried, the result is the test sample. Afterwards the column for a percolation test is filled with a test portion of dried aggregate.

EXAMPLE 2 A piece of flooring is delivered to the laboratory (the laboratory sample). For the purpose of digestion a certain amount is size reduced, the result is the test sample. From the size-reduced test sample a test portion is taken to execute the digestion. If the digest is to be analysed afterwards e.g. by ICP-MS, the whole amount of the digest is the laboratory sample again (and without any further treatment also the test sample), the amount taken for the analytical procedure the test portion.

[SOURCE: EN 16687:2015, 3.2.3]

3.8

instrument detection limit**IDL**

smallest analyte concentration that can be detected with a defined statistical probability using a contaminant free instrument and a blank calibration solution

Note 1 to entry: Usually determined by three times the repeatability standard deviation ($3 \times Sr$) calculated from multiple measurements ($n > 8$) of a solution within a single run

[SOURCE: EN 16687:2015, 4.1.13]

3.9

limit of quantification**LOQ**

lowest value of an analyte (determinant) that can be determined with an acceptable level of accuracy and precision, generally determined as three times the limit of detection of the method

[SOURCE: EN 16687:2015, 4.1.14]

3.10

method detection limit**MDL**

smallest analyte concentration that can be detected with a specified analytical method including sample preparation with a defined statistical probability

Note 1 to entry: Usually determined by three times the repeatability standard deviation ($3 \times Sr$) calculated from multiple measurements ($n > 8$) on different days and in different matrix solutions which contain a low analyte concentration.

[SOURCE: EN 16687:2015, 4.1.12]

4 Symbols and abbreviations

FEP	Hexafluoroethene propene
HDPE	High-density polyethylene
ICP	Inductively coupled plasma
ICS	Interference check solution
IDL	Instrumental detection limit
IEC	Inter-element correction
LOQ	Limit of quantification
MDL	Method detection limit (limit of detection)
MS	Mass spectrometry
OES	Optical emission spectrometry
PFA	Perfluoroalkoxy alkane
PTFE	Polytetrafluorethylene
PVC	Polyvinylchloride

5 Principle

This method describes the multi-elemental determination of analytes by ICP-MS in (diluted) nitric acid or aqua regia digests. The method measures ions produced by a radio-frequency inductively coupled plasma. Analyte species originating in a liquid are nebulized and the resulting aerosol is transported by argon gas into the plasma. The ions produced by high temperatures of the plasma are entrained in the plasma gas and introduced, by means of an interface, into a mass spectrometer, sorted according to their mass-to-charge ratios and quantified with a detector (e.g. channel electron multiplier). Interferences shall be assessed and valid corrections applied. Interference correction shall include compensation for background ions contributed by the plasma gas, reagents, and constituents of the sample matrix.

6 Interferences

6.1 General

Detailed information on spectral and non-spectral interferences is given in EN ISO 17294-1:2006, 6.1.

6.2 Spectral interferences

6.2.1 Isobaric elemental interferences

Isobaric elemental interferences are caused by isotopes of different elements of closely matched nominal mass-to-charge ratio and which cannot be separated due to an insufficient resolution of the mass spectrometer in use (e.g. ^{114}Cd and ^{114}Sn).

Element interferences from isobars may be corrected for taking into account the influence from the interfering element. The isotopes used for correction shall be free of interference if possible. Correction options are often included in the instrument software.

CEN/TS 17200:2018 (E)

6.2.2 Isobaric molecular and doubly charged ion interferences

Isobaric molecular and doubly-charged ion interferences in ICP-MS are caused by ions consisting of more than one atom or charge, respectively. Examples include $^{40}\text{Ar}^{35}\text{Cl}^+$ and $^{40}\text{Ca}^{35}\text{Cl}^+$ ion on the ^{75}As signal and $^{98}\text{Mo}^{16}\text{O}^+$ ions on the $^{114}\text{Cd}^+$ signal. Natural isotope abundances are available from the literature. However, the most precise coefficients for an instrument will be determined from the ratio of the net isotope signals observed for a standard solution.

The accuracy of these types of equations is based upon the constancy of the observed isotopic ratios for the interfering species. Corrections that presume a constant fraction of a molecular ion relative to the "parent" ion have not been found to be reliable, e.g., oxide levels can vary with operating conditions. If a correction for an oxide ion is based upon the ratio of parent-to-oxide ion intensities, the correction shall be adjusted for the degree of oxide formation by the use of an appropriate oxide internal standard previously demonstrated to form a similar level of oxide as the interferent.

Other possibilities to correct for isobaric and doubly charged ion interferences are the use of an instrument with collision/reaction cell technology or high resolution ICP-MS.

The response of the analyte of interest shall be corrected for the contribution of isobaric molecular and doubly charged interferences if their impact can be higher than three times the instrumental detection limit or higher than half the lowest concentration to be reported.

6.3 Non spectral interferences

Physical interferences are associated with the sample nebulization and transport processes as well as with ion-transmission efficiencies. Nebulization and transport processes can be affected if a matrix component causes a change in surface tension or viscosity. Changes in matrix composition can cause significant signal suppression or enhancement. Dissolved solids can deposit on the nebulizer tip of a pneumatic nebulizer and on the cones.

It is recommended to keep the level of total dissolved solids below 0,2 % (2,000 mg/l) to minimize deposition of solids in the sample introduction system of the plasma torch. An internal standard can be used to correct for physical interferences if it is carefully matched to the analyte so that the two elements are similarly affected by matrix changes. Other possibilities to minimize non spectral interferences are matrix matching, particularly matching of the acid concentration, and standard addition.

When intolerable physical interferences are present in a sample, a significant suppression of the internal standard signals (to less than 30 % of the signals in the calibration solution) will be observed. Dilution of the sample (e.g. fivefold) will usually eliminate the problem.

7 Reagents

7.1 General

For the determination of elements at trace and ultra trace level, the reagents shall be of adequate purity. The concentration of the analyte or interfering substances in the reagents and the water should be negligible compared to the lowest concentration to be determined.

7.2 Water, complying with grade 1 as defined in EN ISO 3696:1995 for all sample preparations and dilutions.

7.3 Nitric acid, $c(\text{HNO}_3) = 16 \text{ mol/l}$, $\rho \sim 1,4 \text{ kg/l}$.