



Designation: D3496 – 99 (Reapproved 2005)

Standard Practice for Preparation of Bituminous Mixture Specimens for Dynamic Modulus Testing¹

This standard is issued under the fixed designation D3496; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the preparation of cylindrical specimens of bituminous paving mixture suitable for dynamic modulus tests. The practice is intended for dense-graded bituminous concrete mixtures containing aggregate up to 25.0-mm maximum size.

1.2 The values stated in SI units are the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1560 Test Methods for Resistance to Deformation and Cohesion of Bituminous Mixtures by Means of Hveem Apparatus

D1561 Practice for Preparation of Bituminous Mixture Test Specimens by Means of California Kneading Compactor

D3387 Test Method for Compaction and Shear Properties of Bituminous Mixtures by Means of the U.S. Corps of Engineers Gyratory Testing Machine (GTM)

3. Apparatus

3.1 *California Kneading Compactor*—When the California kneading compactor is used to prepare specimens, the apparatus shall be in accordance with Practice **D1561**, except steel molding cylinders with [6-mm] wall thickness having an inside diameter of 100 mm and height of 250 mm shall be used.

¹ This test method is under the jurisdiction of ASTM Committee **D04** on Road and Paving Materials and is the direct responsibility of Subcommittee **D04.26** on Fundamental/Mechanistic Tests.

Current edition approved Feb. 1, 2005. Published February 2005. Originally approved in 1976. Last previous edition approved in 1999 as D3496 – 99. DOI: 10.1520/D3496-99R05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 *Corps of Engineers Gyratory Testing Machine*—When the Corps of Engineers gyratory testing machine is used to prepare specimens, the apparatus shall be as specified by Test Method **D3387**, except that only those models capable of producing 100-mm diameter by 200-mm high specimens are applicable. The dimensions of the molding cylinders for this machine shall be 100 mm in diameter by 300-mm long.

4. Test Specimens

4.1 *Preparation of Mixture*—Prepare approximately 4000 g of the bituminous mixture in accordance with Test Methods **D1560** or Test Method **D3387** to produce specimens 100 mm in diameter by 200 mm in height.

4.2 *Size of Specimens*—The cylindrical specimens shall be 100 mm in diameter by 200 mm in height.

5. Procedure

5.1 *Compaction Temperature*—The compaction temperature for bituminous mixtures shall be in accordance with Practice **D1561** or Test Method **D3387**, depending on which set of equipment is used.

5.2 *Molding Specimens*—Heat the compaction molds to the temperatures specified in **5.1**.

5.2.1 Specimens prepared using the California kneading compactor shall be prepared using the following procedure for molding specimens. Place the compaction mold in position in the mold holder and insert a paper disk 100 mm in diameter to cover the base plate of the mold holder. Weigh out one half of the required amount of bituminous mixture for one specimen at the specified temperature and place uniformly in the insulated feeder trough, which has been preheated to the compaction temperature for the mixture. By means of the variable transformer controlling the heater, maintain the compactor foot sufficiently hot to prevent the mixture from adhering to it. By means of a paddle of suitable dimensions to fit the cross section of the trough, push 30 approximately equal portions of the mixture continuously and uniformly into the mold while 30 tamping blows at a pressure of 1.7 MPa are applied. Immediately place the remaining one half of the mixture uniformly in the feeder trough. Push 30 approximately equal portions of the