

SLOVENSKI STANDARD

SIST EN 480-13:2015

01-julij-2015

Nadomešča:

SIST EN 480-13:2009+A1:2011

**Kemijski dodatki za beton, malto in injekcijsko maso - Metode preskušanja - 13.
del: Referenčna malta za zidanje za preskušanje kemijskih dodatkov za malte**

Admixtures for concrete, mortar and grout - Test methods - Part 13: Reference masonry mortar for testing mortar admixtures

Zusatzmittel für Beton, Mörtel und Einpressmörtel - Prüfverfahren - Teil 13: Referenz-Baumörtel für die Prüfung von Zusatzmitteln für Mauerwerksmörtel

Adjuvants pour béton, mortier et coulis - Méthodes d'essai - Partie 13: Mortier à maçonner de référence pour les essais menés sur les adjuvants de mortier

Ta slovenski standard je istoveten z: EN 480-13:2015

ICS:

91.100.10	Cement. Mavec. Apno. Malta	Cement. Gypsum. Lime. Mortar
91.100.30	Beton in betonski izdelki	Concrete and concrete products

SIST EN 480-13:2015

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 480-13:2015

<https://standards.iteh.ai/catalog/standards/sist/f85fd240-fa55-401f-a994-d434f0ee53c5/sist-en-480-13-2015>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 480-13

June 2015

ICS 91.100.10

Supersedes EN 480-13:2009+A1:2011

English Version

**Admixtures for concrete, mortar and grout - Test methods - Part
13: Reference masonry mortar for testing mortar admixtures**

Adjuvants pour béton, mortier et coulis - Méthodes d'essai -
Partie 13: Mortier à maçonner de référence pour les essais
menés sur les adjuvants de mortier

Zusatzmittel für Beton, Mörtel und Einpressmörtel -
Prüfverfahren - Teil 13: Referenz-Baumörtel für die Prüfung
von Zusatzmitteln für Mauerwerksmörtel

This European Standard was approved by CEN on 10 April 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

SIST EN 480-13:2015

<https://standards.iteh.ai/catalog/standards/sist/f85fd240-fa55-401f-a994-d434f0ee53c5/sist-en-480-13-2015>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Constituent materials	4
3.1 Cement	4
3.2 Sand	4
3.3 Mixing water	5
4 Reference masonry mortar	5
5 Production of reference mortar with standard consistence	5
5.1 Mix proportions	5
5.2 Mixing procedure	6
5.3 Mortar for test after standing	6
5.4 Mortar for test after extended mixing	6
6 Calculation of water reduction (air entraining/plasticizing admixtures)	6
7 Test report	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 480-13:2015

<https://standards.iteh.ai/catalog/standards/sist/f85fd240-fa55-401f-a994-d434f0ee53c5/sist-en-480-13-2015>

Foreword

This document (EN 480-13:2015) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2015, and conflicting national standards shall be withdrawn at the latest by December 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 480-13:2009+A1:2011.

This standard differs from EN 480-13:2009+A1:2011 as follows:

- a) Subclause 3.1 has been updated with regard to requirements for the specific surface of cement used.
- b) It has been revised editorially.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SIST EN 480-13:2015

<https://standards.iteh.ai/catalog/standards/sist/f85fd240-fa55-401f-a994-d434f0ee53c5/sist-en-480-13-2015>

EN 480-13:2015 (E)**1 Scope**

This European Standard specifies the constituent materials, the composition and the mixing procedure to produce a reference masonry mortar with a prescribed consistence for testing mortar admixtures as defined in EN 934-3. It also describes the determination of the water reduction of the test mix compared to the control mix.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1, *Methods of testing cement - Part 1: Determination of strength*

EN 196-2, *Method of testing cement - Part 2: Chemical analysis of cement*

EN 196-6, *Methods of testing cement - Part 6: Determination of fineness*

EN 197-1, *Cement - Part 1: Composition, specifications and conformity criteria for common cements*

EN 934-3, *Admixtures for concrete, mortar and grout — Part 3: Admixtures for masonry mortar — Definitions, requirements, conformity, marking and labelling*

EN 1008, *Mixing water for concrete - Specification for sampling, testing and assessing the suitability of water, including water recovered from processes in the concrete industry, as mixing water for concrete*

EN 1015-4, *Methods of test for mortar for masonry - Part 4: Determination of consistence of fresh mortar (by plunger penetration)*

EN 1015-7, *Methods of test for mortar for masonry - Part 7: Determination of air content of fresh mortar*

3 Constituent materials**3.1 Cement**

The reference masonry mortar shall be made with CEM I cement of strength class 42,5 or 52,5, conforming to EN 197-1.

The cement used shall have a C₃A content of 7 % to 11 % by mass calculated from chemical analysis according to EN 196-2 and a specific surface of (3 200 to 4 600) cm²/g determined according to EN 196-6.

3.2 Sand

A natural sand of normal density (relative density 2,5 – 2,8) shall be used. The size fractions of the sand shall comply with Table 1. The sand shall be used in an oven dry condition.

Table 1 — Sand for reference masonry mortar

Aperture size (mm)	Percentage by mass passing the test sieve
4,0	100
2,0	90 – 100
1,0	60 – 90
0,5	40 – 75
0,25	25 – 50
0,125	10 – 30
0,063	0 – 10

3.3 Mixing water

Water according to EN 1008 shall be used as mixing water.¹⁾

4 Reference masonry mortar

Where specified, tests on reference mortar are performed as comparative tests. That is comparing the performance of the reference mortar containing an admixture (test mix) with the performance of the reference mortar without an admixture (control mix). The air content of the control mix shall not exceed 5 % by volume when determined in accordance with EN 1015-7, method A.

5 Production of reference mortar with standard consistence

5.1 Mix proportions

The control and test mixes shall be in accordance with Table 2.

Table 2 — Mix details

	Control mix	Test mix
Sand	3 440 g	3 440 g
Cement	640 g	640 g
Admixture	Nil	Compliance Dose
Water	As required	As required
Consistence measured according to EN 1015-4	(40 ± 5) mm	Within ± 3 mm of consistence of control mix

Record to the nearest 1 g the total quantity of water required (including any contributed by the admixture).

For test mix mortars, the quantity of admixture added shall be sufficient to produce the required air content and retardation time if appropriate. The dose of admixture shall be recorded.

¹⁾ Distilled or deionised water can be used for special tests.

EN 480-13:2015 (E)**5.2 Mixing procedure**

Prior to mixing, each of the constituents shall be conditioned to a temperature of $(20 \pm 2) ^\circ\text{C}$.

Place all the sand and then the cement in the mixing bowl of a mixer complying with EN 196-1 and mix for 30 s at low speed.

Continue mixing and add half of the mixing water during the next 30 s and mix for a further 60 s.

During a further 30 s of mixing, add the third quarter of the water and the admixture²⁾.

During a further 30 s of mixing, add the final quarter of the mixing water. If necessary, the quantity of water shall be adjusted to obtain the required consistence.

Continue mixing at low speed for 60 s after all the water has been added.

Stop the mixer for 60 s and during this time remove any unmixed material from the sides and bottom of the bowl using the mixer paddle.

Restart the mixer at high speed and mix for 60 s. Total mixing process time shall be 6 min.

Immediately after completion of mixing, the consistence shall be determined in accordance with EN 1015-4 and the air content in accordance with EN 1015-7, method A. If the required consistence and air content are not achieved, the mix shall be discarded. A new test mix shall be prepared with the water content adjusted.

5.3 Mortar for test after standing

Prepare a test mix as described in 5.1 and 5.2. Cover the mixing bowl to prevent loss of water by evaporation and allow to stand for the period of time prescribed in EN 934-3. After the required standing period from completion of mixing, remix the mortar in the bowl for 10 s using a palette knife.

5.4 Mortar for test after extended mixing

Prepare a test mix as described in 5.1 and 5.2. Then continue mixing at low speed for a further 15 min.

6 Calculation of water reduction (air entraining/plasticizing admixtures)

Calculate the percentage water reduction, W , resulting from inclusion of the admixture, from the following formula:

$$W = \frac{(C - T)}{C} \times 100$$

where

C is the water requirement of the control mix in g;

T is the water requirement of the test mix in g.

The water reduction shall be reported to the nearest 1 %.

²⁾ If recommended by the manufacturer, admixtures can be added at a different time in the mixing sequence.