



Designation: E2367 – 05

Standard Test Method for Measurement of Nighttime Chromaticity of Pavement Marking Materials Using a Portable Retroreflection Colorimeter¹

This standard is issued under the fixed designation E2367; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers measurement of the nighttime chromaticity coordinates (x , y) of horizontal pavement markings, such as traffic stripes and surface symbols, using a portable retroreflection colorimeter that can be placed on the road delineation to measure the chromaticity at a prescribed geometry.

1.2 The entrance and observation angles of the retroreflection colorimeter affect the readings. As specified by the European Committee for Standardization (CEN EN 1436), the entrance and observation angles shall be 88.76° and 1.05° , respectively.

1.3 This test method is intended to be used for field measurement of pavement markings but may be used to measure the chromaticity of materials on sample panels before placing the marking material in the field.

1.4 The portable retroreflection colorimeter may integrate measurement of the coefficient of retroreflected luminance R_L according to Test Method E1710 and thus be an integrated retroreflectometer/ retroreflection colorimeter.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D6628 Specification for Color of Pavement Marking Materials

E284 Terminology of Appearance

¹ This test method is under the jurisdiction of ASTM Committee E12 on Color and Appearance and is the direct responsibility of Subcommittee E12.10 on Retroreflection.

Current edition approved Jan. 1, 2005. Published February 2005. DOI: 10.1520/E2367-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E308 Practice for Computing the Colors of Objects by Using the CIE System

E811 Practice for Measuring Colorimetric Characteristics of Retroreflectors Under Nighttime Conditions

E1710 Test Method for Measurement of Retroreflective Pavement Marking Materials with CEN-Prescribed Geometry Using a Portable Retroreflectometer

2.2 *Other Standard:*

CEN EN 1436 Road Marking Materials—Road Marking Performance for Road Users³

3. Terminology

3.1 The terminology used in this test method generally agrees with that used in Terminology E284. The definitions given in Test Method E1710 and Practice E811 apply in this test method as well.

3.2 *Definitions:*

3.2.1 *reflection colorimeter, n*—an instrument that illuminates a specimen and applies a colorimeter to the light reflected.

3.2.2 *retroreflection colorimeter, n*—a reflection colorimeter for which the illumination (influx) and reception (efflux) directions are within a few degrees of each other.

4. Summary of Test Method

4.1 This test method involves the use of portable retroreflection colorimeters for determining the chromaticity coordinates (x , y) of horizontal coatings materials used in pavement markings.

4.2 The entrance angle is fixed at 88.76° (co-entrance angle e of 1.24°).

4.3 The observation angle is fixed at 1.05° (co-viewing angle a of 2.29°).

4.4 The presentation angle shall be 0° (azimuthal angle b of 180°).

³ Available from European Committee for Standardization, Central Secretariat (CEN), rue de Stassart 36, B1050 Brussels, Belgium

4.5 The retroreflection colorimeters use one or more external panels or other instrument standards of known chromaticity coordinates (x , y), or known spectral distribution of reflected power P_{Si} .

4.6 The portable retroreflection colorimeter is placed so that the measurement area of the retroreflection colorimeter fits within the width of the stripe, and the readings displayed by the retroreflection colorimeter are recorded.

4.7 Readings shall be taken for the direction of traffic (supplementary azimuthal angle d of 0°). Readings shall be taken for each direction of traffic separately for centerlines.

5. Significance and Use

5.1 The chromaticity of the stripe is determined by means of the tristimulus values X , Y and Z for the CIE 1931 (2°) standard observer for CIE standard illuminant A, which are converted to the chromaticity coordinates (x , y) and shown in the CIE 1931 (x , y)-chromaticity diagram. Refer to Practice E308.

5.2 Under the same conditions of illumination and viewing, the chromaticity coordinates (x , y) represent the nighttime color of pavement markings in vehicle headlamp illumination as seen by drivers of the vehicles.

5.3 The chromaticity of pavement (road) markings may change with traffic wear and require periodic measurement to ensure that the chromaticity is maintained within boundaries (see Specification D6628 for examples of color boundaries).

5.4 As specified by CEN EN 1436 and Test Method E1710, the measurement geometry of the instrument is based on a viewing distance of 30 m, a headlamp mounting height of 0.65 m and an eye height of 1.2 m.

5.5 It shall be the responsibility of the user to employ an instrument having the specified observation and entrance angles.

6. Apparatus

6.1 Portable Retroreflection Colorimeter :

6.1.1 The retroreflection colorimeter shall be portable, with the capability to be placed on various horizontal pavement markings in different locations.

6.1.2 The retroreflection colorimeter shall be constructed so that placement on the highway pavement markings will preclude any stray light entering the measurement area of the instrument and affecting the reading. This may be done by shielding against stray light, or by subtraction of the stray light reading, or both. Alternatively, the retroreflection colorimeter shall produce a warning signal when stray light could affect the reading.

6.1.3 For the convenience of the user, a marking shall be placed on the instrument to permit it to be aligned with the direction of traffic, or the instrument design shall itself indicate the measuring direction in an obvious manner.

6.2 Light Source Requirements:

6.2.1 The light source shall comply with requirements of Test Method E1710, Light Source Requirements section concerning projection optics and aperture angle.

6.3 Retroreflection Colorimeter Requirements:

6.3.1 The retroreflection colorimeter shall demonstrate the capability to repeatedly and reproducibly measure values of the coefficient of retroreflected luminance over the range from 100 to 2000 $\text{mcd}\cdot\text{m}^{-2}\cdot\text{lx}^{-1}$ to within 10 % of the assigned value. In exceptional cases, R_L values can be even higher, up to 3000 $\text{mcd}\cdot\text{m}^{-2}\cdot\text{lx}^{-1}$.

6.3.2 The retroreflection colorimeter shall provide X , Y and Z tristimulus values according to the CIE 1931 (2°) color matching functions. The retroreflection colorimeter must be able to apply illumination condition correction for CIE illuminant A, and may either be a tristimulus colorimeter or a spectroradiometer.

6.3.2.1 A tristimulus colorimeter may have filters that can be inserted individually in front of a receiver to provide matches of the combined spectral distribution of the illumination and the spectral responsivity of the receiver to the combined spectral distribution of CIE illuminant A and the CIE 1931 (2°) $x(\lambda)$, $y(\lambda)$ and $z(\lambda)$ color-matching functions, respectively. The $x(\lambda)$ function has two distinct lobes. This may be dealt with by splitting $x(\lambda)$ into $x_{\text{short}}(\lambda)$ and $x_{\text{long}}(\lambda)$, each with a separate filter. The filters may be manually or automatically operated.

6.3.2.2 A spectroradiometer may measure the spectral reflectance in equal wavelength steps covering at least the wavelength range from 400 to 700 nm, with a maximum half power bandwidth of 10 nm in maximum step increment of 10 nm and from these data derive X , Y and Z tristimulus values.

NOTE 1—It is expected that a future version of this test method will include measurement of pavement marking chromaticity under lighting systems other than tungsten approximating CIE standard illuminant A. For some of these, a 5 nanometer half power bandwidth and 5 nanometer increment is recommended.

NOTE 2—Use of filters provides larger signals than measurement of the spectral distribution.

6.3.3 The retroreflection colorimeter shall determine the chromaticity coordinates (x , y) for CIE A and the CIE 1931 Observer of white and yellow pavement markings with a value of the coefficient of retroreflected luminance R_L of 100 $\text{mcd}\cdot\text{m}^{-2}\cdot\text{lx}^{-1}$, or higher, with a minimum reproducibly of 0.005 in both x and y , when calibrated and used according to the instrument manufacturers instructions.

6.3.4 The retroreflection colorimeter shall comply with requirements of Test Method E1710, Receiver Requirements sections concerning respectively receiver aperture, combined stability of the output of the light source and receiver, and linearity.

6.4 Measurement Geometry:

6.4.1 The measurement geometry shall comply with requirements of Test Method E1710, Measurement Geometry section.

7. Standardization and Procedure

7.1 The instrument will either require an external black standard or it will incorporate an internal black standard or some other internal means of zeroing.

7.1.1 If the instrument standardization requires a black standard then the black standard shall have virtually no retroreflection over the range of wavelengths for the visible