

Designation: A 516/A 516M - 01

Used in USDOE-NE Standards

## Standard Specification for Pressure Vessel Plates, Carbon Steel, for Moderate- and Lower-Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A 516/A 516M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon  $(\epsilon)$  indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

## 1. Scope

- 1.1 This specification<sup>2</sup> covers carbon steel plates intended primarily for service in welded pressure vessels where improved notch toughness is important.
- 1.2 Plates under this specification are available in four grades having different strength levels as follows:

Grade U.S. [SI]	Tensile Strength, ksi [MPa]	
55 [380]	55–75 [380–515]	
60 [415]	60–80 [415–550]	
65 [450]	65–85 [450–585]	
70 [485]	70–90 [485–620]	

1.3 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical property requirements; however, current practice normally limits the maximum thickness of plates furnished under this specification as follows:

Grade U.S. [SI]	Maximum Thickness in. [mm]	,
55 [380] ht 60 [415] andards iteh ai/o 65 [450] 70 [485]	12 [305] catalog 8 [205] and 8 8 [205] 8 [205]	

- 1.4 For plates produced from coil, the additional requirements, including additional testing requirements and the reporting of additional test results of Specification A 20/A 20M apply.
- 1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

- 2.1 ASTM Standards:
- A 20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels<sup>3</sup>
- A 435/A435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates<sup>3</sup>
- A 577/A577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates<sup>3</sup>
- A 578/A578M Specification for Straight-Beam Ultrasonic Examination of Plain and Clad Steel Plates for Special Applications<sup>3</sup>

## 3. General Requirements and Ordering Information

- 3.1 Material supplied to this material specification shall conform to Specification A 20/A 20M. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions, and mass, quality and repair of defects, marking, loading, etc.
- 3.2 Specification A 20/A20M also establishes the rules for the ordering information that should be complied with when purchasing material to this specification.
- 3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:
  - 3.3.1 Vacuum treatment,
  - 3.3.2 Additional or special tension testing,
  - 3.3.3 Impact testing, and
  - 3.3.4 Nondestructive examination.
- 3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20/A20M.
- 3.5 Coiled product is excluded from qualification to this specification until it is decoiled, leveled, and cut to length. Plate produced from coil means plate that has been cut to individual lengths from a coiled product and is furnished without heat treatment. The processor decoils, levels, cuts to length, and marks the product. Except as allowed by Section 6 in Specification A 20/A 20M, the processor is responsible for

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 10, 2001. Published Sept. 2001. Originally published as A 516-64. Last previous edition A 516/A 516M-90 (2001).

<sup>&</sup>lt;sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-516/SA-516M in Section II of that Code.

<sup>&</sup>lt;sup>3</sup> Annual Book of ASTM Standards, Vol 01.04.