

SLOVENSKI STANDARD

SIST EN 1555-3:2010+A1:2013

01-februar-2013

Nadomešča:
SIST EN 1555-3:2010

Cevni sistemi iz polimernih materialov za oskrbo s plinastimi gorivi - Polietilen (PE) - 3. del: Fitingi

Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE) - Part 3: Fittings

Kunststoff-Rohrleitungssysteme für die Gasversorgung - Polyethylen (PE) - Teil 3: Formstücke

Systemes de canalisations en plastique pour la distribution de combustibles gazeux - Polyéthylène (PE) - Partie 3: Raccords

<http://standards.iteh.ai>
<http://standards.iteh.ai/catalog/standards/sist/eb4fd104-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013>

Ta slovenski standard je istoveten z: EN 1555-3:2010+A1:2012

ICS:

83.140.30	Cevi, fittingi in ventili iz polimernih materialov	Plastics pipes, fittings and valves
91.140.40	Sistemi za oskrbo s plinom	Gas supply systems

SIST EN 1555-3:2010+A1:2013 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1555-3:2010+A1:2013](https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1555-3:2010+A1

November 2012

ICS 23.040.45

Supersedes EN 1555-3:2010

English Version

Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE) - Part 3: Fittings

Systèmes de canalisations en plastique pour la distribution
de combustibles gazeux - Polyéthylène (PE) - Partie 3 :
Raccords

Kunststoff-Rohrleitungssysteme für die Gasversorgung -
Polyethylen (PE) - Teil 3: Formstücke

This European Standard was approved by CEN on 30 July 2010 and includes Amendment 1 approved by CEN on 4 September 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 1555-3:2010+A1:2013](https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	6
1 Scope	7
2 Normative references	7
3 Terms and definitions, symbols and abbreviations	9
4 Material	10
4.1 PE Compound	10
4.2 Material for non-polyethylene parts	10
4.2.1 General.....	10
4.2.2 Metal parts	10
4.2.3 Elastomers.....	10
4.2.4 Other materials.....	10
5 General characteristics	11
5.1 Appearance	11
5.2 Colour	11
5.3 Design	11
5.4 Appearance of factory made joints.....	11
5.5 Electrical characteristics for electrofusion fittings.....	11
6 Geometrical characteristics.....	12
6.1 Measurement of dimensions	12
6.2 Dimensions of electrofusion socket fittings.....	12
6.2.1 Diameters and lengths of electrofusion sockets.....	12
6.2.2 Wall thicknesses	13
6.2.3 Out-of-roundness of the bore of a fitting (at any point).....	14
6.2.4 Spigots.....	14
6.2.5 Other dimensions	14
6.3 Dimensions of electrofusion saddle fittings.....	14
6.4 Dimensions of spigot end fittings.....	15
6.4.1 Diameters and lengths	15
6.4.2 Wall thickness of the fusion end.....	17
6.4.3 Wall thickness of the fitting body	17
6.4.4 Other dimensions	18
6.5 Dimensions of mechanical fittings	18
6.5.1 General.....	18
6.5.2 Mechanical fittings with polyethylene spigot ends.....	18
6.5.3 Mechanical fittings with polyethylene electrofusion sockets.....	18
6.5.4 Threads	18
7 Mechanical characteristics	18
7.1 General.....	18
7.2 Requirements	19
7.3 Performance requirements	21
8 Physical characteristics.....	21
8.1 Conditioning.....	21
8.2 Requirements	21
9 Performance requirements	22
10 Marking	22
10.1 General.....	22
10.2 Minimum required marking of fittings	22

10.3	Additional marking	23
10.4	Fusion system recognition.....	23
11	Delivery conditions	23
Annex A	(informative) Examples of typical terminal connection for electrofusion fittings	24
Annex B	(normative) Short-term pressure test method	26
B.1	Principle.....	26
B.2	Apparatus	26
B.3	Test piece	26
B.4	Procedure	26
B.5	Test report.....	27
Annex C	(normative) Tensile test for fitting/pipe assemblies	28
C.1	Principle.....	28
C.2	Apparatus	28
C.3	Test piece	28
C.4	Procedure	28
C.5	Test report.....	28
Bibliography	30

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 1555-3:2010+A1:2013](https://standards.iteh.ai/catalog/standards/sist/eb4fd104-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/eb4fd104-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013>

EN 1555-3:2010+A1:2012 (E)**Foreword**

This document (EN 1555-3:2010+A1:2012) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2013, and conflicting national standards shall be withdrawn at the latest by May 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 4 September 2012.

This document supersedes A1 EN 1555-3:2010 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

A1 Due to Amendment 1 to EN 1555-3:2010, this document comprises technical changes to:

— Subclause 7.2, Requirements;

— Subclause 10.2, Minimum required marking of fittings. A1

EN 1555 consists of the following parts:

- EN 1555-1, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*;
- EN 1555-2, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes*;
- EN 1555-3, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 3: Fittings* (this standard);
- prEN 1555-4, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 4: Valves*;
- EN 1555-5, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 5: Fitness for purpose of the system*;
- CEN/TS 1555-7, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 7: Guidance for assessment of conformity*.

NOTE EN 12007-2:2000 [1] prepared by CEN/TC 234 "Gas infrastructure" deals with the recommended practice for installation of plastics pipes system in accordance with EN 1555 (all parts).

System Standards are based on the results of the work being undertaken in ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids", which is a Technical Committee of the International Organization for Standardization (ISO).

They are supported by separate standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and on recommended practice for installation.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 1555-3:2010+A1:2013](https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013>

EN 1555-3:2010+A1:2012 (E)**Introduction**

The System Standard, of which this is Part 3, specifies the requirements for a piping system and its components made from polyethylene (PE) and which is intended to be used for the supply of gaseous fuels.

Requirements and test methods for material and components, other than fittings, are specified in EN 1555-1, EN 1555-2 and prEN 1555-4 [9].

Characteristics for fitness for purpose are covered in EN 1555-5. CEN/TS 1555-7 [2] gives guidance for assessment of conformity. Recommended practice for installation is given in EN 12007-2:2000 [1] prepared by CEN/TC 234.

This part of EN 1555 covers the characteristics of fittings.

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST EN 1555-3:2010+A1:2013](https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/eb4fd04-d074-4d80-91a1-2a1533b36b6e/sist-en-1555-3-2010a1-2013>

1 Scope

This **A1** European Standard **A1** specifies the characteristics of fusion fittings made from polyethylene (PE) as well as of mechanical fittings for piping systems in the field of the supply of gaseous fuels.

It also specifies the test parameters for the test methods referred to in this standard.

In conjunction with Parts 1, 2, 4 and 5 of EN 1555, it is applicable to PE fittings, their joints and to joints with components of PE and other materials intended to be used under the following conditions:

- a) a maximum operating pressure, MOP, up to and including 10 bar ¹⁾;
- b) an operating temperature of 20 °C as reference temperature.

NOTE 1 For other operating temperatures, derating coefficients should be used; see EN 1555-5.

EN 1555 (all parts) covers a range of maximum operating pressures and gives requirements concerning colours and additives.

NOTE 2 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

This European Standard is applicable for fittings of the following types:

- c) electrofusion socket fittings;
- d) electrofusion saddle fittings;
- e) spigot end fittings (for butt fusion using heated tools and electrofusion socket fusion);
- f) mechanical fittings.

The fittings can e.g. be in the form of couplers, equal and reduced tees, reducers, bends or caps.

2 Normative references

A1 The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies. **A1**

EN 682:2002, *Elastomeric Seals — Materials requirements for seals used in pipes and fittings carrying gas and hydrocarbon fluids*

EN 1555-1:2010, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*

EN 1555-2, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes*

EN 1555-5, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 5: Fitness for purpose of the system*

EN 1716, *Plastics piping systems — Polyethylene (PE) tapping tees — Test method for impact resistance of an assembled tapping tee*

1) 1 bar = 0,1 MPa.

EN 1555-3:2010+A1:2012 (E)

EN 10226-1, *Pipe threads where pressure tight joints are made on the threads — Part 1: Taper external threads and parallel internal threads — Dimensions, tolerances and designation*

EN 10226-2, *Pipe threads where pressure tight joints are made on the threads — Part 2: Taper external threads and taper internal threads — Dimensions, tolerances and designation*

EN 12117, *Plastics piping systems — Fittings, valves and ancillaries — Determination of gaseous flow rate/pressure drop relationships*

EN ISO 228-1:2000, *Pipe threads where pressure-tight joints are not made on the threads — Part 1: Dimensions, tolerances and designation (ISO 228-1:2000)*

EN ISO 1133, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics (ISO 1133:2005)*

EN ISO 1167-1:2006, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method (ISO 1167-1:2006)*

EN ISO 1167-4, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 4: Preparation of assemblies (ISO 1167-4:2007)*

EN ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions (ISO 3126:2005)*

ISO 10838-1 ²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 1: Metal fittings for pipes of nominal outside diameter less than or equal to 63 mm*

ISO 10838-2 ²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 2: Metal fittings for pipes of nominal outside diameter greater than 63 mm*

ISO 10838-3 ²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 3: Thermoplastic fittings for pipes of nominal outside diameter less than or equal to 63 mm*

ISO 11357-6:2008, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*

ISO 13950, *Plastics pipes and fittings — Automatic recognition systems for electrofusion joints*

ISO 13951:2001, *Plastics piping systems — Test method for the resistance of polyolefin pipe/pipe or pipe/fitting assemblies to tensile loading*

ISO 13953, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint*

ISO 13954, *Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm*

ISO 13955, *Plastics pipes and fittings — Crushing decohesion test for polyethylene (PE) electrofusion assemblies*

ISO/FDIS 13956, *Plastics pipes and fittings — Determination of cohesive strength — Evaluation of ductility of fusion joint interface by tear test*

2) Under revision.

3 Terms and definitions, symbols and abbreviations

For the purposes of this document, the terms and definitions, symbols and abbreviations given in EN 1555-1:2010 and the following apply.

3.1

electrofusion socket fitting

polyethylene (PE) fitting which contains one or more integral heating elements, that are capable of transforming electrical energy into heat to realise a fusion joint with a spigot end or a pipe

3.2

electrofusion saddle fitting

polyethylene (PE) fitting which contains one or more integral heating elements, that are capable of transforming electrical energy into heat to realise a fusion joint onto a pipe

3.2.1

tapping tee

electrofusion saddle fitting (top loading or wrap round) which contains an integral cutter, to cut through the wall of the main pipe which remains in the body of the tapping tee after installation

3.2.2

branch saddle

electrofusion saddle fitting (top loading or wrap round) which requires an ancillary cutting tool for drilling a hole in the adjoining main pipe

3.3

mechanical fitting

fitting, that generally includes a compression part to provide pressure integrity, leaktightness and resistance to end loads, for assembling polyethylene (PE) pipe to another PE pipe or any other element of the piping system

iTeh STANDARD PREVIEW

(standards.iteh.ai)

SIST EN 1555-3:2010+A1:2013

<https://standards.iteh.ai/catalog/standards/sist/eb46fd04-d074-4d80-91a1-2a1533f36966/sist-en-1555-3-2010-a1-2013>

NOTE 1 A pipe-supporting sleeve providing a permanent support for a polyethylene (PE) pipe to prevent creep in the pipe wall under radial compressive forces, is applicable. The metallic parts of the fitting can be assembled to metallic pipes by screw-threads, compression joints, welded or flanged connections, including PE flanges. In some cases the supporting sleeve at the same time constitutes a grip ring.

NOTE 2 The fitting can allow either a dismantable or permanently assembled joint.

NOTE 3 The mechanical fitting can be supplied for field assembly or pre-assembled by the manufacturer.

3.4

spigot end fitting

polyethylene (PE) fitting where the outside diameter of the spigot end is equal to the nominal outside diameter, d_n , of the corresponding pipe

3.5

voltage regulation

control of energy supplied, during the fusion process of an electrofusion fitting, by means of the voltage parameter

3.6

intensity regulation

control of energy supplied, during the fusion process of an electrofusion fitting, by means of the current parameter

EN 1555-3:2010+A1:2012 (E)**4 Material****4.1 PE Compound**

The PE compound from which the fittings are made shall conform to EN 1555-1.

The stress bearing parts shall only be made from virgin material conforming to EN 1555-1.

4.2 Material for non-polyethylene parts**4.2.1 General**

All components shall conform to the relevant EN standard(s). Alternative standards may be applied in cases where the suitable EN standard(s) do not exist. In all cases fitness for purpose of the components shall be demonstrated.

The materials and the constituent elements used in making the fitting (including elastomers and any metal parts as may be used) shall be as resistant to the external and internal environments as the other elements of the piping system and shall have a life expectancy under the following conditions at least equal to that of the PE pipes conforming to EN 1555-2 with which they are intended to be used:

- a) during storage;
- b) under the effect of the gas conveyed therein;
- c) with respect to the service environment and operating conditions.

The requirements for the level of material performance of non-polyethylene parts shall be at least as stringent as that of the PE compound for the piping system. Reprocessed materials shall not be used for stress bearing polymeric parts.

Other materials used in fittings in contact with the PE pipe shall not adversely affect pipe performance or initiate stress cracking.

NOTE Clause 4.2 does not apply to non-stress bearing fitting parts.

4.2.2 Metal parts

All metal parts susceptible to corrosion shall be adequately protected, providing this is necessary for the durability and function of the system.

When dissimilar metallic materials are used which can be in contact with moisture, steps shall be taken to avoid the possibility of galvanic corrosion.

4.2.3 Elastomers

Elastomeric seals shall conform to EN 682:2002.

Other sealing materials are permitted if suitable for gas service.

4.2.4 Other materials

Greases or lubricants shall not exude onto fusion areas, and shall not affect the long-term performance of fitting materials.