



Designation: D2375 – 05

Standard Test Method for Manganese in Paint Driers by EDTA Method¹

This standard is issued under the fixed designation D2375; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a titrimetric determination of manganese in liquid paint driers that can be dissolved in a toluene-alcohol mixture and utilizes the disodium salt of ethylenediaminetetraacetic acid dihydrate (EDTA).

1.2 This test method is not applicable to drier blends.

1.3 All cations that can be titrated with EDTA in alkaline media interfere and must not be present in the sample.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

D600 Specification for Liquid Paint Driers

D1193 Specification for Reagent Water

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals

E300 Practice for Sampling Industrial Chemicals

3. Summary of Test Method

3.1 The liquid drier is dissolved in toluene and ethyl alcohol and treated with an excess of standard EDTA solution. The excess is titrated with standard zinc chloride solution using Eriochrome Black-T as the indicator.

4. Significance and Use

4.1 The amount of manganese drier used in oxidizing-type coatings significantly affects their drying properties. This test

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Jan. 1, 2005. Published February 2005. Originally approved in 1965. Last previous edition approved in 1999 as D2375 – 85 (1999). DOI: 10.1520/D2375-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

method may be used to confirm the stated manganese content of pure liquid manganese drier soluble in toluene-alcohol and manufactured for use by the coatings industry.

5. Apparatus

5.1 *Centrifuge*, capable of developing 1000 to 2000 g.

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type II of Specification D1193.

6.3 *Ammonium Chloride* (NH₄Cl).

6.4 *Ammonium Hydroxide* (sp gr 0.90)—Concentrated ammonium hydroxide (NH₄OH).

6.5 *l-Ascorbic Acid*.

6.6 *Buffer Solution*—Add 350 mL of concentrated NH₄-OH (sp gr 0.90) to 54 g of NH₄Cl and dilute to 1 L with water.

6.7 *Eriochrome Black-T Indicator*—Triturate 0.2 g of Eriochrome Black-T and 100 g of NaCl, and store the mixture in a tightly stoppered bottle. This mixture remains stable for several years.

6.8 *Ethyl Alcohol* (95 %), pure or denatured.

6.9 *EDTA, Standard Solution* (0.05 M)—Dissolve 18.62 g of EDTA in water and dilute to 1 L. Store in a polyethylene or borosilicate glass bottle.

6.10 *Hydrochloric Acid* (sp gr 1.19)—Concentrated (hydrochloric acid (HCl).

6.11 *Sodium Chloride* (NaCl).

6.12 *Toluene*.

6.13 *Zinc, Granular*.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.