



SLOVENSKI STANDARD
SIST ISO 121:1995
01-november-1995

Magnezij-aluminij-cinkovi litinjski in litinjski odlitki -- Kemski sestava in mehanika lastnosti referenčnih testnih palic

Magnesium-aluminium-zinc alloy ingots and alloy castings -- Chemical composition and mechanical properties of sand cast reference test bars

ITeh STANDARD PREVIEW

Lingots et pièces moulées en alliages magnésium-aluminium-zinc -- Composition chimique et caractéristiques mécaniques des éprouvettes de référence moulées en sable

[SIST ISO 121:1995](https://standards.iteh.ai/catalog/standards/sist/0c07f661-794d-4f50-9417-86d574b4075/sist-iso-121-1995)

[https://standards.iteh.ai/catalog/standards/sist/0c07f661-794d-4f50-9417-](https://standards.iteh.ai/catalog/standards/sist/0c07f661-794d-4f50-9417-86d574b4075/sist-iso-121-1995)

[86d574b4075/sist-iso-121-1995](https://standards.iteh.ai/catalog/standards/sist/0c07f661-794d-4f50-9417-86d574b4075/sist-iso-121-1995)

Ta slovenski standard je istoveten z: ISO 121:1980

ICS:

77.150.01 Izdelki iz neželeznih kovin na splošno Products of non-ferrous metals in general

SIST ISO 121:1995

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 121:1995

<https://standards.iteh.ai/catalog/standards/sist/0c07f661-794d-4f50-9417-86d574f34075/sist-iso-121-1995>

International Standard



121

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Magnesium-aluminium-zinc alloy ingots and alloy castings — Chemical composition, and mechanical properties of sand cast reference test bars

Lingots et pièces moulées en alliages magnésium-aluminium-zinc — Composition chimique et caractéristiques mécaniques des éprouvettes de référence moulées en sable

STANDARD PREVIEW

First edition — 1980-08-01

(standards.iteh.ai)

[SIST ISO 121:1995](https://standards.iteh.ai/catalog/standards/sist/0c07f661-794d-4f50-9417-86d574f34075/sist-iso-121-1995)

<https://standards.iteh.ai/catalog/standards/sist/0c07f661-794d-4f50-9417-86d574f34075/sist-iso-121-1995>

UDC 669.721.5'71'5-412

Ref. No. ISO 121-1980 (E)

Descriptors : magnesium alloys, magnesium aluminium zinc alloys, castings, chemical composition, mechanical properties, tensile properties.

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 121 was developed by Technical Committee ISO/TC 79, *Light metals and their alloys*.

It was submitted directly to the ISO Council, in accordance with clause 5.10.1 of part 1 of the Directives for the technical work of ISO. It cancels and replaces ISO Recommendation R 121-1971, which had been approved by the member bodies of the following countries :

Austria	India	Portugal
Belgium	Israel	South Africa, Rep. of
Canada	Italy	Switzerland
Egypt, Arab Rep. of	Japan	Thailand
Finland	New Zealand	Turkey
France	Norway	USA
Germany, F.R.	Poland	USSR

The member bodies of the following countries had expressed disapproval of the document on technical grounds :

United Kingdom
Sweden

This International Standard also cancels and replaces ISO Recommendation R 122-1959, which had been approved by the member bodies of the following countries :

Austria	Hungary	Portugal
Belgium	Italy	Romania
Canada	Japan	Spain
Chile	Netherlands	Sweden
Czechoslovakia	New Zealand	Switzerland
France	Norway	United Kingdom
Germany, F.R.	Poland	USSR

The member body of the following country had expressed disapproval of the document on technical grounds :

USA

Magnesium-aluminium-zinc alloy ingots and alloy castings – Chemical composition, and mechanical properties of sand cast reference test bars

1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies the chemical compositions of magnesium-aluminium-zinc alloy¹⁾ ingots for casting purposes and of magnesium-aluminium-zinc alloy castings, together with requirements for the mechanical properties of sand cast reference test bars in these alloys in various tempers as defined in ISO/R 2107.

NOTE – The alloys referred to in table 1 belong to the same family of magnesium-aluminium-zinc alloys, but the development of compositions for use in foundries has proceeded, in different countries and at different times, along two distinct lines :

- alloys of relatively high zinc content;
- alloys of relatively low zinc content.

To take account of these differences, it has been necessary to specify the five compositions given in table 1.

Alloy Mg-Al8Zn1, although having wider compositional tolerances, has properties which are suitable for numerous applications for which more closely specified alloys are not necessary.

Differences between these five compositions are less marked in regard to mechanical properties than in regard to some other charac-

teristics, such as casting properties, provided that comparisons are made between alloys in corresponding states.

2 REFERENCES

ISO/R 190, *Tensile testing of light metals and their alloys.*

ISO 2092, *Light metals and their alloys – Code of designation.*²⁾

ISO/R 2107, *Light metals and their alloys – Temper designations.*

ISO 2377, *Magnesium alloy sand castings – Reference test bar.*

3 CHEMICAL COMPOSITION

3.1 Magnesium-aluminium-zinc alloy ingots for casting

See table 1.

TABLE 1

Alloy	Chemical composition, %						
	Al	Zn	Mn	Si, max.	Fe, max.	Cu, max.	Ni, max.
Mg-Al8Zn	7,5 to 8,5	0,3 to 0,8	0,20 to 0,6	0,2	0,03	0,15	0,01
Mg-Al9Zn	8,3 to 9,8	0,3 to 0,8	0,20 to 0,6	0,2	0,03	0,15	0,01
Mg-Al9Zn2	8,0 to 9,5	1,7 to 2,3	0,13 to 0,5	0,2	0,03	0,15	0,01
Mg-Al6Zn3	5,0 to 6,5	2,3 to 3,3	0,15 to 0,5	0,2	0,03	0,15	0,01
Mg-Al8Zn1	7,0 to 9,2	0,4 to 1,8	0,2 min.	0,3	0,05	0,3	0,02

1) For designations, see ISO 2092.

2) At present at the stage of draft. (Revision of ISO/R 2092-1971.)

ISO 121-1980 (E)

3.2 Castings in magnesium-aluminium-zinc alloys

See table 2.

4 MECHANICAL PROPERTIES OF SAND CAST REFERENCE TEST BARS

The required mechanical properties for sand cast reference test bars are given in table 3.

A standard reference test bar and a sand mould comprising a group of four test bars, complying with the requirements of ISO 2377, will allow the minimum characteristics to be obtained.

Alternatively, test bars of diameter not less than 13 mm, which may be machined to a diameter of not less than 11,3 mm, may be used for reference purposes. As is the case for the ISO bar, such alternative test bars shall be cast in groups of four, entirely in sand moulds, with no other form of additional chilling.

5 CASTING METHODS AND TEMPER OF PRODUCTS

The casting methods and the tempers of products made from these alloys are given in table 4; the most widely used are indicated in *italic*.

TABLE 4

Alloy	Casting method	Temper
Mg-Al8Zn	<i>Sand</i>	<i>As cast</i>
	<i>Gravity die</i>	<i>Solution-treated</i>
	<i>Pressure die</i>	Fully heat-treated
Mg-Al9Zn	<i>Sand</i>	<i>As cast</i>
	<i>Gravity die</i>	<i>Solution-treated</i>
	<i>Pressure die</i>	<i>Fully heat-treated</i>
Mg-Al9Zn2	<i>Sand</i>	As cast
	<i>Gravity die</i>	<i>Solution-treated</i>
	<i>Pressure die</i>	<i>Fully heat-treated</i>
Mg-Al6Zn3	<i>Sand</i>	<i>As cast</i>
	<i>Gravity die</i>	Solution-treated
Mg-Al8Zn1	<i>Sand</i>	<i>As cast</i>
	<i>Gravity die</i>	Solution-treated
	<i>Pressure die</i>	

NOTE — Pressure die castings are only supplied "as cast".

TABLE 2

Alloy	Chemical composition, %						
	Al	Zn	Mn	Si, max.	Fe, max.	Cu, max.	Ni, max.
Mg-Al8Zn	7,5 to 9,0	0,2 to 1,0	0,15 to 0,6	0,3	0,05	0,2	0,01
Mg-Al9Zn	8,3 to 10,3	0,2 to 1,0	0,15 to 0,6	0,3	0,05	0,2	0,01
Mg-Al9Zn2	8,0 to 10,0	1,5 to 2,5	0,10 to 0,5	0,3	0,05	0,2	0,01
Mg-Al6Zn3	5,0 to 7,0	2,0 to 3,5	0,10 to 0,5	0,3	0,05	0,2	0,01
Mg-Al8Zn1	7,0 to 9,5	0,3 to 2,0	0,15 min.	0,5	0,05	0,35	0,02

TABLE 3

Alloy	Temper	Tensile strength*	0,2 % yield strength	Elongation
		R_m N/mm ²	$R_{p0,2}$ N/mm ²	A %
Mg-Al8Zn	M	140	75	1
	TB	230	75	6
	TF	235	95	2
Mg-Al9Zn	M	140	75	1
	TB	230	75	6
	TF	235	110	1
Mg-Al9Zn2	M	140	75	1
	TB	230	75	5
	TF	235	110	1
Mg-Al6Zn3	M	160	75	3
Mg-Al8Zn1	M	140	75	(not required)

* See ISO/R 190.