

SLOVENSKI STANDARD
kSIST-TP FprCEN/TR 17330:2018
01-december-2018

Smernice za izbiro, uporabo, nego in vzdrževanje varovalne obleke, ki varuje pred slabim vremenom, vetrom in mrazom

Guidelines for selection, use, care and maintenance of protective clothing against foul weather, wind and cold

Anleitungen für die Auswahl, Anwendung, Pflege und Erhaltung von Schutzkleidung gegen schlechtes Wetter, Wind und Kälte

<https://standards.iteh.ai/catalog/standards/sist/e2907893-9255-4109-ad66-ab7606d6c3e2/sist-tp-cen-tr-17330-2018>

Ta slovenski standard je istoveten z: FprCEN/TR 17330

ICS:

13.340.10	Varovalna obleka	Protective clothing
-----------	------------------	---------------------

kSIST-TP FprCEN/TR 17330:2018	en,fr,de
--------------------------------------	-----------------

TECHNICAL REPORT
RAPPORT TECHNIQUE
TECHNISCHER BERICHT

FINAL DRAFT
FprCEN/TR 17330

October 2018

ICS

English Version

**Guidelines for selection, use, care and maintenance of
protective clothing against foul weather, wind and cold**

Anleitungen für die Auswahl, Anwendung, Pflege und
Erhaltung von Schutzkleidung gegen schlechtes
Wetter, Wind und Kälte

This draft Technical Report is submitted to CEN members for Vote. It has been drawn up by the Technical Committee CEN/TC 162.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a Technical Report. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a Technical Report.

<https://standards.iteh.ai/catalog/standards/sist/e2907893-9255-4109-ad66-ab760fdfe3e2/sist-tp-cen-tr-17330-2019>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Selection	11
4.1 General	11
4.2 Risk assessment.....	11
4.3 Selection of protective clothing based on risk assessment.....	11
4.4 Optimal protective clothing	12
4.5 Request for information	13
4.6 Wearer trials.....	14
4.7 Additional assessment to assist selection process.....	15
4.8 Other considerations	16
5 Use	16
5.1 General.....	16
5.2 Training	17
5.3 Introducing protective clothing into service	17
5.3.1 Record keeping	17
5.3.2 Routine examination (see also 8.2 “Inspections”)	18
5.3.3 In service evaluation and monitoring.....	18
5.3.4 Frequency of cleaning on the protective clothing	19
6 Care	19
6.1 General.....	19
6.2 Cleaning and drying	20
6.2.1 Cleaning	20
6.2.2 Drying.....	21
6.3 Label, Marking and Instruction for Use/Manufacturer’s Instructions/User Instructions	21
6.4 Storage	21
7 Maintenance.....	22
7.1 General.....	22
7.2 Inspection	22
7.2.1 General	22
7.2.2 Inspections scheduled by the user	23
7.2.3 Elements to be inspected.....	23
7.2.4 Decisions	24
7.3 Repairs and alterations.....	24
7.4 Disposal	24
Annex A (informative) EN standards and their performance levels relating to clothing designed to provide protection from foul weather, wind and cold	25
A.1 General.....	25

A.2	Standards describing performance requirements for protective clothing or materials	25
A.2.1	Product Standards.....	25
A.2.2	Test methods.....	25
Annex B (informative)	Risk assessment.....	27
Annex C (informative)	Guidance on some investigated Artic case scenarios	29
C.1	Case Scenario1	29
C.2	Case Scenario 2	30
Bibliography		34

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST-TP CEN/TR 17330:2019

<https://standards.iteh.ai/catalog/standards/sist/e2907893-9255-4109-ad66-ab760fdfe3e2/sist-tp-cen-tr-17330-2019>

FprCEN/TR 17330:2018 (E)**European foreword**

This document (FprCEN/TR 17330:2018) has been prepared by Technical Committee CEN/TC 162 “Protective clothing including hand and arm protection and lifejackets”, the secretariat of which is held by DIN.

This document is currently submitted to the Vote on TR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Regulation (EU) 2016/425 indicates that PPE placed on the market complies with the essential health and safety requirements, and not necessarily with the various relevant EN or EN ISO standards. Nevertheless nearly all PPE meet the essential requirements of the standards, as harmonized standards give presumption of conformity with the requirements of the Directive.

The reader should be aware that if PPE is intended for use at a workplace, national and European legislation intended to ensure the safety of employees usually applies. When one mentions PPE, it must meet the requirements of Regulation (EU) 2016/425.

All Annexes are informative.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST-TP CEN/TR 17330:2019

<https://standards.iteh.ai/catalog/standards/sist/e2907893-9255-4109-ad66-ab760fdfe3e2/sist-tp-cen-tr-17330-2019>

Introduction

This document has the aim to serve as guideline and checklist for companies preparing their own protective clothing program based on risk analysis.

The information in this document has been produced to assist users, employers and purchasers (or the person who advises the employer) in making the necessary decisions regarding the selection, use, care and maintenance of protective clothing, for employees exposed to risks related to cold and cool.

The purpose of this technical report is to establish a guideline for protective clothing against cold and cool with the goal to evaluate and reduce the safety risks and potential health risks associated with poorly maintained, contaminated, or damaged protective clothing. This Selection, Use, Care and Maintenance guideline (SUCAM) provides best practice, answers, criteria, and options related to foul weather, wind and cold to the persons that are selecting or using protective clothing through its life cycle with respect to protection.” The main topics that an employer needs to consider are highlighted in this document. Many paragraphs of the document contain bullet-lists as examples and options that may need to be considered.

The Annexes give additional details that are necessary to describe hazards and risks, the value of the test methods for the end user, etc.

Annex A gives details of the current EN or EN ISO Standards relating to clothing designed to provide protection from cool and cold.

Please be aware of and consider compatibility with other items of PPE that both protect against cold and cool, but consider other risks as well.

For European legislation on PPE see Regulation (EU) 2016/425 of the European Parliament and of Council of 9 March 2016 on personal protective equipment.

[SIST-TP CEN/TR 17330:2019](https://standards.iteh.ai/catalog/standards/sist/e2907893-9255-4109-ad66-ab760fdfe3e2/sist-tp-cen-tr-17330-2019)

<https://standards.iteh.ai/catalog/standards/sist/e2907893-9255-4109-ad66-ab760fdfe3e2/sist-tp-cen-tr-17330-2019>

FprCEN/TR 17330:2018 (E)

1 Scope

This document provides guidance to the employers or persons advising them such as suppliers of PPE or services, inspection, insurance companies etc.) in taking the necessary decisions regarding the selection, use, care and maintenance of protective clothing against foul weather, wind and cold, and is compliant with the applicable European legislation.

This document is not exhaustive in addressing all the safety concerns associated with the use of compliant protective equipment for protection against foul weather, wind and cold and other related risks.

This document does not address all the safety concerns, if any, associated with the use of this document by testing or repair facilities. It is the responsibility of the persons and organizations using this document and any other documents related to PPE:

- to conduct a risk assessment,
- to select the protective clothing and other PPE,
- to ensure that these provide a holistic protection; this can be achieved by not only assessing the risks, but also the work place and the work environment and to determine the applicability of regulatory limitations prior to using this document for any designing, manufacturing, and testing.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 13688, *Protective clothing -- General requirements* 17330:2019

<https://standards.iteh.ai/catalog/standards/sist/e2907893-9255-4109-ad66-ab760fdfe3e2/sist-tp-cen-tr-17330-2019>

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

ageing

change of one or more initial properties of protective materials during the passage of time

[SOURCE: EN ISO 13688:2013, 3.1]

3.2

air permeability

AP

velocity of an air flow passing perpendicularly through a test specimen under specified conditions of test area, pressure drop and time

Note 1 to entry: AP is expressed in millimetres per second.

[SOURCE: EN ISO 9237:1995, 3.1, modified: abbreviation added as admitted term and Note 1 to entry added]

3.3

care

provisions for cleaning, decontamination and storage of the protective clothing

3.4

cold environment

environment characterized by the combination of humidity and wind (wind-chill effect) at air temperature equal to or less than -5°C

[SOURCE: EN 342:2017, 3.1]

3.5

compatibility

ability of clothing (protective clothing and other clothing) to be used in conjunction with other parts of PPE

3.6

cool environment

environment characterized by the combination of humidity and wind (wind cooling effect) at air temperatures above -5°C

[SOURCE: EN 14058:2017, 3.1]

3.7

deterioration

downgrading of the effectiveness or physical characteristics of textile materials due to use, care, maintenance or storage conditions

3.8

ensemble

combination or assembly of multiple items that are individually compliant and provide protection to the head, upper torso together with arms and hands, the lower torso together with feet, and respiratory protection, and that together fulfil all the requirements

3.9

ergonomics

scientific discipline concerned with the understanding of interactions among human and other elements of a system, and the profession that applies theory, principles, data and methods to design in order to optimize human well-being and overall system performance

[SOURCE: EN ISO 26800:2011, 2.2, accepted term and note to entry deleted]

3.10

field evaluation

non-laboratory assessment of an ensemble, ensemble element, or item

3.11

fit

quality, state, and manner in which clothing, when worn, relates to the individual human body or other PPE

FprCEN/TR 17330:2018 (E)**3.12****garment**

individual component of a clothing ensemble covering a part of the body, except separate garment for head, hands and feet and providing protection against hypothermia

[SOURCE: EN 342:2017, 3.2]

3.13**hardware**

non-fabric items used in protective clothing including those made of metal or plastic, e.g. fasteners, rank markings, buttons, zippers

[SOURCE: EN 469:2005, 3.7]

3.14**hazard**

situation which can be the cause of harm or damage to the health of the human body

[SOURCE: EN ISO 13688:2013, 3.2, modified: Note 1 to entry deleted]

3.15**hygiene**

any practice or activity that you do to keep protective clothing healthy and clean

3.16**insulation required****IREQ**

required resultant thermal insulation calculated on the basis of the thermal parameters of the environment (e. g. air temperature, mean radiant temperature, air velocity, relative humidity) and the body metabolism

[SOURCE: EN 14058:2004, 3.6.3, modified: term split into term and acronym, Note 1 to entry deleted]

3.17**integrity**

construction of the protective clothing that ensures the proper functioning of the protective clothing

Note 1 to entry: Seams, zippers and other closures provide integrity if they constitute solid barriers which ensure suitable protection while offering some flexibility by design.

3.18**maintenance**

preservation from loss or deterioration by applying procedures for inspection, repair and ultimate removal from service

3.19**outer shell material**

outermost material of which the protective clothing is made

[SOURCE: EN 342:2017, 3.11]

3.20**protective clothing**

clothing which covers or replaces personal clothing and which is designed to provide protection against one or more hazards

[SOURCE: EN ISO 13688:1998, 3.4]

3.21**resistance to water penetration****WP**

hydrostatic pressure supported by a material as a measure of the opposition to the passage of water through material

Note 1 to entry: WP is expressed in pascal.

[SOURCE: EN 342:2017, 3.9]

3.22**resultant effective thermal insulation** **I_{cler}**

thermal insulation from skin to outer clothing surface under defined conditions measured with or calculated for a moving manikin determined in relation to the naked body surface area

Note 1 to entry: I_{cler} is expressed in square metres Kelvin per watt

[SOURCE: EN 342:2017, 3.8]

3.23**risk**

probability of a specific undesired event occurring so that a hazard is realized

[SOURCE: EN 340:1993, 3.2]

3.24**risk assessment**

overall process that identifies hazards, estimates the potential severity of injury or damage to health, estimates the likelihood of occurrence of injury or danger to health determines the protective clothing against cold and cool and other protection measures required

3.25**selection**

process of determining the type of protective equipment (garments) that is necessary for the required protection

3.26**tensile strength**

force at which a fibre or fabric will break when pulled in one dimension

3.27**textile fabric**

planar structure consisting of yarns or fibres

FprCEN/TR 17330:2018 (E)**3.28****thermal lining**

non-watertight layer providing thermal insulation

[SOURCE: EN 14058:2004, 3.4]

3.29**thermal resistance
insulation** **R_{ct}**

temperature difference between the two faces of a material divided by the resultant heat flux per unit area in the direction of the gradient

Note 1 to entry: It is a quantity specific to textile materials or composites, which determines the dry heat flux across a given area in response to a steady applied temperature gradient. The dry heat flux can consist of one or more conductive, convective and radiant components.

Note 2 to entry: The thermal resistance is expressed in square metres kelvin per watt.

[SOURCE: EN ISO 11092:2014, 2.1]

3.30**trousers**

element of the protective ensemble that provides protection to the lower torso and legs, excluding the ankles and feet

3.31**use**

application of protective clothing including its limitations

3.32**verified independent service provider****ISP**

independent service provider verified by a third-party certification organization and who conducts, as individual or combined services, advanced inspection, advanced cleaning, basic repair, or advanced repair

3.33**water vapour resistance** **R_{et}**

water vapour pressure difference between the two faces of a material divided by the resultant evaporative heat flux per unit area in the direction of the gradient

Note 1 to entry: It is a quantity specific to textile materials or composites, which determines the “latent” evaporative heat flux across a given area in response to a steady applied water vapour pressure gradient. The evaporative heat flux can consist of both diffusive and convective components.

Note 2 to entry: The water vapour resistance is expressed in square metres pascal per watt.

[SOURCE: EN ISO 11092:2014, 2.2]