
**Paints and varnishes —
Determination of resistance to cyclic
corrosion conditions —**

Part 1:

Wet (salt fog)/dry/humidity

iTeh STANDARD PREVIEW

(standards.iteh.ai)

*Peintures et vernis — Détermination de la résistance aux conditions de
corrosion cyclique*

Partie 1: Brouillard salin/sécheresse/humidité

[ISO 11997-1:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/1f57f3f5-a758-4f0f-b6ae-41714d9d39ed/iso-11997-1-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 11997-1:2005](https://standards.iteh.ai/catalog/standards/sist/1f57f3f5-a758-4f0f-b6ae-41714d9d39ed/iso-11997-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/1f57f3f5-a758-4f0f-b6ae-41714d9d39ed/iso-11997-1-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope.....	1
2 Normative references	1
3 Principle	2
4 Required supplementary information	2
5 Salt fog test solution.....	2
6 Apparatus.....	3
7 Sampling	4
8 Test panels	4
9 Method of exposure of test panels.....	5
10 Operating conditions	5
11 Procedure.....	5
12 Examination of test panels.....	6
13 Precision	6
14 Test report.....	6
Annex A (normative) Required supplementary information.....	8
Annex B (informative) Factors to be considered in the design and construction of salt spray cabinets.....	9
Annex C (normative) Cycle A	10
Annex D (normative) Cycle B	11
Annex E (normative) Cycle C	12
Annex F (normative) Cycle D.....	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11997-1 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 11997-1:1998) (including Technical Corrigendum ISO 11997-1:1998/Cor.1:1998), in which cycle A has been revised and cycle D has been added to correlate with ISO 14993:2001, *Corrosion of metals and alloys — Accelerated testing involving cyclic exposure to salt mist, “dry” and “wet” conditions*.

ISO 11997 consists of the following parts, under the general title *Paints and varnishes — Determination of resistance to cyclic corrosion conditions*:

- *Part 1: Wet (salt fog)/dry/humidity*
- *Part 2: Wet (salt fog)/dry/humidity/UV light*

Introduction

Coatings of paints, varnishes and similar materials are exposed to one of four cycles of wet and dry conditions using specified salt solutions in a cabinet in order to simulate, in the laboratory, processes occurring in aggressive outdoor conditions, such as marine environments. Generally, correlation between such outdoor weathering and laboratory testing cannot be expected because of the large number of factors influencing the breakdown process. Correlation can only be expected if the effect on the coating of important parameters (e.g. the nature of the pollutant, the spectral distribution of the incident irradiance in the relevant photochemical region, the temperature of the specimen, the type and cycle of wetting and relative humidity) is known. In contrast to outdoor weathering, laboratory testing in a cabinet is performed with a reduced number of variables which can be controlled, and therefore the effects are more reproducible. The method described may also give a means of checking that the quality of a paint or paint system is being maintained.

The method has been found to be useful in comparing the cyclic salt spray resistance of different coatings. It is most useful in providing relevant ratings for a series of coated panels exhibiting significant differences in cyclic salt spray resistance.

The test cycles included in this part of ISO 11997 have been used successfully, with documented evidence, in the industry for the assessment of performance. The cycles can be summarized as follows.

- **Cycle A (see Annex C):** This cycle is specified in Japanese Automobile Standards JASO M 609-91, *Corrosion test method for automotive materials*, and JASO M610-92, *Cosmetic corrosion test method for automotive parts*.
- **Cycle B (see Annex D):** This is based on the VDA 621-415 cycle and is widely used in Europe. It has also been shown to give good correlation with natural weathering for thermosetting paints in vehicle corrosion.
- **Cycle C (see Annex E):** This cycle was developed in the UK for use with water-soluble and latex paint systems, and has been shown to give good correlation with natural weathering.
- **Cycle D (see Annex F):** This cycle is specified in Japanese Standard JIS K 5621-2003, *Anticorrosive paint for general use*.

It is intended that other cycles will be added at later revisions of this part of ISO 11997, as they are developed for evaluating other paint types.

ISO 11997-2 describes a method for determining the cyclic corrosion resistance of paints which includes UV exposure as part of the cycle. It has been found to give good correlation with natural weathering for industrial maintenance coatings.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 11997-1:2005](https://standards.iteh.ai/catalog/standards/sist/1f57f3f5-a758-4f0f-b6ae-41714d9d39ed/iso-11997-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/1f57f3f5-a758-4f0f-b6ae-41714d9d39ed/iso-11997-1-2005>

Paints and varnishes — Determination of resistance to cyclic corrosion conditions —

Part 1: Wet (salt fog)/dry/humidity

1 Scope

This part of ISO 11997 describes a method for the determination of the resistance of coatings to one of four defined cycles of wet (salt fog)/dry/humidity conditions using specified solutions.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of samples for testing*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4628-1, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 1: General introduction and designation system*

ISO 4628-2, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*

ISO 4628-3, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 3: Assessment of degree of rusting*

ISO 4628-4, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 4: Assessment of degree of cracking*

ISO 4628-5, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 5: Assessment of degree of flaking*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Principle

A coated test panel is exposed to a cyclic wet (salt fog), drying and humidity test schedule and the effects of exposure are evaluated by criteria agreed in advance between the interested parties, these criteria usually being of a subjective nature.

4 Required supplementary information

For any particular application, the test method described in this part of ISO 11997 needs to be completed by the supplementary information given in Annex A.

5 Salt fog test solution

Prepare the salt fog test solution by dissolving the salt or salts as given in Annexes C, D, E and F in water conforming to at least grade 2 of ISO 3696, to produce the required concentration.

The salts shall be of analytical grade or visually white, and conform with the purity requirements given in Table 1.

Table 1 — Purity of salts

Impurity	Maximum mass fraction of impurity %	Method of determination
Total	0,5	Calculated as a percentage of the dry salt
Iodide	0,1	Calculated as a percentage of the dry salt
Copper	0,001	Determined by spectrophotometry or another method of similar accuracy
Nickel	0,001	Determined by spectrophotometry or another method of similar accuracy

If the pH of the solution is outside the required range (see Annexes C, D, E and F), the presence of undesirable impurities in the salt or the water or both shall be investigated. The pH determination shall be based on electrometric measurement at 25 °C, but a narrow-range indicator paper which can be read in increments of 0,3 pH-units or less and which has been calibrated against electrometric measurements may be used in routine checks. Any necessary corrections shall be made by adding hydrochloric acid, sodium hydrogen carbonate (both of purity conforming to the requirements of Table 1) or analytical-grade sodium hydroxide, of appropriate concentrations.

NOTE Attention is drawn to the possible changes in pH resulting from loss of carbon dioxide from the solution when it is sprayed, or from dissolution of carbon dioxide from the ambient atmosphere. Such changes may be avoided by reducing the carbon dioxide content of the solution by, for example, heating it to a temperature above 35 °C before it is placed in the cabinet or making the solution from freshly boiled water.

Filter the solution before placing it in the reservoir of the cabinet, in order to remove any solid matter which might block the apertures of the spraying device.

6 Apparatus

Ordinary laboratory apparatus and glassware, together with the following:

6.1 Spray cabinet, made of, or lined with, material resistant to corrosion by the sprayed solution and having a roof which prevents condensed moisture dripping onto the test specimens. The cabinet shall have a capacity of not less than 0,4 m³ in order to ensure even distribution of the spray.

The size and shape of the cabinet shall be such that the salt fog deposition rate is within the limits given in Annexes C, D, E and F.

NOTE Cabinets with a volume greater than 2 m³ will be difficult to operate unless careful consideration is given to their design and construction.

Factors to be taken into consideration in the design and construction of the cabinet are given in Annex B.

If the cabinet has been used for a spray test, or for any other purpose, using a solution differing from that specified for the current test cycle, it shall be thoroughly cleaned before use.

6.2 Hot-air blowers, capable of maintaining the cabinet and its contents at the specified temperatures and achieving the required heating rates (see Annexes C, D, E and F). The temperature shall be controlled by a thermostat element placed within the cabinet at least 100 mm from the walls of the cabinet.

6.3 Means for spraying the salt solution, comprising a supply of clean compressed air at a controlled pressure, a reservoir to contain the solution to be sprayed, and one or more atomizers made of material resistant to the solution. The compressed-air supply to each atomizer shall be passed through a filter to remove all traces of oil or solid matter, shall be at a suitable pressure depending upon the type of atomizer nozzle and shall be adjusted so that the rate of collection of spray in the cabinet and the concentration of the collected spray are kept within the specified limits (see Annexes C, D, E and F).

The reservoir containing the solution to be sprayed shall be a tank made of material resistant to the solution and shall be provided with means of maintaining a constant flow of solution to the atomizers.

The atomizers shall be made of inert material, for example glass or plastic.

NOTE Baffles may be used to prevent direct impingement of spray on the test specimens, and the use of adjustable baffles is helpful in obtaining uniform distribution of spray throughout the cabinet.

6.4 Drying-air supply, of 20 % to 30 % relative humidity for cycles A and D (see Annexes C and F) and of (50 ± 20) % relative humidity for cycles B and C (see Annexes D and E). The air shall be passed through a filter to remove all traces of oil or solid matter and shall have a flow rate sufficient to ensure that, at the start of a dry phase, no drops of moisture are visible on the panels after the drying time specified for cycles A and D and after 45 min for cycles B and C. The panels shall not be dried by heaters inside the cabinet walls.

NOTE It is common practice to vent the cabinet to the atmosphere outside the laboratory.

6.5 Collecting devices, at least two, of chemically inert material (see Note). The collecting devices shall be placed in the zone of the cabinet where the test panels are placed, one close to the spray atomizer(s) and one remote from the spray atomizer(s). They shall be placed so that only spray and not liquid falling from test panels or from parts of the cabinet is collected. If two or more atomizers are used, the number of collecting devices shall be at least twice the number of atomizers.

NOTE Glass funnels with the stems inserted into graduated cylinders have been found to be suitable collecting devices. Funnels with a diameter of 100 mm have a collecting area of approximately 80 cm².

6.6 Test panel racks, made of inert non-metallic material such as glass, plastic or suitably coated wood. Exceptionally, test panels may be suspended. In this case, the material used shall be synthetic fibre, cotton thread or other inert insulating material; on no account shall metallic material be used. All racks shall be placed at the same level in the cabinet so that the solution cannot drip from panels or racks at one level onto other panels placed below.

6.7 Control equipment, for providing wet (salt fog)/dry/humidity cycles for the times and temperatures specified in Annexes C, D, E and F.

7 Sampling

Take a representative sample of the product to be tested (or of each product in the case of a multi-coat system), as described in ISO 15528.

Examine and prepare each sample for testing, as described in ISO 1513.

8 Test panels

8.1 Material and dimensions

Unless otherwise specified or agreed, the test panels shall be of burnished steel complying with ISO 1514, and of minimum dimensions 100 mm × 70 mm × 0,3 mm.

8.2 Preparation and coating of panels

Unless otherwise specified, prepare each test panel in accordance with ISO 1514 and then coat it by the specified method with the product or system under test.

Unless otherwise specified, the back and edges of the panel shall be coated with the product or system under test.

If the coating on the back and edges of the panel differs from that of the product under test, it shall have a corrosion resistance greater than that of the product under test.

<https://standards.iteh.ai/catalog/standards/sist/1f57b35-a758-4f0f-b6ae-41714d9d39ed/iso-11997-1-2005>

8.3 Drying and conditioning

Dry (or stove) and age (if applicable) each coated test panel for the specified time under the specified conditions, and then, unless otherwise specified, condition them at a temperature and relative humidity as defined in ISO 3270 for at least 16 h, with free circulation of air and without exposing them to direct sunlight. The test procedure shall then be carried out as soon as possible.

8.4 Thickness of coating

Determine the thickness, in micrometres, of the dried coating by one of the non-destructive procedures described in ISO 2808.

8.5 Preparation of scribe

Unless otherwise specified, make a straight scribe with a minimum width of 0,2 mm through the coating to the substrate as follows:

To make the scribe, use a single-blade cutting tool. The scribe shall have an upwards-broadening cross-section which shows a width of 0,2 mm to 1,0 mm of the metallic substrate. Remove any loose debris from the vicinity of the scribe.

Do not cut the scribe with a knife.

For aluminium panels, make two scribes which are perpendicular to, but do not intersect, each other. One scribe shall be parallel to the rolling direction and the other at right angles to it.

All scribes shall be at least 20 mm from each other and from any edge of the test panel, unless agreed otherwise.

Two parallel scribes may also be applied. Unless agreed otherwise, locate the scribes parallel to the longer edge of the test panel.

Care needs to be taken in the production of the scribe to ensure uniformity of results.

9 Method of exposure of test panels

Place the panels in the cabinet in such a way that they are not in the path of spray from the atomizer.

Place the panels facing upwards at an angle of $(20 \pm 5)^\circ$ to the vertical.

The angle at which each panel is exposed in the cabinet is very important.

It is sometimes necessary to expose painted components of different shapes. When such tests are conducted, it is of particular importance to expose the shaped components at the angle at which they are normally used. While satisfying this restriction, the component shall also be placed so as to minimize the disruption of flow. Furthermore, other test panels and components cannot be tested at the same time if the shape of the painted component interferes with the general direction of flow.

The degree of film breakdown may vary with different test specimen orientations, and due consideration shall be given to this when interpreting the results.

Arrange the panels so that they do not come into contact with one another or with the cabinet and so that the surfaces to be tested are exposed to the spray only where it is settling freely.

It is recommended that the positions of the test panels be rotated on a daily basis to ensure positional effects within the cabinet do not interfere with the degradation process.

10 Operating conditions

Set the cabinet to run on the required spray cycle only and determine the salt fog deposition rate. The average rate of collection of solution in each collecting device (6.5) measured over a minimum period of 24 h shall be as given in the appropriate annex (C, D, E or F) for a horizontal collecting area of 80 cm². This gives a more accurate assessment of the deposition rate, as the water will evaporate away from the collection devices during the drying cycles.

The solution collected shall have the concentration given in the appropriate annex (C, D, E or F).

Operate the cabinet to the required cycle (see Annex C, D, E or F) unless otherwise specified, repeating the cycle for the required time.

Do not re-use test solution which has already been sprayed.

11 Procedure

Carry out the determination in duplicate, unless otherwise agreed.

Set up the cabinet as described in Clause 10 and allow equilibrium to be established.

Arrange the test panels in the cabinet (6.1) as described in Clause 9.