



Standard Specification for Pressure Vessel Plates, Alloy Steel, Chromium-Molybdenum¹

This standard is issued under the fixed designation A 387/A 387M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers chromium-molybdenum alloy steel plates intended primarily for welded boilers and pressure vessels designed for elevated temperature service.

1.2 Plates are available under this specification in several grades having different alloy contents as follows:

Grade	Nominal Chromium Content, %	Nominal Molybdenum Content, %
2	0.50	0.50
12	1.00	0.50
11	1.25	0.50
22, 22L	2.25	1.00
21, 21L	3.00	1.00
5	5.00	0.50
9	9.00	1.00
91	9.00	1.00

1.3 Each grade except Grades 21L, 22L, and 91 is available in two classes of tensile strength levels as defined in the Tensile Requirements tables. Grades 21L and 22L are available only as Class 1. Grade 91 is available only as Class 2.

NOTE 1—Grade 911, previously covered by this specification, is now covered by Specification A 1017/A 1017M.

1.4 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical property requirements.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents. Therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

2. Referenced Documents

2.1 *ASTM Standards*:³

A 20/A 20M Specification for General Requirements for Steel Plates for Pressure Vessels

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products

A 435/A 435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates

A 577/A 577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates

A 578/A 578M Specification for Straight-Beam Ultrasonic Examination of Plain and Clad Steel Plates for Special Applications

A 1017/A 1017M Specification for Pressure Vessel Plates, Alloy Steel, Chromium-Molybdenum-Tungsten

3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A 20/A 20M. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions and weight, quality and repair of defects, marking, loading, etc.

3.2 Specification A 20/A 20M also establishes the rules for the ordering information that should be complied with when purchasing material to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

- 3.3.1 Vacuum treatment,
- 3.3.2 Additional or special tension testing,
- 3.3.3 Impact testing, and
- 3.3.4 Nondestructive examination.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved March 1, 2005. Published March 2005. Originally approved in 1955. Last previous edition approved in 2003 as A 387/A 387M – 03.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-387/SA-387M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.



A 387/A 387M – 05

TABLE 1 Chemical Requirements

Element	Composition, %									
	Grade 2 S50460	Grade 12 K11757	Grade 11 K11789	Grade 22 K21590	Grade 22L K21590	Grade 21 K31545	Grade 21L K31545	Grade 5 S50200	Grade 9 K90941	Grade 91 K91560
Carbon:	0.05–0.21	0.05–0.17	0.05–0.17	0.05–0.15 ^A	0.10 max	0.05–0.15 ^A	0.10 max	0.15 max	0.15 max	0.08–0.12
Heat analysis	0.04–0.21	0.04–0.17	0.04–0.17	0.04–0.15 ^A	0.12 max	0.04–0.15 ^A	0.12 max	0.15 max	0.15 max	0.06–0.15
Product analysis	0.05–0.80	0.40–0.65	0.40–0.65	0.30–0.60	0.30–0.60	0.30–0.60	0.30–0.60	0.30–0.60	0.30–0.60	0.30–0.60
Manganese:	0.50–0.88	0.35–0.73	0.35–0.73	0.25–0.66	0.25–0.66	0.25–0.66	0.25–0.66	0.25–0.66	0.25–0.66	0.25–0.66
Heat analysis	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.020
Product analysis	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.025
Sulfur, max:	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.010
Heat analysis	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.012
Product analysis	0.15–0.40	0.15–0.40	0.50–0.80	0.50 max	0.50 max	0.50 max	0.50 max	0.50 max	1.00 max	0.20–0.50
Silicon:	0.13–0.45	0.13–0.45	0.44–0.86	0.50 max	0.50 max	0.50 max	0.50 max	0.55 max	1.05 max	0.18–0.56
Heat analysis	0.50–0.80	0.80–1.15	1.00–1.50	2.00–2.50	2.00–2.50	2.75–3.25	2.75–3.25	4.00–6.00	8.00–10.00	8.00–9.50
Product analysis	0.46–0.85	0.74–1.21	0.94–1.56	1.88–2.62	1.88–2.62	2.63–3.37	2.63–3.37	3.90–6.10	7.90–10.10	7.90–9.60
Chromium:	0.45–0.60	0.45–0.60	0.45–0.65	0.90–1.10	0.90–1.10	0.90–1.10	0.90–1.10	0.45–0.65	0.90–1.10	0.85–1.05
Heat analysis	0.40–0.65	0.40–0.65	0.40–0.70	0.85–1.15	0.85–1.15	0.85–1.15	0.85–1.15	0.40–0.70	0.85–1.15	0.80–1.10
Product analysis	0.40
Nickel, max:	0.43
Heat analysis
Product analysis
Vanadium:	0.18–0.25
Heat analysis	0.16–0.27
Product analysis
Columbium:	0.06–0.10
Heat analysis	0.05–0.11
Product analysis
Boron:
Heat analysis
Product analysis
Nitrogen:	0.030–0.070
Heat analysis	0.025–0.080
Product analysis
Aluminum, max:	0.04
Heat analysis	0.05
Product analysis
Tungsten:
Heat analysis
Product analysis

^A The carbon content for plates over 5 in. [125 mm] in thickness is 0.17 max on product analysis.