



SLOVENSKI STANDARD

SIST EN 15348:2015

01-januar-2015

Nadomešča:
SIST EN 15348:2008

Polimerni materiali - Reciklirani polimerni materiali - Karakterizacija reciklatov polietilen-tereftalata (PET)

Plastics - Recycled plastics - Characterisation of poly(ethylene terephthalate) (PET) recyclates

Kunststoffe - Kunststoff-Rezyklate - Charakterisierung von Polyethylenterephthalat (PET)-Rezyklaten

STANDARD PREVIEW
(standards.iteh.ai)

Plastiques - Plastiques recyclés - Caractérisation des recyclats de poly(éthylène téréphthalate) (PET) <https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ac781f6d/sist-en-15348-2015>

Ta slovenski standard je istoveten z: EN 15348:2014

ICS:

13.030.50	Recikliranje	Recycling
83.080.20	Plastomeri	Thermoplastic materials

SIST EN 15348:2015 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15348:2015

<https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781ffd/sist-en-15348-2015>

EUROPEAN STANDARD

EN 15348

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2014

ICS 13.030.50; 83.080.20

Supersedes EN 15348:2007

English Version

Plastics - Recycled plastics - Characterization of poly(ethylene terephthalate) (PET) recyclates

Plastiques - Plastiques recyclés - Caractérisation des recyclats de poly(éthylène téréphthalate) (PET)

Kunststoffe - Kunststoff-Rezyklate - Charakterisierung von Polyethylenterephthalat (PET)-Rezyklaten

This European Standard was approved by CEN on 20 September 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 15348:2015](https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015)

<https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Characterization of PET recyclates.....	6
5 Quality assurance	7
Annex A (normative) Determination of size and distribution of PET-R flakes by sieving	8
Annex B (normative) Gravimetric method for the determination of residual humidity (water content).....	11
Annex C (normative) Rapid method for the determination of residual impurities.....	13
Annex D (informative) Potentiometric method for the determination of the residual alkalinity.....	15
Annex E (informative) Method for the determination of infusible impurities by filtration	17
Bibliography	19

[SIST EN 15348:2015](https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015)

<https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015>

Foreword

This document (EN 15348:2014) has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2015 and conflicting national standards shall be withdrawn at the latest by May 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 15348:2007.

EN 15348:2014 includes the following significant technical changes with respect to EN 15348:2007:

- a) the deletion of former informative Annex B and replacement by a reference to EN ISO 1133-2 in Table 1;
- b) the use of a porcelain crucible instead of a crucible of platinum in B.5.

This European Standard is one part of a series of CEN publications on Plastics Recycling which is structured as follows:

- EN 15342, *Plastics — Recycled Plastics — Characterization of polystyrene (PS) recyclates*
- EN 15343, *Plastics — Recycled Plastics — Plastics recycling traceability and assessment of conformity and recycled content*
- EN 15344, *Plastics — Recycled Plastics — Characterization of Polyethylene (PE) recyclates*
- EN 15345, *Plastics — Recycled Plastics — Characterization of Polypropylene (PP) recyclates*
- EN 15346, *Plastics — Recycled plastics — Characterization of poly(vinyl chloride) (PVC) recyclates*
- EN 15347, *Plastics — Recycled Plastics — Characterization of plastics wastes*
- EN 15348, *Plastics — Recycled plastics — Characterization of poly(ethylene terephthalate) (PET) recyclates*
- CEN/TR 15353, *Plastics — Recycled plastics — Guidelines for the development of standards for recycled plastics*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Recycling of plastics waste is one type of material recovery process intended to save resources (virgin raw materials, water, and energy), while minimizing harmful emissions into air, water and soil as well as any impacts on human health. The environmental impact of recycling has to be assessed over the whole life cycle of the recycling system (from the waste generation point to the disposal of final residues). To ensure that recycling constitutes the best environmental option for treating the available waste, some prerequisites should preferably be met:

- recycling scheme being contemplated should generate lower environmental impacts than alternative recovery options;
- existing or potential market outlets should be identified that will secure a sustainable industrial recycling operation;
- collection and sorting schemes should be properly designed to deliver recyclable plastics waste fractions fitting reasonably well with the available recycling technologies and with the (changing) needs of the identified market outlets, preferably at minimum costs to society.

This European Standard has been produced in accordance with the guidance produced by CEN on Environmental Aspects and in accordance with CEN/TR 15353.

NOTE CEN/TR 15353 considers the general environmental aspects which are specific to the recycling process.

It is often impossible to trace back each individual product at the end user stage and to check whether the product has been used correctly through its life. Consequently products are out of industrial control for a period of time. It is possible that during this period contamination with other materials might occur that could affect the product's suitability for recycling into the intended application.

<https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015>

1 Scope

This European Standard defines a method of specifying delivery conditions for poly(ethylene terephthalate) (PET) recyclates.

It gives the most important characteristics and associated test methods for assessing PET recyclates intended to be used for the production of semi-finished/finished products. It is intended for use by the supplier and purchaser of such materials, to assist them in agreeing on specifications.

This European Standard is applicable without prejudice to any existing legislation.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

CEN/TR 15353, *Plastics — Recycled plastics — Guidelines for the development of standards for recycled plastics*

EN ISO 472, *Plastics — Vocabulary (ISO 472)*

EN ISO 1133-2, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 2: Method for materials sensitive to time-temperature history and/or moisture (ISO 1133-2)*

EN ISO 11664-4, *Colorimetry — Part 4: CIE 1976 L*a*b* Colour space (ISO 11664-4)*

<https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-4201c8801521/iso-15512>

EN ISO 15512, *Plastics — Determination of water content (ISO 15512)*

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

ISO 1628-5, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 5: Thermoplastic polyester (TP) homopolymers and copolymers*

ISO 3534-2, *Statistics — Vocabulary and symbols — Part 2: Applied statistics*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 472 and CEN/TR 15353 and the following apply.

3.1

sieve retention

percentage-of the recycled test sample retained on a sieve at the end of the test

Note 1 to entry: The sieve retention is expressed in percent (mass fraction).

3.2

container retention

percentage of recycled matter retained in the container at the bottom of a stack of sieves, or under a single sieve, at the end of the test compared to the mass of the sample

EN 15348:2014 (E)**3.3****average particulate dimension**

single value of size, representing the dominant particle size for the whole test sample

4 Characterization of PET recyclates

A single batch is the quantity of recyclate that has homogenous characteristics within the specified tolerances.

The characteristics of PET recyclates, which shall be met for every batch (see ISO 3534-2) of PET recyclate are shown in Table 1, and are divided into two types:

- required characteristics needed to characterize PET recyclates in general and required for all recyclates;
- optional characteristics needed to characterize PET recyclates according to customer specifications and applications.

These characteristics shall be assessed by using the test methods given in Table 1 and detailed below.

A Certificate of Analysis, providing the test results for each batch of recyclate shall be provided by the supplier to the purchaser upon request.

The supplier shall provide the necessary information about the material composition of the recyclates, as specified by the purchaser or required by the applicable regulations.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 15348:2015](https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015)

<https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015>

Table 1 — Characterization of PET recyclates

Characteristics	Unit	Test method	Comments
Required			
Shape		Visual	Flakes, pellets
Maximum particle size	mm		Given by the size of the screen of the grinder
Fine particle content	%	Annex A	Value in percentage of the particles passing the sieve of 1 mm.
Colour		Visual inspection	Unicolour, transparent, mixed
Water content	%	Annex B or EN ISO 15512	
PVC content	mg/kg	Annex C	
Polyolefin content	mg/kg	Annex C	
Optional			
Determination Melt Mass-Flow Rate (MFR)		EN ISO 1133-2	
Intrinsic viscosity (I.V.)	dl/g	ISO 1628-5	
Alkalinity	pH	Annex D	
Filterability	MPa/(h · cm ²)	Annex E	
Other residual content	mg/kg	SIST EN 15348:2015 https://standards.iteh.ai/catalog/standards/sist/d776c80c-0290-4a31-a819-fbd9ae781f6d/sist-en-15348-2015	Analysis according to the appropriate method e.g. FTIR, XRF, DSC...
Colour	L,a,b values	Colourimeter according to EN ISO 11664-4	Injection molded disks from Flakes, pellets
Other tests may be carried out by agreement between the purchaser and the supplier and results reported.			

5 Quality assurance

In order that the purchaser of the recyclate can have confidence in the quality of the product, the supplier shall maintain records of the quality control carried out, including incoming materials, processes and finished products.

NOTE A quality management system certified to EN ISO 9001 may be a suitable guarantee of consistent recyclate quality but not the recycled content.

The specification and the standard deviation or range of values within and between batches of material shall be agreed between the supplier and the purchaser.

Where a statement of recycled content, or the previous history of the material, is requested, documentary evidence shall be provided. These records should be available to the purchaser on request.

Where a recyclate has been produced via a melt process, the supplier may choose to state the level of filtration applied during that process. This will determine the maximum size of any non-melting contaminants present in the recyclate. The statement of filtration level shall include details of the filter. Recyclates that have not passed through a melt process cannot be quantified in the same way, and the supplier may state this.

Annex A (normative)

Determination of size and distribution of PET-R flakes by sieving

A.1 General

This procedure specifies a method for determining the dimensional distribution (size) of PET-R flakes by measuring the quantities retained in a range of sieves having meshes of various sizes.

The results are expressed in terms of quantity retained on the various sieves or as the mean particulate dimension for the whole sample tested (That which has the greatest frequency).

A.2 Principles

A determined sample is filtered through a single sieve, or stack of sieves of various mesh opening sizes, helped by mechanical or manual vibrations. When several sieves are selected to form a stack, the sieves are assembled in ascending order of the mesh opening sizes so that the largest mesh opening is at the top.

(standards.iteh.ai)

A.3 Apparatus

A.3.1 Weighing scale: With a precision of $\pm 0,1$ g.

A.3.2 Sieve: The nominal diameter of 200 mm, in accordance with ISO 565 supplemented by a lid and by a receiving container. Sieves are made of ring wire.

The sieves used have the following square mesh opening sizes of: 1 mm; 2 mm; 3,15 mm; 4 mm; 6,30 mm; 8 mm and 12,5 mm.

A.3.3 Mechanical sieve shaker

A.4 Procedure

A.4.1 Examine the sieve, or the sieves, for the damage to the mesh or any deformation of the matrix of the meshes. Replace all defective meshes.

A.4.2 Weigh the sieve, or each individual sieve, with a margin of 0,1 g.

A.4.3 Weigh the container to the nearest 0,1 g.

A.4.4 Assemble the sieve, or the sieves, and the container, one on top of the other. By assembling a stack of sieves, you ensure that they are gathered in the ascending order of the mesh opening sizes so than the largest opening is at the top.

A.4.5 Weigh 100 g to 300 g with an accuracy of $\pm 0,1$ g of flakes sample to be tested.

A.4.6 Transfer the sample to the uncovered sieve, by avoiding overflow.

A.4.7 Cover the sieve, or the stack of sieves by the lid and secure them in the mechanical device vibrator for sieving.

A.4.8 Set the timer of the vibration device to 12 min.

A.4.9 After the period of shaking, carefully separate the sieve, or the sieves, starting at the top, and weigh each sieve and the container with their contents.

A.5 Number of determinations

Make two determinations for each test sample.

A.6 Determination and expression of the results

A.6.1 The target is to calculate the average mass in grams of flakes maintained in a sieve of a given mesh opening and also the average of retentions on the container. For each sieve and the container, calculate the average mass of maintained flakes for the two determinations as follows:

$$(m_1 - m_2) = m_3 \text{ and } (m_4 - m_5) = m_6 \quad (\text{A.1})$$

$$(m_3 + m_6) / 2 = m_r \quad (\text{A.2})$$

where

m_1 and m_4 are the respective masses of each sieve, or the container, with their contents of retained flakes, for the first and second determinations;

m_2 and m_5 are the respective masses of each sieve, or the empty container;

m_3 and m_6 are the respective masses, of retained flakes on each sieve, or the container, for the first and second determinations;

m_r is the average flakes mass retained on each sieve, or the container.

A.6.2 Calculation of the percentage of the test sample maintained on each sieve or in the container

$$R = m_r \times 100 / m_s \quad (\text{A.3})$$

where

R is % of flakes maintained on sieve or in the container;

m_s is the average mass in grams of the two test samples taken;

m_r is the average flakes mass retained on each sieve, or the container.

A.7 Test report

The test report should contain the following particular conditions:

- reference to this European Standard (EN 15348:2014);
- reference of the batch of PET flakes to test;
- average mass in grams of the sample used for the test;