



Designation: D 2370 – 98

## Standard Test Method for Tensile Properties of Organic Coatings<sup>1</sup>

This standard is issued under the fixed designation D 2370; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method covers the determination of the elongation, tensile strength, and stiffness (modulus of elasticity) of organic coatings when tested as free films.

1.2 The values stated in inch–pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Section 7.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels<sup>2</sup>
- D 882 Test Methods for Tensile Properties of Thin Plastic Sheeting<sup>3</sup>
- D 1005 Test Methods for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers<sup>2</sup>
- D 3980 Practice for Interlaboratory Testing of Paint and Related Materials<sup>4</sup>
- D 4708 Practice for Preparation of Uniform Free Films of Organic Coatings<sup>2</sup>

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *elongation*—the increase in specimen length from the point of initial load application to the point of film rupture in a tension test.

3.1.2 *gage length*—the initial length of the test specimen between the jaws of the tensile tester.

3.1.3 *stiffness (modulus of elasticity)*—the load per unit area required to elongate the film 1 % from the first point in the stress-strain curve where the slope becomes constant.

3.1.4 *stress-strain curve*—the curve resulting from a plot of tensile load against the distance of jaw separation (elongation of specimen).

3.1.5 *tensile strength (nominal)*—the load per original unit area at which a specimen fails or yields in a tension (pull) test.

### 4. Summary of Test Method

4.1 Free unsupported films of the materials to be tested are prepared. The tensile properties of the free films are determined by means of a tensile testing apparatus.

### 5. Significance and Use

5.1 Tensile properties determined by this method are of value in studying the behavior of coatings subjected to environmental stresses, such as those produced by aging and weathering. (See Refs. (1-10).)<sup>5</sup>

5.2 Tensile properties may vary with specimen thickness, method of preparation, gage length, rate of load application, tensile tester response, and type of grips used. Consequently, where precise comparative results are desired, these factors must be carefully controlled.

### 6. Apparatus

6.1 Equipment for applying films of uniform thickness as described in Practices D 823.

6.2 *Micrometer Film Thickness Gage* as described in Test Method D 1005.

6.3 *Tensile Tester* of the constant rate of jaw separation type, equipped with load cells having capacities of 0.2 to 4.4 lb (100 to 2000 g), and equipped with an indicating device such

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.23 on Physical Properties of Applied Paint Films.

Current edition approved Dec. 10, 1998. Published February 1999. Originally published as D 2370 – 65 T. Last previous edition D 2370 – 92.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 08.01.

<sup>4</sup> Discontinued 1998; see 1997 *Annual Book of ASTM Standards*, Vol 06.01.

<sup>5</sup> Boldface numbers in parentheses refer to the list of references at the end of this standard.

as an electronic constant speed chart recorder, a digital device that displays numerical values, or a printer that records the numerical values.

6.4 *Precision Specimen Cutter* having a double blade with a foot to hold the sample in place.<sup>6</sup>

6.5 *Alternative Substrates* on which test material can be deposited.

6.5.1 *Dental Tin Foil*, preferably 1 mil (25  $\mu\text{m}$ ) thick.<sup>7</sup>

6.5.2 *Sheet of FEP* (fluorinated ethylene-propylene),<sup>8</sup> preferably 2 mils (50  $\mu\text{m}$ ) thick, coated with a dry lubricant.<sup>9</sup>

NOTE 1—Other substrates that may be suitable are 10-mil (250- $\mu\text{m}$ ) thick polyethylene (7), photographic paper (8), polished steel (9), and fluoropolymer coated metal panels.

## 7. Hazards

7.1 *Mercury*—Mercury is a toxic metallic liquid. Its vapors are extremely hazardous. Small amounts of spilled mercury can vaporize sufficiently at room temperature to exceed the threshold limit values (TLV) of the vapor. Use with adequate ventilation (in a hood) and clean up spills immediately. Wear gloves when handling mercury. Keep containers closed. Droplets of mercury can be picked up by using a small glass pipet connected to a suction flask with a rubber hose.

## 8. Test Specimens

8.1 The test specimens shall be free films having a width that is between  $\frac{1}{2}$  and 1 in. (13 and 25 mm). No specimen shall vary by more than  $\pm 2\%$  in width along its entire length. The length shall be at least 2 in. (50 mm) longer than the gage length selected for the test.

8.2 Prepare free films by one of the procedures described in Test Method D 4708.

## 9. Calibration

9.1 Balance, zero, and calibrate the load weighing and recording system of the tensile tester in accordance with methods specified by the manufacturer.

## 10. Conditioning

10.1 Unless otherwise agreed upon between the producer and the user, condition the test specimens for at least 24 h at  $73.5 \pm 3.5^\circ\text{F}$  ( $23 \pm 2^\circ\text{C}$ ) and 50 % relative humidity and test in the same environment.

<sup>6</sup> The sole source of supply of the JDC precision cutter known to the committee at this time is the Thwing-Albert Instrument Co., 10960 Dutton Rd., Philadelphia, PA 19154. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>7</sup> Dental tin foil is suitable for this purpose.

<sup>8</sup> Teflon FEP 2-mil film thickness (Card No. 03111, Item #29499) from E. I. du Pont de Nemours & Co., Inc., Wilmington, DE 19898, was found suitable for this purpose. However, it is no longer available. See Note 1 for alternatives.

<sup>9</sup> The sole source of supply of a dry lubricant (MS-122 Fluorocarbon Release Agent), known to the committee at this time is the Miller-Stephenson Chemical Co., Inc., 55 Backus Ave., Danbury, CT 06810. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

## 11. Procedure

11.1 Select a mutually agreed upon gage length in the range of 1 to 5 in. (25 to 125 mm).

11.2 Prepare 10 test specimens for each material to be evaluated. These specimens should not exhibit any nicks or flaws. Measure the thickness of each specimen to  $\pm 0.1$  mil (2.5  $\mu\text{m}$ ) with a micrometer in accordance with Test Methods D 1005, taking five measurements within the gage length area.

11.3 Set the jaw separation of the tensile tester at the gage length selected. Place the test specimen in the grips of the testing machine, taking care to align the long axis of the specimen with an imaginary line joining the points of attachment of the grips to the machine. Tighten the grips evenly and firmly to the degree necessary to minimize slipping of the specimen during test.

NOTE 2—Mounting is facilitated by the use of air activated jaws. Line-type jaws will minimize slippage and breakage. The application of pressure-sensitive cloth to the ends of the film can improve jaw grip.

11.4 Select a mutually agreed upon rate of elongation (strain rate) that is in the range of 5 to 100 %/min. Set the crosshead speed of the tensile tester to provide this rate for the gage length chosen.

NOTE 3—A rate of elongation should be selected that is optimum for testing the types of materials to be evaluated. For relatively brittle films, elongation rates of 5 to 20 % are suggested. For relatively extensible films, elongation rates of 50 to 100 % are suggested. (Refer to Test Methods D 882 for relation of elongation rate to elongation at break).

11.5 Elongate the test specimen until rupture of the film occurs and evaluate the stress-strain curve as follows:

11.5.1 Determine the specimen elongation by measuring the increase in jaw separation from the point of original load application to the point of rupture.

11.5.2 Measure the tensile pull in pounds (kg) required to rupture the film.

11.5.3 If stiffness is desired, determine the tensile pull in pounds (kg) to elongate the film 1 % from the first point in the stress-strain curve where the slope becomes constant.

11.6 Using the procedures in 11.1-11.5, run ten test specimens for each material under test.

## 12. Calculations

12.1 For each specimen compute the following:

12.1.1 The elongation  $E$ , in percent from the following equation:

$$E = 100 \left( \frac{\Delta L}{L} \right) \quad (1)$$

where:

$\Delta L$  = increase in specimen length to break, and

$L$  = initial specimen length (gage length).

12.1.2 The tensile strength,  $TS$ , in pounds per square inch, from the equation:

$$TS = (P_R)/(TW) \quad (2)$$

where:

$P_R$  = tensile pull to rupture, lb (kg),