



SLOVENSKI STANDARD
SIST EN 12166:2016

01-oktober-2016

Nadomešča:
SIST EN 12166:2011

Baker in bakrove zlitine - Žica za splošno uporabo

Copper and copper alloys - Wire for general purposes

Kupfer und Kupferlegierungen - Drähte zur allgemeinen Verwendung

Cuivre et alliages de cuivre - Fils pour usages généraux

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: ~~SIST EN 12166:2011~~ EN 12166:2016

<https://standards.iteh.ai/catalog/standards/sist/a0251a7e-5ce3-46e3-896d-b196e7750a9/sist-en-12166-2016>

ICS:

77.150.30 Bakreni izdelki Copper products

SIST EN 12166:2016 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 12166:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/a0251a7e-5ce3-46e3-896d-b196e77509a9/sist-en-12166-2016>

EUROPEAN STANDARD

EN 12166

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2016

ICS 77.150.30

Supersedes EN 12166:2011

English Version

Copper and copper alloys - Wire for general purposes

Cuivre et alliages de cuivre - Fils pour usages généraux

Kupfer und Kupferlegierungen - Drähte zur
allgemeinen Verwendung

This European Standard was approved by CEN on 9 April 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 12166:2016](https://standards.iteh.ai/catalog/standards/sist/a0251a7e-5ce3-46e3-896d-b196e77509a9/sist-en-12166-2016)

<https://standards.iteh.ai/catalog/standards/sist/a0251a7e-5ce3-46e3-896d-b196e77509a9/sist-en-12166-2016>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	4
Introduction	6
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Designation.....	8
4.1 Material.....	8
4.1.1 General.....	8
4.1.2 Symbol.....	8
4.1.3 Number	8
4.2 Material condition	8
4.3 Product.....	8
5 Ordering information	10
6 Requirements	13
6.1 Composition	13
6.2 Mechanical properties.....	13
6.3 Grain size.....	13
6.4 Dimensions and tolerances	13
6.4.1 Diameter or width across flats.....	13
6.4.2 Shape tolerances for round wire	13
6.4.3 Corner and edge geometry (wire with square and rectangular cross-section only)	13
6.5 Joins.....	14
6.6 Surface quality.....	14
7 Sampling.....	14
7.1 General.....	14
7.2 Analysis.....	14
7.3 Tensile, hardness and grain size tests	15
8 Test methods	15
8.1 Analysis.....	15
8.2 Tensile test	15
8.3 Hardness test.....	15
8.4 Estimation of average grain size.....	16
8.5 Retests.....	16
8.6 Rounding of results	16
9 Declaration of conformity and inspection documentation.....	16
9.1 Declaration of conformity	16
9.2 Inspection documentation.....	17
10 Marking, packaging, labelling.....	17
Annex A (informative) Position of wire cross-section within a coil, reel, spool or drum	40
Bibliography.....	42

Figures

Figure 1 — Calculation of corner radii	14
Figure A.1 — Illustration of position of wire cross-section within the coil (bunched wound or stagger/traverse wound)	40
Figure A.2 — Illustration of position of wire cross-section within the reel/spool/drum (stagger/traverse wound)	40
Figure A.3 — Illustration of position of wire cross-section within the coil (bunched wound or stagger/traverse wound)	41
Figure A.4 — Illustration of position of wire cross-section within the reel/spool/drum (stagger/traverse wound)	41

Tables

Table 1 — Composition of low alloyed copper alloys	18
Table 2 — Composition of copper-nickel-zinc alloys	21
Table 3 — Composition of copper-tin alloys	21
Table 4 — Composition of copper-zinc alloys	22
Table 5 — Composition of copper-zinc-lead alloys	23
Table 6 — Composition of complex copper-zinc alloys	24
Table 7 — Mechanical properties of wire of low alloyed copper alloys	24
Table 8 — Mechanical properties of wire of copper-nickel-zinc alloys	27
Table 9 — Mechanical properties of wire of copper-tin alloys	29
Table 10 — Mechanical properties of wire of copper-zinc alloys	31
Table 11 — Mechanical properties of wire of copper-zinc-lead alloys	35
Table 12 — Mechanical properties of wire of complex copper-zinc alloys	36
Table 13 — Grain size designations	37
Table 14 — Tolerances on diameter of round wire	37
Table 15 — Tolerances on width across-flats of square or regular polygonal wire	38
Table 16 — Tolerances on width and thickness of rectangular wire	38
Table 17 — Corner radii for square or rectangular wire	39
Table 18 — Sampling rate	39

EN 12166:2016 (E)**European foreword**

This document (EN 12166:2016) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2017, and conflicting national standards shall be withdrawn at the latest by January 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12166:2011.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 4 “Extruded and drawn products, forgings and scrap” to revise the following standard:

— EN 12166:2011, *Copper and copper alloys — Wire for general purposes*.

This document is one of a series of European Standards for the copper and copper alloy products rod, wire, profile and forgings. Other products are specified as follows:

- STANDARD PREVIEW**
(standards.iteh.ai)
- EN 12163, *Copper and copper alloys — Rod for general purposes*;
 — EN 12164, *Copper and copper alloys — Rod for free machining purposes*;
 — EN 12165, *Copper and copper alloys — Wrought and unwrought forging stock*;
 — EN 12167, *Copper and copper alloys — Profiles and bars for general purposes*;
 — EN 12168, *Copper and copper alloys — Hollow rod for free machining purposes*;
 — EN 13601, *Copper and copper alloys — Copper rod, bar and wire for general electrical purposes*;
 — EN 13602, *Copper and copper alloys — Drawn, round copper wire for the manufacture of electrical conductors*;
 — EN 13605, *Copper and copper alloys — Copper profiles and profiled wire for electrical purposes*.

In comparison with EN 12166:2011, the following significant technical changes were made:

- a) introduction of an optional procedure how to refer to restrictions to the chemical composition imposed by the 4 MS Common Composition List for materials used for products accepted for contact with drinking water;
- b) provisions for surface quality added.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta,

Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 12166:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/a0251a7e-5ce3-46e3-896d-b196e77509a9/sist-en-12166-2016>

Introduction

The European Committee for Standardization (CEN) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent concerning the alloy CuZn21Si3P (CW724R) given in 6.1.

CEN takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has ensured the CEN that he is willing to negotiate licenses either free of charge or under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with CEN. Information may be obtained from:

Wieland Werke AG
Graf Arco Straße 36
D-89079 Ulm
GERMANY

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. CEN shall not be held responsible for identifying any or all such patent rights.

CEN and CENELEC maintain online lists of patents relevant to their standards. Users are encouraged to consult the lists for the most up to date information concerning patents (<ftp://ftp.cencenelec.eu/EN/IPR/Patents/IPRdeclaration.pdf>).

Due to developing legislation, the composition of a material may be restricted to the composition specified in this European Standard with respect to individual uses (e.g. for the use in contact with drinking water in some Member States of the European Union). These individual restrictions are not part of this European Standard. Nevertheless, for materials for which traditional and major uses are affected, these restrictions are indicated. The absence of an indication, however, does not imply that the material can be used in any application without any legal restriction.

1 Scope

This European Standard specifies the composition, property requirements and dimensional tolerances for copper alloy wire, finally produced by drawing, rolling or extruding, intended for general purposes, spring and fastener manufacturing applications.

The sampling procedures and the methods of test for verification of conformity to the requirements of this European Standard are also specified.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1173, *Copper and copper alloys - Material condition designation*

EN 1412, *Copper and copper alloys - European numbering system*

EN 1655, *Copper and copper alloys - Declarations of conformity*

EN 10204, *Metallic products - Types of inspection documents*

EN ISO 2624, *Copper and copper alloys - Estimation of average grain size (ISO 2624)*

EN ISO 6507-1, *Metallic materials - Vickers hardness test - Part 1: Test method (ISO 6507-1)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

ISO 1190-1, *Copper and copper alloys — Code of designation — Part 1: Designation of materials*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

wire

wound product of uniform cross-section along its whole length

Note 1 to entry: Rectangles may have round or sharp corners.

3.2

deviation from circular form

difference between the maximum and the minimum diameters measured at any one cross-section of a round product

[SOURCE: EN 12163:2016, 3.2]

EN 12166:2016 (E)

4 Designation

4.1 Material

4.1.1 General

The material is designated either by symbol or by number (see Tables 1 to 6).

4.1.2 Symbol

The material symbol designation is based on the designation system given in ISO 1190-1.

NOTE Although material symbol designations used in this standard might be the same as those in other standards using the designation system given in ISO 1190-1, the detailed composition requirements are not necessarily the same.

4.1.3 Number

The material number designation is in accordance with the system given in EN 1412.

4.2 Material condition

For the purposes of this standard, the following designations, which are in accordance with the system given in EN 1173, apply for the material condition:

M	material condition for the product as manufactured, without specified mechanical properties;
R...	material condition designated by the minimum value of tensile strength requirement for the product with mandatory tensile property requirements;
H...	material condition designated by the minimum value of Vickers hardness requirement for the product with mandatory hardness requirements;
S (suffix)	material condition for a product which is stress relieved.
G...	material condition designated by the mid-range value of grain size requirement for the product with mandatory grain size requirements (Table 13).

NOTE The G... material condition is normally applicable only to round wires in the soft material condition made from alloys given in Tables 3, 4 and non-leaded alloys given in Table 2.

Exact conversion between material conditions designated R..., H... and G... is not possible.

Except when the suffix S is used, material condition is designated by only one of the above designations.

4.3 Product

The product designation provides a standardized pattern of designation from which a rapid and unequivocal description of a product can be conveyed in communication. It provides mutual comprehension at the international level with regard to products which meet the requirements of the relevant European Standard.

The product designation is no substitute for the full content of the standard.


The product designation for products to this standard shall consist of:

— denomination (Wire);

- number of this European Standard (EN 12166);
- material designation, either symbol or number (see Tables 1 to 6);
- DW for compliance in the chemical composition according to the 4 MS Common Composition List. This information is mandatory in the case in which the product is used for drinking water applications according to the 4 MS Common Composition List and not to be given in other cases;
- material condition designation (see 4.2 and Tables 7 to 13);
- cross-sectional shape (the following designations shall be used as appropriate: RND for round, SQR for square, RCT for rectangular, HEX for hexagonal, OCT for octagonal, PFL for profile);
- nominal cross-sectional dimension(s) (or the number of the profile or a fully dimensioned and toleranced drawing);
- tolerance class for round, square or polygonal wire, (see Tables 14 and 15);
- for square, rectangular or polygonal wire, the corner shape (the following designations shall be used as appropriate: SH for sharp, RD for rounded), (see Table 17).


The derivation of a product designation is shown in the following examples.

EXAMPLE 1 Wire conforming to this standard, in material designated either CuZn40Pb2 or CW617N, for standard applications in material condition H115, rectangular, nominal cross-sectional dimensions 6,0 mm × 5,0 mm, with sharp corners, will be designated as follows:



EN 12166:2016 (E)

EXAMPLE 2 Wire conforming to this standard, in material designated either CuZn40Pb2 or CW617N, for drinking water applications according to the 4 MS Common Composition List, in material condition H115, rectangular, nominal cross-sectional dimensions 6,0 mm × 5,0 mm, with sharp corners, will be designated as follows:



iTeh STANDARD PREVIEW
(standards.iteh.ai)

EXAMPLE 3 Wire conforming to this standard, in material designated either CuZn39Pb3 or CW614N, for standard applications in material condition R430, round, nominal diameter 6,0 mm, tolerance class B, will be designated as follows:

<https://standards.iteh.ai/catalog/standards/sist/a0251a7e-5ce3-46e3-896d-b196e77509a9/sist-en-12166-2016>

Wire EN 12166 — CuZn39Pb3 — R430 — RND6,0B

or

Wire EN 12166 — CW614N — R430 — RND6,0B

5 Ordering information

In order to facilitate the enquiry, order and confirmation of order procedures between the purchaser and the supplier, the purchaser shall state on his enquiry and order the following information:

- a) mass of product required;
- b) denomination (Wire);
- c) number of this European Standard (EN 12166);
- d) material designation (see Tables 1 to 6);
- e) material condition designation (see 4.2 and Tables 7 to 13) if other than M;
- f) DW for compliance in the chemical composition according to the 4 MS Common Composition List. This information is mandatory in the case in which the product is used for drinking water applications according to the 4 MS Common Composition List and not to be given in other cases;

- g) cross-sectional shape;
- h) nominal cross-sectional dimension(s) (diameter or width across-flats);
- i) for round, square and regular polygonal wire, the tolerance class required, unless the tolerance class shall be left to the discretion of the supplier (see Tables 14 and 15); for profiles, the tolerances required (or a drawing with dimensions and tolerances);
- j) for square or rectangular wire, whether 'sharp' or 'rounded' corners are required, unless the corner radii shall be left to the discretion of the supplier (see Table 17);

It is recommended that the product designation, as described in 4.3, is used for items b) to j).

In addition, the purchaser shall also state on the enquiry and order any of the following, if required:

- k) for profiles, if the shape is such that the position of the cross-section within the coil, reel, spool or drum is of importance to the purchaser, this should be stated on the drawing (see Annex A for illustration);
- l) for profiles, whether mechanical properties are required; if so, the method of test and the level of properties shall be agreed between the purchaser and the supplier;
- m) whether the products shall be supplied in a thermally stress relieved material condition;
- n) whether special surface quality is required (see 6.6);
- o) whether a declaration of conformity is required (see 9.1);
- p) whether an inspection document is required, and if so, which type (see 9.2);
- q) whether there are any special requirements for marking, labelling or packaging including, if necessary, any limitation on dimensions or mass of coils, spools, reels or drums (see Clause 10).

EXAMPLE 1 Ordering details for 1 000 kg wire for general purposes conforming to EN 12166, in material designated either CuZn39Pb3 or CW614N, in material condition H115, rectangular, nominal cross-sectional dimensions 6,0 mm × 5,0 mm, with sharp corners, in 25 kg coils:

1 000 kg **Wire — CuZn39Pb3 — H115 — RCT 6,0 × 5,0 — SH**
EN 12166
— 25 kg coils

or

1 000 kg **Wire — CW614N — H115 — RCT 6,0 × 5,0 — SH**
EN 12166
— 25 kg coils

EXAMPLE 2 Ordering details for 5 000 kg wire for general purposes conforming to EN 12166, in material designated either CuZn40Pb2 or CW617N, for drinking water application according to the 4 MS Common Composition List, in material condition R430, round, nominal diameter 6,0 mm, tolerance class B, on 1 000 kg spools:

5 000 kg **Wire — CuZn40Pb2 — DW — R430 — RND6,0B**
EN 12166
— 1 000 kg spools