
**Destructive tests on welds in metallic
materials — Hot cracking tests for
weldments — Arc welding processes —**

**Part 1:
General**

iTeh STANDARD PREVIEW

(standards.iteh.ai)
*Essais destructifs des soudures sur matériaux métalliques — Essais de
fissuration à chaud des assemblages soudés — Procédés de soudage
à l'arc —*

Partie 1: Généralités

[https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-
f460c8ff574e/iso-17641-1-2004](https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 17641-1:2004](https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17641-1 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Throughout the text of this document, read “...this European Standard...” to mean “...this International Standard...”.

<http://www.iso.org>

ISO 17641 consists of the following parts, under the general title *Destructive tests on welds in metallic materials — Hot cracking tests for weldments — Arc welding processes*:

- *Part 1: General*
- *Part 2: Self-restraint tests*
- *Part 3: Externally loaded tests* [Technical Report]

Contents

page

Foreword.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	1
4 Symbols, designations and units.....	2
5 Fundamentals of hot cracking.....	2
6 Types of test.....	3
7 Description of tests	3
8 Summary of applications	4

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 17641-1:2004](https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004>

Foreword

This document (EN ISO 17641-1:2004) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2005, and conflicting national standards shall be withdrawn at the latest by February 2005.

EN ISO 17641 consists of the following parts, under the general title *Destructive tests on welds in metallic materials – Hot cracking tests for weldments – Arc welding processes*:

- Part 1: General
- Part 2: Self-restraint tests
- Part 3: Externally loaded tests¹

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

[ISO 17641-1:2004](https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004>

¹ Part 3 will be published as a Technical Report with the same general title.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 17641-1:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004>

1 Scope

This standard gives an introduction to the fundamentals of hot cracking in weld metals and parent alloys, and briefly describes the tests available for arc welding processes.

- Part 2: Self restraint tests - specifies the tests which should be used to assess the susceptibility to hot cracking of weld metals. The strains to cause cracking are provided by the restraint of the weldment.
- Part 3: Externally loaded tests - describes the tests which can be used to assess the susceptibility to hot cracking of parent alloys and weld metals. The strains to cause cracking are provided by external loading on the test specimen.

NOTE The tests in part 3 require the use of non-standardised proprietary equipment and different laboratories use various procedures, test conditions and specimen sizes, therefore reproducibility within a given laboratory is usually good but differences between laboratories are sometimes found.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO 17641-2:2004, *Destructive tests on welds in metallic materials - Hot cracking tests for weldments - Arc welding processes - Part 2: Self-restraint tests (ISO 17641-2:2004)*.

prCEN ISO/TR 17641-3:2003, *Destructive tests on welds in metallic materials - Hot cracking tests for weldments - Arc welding processes - Part 3: Externally loaded tests (ISO/DTR 17641-3:2003)*.

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1

hot cracks

material separations occurring at high temperatures along the grain boundaries (dendrite boundaries) when the level of strain and the strain rate exceed a certain level

NOTE Small cracks visible only at magnifications greater than X50, are often described as microcracks.

3.1.1

solidification cracks

hot cracks formed during solidification from the liquid phase of weld metals

NOTE They usually extend up to the surface of the weld metal, but sometimes can be subsurface.

3.1.2

liquation cracks

hot cracks formed by liquation of the heat affected zone (HAZ) of the parent material or in multipass welds where weld metal is reheated by subsequent weld beads

3.1.3

ductility dip cracks

hot cracks formed during welding by a reduction in hot ductility. As with liquation cracks they can occur in the HAZ of the parent material or in multi-pass welds

3.2

self restraint tests

tests where specimen loading is produced by strains developed during welding of a restrained weldment

3.3

externally loaded tests

tests where strains are developed in the specimen by the application of external loads in specific test equipment

4 Symbols, designations and units

For the purposes of this European Standard, the symbols and units given in Table 1 apply.

Table 1 – Symbols, designations and units

Symbol	Designation	Unit
MSI _(TT)	Microcracks sensitivity indicator (tensile test) ^a	mm/mm ²
MSI _(LBT)	Microcrack sensitivity indicator (longitudinal bend test) ^b	mm/mm ²
L _{tot}	Total length of all detected hot cracks	mm
V _{crit}	Critical strain to form the first hot crack	mm/s
BTR	Brittle temperature range, i.e. difference between NST and DTR (see prCEN ISO/TR 17641-3:2003, Figure 2)	K
^a MSI = $L_{MF} / L_o \times d \times \pi$ ^b MSI = $L_{MF} / b \times l_o$		

5 Fundamentals of hot cracking

Hot cracks are produced in the weld metal and in the HAZ of parent materials when the strains developed during cooling of a welded joint, or imposed externally, exceed the ductility of a particular part of the joint. They range in size from very small liquation cracks (<1 mm in length) in HAZ's or multipass welds up to large solidification cracks, which may extend along the complete length of the welded joints.

NOTE 1 These cracks should not be confused with cold cracks, which always occur at temperatures below 200 °C.

Hot cracks are not confined to any particular alloy system and can occur in steels, stainless steels, nickel-base alloys, copper and aluminium based alloys. The reasons for the incidence of hot cracks are many and complex, but in general terms they occur when localised ductility is insufficient to support imposed strains. The lack of ductility can depend upon micro structural features and orientation (relative to the strains) and in some cases upon the presence of brittle impurities and low melting point (or liquated) films. In this respect some alloy systems are highly sensitive to the presence of impurity elements such as Sulphur, Phosphorus, Lead, etc. It is generally recognised that fully austenitic single-phase microstructures, particularly weld metals, are susceptible to hot cracking, of one form or another. Impurity levels influence the incidence of cracking in such structures.

NOTE 2 Precise mechanisms for the occurrence of hot cracking have not yet been fully established.

6 Types of test

6.1 Self-restraint tests

These tests depend upon the restraint of the weldment to provide sufficient strain to induce cracking. The tests include:

- a) Those tests consisting of a highly restrained weldment where the test weld is examined directly for the presence of cracking;
- b) Tests consisting of a full thickness butt weld where the test specimen is taken from the weld metal in the butt weld and subjected to additional straining to reveal pre-existing hot cracking (particularly micro fissures) and facilitate their detection and measurement. The post weld straining is applied either by tension or by bending. It is not designed to induce any new cracking.

The self-restraint tests are only suitable for the assessment of hot cracking in weld metals.

6.2 Externally loaded tests

These tests depend upon external loading on the specimen, either during the welding process or on a welded specimen which is simultaneously heated and loaded. The tests include:

- a) tests where loading is imposed as the weld is deposited;
- b) tests where a weld is reheated and loaded simultaneously to allow an assessment of susceptibility to be determined.

These externally loaded tests are suitable for the assessment of hot cracking in weld metals, parent materials and heat affected zones.

<https://standards.iteh.ai/catalog/standards/sist/fcc096bc-0cbf-44c2-8854-f460c8ff574e/iso-17641-1-2004>
 (standards.iteh.ai)

7 Description of tests

7.1 Self restraint tests

7.1.1 General

Details of the test procedures are given in EN ISO 17641-2.

7.1.2 T-joint weld cracking test

The test procedure is designed to assess the solidification cracking susceptibility of weld metal in a single pass restrained fillet weld. Three types of test are available, with increasing restraint being provided by increasing the thickness and/or stiffness of the plates used in the test assembly. The assessment is essentially qualitative since no direct measurement of strains is available. Assessment is based upon the length and position of cracking (if any) in the test weld.

7.1.3 Weld metal tensile test

This test is designed to assess the susceptibility to liquation and ductility dip cracking of weld metal taken from a butt weld. Applying a load to rupture a cylindrical all-weld metal specimen taken from a butt weld opens cracks initiated during the welding operation. The regions adjacent to the fracture are examined and any cracking can be detected and measured.

NOTE See EN ISO 17641-2:2004, Figures 2 and 3.