



Designation: A232/A232M – 05

Standard Specification for Chromium-Vanadium Alloy Steel Valve Spring Quality Wire¹

This standard is issued under the fixed designation A232/A232M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers the highest quality of round chromium-vanadium alloy steel valve spring wire, uniform in quality and temper, intended for the manufacture of valve springs and other springs requiring high-fatigue properties when used at moderately elevated temperatures. This wire shall be either in the annealed and cold-drawn or oil-tempered condition as specified by the purchaser.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the inch-pound units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independent of the other.

2. Referenced Documents

2.1 *ASTM Standards*:²

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.2 *ANSI Standard*:³

B 32.4 Preferred Metric Sizes for Round, Square, Rectangular, and Hexagon Metal Products

2.3 *Federal Standard*:⁴

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

2.4 *Military Standard*:⁴

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

2.5 *AIAG Standard*:⁵

AIAG B-5 02.00 Primary Metals Identification Tag Application Standard

3. Ordering Information

3.1 Orders for material under this specification should include the following information for each ordered item:

3.1.1 Quantity (mass),

3.1.2 Name of material (chromium-vanadium alloy steel valve spring quality wire),

3.1.3 Dimensions (Table 1 and Section 8),

3.1.4 Condition (Section 6),

3.1.5 Packaging (Section 14),

3.1.6 Heat analysis report, if requested (5.2),

3.1.7 Certification or test report, or both, if specified (Section 13), and

3.1.8 ASTM designation and year of issue.

NOTE 1—A typical ordering description is as follows: 20 000 kg oil-tempered chromium-vanadium alloy steel valve spring quality wire, size 6.00 mm in 150 kg coils to ASTM A232/A232M dated _____, or for inch-pound units, 40 000 lb oil-tempered chromium-vanadium alloy steel valve spring quality wire, size 0.250 in. in 350-lb coils to ASTM A232/A232M dated _____.

4. Materials and Manufacture

4.1 The steel may be made by any commercially accepted steel making process. The steel shall be continuously cast.

4.2 The finished wire shall be free from detrimental pipe and undue segregation.

5. Chemical Composition

5.1 The steel shall conform to the requirements for chemical composition specified in Table 2.

5.2 *Heat Analysis*—Each heat of steel shall be analyzed by the manufacturer to determine the percentage of elements prescribed in Table 2. This analysis shall be made from a test specimen preferably taken during the pouring of the heat. When requested, this shall be reported to the purchaser and shall conform to the requirements of Table 2.

⁵ Available from Automotive Industry Action Group (AIAG), 26200 Lahser Rd., Suite 200, Southfield, MI 48034.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A1.03 on Steel Rod and Wire.

Current edition approved March 1, 2005. Published March 2005. Originally approved in 1939. Last previous edition approved in 1999 as A232/A232M – 99. DOI: 10.1520/A0232_A0232M-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Tensile Requirements^A

SI Units			
Diameter, ^B mm	MPa, min	MPa, max	Reduction of Area, min, %
0.50	2060	2260	C
0.55	2050	2240	C
0.60	2030	2220	C
0.65	2010	2200	C
0.70	2000	2160	C
0.80	1980	2140	C
0.90	1960	2120	C
1.00	1940	2100	C
1.10	1920	2080	C
1.20	1900	2060	C
1.40	1860	2020	C
1.60	1820	1980	C
1.80	1800	1960	C
2.00	1780	1930	C
2.20	1750	1900	C
2.50	1720	1860	45
2.80	1680	1830	45
3.00	1660	1800	45
3.50	1620	1760	45
4.00	1580	1720	40
4.50	1560	1680	40
5.00	1520	1640	40
5.50	1480	1620	40
6.00	1460	1600	40
6.50	1440	1580	40
7.00	1420	1560	40
8.00	1400	1540	40
9.00	1380	1520	40
10.00	1360	1500	40
11.00	1340	1480	40
12.00	1320	1460	40

Inch-Pound Units			
Diameter, in.	ksi, min	ksi, max	Reduction of Area, min, %
0.020	300	325	C
0.032	290	315	C
0.041	280	305	C
0.054	270	295	C
0.062	265	290	C
0.080	255	275	C
0.105	245	265	45
0.135	235	255	45
0.162	225	245	40
0.192	220	240	40
0.244	210	230	40
0.283	205	225	40
0.312	203	223	40
0.375	200	220	40
0.438	195	215	40
0.500	190	210	40

^A Tensile strength values for intermediate diameters may be interpolated.

^B Preferred sizes. For a complete list, refer to ANSI B32.4.

^C The reduction of area test is not applicable to wire diameters under 0.092 in. [2.34 mm].

TABLE 2 Chemical Requirements

	Analysis, %	Product Analysis Tolerance, %
Carbon	0.48–0.53	±0.02
Manganese	0.70–0.90	±0.03
Phosphorus	0.020 max	+0.005
Sulfur	0.035 max	+0.005
Silicon	0.15–0.35	±0.02
Chromium	0.80–1.10	±0.05
Vanadium	0.15 min	–0.01

5.3 *Product Analysis*—An analysis may be made by the purchaser from finished wire representing each heat of steel. The average of all the separate determinations made shall be within the limits specified in the analysis column. Individual determinations may vary to the extent shown in the product analysis tolerance column, except that the several determinations of a single element in any one heat shall not vary both above and below the specified range.

5.4 For referee purposes, Test Methods, Practices, and Terminology A751 shall be used.

6. Mechanical Properties

6.1 *Annealed and Cold-Drawn*—When purchased in the annealed and cold-drawn condition, the wire shall have been given a sufficient amount of cold working to meet the purchaser's coiling requirements and shall be in a suitable condition to respond properly to heat treatment. In special cases the hardness, if desired, shall be stated in the purchase order.

6.2 *Oil Tempered*—When purchased in the oil-tempered condition, the tensile strength and minimum percent reduction of area, sizes 2.50 mm [0.105 in.] and coarser, of the wire shall conform to the requirements prescribed in Table 1.

6.2.1 *Number of Tests*—One test specimen shall be taken for each five coils, or fraction thereof, in a lot. Each heat in a given lot shall be tested.

6.2.2 *Location of Tests*—Test specimens shall be taken from either end of the coil.

6.2.3 *Test Method*—The tension test shall be made in accordance with Test Methods and Definitions A370.

6.3 Wrap Test:

6.3.1 Oil-tempered or cold-drawn wire 4.00 mm [0.162 in.] and smaller in diameter shall wind on itself as an arbor without breakage. Larger diameter wire up to and including 8.00 mm [0.312 in.] in diameter shall wrap without breakage on a mandrel twice the wire diameter. The wrap test is not applicable to wire over 8.00 mm in diameter.

6.3.2 *Number of Tests*—One test specimen shall be taken for each five coils, or fraction thereof, in a lot. Each heat in a given lot shall be tested.

6.3.3 *Location of Test*—Test specimens shall be taken from either end of the coil.

6.3.4 *Test Method*—The wrap test shall be made in accordance with Test Methods and Definitions A370.

6.4 *Special Surface Inspection*—When specified, the entire length of every coil shall be inspected for surface imperfections with a magnetic or eddy current defect analyzer, or both, or equivalent. The defect depth of this surface inspection shall be agreed upon between the manufacturer and the purchaser. All detected defects shall be properly marked so the purchaser has the ability to identify and discard that length of wire.

7. Metallurgical Requirements

7.1 Surface Condition:

7.1.1 The surface of the wire as received shall be free of imperfections such as pits, die marks, scratches, seams, and other defects tending to impair the fatigue value of the springs.

7.1.2 *Number of Tests*—One test specimen shall be taken from each end of every coil.