



SLOVENSKI STANDARD
oSIST prEN ISO 20200:2014
01-februar-2014

Polimerni materiali - Ugotavljanje razpada polimernih materialov pri simuliranem kompostiranju v laboratorijskem merilu (ISO/DIS 20200:2013)

Plastics - Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test (ISO/DIS 20200:2013)

Kunststoffe - Bestimmung des Zersetzungsgrades von Kunststoffmaterialien unter nachgebildeten Kompostierungsbedingungen mittels einer Prüfung im Labormaßstab (ISO/DIS 20200:2013)

Plastiques - Détermination du degré de désintégration de matériaux plastiques dans des conditions de compostage simulées lors d'un essai de laboratoire (ISO/DIS 20200:2013)

Ta slovenski standard je istoveten z: prEN ISO 20200

ICS:

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	--------------------------------	---------------------

oSIST prEN ISO 20200:2014

en,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 20200

ISO/TC 61/SC 5

Secretariat: DIN

Voting begins on:
2013-12-19Voting terminates on:
2014-05-19

Plastics — Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test

Plastiques — Détermination du degré de désintégration de matériaux plastiques dans des conditions de compostage simulées lors d'un essai de laboratoire

[Revision of first edition (ISO 20200:2004)]

ICS: 83.080.01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 20200:2016

<https://standards.iteh.ai/catalog/standards/sist/5fe054ff-bd36-4d25-bb83-e0ece8c177ff/sist-en-iso-20200-2016>

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



Reference number
ISO/DIS 20200:2013(E)

© ISO 2013

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 20200:2016

<https://standards.iteh.ai/catalog/standards/sist/5fe054ff-bd36-4d25-bb83-e0ece8c177ff/sist-en-iso-20200-2016>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents		Page
Foreword		iv
Introduction		v
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 Principle		2
5 Synthetic solid waste		2
6 Composting reactor		3
7 Procedure		3
7.1 Test material preparation		3
7.2 Start-up of the test		4
7.3 Thermophilic incubation period (high temperature)		4
7.4 Mesophilic incubation period (at room temperature)		4
8 Monitoring the composting process		5
9 Diagnostic parameters		5
9.1 Odour		5
9.2 Visual appearance		5
9.3 Chemical analysis		5
9.4 Determination of dry mass and volatile solids		6
10 Termination of the test and measurement of the degree of disintegration		6
11 Calculation of degree of disintegration		6
12 Expression of results		6
13 Validity of the test		7
14 Test report		7

ISO/DIS 20200

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 20200 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

The main changes are:

- a) the term "heavy metal" has been replaced by "regulated metal" (3.2);
- b) the term "commercial" has been replaced by "municipal or industrial" (clause 4 and 5);
- c) the numerical value of R 42,8% has been replaced by 42,3% (clause 13);
- d) the variability of the results has been raised from 10 % to 20 % (clause 13).

Introduction

The test method described in this International Standard determines the degree of disintegration of plastic materials when exposed to a composting environment. The method is simple and inexpensive, does not require special bioreactors and is scaled for use in any general-purpose laboratory. It requires the use of a standard and homogeneous synthetic solid waste. The synthetic waste components are dry, clean, safe products which can be stored in the laboratory without any odour or health problems. The synthetic waste is of constant composition and devoid of any undesired plastic material which could be erroneously identified as test material at the end of testing, altering the final evaluation. The bioreactors are small, as is the amount of synthetic waste to be composted (approximately 3 l). With the limited amount of test material, this method provides a simplified test procedure. This test method is not aimed at determining the biodegradability of plastic materials under composting conditions. Further testing will be necessary before being able to claim compostability.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 20200:2016](https://standards.iteh.ai/catalog/standards/sist/5fe054ff-bd36-4d25-bb83-e0ece8c177ff/sist-en-iso-20200-2016)

<https://standards.iteh.ai/catalog/standards/sist/5fe054ff-bd36-4d25-bb83-e0ece8c177ff/sist-en-iso-20200-2016>

Plastics — Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test

1 Scope

This International Standard specifies a method of determining the degree of disintegration of plastic materials when exposed to a laboratory-scale composting environment. The method is not applicable to the determination of the biodegradability of plastic materials under composting conditions. Further testing is necessary to be able to claim compostability.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3310-1:2000, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

compost

organic soil conditioner obtained by biodegradation of a mixture consisting principally of vegetable residues, occasionally with other organic material and having a limited mineral content

3.2

compostability

ability of a material to be biodegraded in a composting process

Note 1 to entry: To claim compostability it must have been demonstrated that a material can be biodegraded and disintegrated in a composting system (as can be shown by standard test methods) and completes its biodegradation during the end-use of the compost. The compost must meet the relevant quality criteria. Quality criteria are e.g. low regulated metal content, no ecotoxicity, no obviously distinguishable residues.

3.3

composting

aerobic process designed to produce compost

3.4

disintegration

physical breakdown of a material into very small fragments

3.5

dry mass

mass of a sample measured after drying

Note 1 to entry: Dry mass is expressed as a percentage of the mass of the wet sample.

ISO/DIS 20200

- 3.6 mesophilic incubation period**
incubation at 25 °C to allow the development of microorganisms growing at room temperature
- 3.7 thermophilic incubation period**
incubation at 58 °C to allow the development of microorganisms growing at high temperature
- 3.8 total dry solids**
amount of solids obtained by taking a known volume of test material or compost and drying at about 105 °C to constant mass
- 3.9 volatile solids**
amount of solids obtained by subtracting the residue obtained from a known volume of test material or compost after incineration at about 550 °C from the total dry solids content of the same sample

Note 1 to entry: The volatile-solids content is an indication of the amount of organic matter present.

4 Principle

The method determines the degree of disintegration of test materials on a laboratory scale under conditions simulating an intensive aerobic composting process. The solid matrix used consists of a synthetic solid waste inoculated with mature compost taken from a municipal or industrial composting plant. Pieces of the plastic test material are composted with this prepared solid matrix. The degree of disintegration is determined after a composting cycle, by sieving the final matrix through a 2 mm sieve in order to recover the non-disintegrated residues. The reduction in mass of the test sample is considered as disintegrated material and used to calculate the degree of disintegration.

5 Synthetic solid waste

SIST EN ISO 20200:2016

<https://standards.iteh.ai/catalog/standards/sist/5fe054ff-bd36-4d25-bb83-e0ece8c177ff/sist->

The composition of the synthetic waste used in this method is described in Table 1.

Well aerated compost from a municipal or industrial aerobic composting plant shall be used as the inoculum. The compost inoculum shall be homogeneous and free from large inert objects such as glass, stones or pieces of metal. Remove any such objects manually and then sieve the compost on a screen of mesh aperture between 0,5 cm and 1 cm. It is recommended that compost from a plant composting the organic fraction of solid municipal waste be used in order to ensure sufficient diversity of microorganisms. If such a compost is not available, then compost from plants treating farmyard waste or mixtures of garden waste and solid municipal waste may be used. The compost shall not be older than 4 months.

Prepare the synthetic waste manually by mixing the different components listed in Table 1. The allowed tolerance on the mass measurements of the synthetic waste components, water included, is 5 %. Add chlorine-free tap water, or de-ionized or distilled water, to the mixture to adjust its final water content to 55 % in total. Perform this operation just before start-up. The synthetic waste shall have a carbon:nitrogen (C/N) ratio of between 20:1 and 40:1. The urea concentration can be changed to adjust the C/N ratio to the required range. In this case, the concentration of the other components shall be adjusted proportionately in order to bring the total dry mass of the solid waste to 100 %.