



Designation: D 2397 – 98

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Cationic Emulsified Asphalt¹

This standard is issued under the fixed designation D 2397; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers seven grades of cationic emulsified asphalt for use in pavement construction in the manner designated.

2. Referenced Documents

2.1 ASTM Standards:

- D 140 Practice for Sampling Bituminous Materials²
- D 244 Test Methods for Emulsified Asphalts²

3. Requirements

3.1 The emulsified asphalt shall be tested within 14 days of delivery. The emulsified asphalt shall be homogeneous after thorough mixing provided separation has not been caused by freezing. Emulsions separated by freezing shall not be tested.

¹ This specification is under the jurisdiction of ASTM Committee D-4 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.41 on Emulsified Asphalt Specifications.

Current edition approved Dec. 10, 1998. Published March 1999. Originally published as D 2397 – 65 T. Last previous edition D 2397 – 97.

² *Annual Book of ASTM Standards*, Vol 04.03.

3.2 Emulsified asphalt shall conform to the requirements prescribed in Table 1.

4. Sampling

- 4.1 Samples of emulsified asphalt shall be taken in accordance with Practice D 140.
- 4.2 Samples shall be stored in clean, airtight sealed containers at a temperature of not less than 4°C until tested.

5. Test Methods

5.1 The properties of the emulsified asphalts given in Table 1 shall be determined in accordance with Test Methods D 244, with the following exception:

5.1.1 *Sieve Test*—Use distilled water in all wetting and washing operations in place of sodium oleate solution (2%).

6. Keywords

6.1 cationic; emulsified asphalt; emulsion; medium setting; rapid setting; slow setting

ASTM D2397-98

<https://standards.iteh.ai/catalog/standards/sist/5809cafl-fab7-41b2-be0a-d3d515085651/astm-d2397-98>