

---

**Preskusi geometričnih lastnosti agregatov - 9. del: Ugotavljanje finih delcev -  
Preskus z metilen modrim (vključno z dopnilom A1)**

Tests for geometrical properties of aggregates - Part 9: Assessment of fines - Methylene blue test

Prüfverfahren für geometrische Eigenschaften von Gesteinskörnungen - Teil 9:  
Beurteilung von Feinanteilen-Methylenblau-Verfahren

Essais pour déterminer les caractéristiques géométriques des granulats - Partie 9 :  
Qualification des fines - Essai au bleu de méthylène

<https://standards.iteh.ai/catalog/standards/sist/ce85bc8f-8eb9-4176-a10e-7e60708233a3/sist-en-933-9-2009a1-2013>

**Ta slovenski standard je istoveten z: EN 933-9:2009+A1:2013**

---

**ICS:**

91.100.15      Mineralni materiali in izdelki      Mineral materials and products

**SIST EN 933-9:2009+A1:2013**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 933-9:2009+A1:2013](https://standards.iteh.ai/catalog/standards/sist/ce85bc8f-8eb9-4176-a10e-7e60708233a3/sist-en-933-9-2009a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/ce85bc8f-8eb9-4176-a10e-7e60708233a3/sist-en-933-9-2009a1-2013>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 933-9:2009+A1**

April 2013

ICS 91.100.15

Supersedes EN 933-9:2009

English Version

## Tests for geometrical properties of aggregates - Part 9: Assessment of fines - Methylene blue test

Essais pour déterminer les caractéristiques géométriques  
des granulats - Partie 9 : Qualification des fines - Essai au  
bleu de méthylène

Prüfverfahren für geometrische Eigenschaften von  
Gesteinskörnungen - Teil 9: Beurteilung von Feinanteilen-  
Methylenblau-Verfahren

This European Standard was approved by CEN on 12 June 2009 and includes Amendment 1 approved by CEN on 12 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 933-9:2009+A1:2013](https://standards.iteh.ai/catalog/standards/sist/ce85bc8f-8eb9-4176-a10e-7e60708233a3/sist-en-933-9-2009a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/ce85bc8f-8eb9-4176-a10e-7e60708233a3/sist-en-933-9-2009a1-2013>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

<b>Contents</b>	<b>Page</b>
Foreword .....	3
1 Scope.....	5
2 Normative references .....	5
3 Terms and definitions.....	5
4 Principle .....	6
5 Reagents .....	6
6 Apparatus .....	6
7 Preparation of test portions .....	7
8 Procedure .....	7
8.1 Description of the stain test.....	7
8.2 Preparation of suspension.....	7
8.3 Determination of the quantity of dye adsorbed .....	8
9 Calculation and expression of results .....	8
10 Test report .....	9
10.1 General .....	9
10.2 Required data .....	9
10.3 Optional data .....	9
<b>Annex A</b> (normative) <b>Procedure for the determination of the methylene blue value (<math>MB_F</math>) of the 0/0,125 mm fraction</b> .....	10
<b>Annex B</b> (informative) <b>Test of conformity in relation to a specified MB value</b> .....	11
<b>Annex C</b> (normative) <b>Preparation of 10 g/l methylene blue solution</b> .....	12
<b>Annex D</b> (normative) <b>Procedure for the determination of the methylene blue value of kaolinite (<math>MB_K</math>)</b> .....	14
<b>Annex E</b> (informative) <b>Example of a test data sheet</b> .....	15

## Foreword



This document (EN 933-9:2009+A1:2013) has been prepared by Technical Committee CEN/TC 154 "Aggregates", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2013, and conflicting national standards shall be withdrawn at the latest by October 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes  EN 933-9:2009. 

This document includes Amendment 1 approved by CEN on 2013-02-12.

The start and finish of text introduced or altered by amendment is indicated in the text by tags  .

This Standard forms part of a series of tests for geometrical properties of aggregates. Test methods for other properties of aggregates will be covered by parts of the following European Standards:

- EN 932, *Tests for general properties of aggregates*
- EN 1097, *Tests for mechanical and physical properties of aggregates*
- EN 1367, *Tests for thermal and weathering properties of aggregates*
- EN 1744, *Tests for chemical properties of aggregates*
- EN 13179, *Tests for filler aggregate used in bituminous mixtures*

The other parts of EN 933 will be:

- Part 1: Determination of particle size distribution — Sieving method
- Part 2: Determination of particle size distribution — Test sieves, nominal size of apertures
- Part 3: Determination of particle shape — Flakiness index
- Part 4: Determination of particle shape — Shape index
- Part 5: Determination of percentage of crushed and broken surfaces in coarse aggregate particles
- Part 6: Assessment of surface characteristics — Flow coefficient for coarse aggregates
- Part 7: Determination of shell content — Percentage of shells in coarse aggregates
- Part 8: Assessment of fines — Sand equivalent test
- Part 10: Assessment of fines — Grading of fillers (air jet sieving)

**EN 933-9:2009+A1:2013 (E)**

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

[SIST EN 933-9:2009+A1:2013](https://standards.iteh.ai/catalog/standards/sist/ce85bc8f-8eb9-4176-a10e-7e60708233a3/sist-en-933-9-2009a1-2013)

<https://standards.iteh.ai/catalog/standards/sist/ce85bc8f-8eb9-4176-a10e-7e60708233a3/sist-en-933-9-2009a1-2013>

## 1 Scope

This standard describes the reference method used for type testing and in cases of dispute for the determination of the methylene blue value of the 0/2 mm fraction in fine aggregates or all-in aggregates (MB). It also describes the reference method for the determination of the methylene blue value of the 0/0,125 mm fraction (MB<sub>F</sub>) in Annex A. For other purposes, in particular factory production control, other methods may be used provided that an appropriate working relationship with the suitable reference method has been established.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 932-2, *Tests for general properties of aggregates — Part 2: Methods for reducing laboratory samples*

EN 932-5, *Tests for general properties of aggregates — Part 5: Common equipment and calibration*

## 3 Terms and definitions

For the purposes of this document the following terms and definitions apply.

### 3.1

#### **subsample**

sample obtained by means of a sample reduction procedure

### 3.2

#### **test portion**

sample used as a whole in a single test

### 3.3

#### **finer**

particle size fraction of an aggregate which passes the 0,063 mm sieve

### 3.4

#### **particle size fraction**

fraction of an aggregate passing the larger of two sieves and retained on the smaller

NOTE The lower limit can be zero.

### 3.5

#### **constant mass**

successive weighings after drying at least 1 h apart not differing by more than 0,1 %

NOTE In many cases constant mass can be achieved after a test specimen has been dried for a pre-determined period in a specified oven at  $(110 \pm 5)$  °C. Test laboratories can determine the time required to achieve constant mass for specific types and sizes of sample dependent upon the drying capacity of the oven used.

## EN 933-9:2009+A1:2013 (E)

## 4 Principle

Increments of a solution of methylene blue are added successively to a suspension of the test portion in water. The adsorption of dye solution by the test portion is checked after each addition of solution by carrying out a stain test on filter paper to detect the presence of free dye.

When the presence of free dye is confirmed the methylene blue value ( $MB$  or  $MB_F$ ) is calculated and expressed as grams of dye adsorbed per kilogram of the size fraction tested.

NOTE A conformity check, adding a single quantity of dye solution equivalent to a specified limiting value and which may be used as part of a production control process, is described in Annex B.

## 5 Reagents

**5.1** *Dye solution*, solution of standard or technical quality methylene blue,  $(10,0 \pm 0,1)$  g/l (see Annex C). The maximum period of use of the solution shall be 28 days. It shall be stored away from light.

**5.2** Distilled or demineralised water.

**5.3** *Kaolinite*, of known methylene blue value ( $MB_K$ ) (see Annex D).

NOTE Kaolinite of  $MB_K$  value between 1 g and 2 g per 100 g of kaolinite is preferable in order to avoid excessive use of dye.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

## 6 Apparatus

All apparatus shall conform to the general requirements of EN 932-5.

**6.1** *Burette*, with capacity of either 100 ml or 50 ml and graduation of either 1/10 ml or 1/5 ml, or one 5 ml and one 2 ml micro-pipette.

**6.2** *Filter paper*, quantitative and ash-free ( $< 0,010$  %);  $95 \text{ g/m}^2$ ; thickness 0,20 mm; filtration speed 75 s; pore size  $8 \mu\text{m}$ .

**6.3** *Glass rod*, length 300 mm; diameter 8 mm.

**6.4** *Impeller agitator*, capable of controlled variable rotation rates up to  $(600 \pm 60) \text{ min}^{-1}$  with three or four impeller blades of  $(75 \pm 10)$  mm diameter.

NOTE Alternative types of mixer can be used if it can be shown that results obtained agree with results produced using an impeller agitator as specified above.

**6.5** *Balance*, readable to 0,1 % of the mass to be weighed.

**6.6** *Stopwatch or stopclock*, readable to 1 s.

**6.7** *Test sieve*, 2 mm aperture, with guard sieve (if necessary).

**6.8** *Beaker*, glass or plastic, capacity about 1 l or about 2 l.

**6.9** *Flask*, glass, capacity 1 l.

**6.10** *Ventilated oven*, thermostatically controlled to maintain a temperature of  $(110 \pm 5) ^\circ\text{C}$ .

**6.11** *Thermometer*, readable to  $1 ^\circ\text{C}$ .



6.12 *Spatula.*

6.13 *Desiccator.*

## 7 Preparation of test portions

$\text{A}_1$  The laboratory samples shall be reduced in accordance with EN 932-2 to produce two subsamples, each containing at least 200 g of 0/2 mm particle size. Sieve each subsample on a 2 mm sieve protected if necessary by a guard sieve, and using a sieve brush to ensure effective separation and collection of all particles in the 0/2 mm fraction. Discard any particles retained on the 2 mm sieve.

The subsamples may be pre-dried at less than 45 °C in order to facilitate the sieving operation.

Weigh one of the subsamples as M. Dry it to constant mass, then weigh it again as M'. Determine and record the water content of this subsample as  $W (\%) = 100 \times (M - M') / M'$ . Discard this subsample.

NOTE The determination of the water content can be achieved by other means than drying in a ventilated oven, such as drying in a microwave for example.

Take the other subsample and, if necessary, achieve further reduction in accordance with EN 932-2 to obtain a test portion of mass at least  $[200 \times (1 + W/100)]$  g. The mass of the test portion shall be larger than  $[200 \times (1 + W/100)]$  g but not of an exact predetermined value. Weigh the test portion as M0 and determine its dry mass M1 to the nearest 1 g according to the following:

$$M1 = M0 / (1 + W/100) \quad (1) \text{A}_1$$

## 8 Procedure

### 8.1 Description of the stain test

After each injection of dye, the stain test consists of taking a drop of suspension by means of the glass rod and depositing it on the filter paper. The stain which is formed is composed of a central deposit of material, of a generally solid blue colour, surrounded by a colourless wet zone.

The amount of drop taken shall be such that the diameter of the deposit is between 8 mm and 12 mm.

The test is deemed to be positive if, in the wet zone, a halo consisting of a persistent light blue ring of about 1 mm is formed around the central deposit.

NOTE As the end-point is approached, the halo will appear, but can then disappear again, because the clay minerals can take some time to complete their adsorption of the dye. For this reason the end-point is confirmed by repeating the stain test at 1 min intervals for 5 min without adding more dye solution.

### 8.2 Preparation of suspension

Place  $(500 \pm 5)$  ml of distilled or demineralised water in the beaker and add the  $\text{A}_1$  *deleted text*  $\text{A}_1$  test portion stirring well with the spatula.

Stir the dye solution (see 5.1) or alternatively mix it thoroughly. Fill the burette with dye solution and return the stock of dye solution to a dark place.

Set the agitator to a speed of  $600 \text{ min}^{-1}$  and position the impeller about 10 mm above the base of the beaker.