



SLOVENSKI STANDARD

SIST ISO 11475:2011

01-maj-2011

Papir, karton in lepenka - Določanje beline po CIE, D65/10° (zunanja dnevna svetloba)

Paper and board -- Determination of CIE whiteness, D65/10 degrees (outdoor daylight)

Papier et carton -- Détermination du degré de blanc CIE, D65/10 degrés (lumière du jour extérieure)

STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: ISO 11475:2004

SIST ISO 11475:2011
<https://standards.iteh.ai/catalog/standards/sist/b455158f-b344-4aaf-ac9f-ed7fd694772a/sist-iso-11475-2011>

ICS:

85.060

Papir, karton in lepenka

Paper and board

SIST ISO 11475:2011

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 11475:2011](#)

<https://standards.iteh.ai/catalog/standards/sist/b453138f-f344-4aaf-ae9f-ed7fd694772a/sist-iso-11475-2011>

INTERNATIONAL
STANDARD

ISO
11475

Second edition
2004-11-15

**Paper and board — Determination of CIE
whiteness, D65/10° (outdoor daylight)**

*Papier et carton — Détermination du degré de blanc CIE, D65/10°
(lumière du jour extérieure)*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 11475:2011

<https://standards.iteh.ai/catalog/standards/sist/b453138f-f344-4aaf-ae9f-ed7fd694772a/sist-iso-11475-2011>



Reference number
ISO 11475:2004(E)

© ISO 2004

ISO 11475:2004(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 11475:2011

<https://standards.iteh.ai/catalog/standards/sist/b453138f-f344-4aaf-ae9f-ed7fd694772a/sist-iso-11475-2011>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

| | Page |
|--|------|
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 4 Principle | 2 |
| 5 Apparatus and equipment | 2 |
| 6 Calibration | 3 |
| 7 Sampling | 4 |
| 8 Preparation of test pieces | 4 |
| 9 Procedure | 4 |
| 10 Calculation and expression of results | 5 |
| 11 Precision | 6 |
| 12 Test report | 6 |
| Annex A (normative) Spectral characteristics of reflectometers for determining tristimulus values .. | 7 |
| Annex B (normative) UV-calibration service | 10 |
| Bibliography | 12 |

ITeH STANDARD PREVIEW
 (standards.iteh.ai)

SIST ISO 11475:2011

<https://standards.iteh.ai/catalog/standards/sist/b453138f-f344-4aaf-ae9f-ed7fd694772a/sist-iso-11475-2011>

ISO 11475:2004(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11475 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This second edition cancels and replaces the first edition (ISO 11475:1999), of which it constitutes a minor technical revision: the only change is in B.4.3 which indicates that the IR2 and IR3 standards shall have a CIE whiteness value of at least 130 and a fluorescent component of the whiteness of at least 50.

It is based on the CIE whiteness formula, published in CIE Publication 15.2-1986, *Colorimetry*^[11].

[SIST ISO 11475:2011](https://standards.iteh.ai/catalog/standards/sist/b453138f-f344-4aaf-ae9f-ed7fd694772a/sist-iso-11475-2011)

<https://standards.iteh.ai/catalog/standards/sist/b453138f-f344-4aaf-ae9f-ed7fd694772a/sist-iso-11475-2011>

Paper and board — Determination of CIE whiteness, D65/10° (outdoor daylight)

1 Scope

This International Standard specifies the procedure to be used for determining the whiteness of papers and boards. The values obtained correspond to the visual appearance of white papers and boards with or without fluorescent whitening agents when they are viewed under the CIE D65 daylight illuminant. It is based on reflectance data obtained over the full visible spectral range (VIS) in contrast to the measurement of ISO brightness which is limited to the blue region of VIS.

In addition, it specifies a method for adjustment of the UV-content to correspond to the D65 daylight illuminant^{[8][9]}, insofar as results obtained when fluorescent whitening agents are present are dependent upon the UV-content of the radiation falling upon the sample. It is specific for the measurement of fluorescence in the blue region of the spectrum.

This method is not applicable to coloured papers containing fluorescent dyes.

This International Standard should be read in conjunction with ISO 2469.

NOTE A related standard, ISO 11476^[4], specifying the procedure for obtaining values corresponding to the appearance of these products under indoor illumination, has also been published.

<https://standards.iteh.ai/catalog/standards/sist/b453138f-f344-4aaf-ae9f-ed7fd694772a/sist-iso-11475-2011>

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2469, *Paper, board and pulps — Measurement of diffuse reflectance factor*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

reflectance factor

R

ratio of the radiation reflected by a body to that reflected by the perfect reflecting diffuser under the same conditions

NOTE The ratio is expressed as a percentage.

3.2

intrinsic reflectance factor

reflectivity

R_{∞}

reflectance factor of a layer or pad of the material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

ISO 11475:2004(E)

3.3

radiance factor

 β

ratio of the radiance of a body to that of the perfect reflecting diffuser under the same conditions of illumination and viewing

NOTE For fluorescent (luminescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_S , and the luminescent radiance factor, β_L , so that

$$\beta = \beta_S + \beta_L$$

For non-fluorescent materials, the reflected radiance factor, β_S , is simply the reflectance factor, R .

3.4

CIE whiteness value

 W_{10}

measure of whiteness derived from the CIE tristimulus values determined under the conditions specified in this International Standard

NOTE CIE whiteness is dimensionless and is expressed as whiteness units.

3.5

green/red tint value

 $T_{W,10}$

measure of the deviation from whiteness of the test material towards the green or red region

NOTE 1 The tint value is dimensionless and is expressed as tint units.

NOTE 2 A positive value of $T_{W,10}$ indicates a greenish tint and a negative value indicates a reddish tint.

3.6

fluorescence component

 F_{10}

measure of the extent to which the whiteness of the material is affected by excitation of the added fluorescent whitening agent (FWA) under the conditions specified in this International Standard

NOTE The suffix 10 is used to indicate that the value refers to the CIE 1964 (10°) observer.

4 Principle

The diffuse radiance factor of the material is determined under standardized conditions after the instrument has been adjusted so that a reference standard has the same CIE whiteness value as it would have under CIE standard D65 illumination, and the CIE whiteness value and the tint value are calculated. The fluorescence component of the whiteness is calculated from the difference between this whiteness value and the whiteness value obtained when the fluorescence emission from the material is eliminated, for instance by the introduction into the light beams of a sharp cut-off UV-absorbing filter.

5 Apparatus and equipment

5.1 Reflectometer or spectrophotometer, having the geometric, spectral and photometric characteristics described in ISO 2469, Annex A, calibrated in accordance with the provisions of ISO 2469, Annex B, and equipped with a radiation source having an adequate UV-content and a means of adjusting the relative UV-content so that the measured CIE whiteness value agrees with that corresponding to the D65 illuminant^[6].

NOTE In the 1994 edition of ISO 2469, the reflectometer characteristics are described in Annex A and the calibration service is described in Annex B. When ISO 2469 is revised, the numbering may change; users of editions subsequent to 1994 should therefore determine which elements of text specify these characteristics and this service.

For the measurement of reflectance factors with the fluorescence effect eliminated, the instrument shall be equipped with a sharp cut-off, UV-absorbing filter having a transmittance not exceeding 5,0 % at and below a

wavelength of 410 nm and not exceeding 50 % at a wavelength of 420 nm. The cut-off filter shall have characteristics such that a reliable reflectance value is obtained at 420 nm. The reflectance value obtained at 420 nm shall then be considered for computational purposes to be the value which applies at all lower wavelengths, at which it is not possible to make any measurement.

For the measurement of fluorescent papers, photometric linearity up to a scale reading of at least 200 % is necessary in the wavelength region corresponding to the fluorescent emission.

5.1.1 In the case of a filter reflectometer, pairs of filters giving the photoelectric detectors of the reflectometer responses equivalent to the CIE tristimulus values X , Y , Z of the test piece, evaluated for the CIE standard illuminant D65 and CIE 1964 (10°) observer^[7].

5.1.2 In the case of an abridged spectrophotometer, a means of calculating the weighted means according to the requirements of the CIE illuminant D65 and CIE 1964 (10°) observer using the weighting functions given in Annex A^[10].

5.2 Working standards

5.2.1 Two plates of flat opal glass or ceramic material, cleaned as described in ISO 2469.

5.2.2 A stable plastic or other tablet incorporating a fluorescent whitening agent.

5.3 Reference standards for calibration of the instrument and working standards

5.3.1 Non-fluorescent reference standard for calibration, fulfilling the requirements for ISO reference standards of level 3 as prescribed in ISO 2469.

5.3.2 Fluorescent reference standard for use in adjusting the UV-content of the radiation incident upon the sample, having whiteness values and other relevant data as specified in Annex B and fulfilling the requirements for ISO reference standards of level 3.

SIST ISO 11475:2011

Use new reference standards sufficiently frequently to ensure satisfactory calibration and UV-adjustment.

5.4 Black cavity, having a reflectance factor which does not differ from its nominal value by more than 0,2 % at all wavelengths. The black cavity shall be stored upside down in a dust-free environment or with a protective cover.

NOTE The condition of the black cavity should be checked by reference to the instrument maker.

6 Calibration

6.1 Using the values assigned to the non-fluorescent reference standard (5.3.1), calibrate the instrument with the UV-cut-off filters removed from the radiation beams. The setting of the UV-adjustment filter is not important at this stage.

6.2 Using the appropriate measurement procedure, measure the radiance factors of the fluorescent reference standard (5.3.2); calculate the whiteness value (10.1) and compare the value obtained with that assigned to the fluorescent reference standard.

A measured whiteness value higher than the assigned value indicates that the relative UV-content is too high and vice versa.

6.3 Using the UV-adjustment filter or other adjustment device, adjust the UV-content of the illumination until measurement gives the correct whiteness value.

NOTE If the UV-content is too low, it may be necessary to replace the UV-adjustment filter with a filter which raises rather than lowers the relative UV-content.

6.4 Repeat the calibration as described in 6.1 using the non-fluorescent reference standard (5.3.1) with the UV-adjustment filter in the position which gave the correct whiteness value. Repeat the measurement of the