



SLOVENSKI STANDARD
oSIST prEN 16828:2015
01-junij-2015

Vroče valjani jekleni profili U, I in H - Mere in mase

Hot rolled steel channels, I and H sections - Dimensions and masses

Warmgewalzter U-Profilstahl, I und H Träger - Maße und Masse

Profilés en U en aciers laminés à chaud, poutrelles I et H - Dimensions, masses et propriétés des profilés

Ta slovenski standard je istoveten z: prEN 16828

ICS:

77.140.70

Jekleni profili

Steel profiles

oSIST prEN 16828:2015

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 16828

March 2015

ICS 77.140.70

English Version

Hot rolled steel channels, I and H sections - Dimensions and masses

Profilés en U en aciers laminés à chaud, poutrelles I et H -
Dimensions, masses et propriétés des profilés

Warmgewalzter U-Profilstahl, I und H Träger - Maße und
Masse

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ECISS/TC 103.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.

<https://standards.iteh.ai>
SIST EN 10365:2017

<https://standards.iteh.ai/catalog/standards/sist/c4d333ae-c14e-4688-9b4a-5e13d310cc6c/sist-en-10365-2017>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	5
4	Designation	5
5	Dimensions and masses.....	5
6	Tolerances on dimensions, shape and mass	9
7	Material	9

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 10365:2017](https://standards.iteh.ai/catalog/standards/sist/c4d333ae-c14e-4688-9b4a-5e13d310cc6c/sist-en-10365-2017)

<https://standards.iteh.ai/catalog/standards/sist/c4d333ae-c14e-4688-9b4a-5e13d310cc6c/sist-en-10365-2017>

Foreword

This document (prEN 16828:2015) has been prepared by Technical Committee ECISS/TC 103 “Structural steels other than reinforcements”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 10365:2017](https://standards.iteh.ai/catalog/standards/sist/c4d333ae-c14e-4688-9b4a-5e13d310cc6c/sist-en-10365-2017)

<https://standards.iteh.ai/catalog/standards/sist/c4d333ae-c14e-4688-9b4a-5e13d310cc6c/sist-en-10365-2017>

prEN 16828:2015 (E)**1 Scope**

This European Standard specifies the nominal dimensions and masses of the hot rolled steel channels, I and H sections.

The following shapes are covered by this European Standard:

Sections:

- Parallel flange I sections IPE
- Wide flange beams HE
- Extra wide flange beams HL
- Wide flange columns HD
- Wide flange bearing piles HP and UBP
- Universal beams UB
- Universal columns UC
- Taper flange I sections IPN and J

Channels:

- Parallel flange channels UPE and PFC
- Taper flange channels UPN, U and CH

These requirements do not apply to hot rolled steel channels, I and H sections from stainless steel.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10024, *Hot rolled taper flange I sections — Tolerances on shape and dimensions*

EN 10025-1, *Hot rolled products of structural steels — Part 1: General technical delivery conditions*

EN 10025-2, *Hot rolled products of structural steels — Part 2: Technical delivery conditions for non-alloy structural steels*

EN 10025-3, *Hot rolled products of structural steels — Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels*

EN 10025-4, *Hot rolled products of structural steels — Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels*

EN 10025-5, *Hot rolled products of structural steels — Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance*

EN 10028-2, *Flat products made of steels for pressure purposes — Part 2: Non-alloy and alloy steels with specified elevated temperature properties*

EN 10034, *Structural steel I and H sections — Tolerances on shape and dimensions*

EN 10079, *Definition of steel products*

EN 10225, *Weldable structural steels for fixed offshore structures — Technical delivery conditions*

EN 10273, *Hot rolled weldable steel bars for pressure purposes with specified elevated temperature properties*

EN 10279, *Hot rolled steel channels — Tolerances on shape, dimensions and mass*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10079 apply.

4 Designation

A section shall be designated according to Table 1 to Table 15.

This form of designation shall be used in any enquiry and order.

5 Dimensions and masses

Hot rolled steel channels, I and H sections complying with this European Standard shall be manufactured with the specified dimensions given in the Table 1 to Table 15 and according to Figure 1 to Figure 4 below.

Radii of fillets and toes of shape profiles vary with individual manufacturers and therefore are not specified.

The masses per unit length specified in Table 1 to Table 15 were calculated on the basis of a density of 7,85 kg/dm³.

[SIST EN 10365:2017](https://standards.iteh.ai/catalog/standards/sist/c4d333ae-c14e-4688-9b4a-5e13d310cc6c/sist-en-10365-2017)

<https://standards.iteh.ai/catalog/standards/sist/c4d333ae-c14e-4688-9b4a-5e13d310cc6c/sist-en-10365-2017>





Figure 1 — IPE, HE, HL, HD, HP, UBP, UB and UC parallel flange sections



SIST EN 10365:2017
Figure 2 — Taper flange I sections IPN and J

<https://standards.itech.ai/catalog/standards/sist/c4d555a0-e14c-4088-9b4a-9c13d310cc6c/sist-en-10365-2017>




Figure 3 — Parallel flange channels UPE and PFC




Figure 4 — Taper flange channels UPN, U and CH

6 Tolerances on dimensions, shape and mass

Tolerances on dimensions, shape and mass shall be as given in EN 10034 for I (parallel flanges) and H sections.

Tolerances on dimensions, shape and mass shall be as given in EN 10024 for taper flange I sections.

Tolerances on dimensions, shape and mass shall be as given in EN 10279 for channels.

Tolerances for shapes not included in the mentioned standards shall be as agreed upon between the manufacturer and the purchaser.

7 Material

Sections and channels shall preferably be made from steel of a grade as specified in EN 10025-1, EN 10025-2, EN 10025-3, EN 10025-4 and EN 10025-5. Other steel grades as specified in EN 10225, EN 10028-2 and EN 10273 may also be used for specific applications.

Table 1 — Parallel flange I sections IPE

Designation	<i>G</i> kg/m	Dimensions				<i>A</i> cm ²
		<i>h</i> mm	<i>b</i> mm	<i>t_w</i> mm	<i>t_f</i> mm	
IPE AA 80	4,9	78,0	46,0	3,2	4,2	6,3
IPE A 80	5,0	78,0	46,0	3,3	4,2	6,4
IPE 80	6,0	80,0	46,0	3,8	5,2	7,6
IPE AA 100	6,7	97,6	55,0	3,6	4,5	8,6
IPE A 100	6,9	98,0	55,0	3,6	4,7	8,8
IPE 100	8,1	100,0	55,0	4,1	5,7	10,3
IPE AA 120	8,4	117,0	64,0	3,8	4,8	10,7
IPE A 120	8,7	117,6	64,0	3,8	5,1	11,0
IPE 120	10,4	120,0	64,0	4,4	6,3	13,2
IPE AA 140	10,1	136,6	73,0	3,8	5,2	12,8
IPE A 140	10,5	137,4	73,0	3,8	5,6	13,4
IPE 140	12,9	140,0	73,0	4,7	6,9	16,4
IPE AA 160	12,1	156,4	82,0	4,0	5,6	15,4
IPE A 160	12,7	157,0	82,0	4,0	5,9	16,2
IPE 160	15,8	160,0	82,0	5,0	7,4	20,1
IPE AA 180	14,9	176,4	91,0	4,3	6,2	19,0
IPE A 180	15,4	177,0	91,0	4,3	6,5	19,6
IPE 180	18,8	180,0	91,0	5,3	8,0	23,9
IPE O 180	21,3	182,0	92,0	6,0	9,0	27,1
IPE AA 200	18,0	196,4	100,0	4,5	6,7	22,9
IPE A 200	18,4	197,0	100,0	4,5	7,0	23,5
IPE 200	22,4	200,0	100,0	5,6	8,5	28,5
IPE O 200	25,1	202,0	102,0	6,2	9,5	32,0