
**Paper and board — Determination of
opacity (paper backing) — Diffuse
reflectance method**

*Papier et carton — Détermination de l'opacité sur fond papier —
Méthode de réflexion en lumière diffuse*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2471:2008](https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008)

[https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-
e9c144fb723a/iso-2471-2008](https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2471:2008

<https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle.....	2
5 Apparatus	2
6 Sampling and conditioning	3
7 Preparation of test pieces.....	3
8 Procedure	3
9 Calculation of results	4
10 Precision.....	4
11 Test report.....	5
Annex A (normative) Spectral characteristics of reflectometers for measuring luminance factor.....	6
Bibliography.....	8

ISO 2471:2008

<https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2471 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This fourth edition cancels and replaces the third edition (ISO 2471:1998), which has been technically revised, in that a UV adjustment to conform to the CIE illuminant C is required if fluorescent whitening agents are present in the paper or board.

ISO 2471:2008
<https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008>

Introduction

The opacity value depends on the principle used for its evaluation, and a method should be chosen which most closely relates to the interpretation to be placed upon the results. The method described in this International Standard is applicable when it is desired to measure that property of a paper which governs the extent to which one sheet visually obscures printed matter on underlying sheets of similar paper. It should not be confused with methods based on the reduction in a standard contrast by interposition of the paper, opacity (white backing), formerly known as contrast ratio, nor with the assessment of the amount and condition of light penetrating a sheet (transparency or translucency).

The calculation of opacity requires luminance-factor data obtained by measurement under specified conditions. The luminance factor depends on the conditions of measurement, and particularly on the spectral and geometric characteristics of the instrument used for its determination. This International Standard should therefore be read in conjunction with ISO 2469.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 2471:2008](https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008)

<https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2471:2008

<https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008>

Paper and board — Determination of opacity (paper backing) — Diffuse reflectance method

1 Scope

This International Standard specifies a method for the determination of the opacity (paper backing) of paper by diffuse reflectance.

It can be used to determine the opacity of papers or boards which contain fluorescent whitening agents, provided the UV content of the radiation incident on the test piece has been adjusted to conform to that in the CIE illuminant C using a fluorescent reference standard provided by an ISO/TC 6 authorized laboratory as described in ISO 2470-1.

This International Standard is not applicable to coloured papers or boards which incorporate fluorescent dyes or pigments.

2 Normative references

iTeh STANDARD PREVIEW
(standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 reflectance factor

R

ratio of the radiation reflected by a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that reflected by the perfect reflecting diffuser under the same conditions of irradiation

NOTE The ratio is often expressed as a percentage.

3.2
luminance factor (C)
luminous reflectance factor
 $Y(C/2^\circ)$ -value
 R_y
reflectance factor or radiance factor defined with reference to the CIE illuminant C and the visual efficiency function $V(\lambda)$

NOTE 1 The visual efficiency function describes the sensitivity of the eye to light, so that the luminance factor (C) corresponds to the attribute of visual perception of the reflecting surface.

NOTE 2 For computational purposes, the $V(\lambda)$ function is identical with the CIE 1931 colour-matching function $\bar{y}(\lambda)$.

NOTE 3 The luminance factor (C) is also known as the $Y(C/2^\circ)$ -value. In previous editions of this International Standard it was referred to as the luminous reflectance factor.

3.3
single-sheet luminance factor (C)
 R_0
luminance factor (C) of a single sheet of paper with a black cavity as backing

3.4
intrinsic luminance factor (C)
 R_∞
luminance factor (C) of a layer or pad of material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

3.5
opacity (paper backing)
ratio of the single-sheet luminance factor (C), R_0 , to the intrinsic luminance factor (C), R_∞ , of the same sample

NOTE Opacity is expressed as a percentage.

4 Principle

The luminance factor of a single sheet of the paper over a black cavity and the intrinsic luminance factor of the paper are determined. The opacity is calculated as the ratio of these two luminance factor values.

5 Apparatus

5.1 Reflectometer.

5.1.1 Reflectometer, having the geometric, spectral and photometric characteristics described in ISO 2469, calibrated in accordance with the provisions of ISO 2469 and equipped for the measurement of luminance factor (C).

Because materials to be measured may contain fluorescent whitening agents, the reflectometer shall be equipped with a radiation source having an adequate UV content control adjusted to a UV condition corresponding to the C illuminant by the use of a reference standard, as described in ISO 2470-1.

5.1.2 In the case of a **filter reflectometer**, a **filter** that, in conjunction with the optical characteristics of the basic instrument, gives an overall response equivalent to the CIE tristimulus value Y of the CIE 1931 standard colorimetric system of the test piece evaluated for the CIE illuminant C.

5.1.3 In the case of an **abridged spectrophotometer**, a **function** that permits calculation of the CIE tristimulus value Y of the CIE 1931 standard colorimetric system of the test piece, evaluated for the CIE illuminant C using the weighting functions given in Annex A.

5.2 Reference standards for calibration of the instrument and the working standards, used often enough to ensure satisfactory calibration and UV adjustment.

5.2.1 Non-fluorescent reference standard for photometric calibration, issued by an ISO/TC 6 authorized laboratory in accordance with the provisions of ISO 2469.

5.2.2 Fluorescent reference standard, for use in adjusting the UV content of the radiation incident upon the sample in order to adjust the UV setting of the instrument to conform to UV(C) conditions, as described in ISO 2470-1.

5.3 Working standards.

5.3.1 Two plates of flat opal glass, ceramic or other suitable material, cleaned and calibrated as described in ISO 2469.

NOTE In some instruments, the function of the primary working standard can be fulfilled by a built-in internal standard.

5.4 Black cavity, having a reflectance factor which does not differ from its nominal value by more than 0,2 %, at all wavelengths.

The black cavity should be stored upside down in a dust-free environment or with a protective cover.

NOTE 1 The condition of the black cavity can be checked by reference to the instrument manufacturer.

NOTE 2 The nominal value is given by the manufacturer.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6 Sampling and conditioning

If the tests are being made to evaluate a lot, the sample should be selected in accordance with ISO 186. If the tests are made on another type of sample, make sure that the test pieces taken are representative of the sample received. <https://standards.iteh.ai/catalog/standards/sist/4b8047b0-5d5d-4e8a-9f8e-e9c144fb723a/iso-2471-2008>

Conditioning according to ISO 187 is recommended but not required, but preconditioning at elevated temperatures should not be applied since it might change the optical properties.

7 Preparation of test pieces

Avoiding watermarks, dirt and obvious defects, cut rectangular test pieces approximately 75 mm × 150 mm. Assemble at least 10 of the test pieces in a pad with their top sides uppermost; the number of test pieces should be such that doubling the number does not alter the reflectance factor. Protect the pad by placing an additional sheet on both the top and bottom of the pad. Avoid contamination and unnecessary exposure to light or heat.

Mark the top test piece in one corner to identify the sample and its top side. If the top side can be distinguished from the wire side, it shall be uppermost; if not, as may be the case for papers manufactured on double-wire machines, ensure that the same side of the sheet is uppermost.

8 Procedure

8.1 Because the sample may contain a fluorescent whitening agent, check that the UV setting of the instrument has been adjusted to conform to UV(C)-conditions, using a fluorescent reference standard provided by an ISO/TC 6 authorized laboratory as described in ISO 2470-1.

8.2 Remove the protecting sheets from the test-piece pad. Without touching the test area, use the procedure appropriate to the instrument, to measure the intrinsic luminance factor R_{∞} of the top side of the test-piece pad. Read and record the value to the nearest 0,01 % of the reflectance factor.