



# SLOVENSKI STANDARD

## SIST EN 13121-3:2016

01-junij-2016

Nadomešča:

SIST EN 13121-3:2008+A1:2010

SIST EN 13121-3:2008+A1:2010/AC:2011

---

**Nadzemni rezervoarji in posode iz umetnih mas, ojačanih s steklenimi vlakni - 3. del: Konstruiranje in izdelava**

GRP tanks and vessels for use above ground - Part 3: Design and workmanship

Oberirdische GFK-Tanks und -Behälter - Teil 3: Auslegung und Herstellung

Réservoirs et récipients en PRV pour applications hors sol - Partie 3 : Conception et fabrication

**ITeh STANDARD PREVIEW**  
**(standards.iteh.ai)**  
<https://standards.iteh.ai/catalog/standards/sist/94e98a57-e6e9-40f1-8d21-e5d50f7c3ce5/sist-en-13121-3-2016>

**Ta slovenski standard je istoveten z: EN 13121-3:2016**

---

**ICS:**

23.020.10	Nepremične posode in rezervoarji	Stationary containers and tanks
-----------	----------------------------------	---------------------------------

**SIST EN 13121-3:2016**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 13121-3:2016

<https://standards.iteh.ai/catalog/standards/sist/94e98a57-e6e9-40f1-8d21-e5d50f7c3ce5/sist-en-13121-3-2016>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 13121-3**

April 2016

ICS 23.020.10

Supersedes EN 13121-3:2008+A1:2010

English Version

**GRP tanks and vessels for use above ground - Part 3:  
Design and workmanship**

Réservoirs et récipients en PRV pour applications hors  
sol - Partie 3 : Conception et fabrication

Oberirdische GFK-Tanks und -Behälter - Teil 3:  
Auslegung und Herstellung

This European Standard was approved by CEN on 10 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/94e98a57-e6e9-40f1-8d21-e5d50f7c3ce5/sist-en-13121-3-2016>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

	Page
European foreword .....	8
Introduction.....	9
<b>1 Scope .....</b>	<b>10</b>
<b>2 Normative references .....</b>	<b>10</b>
<b>3 Terms and definitions.....</b>	<b>12</b>
<b>4 Symbols and abbreviations.....</b>	<b>13</b>
<b>5 Information and requirements to be supplied and documented.....</b>	<b>16</b>
5.1 General .....	16
5.2 Information to be obtained by the manufacturer.....	16
5.3 Information to be prepared by the manufacturer.....	17
5.4 Final documentation .....	18
<b>6 Material.....</b>	<b>18</b>
6.1 General .....	18
6.2 Chemical protective barrier .....	18
6.2.1 General .....	18
6.2.2 Thermoplastics linings.....	18
6.2.3 Resin based linings .....	18
6.3 Flammability .....	18
6.4 Electrical resistivity.....	19
<b>7 Mechanical properties.....</b>	<b>19</b>
7.1 General .....	19
7.2 Heat deflection temperature.....	19
7.3 Laminate construction.....	19
7.4 Laminate thickness.....	21
7.5 Laminate properties.....	21
7.6 Inter-laminar shear strength .....	21
7.6.1 Laminate .....	21
7.6.2 Thermoplastics linings.....	21
7.7 Peel strength of laminates.....	22
7.8 Pull-off strength of laminates and thermoplastic liner .....	22
7.9 Selection of physical properties of materials and allowable design factors.....	22
7.9.1 General .....	22
7.9.2 Basic design .....	22
7.9.3 Advanced design .....	23
7.9.4 Design factors .....	24
7.9.5 Overall design factors <i>K</i> and <i>F</i> .....	24
<b>8 Determination of design strain and loadings.....</b>	<b>27</b>
8.1 General .....	27
8.2 Limit design strains .....	28
8.2.1 General .....	28
8.2.2 Limit resin strain $\epsilon_{ar}$ .....	28
8.2.3 Limit strain for laminate or lamina $\epsilon_{lim}$ .....	28
8.2.4 Limit test strain $\epsilon_{test}$ .....	29
8.3 Limit design laminate loadings .....	29
8.4 Determination of the mechanical values from laminates.....	29

8.4.1	General .....	29
8.4.2	Calculation of laminate values without experimental test data .....	29
8.4.3	Laminate with experimental data .....	30
8.5	Laminate thickness .....	30
9	Design .....	30
9.1	Introduction.....	30
9.2	Determination of external loads .....	31
9.2.1	Snow loads.....	31
9.2.2	Wind loads.....	31
9.2.3	Seismic loads .....	32
9.2.4	Insulation loads.....	33
9.2.5	Loads resulting from connections .....	33
9.2.6	Agitation.....	34
9.2.7	Pressure due to inadequate venting.....	34
9.2.8	Personnel loading.....	34
9.2.9	Internal stresses in vessels and tanks due temperatures.....	34
9.3	Verification by the partial factor method .....	34
9.3.1	General .....	34
9.3.2	Dimensioning by using $(A_5 \cdot \gamma)$ -factored loads.....	40
9.4	Drawings and design calculations .....	41
9.5	Design details.....	41
9.5.1	Design temperature $T_S$ .....	41
9.5.2	Pressure .....	41
10	Design analysis .....	42
10.1	Symbols and units.....	42
10.2	Vertical vessels or tanks, cylinders under loads ( $t < 0,01 \cdot D$ ) .....	44
10.2.1	Circumferential loadings .....	44
10.2.2	Combined axial loading .....	45
10.3	Cylindrical shells subject to compressive loadings — critical buckling criteria .....	46
10.3.1	General .....	46
10.3.2	Critical axial buckling load.....	46
10.3.3	Critical circumferential buckling pressure .....	47
10.3.4	Combined axial and radial compressive loadings .....	48
10.3.5	Critical buckling pressure for cylindrical shell stiffened with external or internal rings .....	49
10.4	Conical shells.....	50
10.4.1	General requirements.....	50
10.4.2	Shallow conical ends.....	52
10.4.3	Conical ends subject to internal pressure .....	52
10.4.4	Conical ends subject to external pressure.....	54
10.4.5	Shell conical covers.....	56
10.5	Dished end.....	57
10.5.1	General requirements.....	57
10.5.2	Dished ends subject to internal pressure .....	58
10.5.3	Stability for dished ends subject to external pressure .....	59
10.6	Design of flat bottoms and skirts for vertical tanks and vessels .....	60
10.6.1	Definitions.....	60
10.6.2	Fully supported, flat bottom tanks.....	60
10.6.3	Vessels with flat bases subjected to pressure .....	67
10.6.4	Dished bottom and conical bottom configurations.....	67
10.7	Circumferential seams for cylindrical joints .....	77
10.7.1	General .....	77
10.7.2	Construction without thermoplastics liner.....	79
10.7.3	Construction with thermoplastics liner .....	79

<b>10.8</b>	<b>Openings, branches and compensating laminate .....</b>	<b>79</b>
10.8.1	General .....	79
10.8.2	Symbols .....	80
10.8.3	Compensation requirements for openings .....	80
10.8.4	Pull out load from nozzles .....	87
10.8.5	Prevention of failure in peel.....	87
10.8.6	Pad connections .....	87
10.8.7	Screwed connections.....	89
10.8.8	Access and inspecting openings .....	89
10.8.9	Gusset on branches .....	89
<b>10.9</b>	<b>Flat Panels or Blind flanges.....</b>	<b>89</b>
10.9.1	General .....	89
10.9.2	Symbols .....	90
10.9.3	Circular panels.....	90
<b>10.10</b>	<b>Horizontal tanks and vessels.....</b>	<b>93</b>
10.10.1	Types of supports.....	93
10.10.2	Symbols.....	95
10.10.3	Unit loads of the cylindrical shell .....	96
10.10.4	Unit loads on saddle position.....	103
10.10.5	Unit loads for horizontal loads at the vessel .....	109
<b>10.11</b>	<b>Large diameter pipes and pipe fittings.....</b>	<b>110</b>
10.11.1	General.....	110
10.11.2	Joints .....	111
10.11.3	Elbows .....	112
10.11.4	Large cut-outs and Tees .....	112
<b>11</b>	<b>Bolted flange connections .....</b>	<b>115</b>
11.1	General .....	115
<b>11.2</b>	<b>Full face flanges design.....</b>	<b>121</b>
11.2.1	General .....	121
11.2.2	Symbols .....	122
11.2.3	Pipe loads on flanges.....	124
11.2.4	Gasket load and bolt torque.....	124
11.2.5	Summary of loads .....	125
11.2.6	Total bending moment .....	125
11.2.7	Flange design.....	125
11.2.8	Flange slope.....	127
<b>11.3</b>	<b>Stub flange design with backing ring .....</b>	<b>133</b>
11.3.1	General .....	133
11.3.2	Loads, bending moment and design for backing ring made of steel or GRP .....	134
11.3.3	Stub flange loadings.....	135
11.3.4	Stub shear interface design.....	135
11.3.5	Stub end or flange design.....	135
11.3.6	Seating stress .....	136
<b>11.4</b>	<b>Butt and strap jointed flanges at vessels or tanks .....</b>	<b>138</b>
<b>12</b>	<b>Supports for vessels and tanks .....</b>	<b>138</b>
12.1	General .....	138
<b>12.2</b>	<b>Supports and mountings for tanks and vessels .....</b>	<b>139</b>
12.2.1	General considerations for supports.....	139
12.2.2	Supports for vertical vessels .....	139
<b>13</b>	<b>Seismic loading.....</b>	<b>145</b>
<b>14</b>	<b>Design calculation for tank and vessel anchorage .....</b>	<b>145</b>
14.1	General .....	145
14.2	Design for uplift.....	145

14.3	Design for anchor bolts.....	145
15	Structures and fittings .....	149
15.1	General .....	149
15.2	Internal structures and fittings .....	149
15.3	External structures and fittings.....	149
15.4	Lifting devices .....	149
16	Local load analysis .....	154
17	Quality Control.....	154
17.1	General .....	154
17.2	Works requirements .....	154
17.2.1	General .....	154
17.2.2	Raw materials storage .....	154
17.2.3	Manufacturing area.....	154
17.2.4	Conditions for laminating.....	154
17.3	Documentation to be prepared by the manufacturer .....	155
17.3.1	Technical documentation .....	155
17.3.2	Records and documentation requirements for raw materials .....	155
17.3.3	Manufacturing documentation requirements .....	156
17.3.4	Quality control documentation requirements.....	156
17.4	Manufacture.....	161
17.4.1	General .....	161
17.4.2	Fabrication of thermoplastics liners .....	162
17.4.3	Fabrication of laminates .....	162
17.4.4	Imperfections in laminates .....	163
17.4.5	Curing.....	163
17.5	Inspection and testing after completion of fabrication .....	163
17.5.1	Visual and dimensional inspection .....	163
17.5.2	Physical test to be carried out .....	164
17.5.3	Coupon testing .....	164
17.6	Experimental Design Verification Method for pressure vessel .....	165
17.6.1	General .....	165
17.6.2	Manufacture of the prototype vessel.....	165
17.6.3	Tests to be applied to prototype vessels.....	166
18	Marking .....	166
Annex A	(informative) Product testing for serial or batch production process .....	168
A.1	Initial type testing (ITT).....	168
A.2	Testing of samples.....	168
A.2.1	General .....	168
A.2.2	Batch release tests (BRT).....	168
A.2.3	Process control tests.....	169
A.3	Inspection and test records .....	170
A.3.1	General .....	170
A.3.2	Marking .....	170
A.3.3	Delivery, installation, maintenance.....	170
Annex B	(informative) Derivation of laminate properties from laminate properties .....	171
B.1	General .....	171
B.2	Lamina/laminate thickness .....	171
B.3	Laminate modulus.....	172
B.4	Determination of laminate flexural stiffness .....	173
B.5	Determination of laminate strains from load resultants.....	173
Annex C	(normative) Pressure and leak testing.....	175

## EN 13121-3:2016 (E)

C.1	General	175
C.2	Open top tanks	175
C.3	Static head test of closed tanks and vessels	176
C.3.1	Contents having a specific gravity up to 1,0	176
C.3.2	Contents having a specific gravity greater than 1,0	176
C.4	Hydraulic pressure test	176
C.4.1	Test done in the working attitude	176
C.4.2	Tests done in other than the working attitudes	176
C.4.3	Pneumatic testing	177
C.4.4	Vacuum test	177
Annex D	(normative) Methods of tests	178
D.1	General	178
D.1.1	Tests	178
D.1.2	Accuracy of test equipment	178
D.2	Loss on ignition	179
D.3	Tensile strength of thermoplastics welds	179
D.4	Bend test for thermoplastics welds	179
D.4.1	Introduction	179
D.4.2	Test arrangement	179
D.4.3	Test pieces	180
D.4.4	Method of test	180
D.4.5	Requirements from flexural test	180
D.4.6	Test report	180
D.5	Ultimate tensile unit strength of laminates	181
D.5.1	Test pieces and procedure	181
D.5.2	Simple laminates	181
D.5.3	Combined laminates	181
D.6	Unit tensile modulus of laminates	182
D.7	Inter laminar shear strength of laminates	184
D.7.1	Form of test specimen	184
D.7.2	Number of test specimens	184
D.7.3	Procedure	184
D.7.4	Results	184
D.7.5	Report	184
D.8	Lap shear strength of bond between thermoplastics lining and laminate or between laminates	185
D.8.1	Form of the test specimen	185
D.8.2	Number of test specimens	185
D.8.3	Procedure	185
D.8.4	Report	186
D.9	Peel strength of bond between laminate layers	186
D.9.1	Form of the specimen	186
D.9.2	Number of specimens	186
D.9.3	Procedure	187
D.9.4	Report	187
D.10	Flexural short-term creep test (flexural modulus $E_{1h}$ and $E_{24h}$ test)	189
D.10.1	General	189
D.10.2	Definitions	189
D.10.3	Test device	189
D.10.4	Test pieces	190
D.10.5	Procedure	190
D.10.6	Calculation	190
D.11	Barcol hardness	191
D.12	Determination of electrical resistivity	191



D.13	Glass transition temperature by DSC of cured resin.....	191
D.14	Spark testing of thermoplastics welds.....	191
D.14.1	General .....	191
D.14.2	Apparatus .....	192
D.14.3	Procedure.....	192
D.15	Long term flexural creep test.....	192
D.15.1	General .....	192
D.15.2	Definitions.....	192
D.15.3	Test device .....	192
D.15.4	Test pieces.....	193
D.15.5	Procedure .....	193
D.15.6	Calculation.....	193
D.16	Hardness of rubber .....	194
D.17	Flash point test .....	194
D.18	Heat deflection temperature test.....	194
D.19	Flexural strength of laminate.....	194
D.20	Pull-off strength from laminates.....	194
Annex E	(normative) Approval testing of laminators .....	196
E.1	General .....	196
E.2	Assessment of the laminator .....	196
E.3	Procedure .....	196
E.4	Theory exam.....	197
E.5	Test pieces.....	197
E.6	Evaluation of test pieces.....	197
E.6.1	General .....	197
E.6.2	Test procedure 1.....	198
E.6.3	Test procedure 2.....	198
E.6.4	Test procedure 3.....	198
E.7	Minimum requirements for acceptance.....	198
E.8	Test certificate .....	199
E.9	Validity and renewal .....	199
E.10	Range of approval.....	199
Annex F	(informative) Design by stress analysis .....	201
F.1	General .....	201
F.2	Typical methods.....	201
F.3	General requirements.....	201
F.4	Important determination results .....	201
F.5	Design factors.....	201
Annex G	(normative) Environmental aspects .....	202
G.1	Principle.....	202
G.2	Design and Manufacturing .....	202
G.3	Effects of materials on water .....	202
G.4	Effects of materials on food.....	203
G.5	Recycling.....	203
G.6	Storage of substances hazardous to water .....	203
Annex ZA	(informative) Relationship between this European Standard and the essential requirements of Directive 2014/68/EU aimed to be covered .....	204
Bibliography	.....	206

**EN 13121-3:2016 (E)****European foreword**

This document (EN 13121-3:2016) has been prepared by Technical Committee CEN/TC 210 "GRP tanks and vessels", the secretariat of which is held by SFS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2016, and conflicting national standards shall be withdrawn at the latest by October 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13121-3:2008+A1:2010.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive.

For relationship with EU Directive, see informative Annex ZA, which is an integral part of this document.

The following changes were made in this new edition of EN 13121-3:

- the standard was totally revised so as to make it comply with EN 1990; and
- sections covering "Flat panels" and "Loading from local loads" removed from the standard.

EN 13121, *GRP tanks and vessels for use above ground*, is currently composed of the following parts:

- *Part 1: Raw materials — Specification conditions and acceptance conditions;*
- *Part 2: Composite materials — Chemical resistance;*
- *Part 3: Design and workmanship;*
- *Part 4: Delivery, installation and maintenance;*
- *Part 5: Example of calculation* (CEN/TR 13121-5; in preparation).

A European Standard does not purport to include all the necessary provisions of a contract. Users of European Standards are responsible for their correct application.

Compliance with a European Standard does not of itself confer immunity from legal obligations.

It has been assumed in the drafting of this European Standard that the execution of its provisions is entrusted to appropriately qualified and experienced people.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

The five parts of EN 13121 together define the responsibilities of the tank or vessel manufacturer and the materials to be used in their manufacture.

EN 13121-1 specifies the requirements and acceptance conditions for the raw materials - resins, curing agents, thermoplastics linings, reinforcing materials and additives. These requirements are necessary in order to establish the chemical resistance properties determined in EN 13121-2 and the mechanical, thermal and design properties determined in this part of EN 13121. Together with the workmanship principles determined in this Part 3, requirements and acceptance conditions for raw materials ensure that the tank or vessel will be able to meet its design requirements. EN 13121-4 of this standard specifies recommendations for delivery, handling, installation and maintenance of GRP tanks and vessels

The design and manufacture of GRP tanks and vessels involve a number of different materials such as resins, thermoplastics and reinforcing fibres and a number of different manufacturing methods. It is implicit that vessels and tanks covered by this standard are made only by manufacturers who are competent and suitably equipped to comply with all the requirements of this standard, using materials manufactured by competent and experienced material manufacturers.

Metallic vessels, and those manufactured from other isotropic, homogeneous materials, are conveniently designed by calculating permissible loads based on measured tensile and ductility properties. GRP, on the other hand, is a laminar material, manufactured through the successive application of individual layers of reinforcement. As a result there are many possible combinations of reinforcement type that will meet the structural requirement of any one design case. This allows the designer to select the laminate construction best suited to the available manufacturing facilities and hence be most cost effective.

In considering a layered GRP structure it is assumed that it is the glass reinforcement that provides the stiffness and strength required to resist mechanical loadings. Also, since the quantity of glass reinforcement is most readily assessed by weight, the weight of glass per unit area ( $m$ ) is used instead of thickness in determining mechanical properties, thus the concepts of load and modulus are replaced by unit strength ( $u$ ) and unit modulus ( $X$ ), these being defined in Table 1.

It is possible that future advances in resin technology would allow tanks and vessels to be considered for operating temperatures above 120 °C. Should such a situation arise and a manufacturer wish to take advantage of such developments then all other requirements of this standard will be maintained and such tanks and vessels will only be designed in accordance with the advanced design method given in 7.9.3.

**NOTE** To convert a unit load, or a unit modulus to a load and a modulus respectively,  $U$  and  $X$  may be simply divided by  $t$ , where  $t$  is the thickness per weight of glass per unit area of the lamina, or laminate under consideration.

**EN 13121-3:2016 (E)****1 Scope**

This European Standard gives requirements for the design, fabrication, inspection, testing and verification of GRP tanks and vessels with or without thermoplastics lining for storage or processing of fluids, factory made or site built, non-pressurized or pressurized up to 10 bar, for use above ground. Further requirements are presented in normative Annex G.

The terms vessels and tanks as used in this part of EN 13121 include branches up to the point of connection to pipe work or other equipment by bolting and supports, brackets or other attachments bonded directly to the shell.

This part of EN 13121 covers vessels and tanks subject to temperatures between – 40 °C and 120 °C.

Excluded from this part of EN 13121 are:

- tanks and vessels for the transport of fluids;
- underground storage tanks;
- spherical vessels;
- vessels and tanks of irregular shape;
- tanks and vessels with double containment where the double wall is considered structural;
- tanks and vessels which are subject to the risk of explosion, or failure of which may cause an emission of radioactivity;
- specification for fibre reinforced cisterns of one piece and sectional construction for the storage, above ground, of cold water (see EN 13280);

<https://standards.iteh.ai/catalog/standards/sist/94e98a57-e6e9-40f1-8d21-e5d50f7c3ce5/sist-en-13121-3-2016>

**2 Normative references**

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 59, *Glass reinforced plastics — Determination of indentation hardness by means of a Barcol hardness tester*

EN 1092-1, *Flanges and their joints — Circular flanges for pipes, valves, fittings and accessories, PN designated — Part 1: Steel flanges*

EN 1990, *Eurocode — Basis of structural design*

EN 1991-1-1, *Eurocode 1: Actions on structures — Part 1-1: General actions — Densities, self-weight, imposed loads for buildings*

EN 1991-1-3, *Eurocode 1 — Actions on structures — Part 1-3: General actions - Snow loads*

EN 1991-1-4, *Eurocode 1: Actions on structures — Part 1-4: General actions - Wind actions*

EN 1991-1-5, *Eurocode 1: Actions on structures — Part 1-5: General actions - Thermal actions*

EN 1991-4, *Eurocode 1 — Actions on structures — Part 4: Silos and tanks*

EN 1993 (all parts), *Eurocode 3: Design of steel structures*

- EN 1993-1-1, *Eurocode 3: Design of steel structures — Part 1-1: General rules and rules for buildings*
- EN 1993-1-6:2007, *Eurocode 3 — Design of steel structures — Part 1-6: Strength and Stability of Shell Structures*
- EN 1998 (all parts), *Eurocode 8 — Design of structures for earthquake resistance*
- EN 1998-1, *Eurocode 8: Design of structures for earthquake resistance — Part 1: General rules, seismic actions and rules for buildings*
- EN 1998-4:2006, *Eurocode 8 — Design of structures for earthquake resistance — Part 4: Silos, tanks and pipelines*
- EN 10025-2, *Hot rolled products of structural steels — Part 2: Technical delivery conditions for non-alloy structural steels*
- EN 13067, *Plastics welding personnel — Qualification testing of welders — Thermoplastics welded assemblies*
- EN 13121-1:2003, *GRP tanks and vessels for use above ground — Part 1: Raw materials — Specification conditions and acceptance conditions*
- EN 13121-2:2003, *GRP tanks and vessels for use above ground — Part 2: Composite materials — Chemical resistance*
- EN 13121-4, *GRP tanks and vessels for use above ground — Part 4: Delivery, installation and maintenance*
- EN 13445-3:2014, *Unfired pressure vessels — Part 3: Design*
- EN 13555, *Flanges and their joints — Gasket parameters and test procedures relevant to the design rules for gasketed circular flange connections*
- EN 13923, *Filament-wound FRP pressure vessels — Materials, design, manufacturing and testing*
- EN ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite (ISO 75-2)*
- EN ISO 291, *Plastics — Standard atmospheres for conditioning and testing (ISO 291)*
- EN ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites (ISO 527-4)*
- EN ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep (ISO 899-1)*
- EN ISO 899-2, *Plastics — Determination of creep behaviour — Part 2: Flexural creep by three-point loading (ISO 899-2)*
- EN ISO 1172, *Textile-glass-reinforced plastics — Prepregs, moulding compounds and laminates — Determination of the textile-glass and mineral-filler content — Calcination methods (ISO 1172)*
- EN ISO 2592, *Determination of flash and fire points — Cleveland open cup method (ISO 2592)*
- EN ISO 3915, *Plastics — Measurement of resistivity of conductive plastics (ISO 3915)*

**EN 13121-3:2016 (E)**

EN ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system (ISO 7500-1)*

EN ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing (ISO 9513)*

EN ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and glass transition step height (ISO 11357-2)*

EN ISO 14125, *Fibre-reinforced plastic composites — Determination of flexural properties (ISO 14125)*

EN ISO 14692-3:2002, *Petroleum and natural gas industries — Glass-reinforced plastics (GRP) piping — Part 3: System design (ISO 14692-3:2002)*

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ASTM D4541-09, *Standard Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers*

ASME B16.5/16.47, *Pipe Flanges and Flanged Fittings: NPS 1/2 Through NPS 24 Metric/Inch Standard*

**3 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

**3.1****manufacturer**

organization that designs, manufactures and tests the vessel or tank in accordance with this standard

[SIST EN 13121-3:2016](https://standards.iteh.ai/catalog/standards/sist/94e98a57-e6e9-40f1-8d21-e5d50f7c3ce5/sist-en-13121-3-2016)

**3.2****purchaser**

organization or individual that buys the finished vessel or tank and specifies the process requirements

<https://standards.iteh.ai/catalog/standards/sist/94e98a57-e6e9-40f1-8d21-e5d50f7c3ce5/sist-en-13121-3-2016>

**3.3****authorized inspecting authority**

body or organization that maybe required to check that the design, materials and construction comply with this standard

Note 1 to entry: For this standard, when  $PS \leq 0,5$  bar.

**3.4****vessel**

closed container subject to applied pressure or vacuum, with or without hydrostatic head, including branches up to the first flanged connection

**3.5****notified body**

certificated organization listed by the European commission of pressure equipment

Note 1 to entry: For this standard, when  $PS > 0,5$  bar.

**3.6****internal inspection authority**

inspector from the manufacturer which is independent from the workshop

**3.7****tank**

container for the storage of fluids subject only to the fluid hydrostatic head and freely vented to atmosphere, including branches up to the first flanged connection

**3.8****laminate**

resin reinforced with glass fibre

**3.9****gel coat**

thin layer of resin on the surface of a laminate that may or not be reinforced with a glass or a synthetic fibre tissue

**3.10****cure**

chemical reaction resulting in the polymerized laminate

**3.11****post cure**

application of heat to take the polymerization to a final stage

**3.12****maximum allowable pressure****PS**

maximum pressure for which the equipment is designed, as specified by the manufacturer

**3.13****differential pressure****PS**

difference of pressure on both sides of a component

**3.14****design pressure** **$p_D$** 

design pressure used in the calculations for a component

**3.15****maximum/minimum allowable temperature****TS**

maximum/minimum temperatures for which the equipment is designed, as specified by the manufacturer

**3.16****test temperature**

temperature at which the pressure test of the equipment is carried out

**3.17****test pressure****PT**

pressure to which the tank or vessel is tested

**4 Symbols and abbreviations**

For the purposes of this document, the symbols and abbreviations common to all clauses and annexes are given in Table 1. All dimensions are given in millimetres.

Further symbols are defined in the relevant clauses as required.