



Designation: A982/A982M – 05

Standard Specification for Steel Forgings, Stainless, for Compressor and Turbine Airfoils¹

This standard is issued under the fixed designation A982/A982M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers stainless steel forgings for compressor and turbine bucket, blade, and airfoil applications.

1.2 This specification is expressed in both inch-pound units and in SI units; however, unless the purchase order or contract specifies the applicable *M* designation (SI units), the inch-pound units shall apply. The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

[A275/A275M Practice for Magnetic Particle Examination of Steel Forgings](#)

[A788/A788M Specification for Steel Forgings, General Requirements](#)

[A994 Guide for Editorial Procedures and Form of Product Specifications for Steel, Stainless Steel, and Related Alloys](#)

[E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings](#)

[E562 Test Method for Determining Volume Fraction by Systematic Manual Point Count](#)

3. Ordering Information

3.1 In addition to the ordering information required by Specification [A788/A788M](#), the purchaser shall include a sketch or written description of the forging with the inquiry and order.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved March 1, 2005. Published March 2005. Originally published in 1998. Last previous edition approved in 2002 as A 982 – 02. DOI: 10.1520/A0982_A0982M-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. General Requirements

4.1 Materials supplied to this specification shall conform to the requirements of Specification [A788/A788M](#), which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations and additional supplementary requirements.

4.2 If the requirements of this specification are in conflict with the requirements of Specification [A788/A788M](#), the requirements of this specification shall prevail.

5. Manufacture

5.1 *Melting Process*—All melting processes of Specification [A788/A788M](#) are permitted unless Supplementary Requirement S1 is invoked by the purchaser.

5.2 *Forging Process*—Either the closed impression die or the open die forging processes may be utilized unless the purchaser specifies one or the other.

5.2.1 *Forging Temperature*—The maximum part temperature during forging shall be 2150°F [1175°C].

5.3 *Heat Treatment*—Heat treating all forgings is required in accordance with [Table 1](#) to develop the required mechanical properties.

5.3.1 *Number of Heat Treatments*—Two complete heat treatments, consisting of an austenitize, quench, and temper, are permitted. Purchaser approval is required prior to any additional heat treatments.

5.3.2 *Temperature Variation*—Heat treating temperatures shall be controlled in the range of $\pm 25^\circ\text{F}$ [$\pm 14^\circ\text{C}$].

5.4 *Stress Relief*—When heat treatment for mechanical properties is followed by straightening, a stress-relieving heat treatment is required at a temperature meeting the requirements of [Table 1](#).

5.4.1 *Quenching after Stress Relief*—Water or oil quenching of stress-relieved forgings is prohibited.

6. Chemical Composition

6.1 The steel shall conform to the requirements for chemical composition prescribed in [Table 2](#).

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Heat Treatment, °F [°C]

	Grade A	Grade B	Grade C		Grade D	Grade E		Grade F
	Classes 1 & 2	Class 1	Class 1	Class 2	Classes 1 & 2	Class 1	Class 2	Class 1
Austenitizing	1725-1775 [940-970]	1600-1750 [870-955]	1825-1875 [995-1025]	1725-1875 [940-1025]	1875-1925 [1025-1050]	2075-2125 [1135-1165]	1725-1775 [940-970]	1875-1925 [1025-1050]
Quenching	Air or liquid	Air or liquid	Air or liquid	Air or liquid	Air or liquid	Air or liquid	Air or liquid	Air or liquid
Single tempering	1050 min [565 min]	1050 min [565 min]	1050 min [565 min]	1050 min [565 min]	1150 min [620 min]	1250 min [675 min]	1100 min [595 min]	...
Double tempering	1025 min [550 min]	1025 min [550 min]
Aging	1135-1165 [615-630]
Stress Relieving	1025 min [550 min]	1025 min [550 min]	1000 min [540 min]	1000 min [540 min]	1100 min [595 min]	1200 min [650 min]	1050 min [565 min]	1100 min [595 min]

TABLE 2 Chemical Requirements

UNS Designation	Composition %					
	Grade A	Grade B	Grade C	Grade D	Grade E	Grade F
	S41000	S41005	S41428	S42225	S41041	S17400
Carbon	0.15 max	0.10-0.15	0.10-0.17	0.20-0.25	0.13-0.18	0.07 max
Manganese	1.0 max	0.25-0.80	0.65-1.05	0.5-1.0	0.4-0.6	1.0 max
Phosphorus, max	0.018	0.018	0.020	0.020	0.030	0.040
Sulfur, max	0.015	0.015	0.015	0.010	0.030	0.030
Silicon	0.5 max	0.5 max	0.10-0.35	0.20-0.50	0.5 max	1.0 max
Nickel	0.75 max	0.75 max	2.25-3.25	0.5-1.0	0.5 max	3.0-5.0
Chromium	11.5-13.0	11.5-13.0	11.25-12.75	11.0-12.5	11.5-13.0	15.0-17.5
Molybdenum	0.5 max	0.5 max	1.5-2.0	0.9-1.25	0.20 max	...
Vanadium	...	Report only	0.25-0.40	0.20-0.30
Tungsten	...	0.10 max	0.10 max	0.9-1.25
Nitrogen	...	0.08 max	0.020-0.045	Report only
Aluminum	...	0.025 max	0.025 max	0.025 max	0.05 max	...
Columbium	...	0.20 max	...	0.05 max	0.15-0.45	0.15-0.45
Cobalt	0.20 max
Titanium	...	0.05 max	0.05 max	0.025 max
Copper	...	0.15 max	0.15 max	0.15 max	...	3.0-5.0
Tin	...	0.05 max	0.05 max	0.02 max

7. Mechanical Properties

7.1 *Tension, Impact, and Hardness Tests*—All testing shall be performed after heat treatment and stress relief, as applicable. The test specimens shall meet the requirements of **Table 3**.

7.1.1 *Number of Tests*—A minimum of two forgings from each lot shall be randomly selected for longitudinal tensile, impact, and hardness testing. Hardness values of the tension test specimen shall be reported with the tensile data.

7.1.1.1 *Lot Size*—A lot shall consist of all forgings of the same size from one electric furnace heat of steel and heat

treated either in the same charge in either a batch furnace or a continuous type furnace.

7.1.1.2 *Continuous Heat Treating Furnaces*—Test forgings shall be taken from each of the first and last push or tray to exit the furnace. Additional forgings shall be taken so that the maximum time between samples is 4 h.

7.1.1.3 *Test Locations*—One tension test specimen and one set of three impact test specimens shall be machined from the center portion of the air foil vane section.

TABLE 3 Tensile, Impact, and Hardness Requirements

	Grade A		Grade B	Grade C		Grade D		Grade E		Grade F
	Class 1	Class 2	Class 1	Class 1	Class 2	Class 1	Class 2	Class 1	Class 2	Class 1
Tensile strength, min, ksi [MPa]	100 [690]	110 [760]	110 [760]	145 [1000]	160 [1105]	140 [965]	140 [965]	115 [795]	110 [760]	135 [935]
Yield strength, min, ksi [MPa], 0.2 % offset	70 [485]	80 [555]	90 [620]	115 [795]	120 [825]	90 [620]	100 [690]	75 [515]	80 [555]	105 [725]
Elongation in 2 in., min, %	20	18	18	15	16	13	13	15	18	16
Reduction of area, min, %	60	50	50	30	50	30	35	50	55	50
Impact strength, min, av., Cv [J], Rt, ft-lb	30	25	30	30	40	8	13	20	25	41
Hardness, Brinell, max	[40]	[33]	[40]	[40]	[55]	[11]	[18]	[27]	[34]	[55]
	255	269	269	352	375	331	331	277	262	341