
**Steel — Ultrasonic testing for steel flat
products of thickness equal to or greater
than 6 mm**

*Aciers — Contrôle ultrasonore des produits plats en acier d'épaisseur
égale ou supérieure à 6 mm*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 17577:2006](#)

[https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-
a538-558b4b5c81ee/iso-17577-2006](https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-a538-558b4b5c81ee/iso-17577-2006)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17577:2006

<https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-a538-558b4b5c81ee/iso-17577-2006>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Personnel	2
6 Testing system	3
6.1 General requirements	3
6.2 Manual-testing instrument	3
6.3 Automated testing system	3
6.4 Performance of electronic equipment	4
6.5 Probes	4
6.6 Coupling medium	5
7 Procedure	5
7.1 Inspection timing	5
7.2 Scanning plan	5
7.2.1 General	5
7.2.2 Testing of the flat-product body	5
7.2.3 Testing of the edges of the flat products	6
7.3 Scanning condition	6
7.4 Sensitivity and range setting	6
8 Determination of the discontinuity size	8
8.1 Testing the flat-product body	8
8.1.1 Testing with dual-element probes	8
8.1.2 Testing with single-element probes	8
8.2 Testing the edges	8
9 Acceptance criteria	9
10 Test report	9
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17577 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 7, *Methods of testing (other than mechanical tests and chemical analysis)*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 17577:2006

<https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-a538-558b4b5c81ee/iso-17577-2006>

Steel — Ultrasonic testing for steel flat products of thickness equal to or greater than 6 mm

1 Scope

This International Standard specifies a method for the automated and/or manual ultrasonic testing of uncoated steel flat products for internal discontinuities by the reflection method. It is applicable to non-alloyed or alloyed steel flat products, in a nominal thickness range of 6 mm to 200 mm. However, this standard may be applied to austenitic and austenitic-ferritic steels, provided that the difference between the amplitude of the noise signal and that of the echo detection threshold is sufficient for the limit fixed. Unless otherwise agreed, for testing of steel flat products for welded steel tubes, ISO 12094 applies.

Other methods of testing (e.g. by transmission) or other test equipment may be used at the manufacturer's discretion, provided that they give identical results to those obtained under the conditions of this standard. In the event of a dispute, only the method defined in this standard will prevail.

Testing of flat products, of thickness less than 6 mm and over 200 mm, may be the subject of special agreements between the parties concerned.

The inspection is normally carried out in the place of production or on the premises of the supplier.

2 Normative references

ISO 17577:2006

[https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-](https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-a538-558b4b5c81ee/iso-17577-2006)

[a538-558b4b5c81ee/iso-17577-2006](https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-a538-558b4b5c81ee/iso-17577-2006)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9712, *Non-destructive testing — Qualification and certification of personnel*

ISO 12094, *Welded steel tubes for pressure purposes — Ultrasonic testing for the detection of laminar imperfections in strips/plates used in the manufacture of welded tubes*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

internal discontinuity

any imperfection lying within the thickness of the flat products, e.g. planar or laminar imperfection, single-plane or multi-plane inclusion bands or clusters

3.2

defect

unacceptable internal discontinuities, i.e. exceeding the specified maximum size or population density limits

3.3

population density

number of individual internal discontinuities of a size greater than a specified minimum size and less than a specified maximum size per specified area of body or length of edge zone

3.4

manual and assisted manual testing

testing by an operator applying an ultrasonic probe to the flat-product surface, manually executing the appropriate scanning pattern on the flat-product surface and visually assessing ultrasonic signal indications on the electronic equipment screen either by direct viewing or by built-in signal amplitude alarm devices

3.5

automated and semi-automated testing

testing using a mechanized means of applying the ultrasonic probe or probes to the flat-product surface and executing the appropriate scanning pattern, together with ultrasonic signal evaluation by electronic means

NOTE Such testing can be either fully automated with no operator involvement or semi-automated when the operator performs basic equipment operation functions.

3.6

dead zone

zone to be measured as the point of time base where the transmitted pulse or surface echo drops to less than 20 % of screen height under the specified test sensitivity.

4 Principle

The method used is based on the reflection of ultrasonic waves (generally longitudinal), the mean direction of which is perpendicular to the main surface of the flat products.

The examination consists of the following:

- a) Locating any discontinuity by comparing the amplitude of the discontinuity echo with the amplitude of the echo of a flat-bottomed hole of a given diameter and located at the same depth as the discontinuity.

NOTE Only those discontinuities giving an echo height exceeding in amplitude that of the echo obtained with the reference flat-bottomed hole are taken into consideration.

- b) Then determining its area, the contour of the discontinuity being defined by the positions of the center of the probe corresponding to an echo amplitude of half the maximum amplitude of the discontinuity under consideration (6 dB method).

The examination is carried out during the first ultrasonic scan for all the flat-product thicknesses and from one side only.

In the case of automated testing, the location of a discontinuity and the determination of its area can be realized using different algorithms together with high scanning density. In case of dispute, the 6 dB technique in 8.1.1 should be used.

5 Personnel

Testing shall be carried out by qualified personnel under the responsibility of a Level 3 individual, certified in accordance with ISO 9712 or an appropriate national/regional standard.

NOTE Examples of appropriate standards are listed in the Bibliography.

6 Testing system

6.1 General requirements

- a) The normal beam technique and the reflection technique shall be used for the ultrasonic testing method.
- b) The apparatus shall be equipped with time-base regulation and the gain control shall be calibrated in decibels.
- c) The electronic equipment shall be appropriate for the ultrasonic probes and frequencies used.
- d) The transmitted pulse repetition frequency shall be appropriate for the applied scanning speed.
- e) The apparatus shall detect the ultrasonic signals of internal discontinuities by using a gate function. The output signal shall be provided for devices like display monitor or recording equipment.
- f) The coupling medium shall ensure an adequate contact between the probe and the surface of the flat products and maintain sufficient coupling.

6.2 Manual-testing instrument

The instrument shall be equipped with an A-scan display monitor that allows the assessment of the path of ultrasonic waves in the flat products. The oscillograms shall be clearly visible, the peaks corresponding to the successive echoes being sharp and very clear.

6.3 Automated testing system

The automated testing system shall be equipped with the following:

- a) a suitable mechanical means for scanning the surface of flat products with a defined density;
- b) probe holders which are capable of following the surface contour of a flat product to be tested, in order to maintain straight incidence;
- c) appropriate electronics including, for example, transmitters, receivers, multiplexer, gates, display monitor, as well as a means for data collection;
- d) appropriate means for signal evaluation, recording (e.g. mapping) and storing;
- e) means for calibration of the equipment (i.e. sensitivity, time base and gate position), for example, by the use of reference blocks, input of artificial signals, input of distance-amplitude curves (DAC) or input of stored calibration files;
- f) means for control of pulse repetition frequency related to the scanning speed;
- g) means for coupling and function check (e.g. by surveillance of back-wall echo);
- h) function to indicate the location of discontinuities from the edge of flat products (printer, recorder or display).

6.4 Performance of electronic equipment

The electronic equipment shall have the following performance.

a) Linearity

- Linear amplifiers: The deviation of the vertical linearity shall not exceed ± 1 dB in any part of a 20 dB span.
- Logarithmic amplifiers: The deviation of the vertical linearity shall not exceed ± 1 dB in any part of a 20 dB span and ± 2 dB in any part of a 60 dB span.
- Horizontal linearity: The deviation of the horizontal linearity shall not exceed $\pm 2\%$ of the testing range.

The vertical linearity shall be checked at least once a year, unless the conditions dictate a higher frequency of checking. The results of all checks shall be recorded.

b) Dead zone

The dead zone of single-element probes shall be as small as possible, i.e. max. 15 % of the thickness of the flat products or 15 mm, whichever is the smaller. For product thicknesses less than 10 mm, their dead zone shall be less than or equal to 1,5 mm.

6.5 Probes

iTeh STANDARD PREVIEW

The probes shall be single-element probes, dual-element probes or multiple dual-element probes, depending on the thickness of the flat products as given in Table 1.

ISO 17577:2006
<https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-2015-58641-proc/iso-17577-2006>
Table 1 — Type of probe

Specified thickness of the flat products or path length (<i>e</i>) mm	Type of probe ^{a, b}
$6 \leq e \leq 60$	Dual-element probe
$60 < e \leq 200$	Single or dual-element probe
^a In the event of dispute, the type of probe to be used shall be the subject of an agreement between the purchaser and manufacturer. ^b As long as the stipulation of the dead zone is satisfied, where testing is carried out using immersion or water-column techniques, it is permissible to use single probes for flat products of less than or equal to 60 mm thickness.	

The probes shall have a nominal frequency in the range of 2 MHz to 5 MHz. Probes with a frequency outside the range of 2 MHz to 5 MHz can be used for the material that has high attenuation or special acoustic characteristics, if agreed between the purchaser and manufacturer.

The focusing zone of dual-element probes shall be adapted to the thickness of the flat products.

The relevant dimension of transducers is less than or equal to 30 mm in diameter or in rectangularity.

6.6 Coupling medium

The coupling medium shall ensure an adequate coupling between the probe and the surface of the flat products.

Water is normally used, but other coupling media (e.g. oil, paste) may be used at the discretion of the supplier.

The coupling medium should be chosen to avoid intercrystalline corrosion, e.g. when applied to austenitic steel, and in such cases should be adequately removed after testing by an appropriate method.

7 Procedure

7.1 Inspection timing

Unless otherwise agreed, the ultrasonic test shall be carried out at the final stage.

7.2 Scanning plan

7.2.1 General

For the flat-product body, the testing is based on statistical methods unless otherwise specified in the order. Scanning of the flat products shall be carried out in accordance with 7.2.2 and/or 7.2.3 and corresponding to the required quality class.

By agreement at the time of ordering, a scanning with a defined scan coverage or a scanning of all body parts of the flat products may be provided, the operating conditions being included in the agreement.

7.2.2 Testing of the flat-product body ISO 17577:2006

[https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-](https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-538-558b4b5c81ee/iso-17577-2006)

[538-558b4b5c81ee/iso-17577-2006](https://standards.iteh.ai/catalog/standards/sist/d3638908-9130-4d75-538-558b4b5c81ee/iso-17577-2006)

The following testing conditions apply.

- a) For the flat-product body, the scanning comprises continuous examination along the lines of a grid parallel to the edges of the flat products, or along the parallel or oscillating lines distributed uniformly over the area, given the same degree of control.
- b) For Classes B₁ and B₂, the scanning shall be the lines of grid of a 200 mm square, or along vertical or horizontal lines at 100 mm pitch.
- c) For Classes B₃ and B₄, the scanning shall be the lines of grid of a 100 mm square, or along vertical or horizontal lines at 50 mm pitch.
- d) In the event of probe failure, the above-mentioned pitch requirements can be exempted, as long as defective probes are not consecutive and if the following requirements for coverage rates are met:
 - 1) Classes B₁ and B₂: the required coverage rate of the scanning area shall be equal to or larger than 20 %.
 - 2) Classes B₃ and B₄: the required coverage rate of the scanning area shall be equal to or larger than 40 %.
 - 3) These coverage rates shall be calculated, based on the width of operating probes including the scanned area of the flat-product edges.