

# INTERNATIONAL STANDARD

**ISO**  
**6871-1**

First edition  
1994-09-15

**AMENDMENT 1**  
2005-06-15

---

---

## Dental base metal casting alloys — Part 1: Cobalt-based alloys AMENDMENT 1

**iTeh STANDARD PREVIEW** —  
*Alliages dentaires non précieux à couler —  
Partie 1: Alliages à base de cobalt*  
**(standards.iteh.ai)**  
AMENDEMENT 1

ISO 6871-1:1994/Amd 1:2005

<https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005>



Reference number  
ISO 6871-1:1994/Amd.1:2005(E)

© ISO 2005

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 6871-1:1994/Amd 1:2005](https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 6871-1:1994 was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 2, *Prosthetic materials*.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 6871-1:1994/Amd 1:2005](https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 6871-1:1994/Amd 1:2005](https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005>

# Dental base metal casting alloys —

## Part 1: Cobalt-based alloys

### AMENDMENT 1

#### *Page iv, Introduction*

Replace the text in the Introduction with the following text:

“Dental base metal casting alloys are suitable for use in fabrication of removable dental appliances. Specific qualitative and quantitative requirements of freedom from biological hazards are not included in this part of ISO 6871 but when assessing possible biological or toxicological hazards, it is recommendable to refer to ISO 7405 and ISO 10993-1.

For other compositions, the manufacturer has to present adequate evidence of biological investigations in accordance with ISO 7405 or ISO 10933-1, and/or clinical investigations in order to assess the biological response of the material.

Specific quantitative requirements for corrosion resistance are not included in this part of ISO 6871. In order to obtain information on the kind and amount of metal ions leached from the alloy, see ISO 10271, and the static immersion test, described in Annex A.”

#### *Page 1, Clause 2*

Replace the following normative references with the latest editions:

ISO 6892:1998, *Metallic materials — Tensile testing at ambient temperature*

ASTM B600-91(2002), *Standard guide for descaling and cleaning titanium and titanium alloy surfaces*

#### *Page 1, subclause 4.1*

Replace subclause 4.1 with the following text:

“The chemical composition of the casting alloy shall meet the following requirements:

Cobalt	main constituent
Chromium	≥ 25 % [mass fraction <sup>1)</sup> ]
Molybdenum	≥ 4 % (mass fraction)
Cobalt + nickel + chromium	≥ 85 % (mass fraction)

1) The unit (*mlm*) is deprecated. In accordance with ISO 31-0:1992, 2.3.3, Note 4, the correct expression is mass fraction.

## ISO 6871-1:1994/Amd.1:2005(E)

The alloy shall not contain more than 0,02 % (mass fraction) of beryllium.

Constituents of the alloy in excess of 20 % (mass fraction) shall be within 2 % (mass fraction) of the value stated [see Clause 8 b) and 9.2 d)]. Constituents in excess of 2 % (mass fraction) but not in excess of 20 % (mass fraction) shall be within 1 % (mass fraction) of the value stated [see Clause 8 b) and 9 d)]. The percentage of nickel shall not be greater than the percentage indicated on the package label or insert (see Clause 8)."

Page 3, Clause 8 b)

Replace Clause 8 b) with the following text:

"b) a list of all the elements present in concentrations equal to or greater than 0,1 % (mass fraction), and their percentage concentration (mass fraction) if present in concentrations equal to or greater than 2 %."

Page 6, Annex B

Delete "Annex B (informative)" so that it reads simply "Bibliography".

Replace the following references with the latest editions:

- [1] ISO 1942, *Dentistry — Vocabulary* <sup>2)</sup>
- [2] ISO 7405:1997, *Dentistry — Preclinical evaluation of biocompatibility of medical devices used in dentistry — Test methods for dental materials*
- [3] ISO 10271:2001, *Dental metallic materials — Corrosion test methods*
- [4] ISO 10993-1:2003, *Biological evaluation of medical devices — Part 1: Evaluation and testing*  
<https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005>

---

2) To be published. (Revision of ISO 1942-1:1989, ISO 1942-2:1989, ISO 1942-3:1989, ISO 1942-4:1989 and ISO 1942-5:1989)

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 6871-1:1994/Amd 1:2005](https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 6871-1:1994/Amd 1:2005](https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005)  
[https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-  
e96a24ed2626/iso-6871-1-1994-amd-1-2005](https://standards.iteh.ai/catalog/standards/sist/c49d177f-784e-4bfd-831c-e96a24ed2626/iso-6871-1-1994-amd-1-2005)

---

---

**ICS 11.060.10**

Price based on 2 pages