



Designation: B 94 – 05

## Standard Specification for Magnesium-Alloy Die Castings<sup>1</sup>

This standard is issued under the fixed designation B 94; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers magnesium-alloy die castings. Current alloy compositions are specified under the designations shown in [Table 1](#).<sup>2</sup>

1.2 The values stated in inch-pound units are standard. The SI values in parentheses are provided for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 The following documents of the issue in effect on date of order acceptance form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:<sup>3</sup>

**B 93/B 93M** Specification for Magnesium Alloys in Ingot Form for Sand Castings, Permanent Mold Castings, and Die Castings

**B 275** Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

**B 557** Test Methods of Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products

**B 660** Practices for Packaging/Packing of Aluminum and Magnesium Products

**E 23** Test Methods for Notched Bar Impact Testing of Metallic Materials

**E 29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

**E 35** Test Methods for Chemical Analysis of Magnesium

and Magnesium Alloys

**E 88** Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition

**E 505** Reference Radiographs for Inspection of Aluminum and Magnesium Die Castings

**E 527** Practice for Numbering Metals and Alloys (UNS)

2.3 *American Die Casting Institute*:<sup>3</sup>

“E” Series Product Standards

2.4 *Federal Standards*:<sup>4</sup>

**Fed. Std. No. 123** Marking for Shipment (Civil Agencies)

**Fed. Std. No. 184** Identification Marking of Aluminum, Magnesium and Titanium

2.5 *Military Standard*:<sup>4</sup>

**MIL-STD-129** Marking for Shipment and Storage

### 3. Terminology

3.1 *Definition*:

3.1.1 *die casting*—a metal object produced by the introduction of molten metal under substantial pressure into a metal die and characterized by a high degree of fidelity to the die cavity.

### 4. Ordering Information

4.1 Orders for die castings shall include the following basic information:

4.1.1 This specification number and date,

4.1.2 Quantity and delivery schedule, as required,

4.1.3 Part name and number,

4.1.4 Alloy ([Table 1](#)), and

4.1.5 Drawing of die casting, when required, giving all necessary dimensions and showing latest revisions and allowances for machining, if any. Location of ejector pin marks or parting lines shall be at the option of the producer, unless specifically designated on the drawing.

4.2 Additional tests, options, and special inspection requirements as provided below should be justified only on the basis of need. These shall be specified in the contract or purchase order, as additional procedures and extended delivery time may be involved.

4.2.1 Chemical analysis ([7.1.1](#)),

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys, and is the direct responsibility of Subcommittee B07.04 on Magnesium Alloy Cast and Wrought Products.

Current edition approved April 1, 2005. Published April 2005. Originally approved in 1934. Last previous edition approved in 2004 as B 94 – 04.

<sup>2</sup> SAE specifications No. 501 and 501A conform to the requirements for Alloy AZ91A and AZ91B respectively.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>4</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.

\*A Summary of Changes section appears at the end of this standard.

**TABLE 1 Chemical Requirements<sup>A,B,C,D</sup>**

Alloy		Composition, %										
Designation <sup>B</sup>	UNS	Aluminum	Manganese	Rare Earth	Strontium	Zinc	Copper, max	Iron, max	Silicon	Nickel	Other Metallic Impurities, max, each	Magnesium
AS41A	M10410	3.5-5.0	0.20-0.50	...	...	0.12	0.06	...	0.50-1.5	0.03	...	remainder
AS41B	M10412	3.5-5.0	0.35-0.7 <sup>E</sup>	...	...	0.12	0.02	0.0035 <sup>E</sup>	0.50-1.5	0.002	0.02	remainder
AM50A	M10500	4.4-5.4	0.26-0.6 <sup>E</sup>	...	...	0.22	0.010	0.004 <sup>E</sup>	0.10	0.002	0.02	remainder
AM60A	M10600	5.5-6.5	0.13-0.6	...	...	0.22	0.35	...	0.50	0.03	...	remainder
AM60B	M10602	5.5-6.5	0.24-0.6 <sup>E</sup>	...	...	0.22	0.010	0.005 <sup>E</sup>	0.10	0.002	0.02	remainder
AZ91A	M11910	8.3-9.7	0.13-0.50	...	...	0.35-1.0	0.10	...	0.50	0.03	...	remainder
AZ91B	M11912	8.3-9.7	0.13-0.50	...	...	0.35-1.0	0.35	...	0.50	0.03	...	remainder
AZ91D	M11916	8.3-9.7	0.15-0.50 <sup>E</sup>	...	...	0.35-1.0	0.030	0.005 <sup>E</sup>	0.10	0.002	0.02	remainder
AJ52A <sup>F</sup>	M17520	4.5-5.5	0.24-0.6 <sup>E</sup>	...	1.7-2.3	0.22	0.010	0.004 <sup>E</sup>	0.10	0.001	0.01	remainder
AJ62A <sup>F</sup>	M17620	5.5-6.6	0.24-0.6 <sup>E</sup>	...	2.0-2.8	0.22	0.010	0.004 <sup>E</sup>	0.10	0.001	0.01	remainder
AS21A	M10210	1.8-2.5	0.18-0.7	...	...	0.20	0.01	0.005	0.7-1.2	0.001	0.01	remainder
AS21B <sup>F</sup>	M10212	1.8-2.5	0.05-0.15	0.06-0.25	...	0.25	0.008	0.0035	0.7-1.2	0.001	0.01	remainder

<sup>A</sup> Analysis shall regularly be made only for the elements specifically mentioned in this table. If, however, the presence of other elements is suspected or indicated in the course of routine analysis, further analysis shall be made to determine that these other elements are not in excess of 0.3 %.

<sup>B</sup> The following applies to all specified limits in this table: For purposes of acceptance and rejection an observed value or a calculated value obtained from analysis should be rounded to the nearest unit in the last right-hand place of figures used in expressing the specified limit in accordance with the rounding procedure prescribed in Section 3 of Practice E 29.

<sup>C</sup> Where single units are shown, these indicate the maximum amounts permitted.

<sup>D</sup> ASTM alloy designations were established in accordance with Practice B 275. UNS designations were established in accordance with Practice E 527.

<sup>E</sup> In alloys AS41B, AM50A, AJ52A, AM60B, AJ62A, and AZ91D, if either the minimum manganese limit or the maximum iron limit is not met, then the iron/manganese ratio shall not exceed 0.010, 0.015, 0.015, 0.021, 0.021, and 0.032, respectively.

<sup>F</sup> Alloys AJ52A, AJ62A, and AS21B are patented compositions for elevated temperature applications. Interested parties are invited to submit information regarding the identification of alternatives to these compositions to ASTM International. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

4.2.2 Quality assurance (Section 6),

4.2.3 Special proof tests or mechanical properties (Section

8), <https://standards.iteh.ai/catalog/standards/sist/c16d5530-5470-4930-9600-53512229a793/astm-b94-05>

4.2.4 General quality options for internal soundness or for finish (Section 10),

4.2.5 Source inspection (Section 11),

4.2.6 Certification (Section 12),

4.2.7 Marking for identification (Section 14), and

4.2.8 Special packaging (Section 15).

## 5. Materials

5.1 The magnesium alloys used for the manufacture of die castings shall be such that the die castings produced will conform to the chemical composition requirements of this specification. Ingot in accordance with Specification B 93/ B 93M may be used but is not restricted to this source.

## 6. Quality Assurance

6.1 *Responsibility for Inspection*—When specified in the contract or purchase order, the producer or supplier is responsible for the performance of all inspection and test requirements specified herein. Except as otherwise specified in the contract or order, the producer or supplier may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification.

Quality assurance standards shall be agreed upon between the producer or supplier and purchaser at the time a contract or order is placed.

6.2 *Lot Definition*—An inspection lot shall be defined as follows:

6.2.1 An inspection lot shall consist of the production from each die or compound die on each machine for each 24 h during the first week of normal operation and the production for each 48 h thereafter of normal operation. Any significant change in the machine, composition, die, or continuity of operation shall be considered as the start of a new lot. Die castings inspected by this method shall be so marked or handled during the finishing operations as not to lose their identity.

6.2.2 Each die casting of a randomly selected sample shall be examined to determine conformance to the requirements with respect to general quality, dimensions, and identification marking. The producer or supplier may use a system of statistical quality control for such examinations.

## 7. Chemical Composition

7.1 *Limits*—The die casting shall conform to the requirements as to chemical composition prescribed in Table 1. Conformance shall be determined by the producer by analyzing samples taken at the time castings are made. If the producer has determined the chemical composition of the metal during the

course of manufacture, he shall not be required to sample and analyze the finished product.

7.1.1 When a detailed chemical analysis is required with a shipment, it shall be called for in the contract or purchase order.

7.1.2 If the producer's or supplier's method of composition control is acceptable, sampling for chemical analysis may be waived at the discretion of the purchaser.

7.2 *Number of Samples*—When required, samples for determination of chemical composition shall be taken to represent the following:

7.2.1 A sample shall be taken from each of two representative castings selected from each lot defined in Section 6.2.1.

7.3 *Methods of Sampling*—Samples from die castings for determination of chemical composition shall be taken in accordance with one of the following methods:

7.3.1 Samples for chemical analysis shall be taken from the material by drilling, sawing, milling, turning, or clipping a representative piece or pieces to obtain a weight of prepared sample not less than 75 g. Sampling shall be in accordance with Practice E 88.

7.3.2 By agreement, an appropriate spectrographic sample may be prepared at time of manufacture.

7.3.3 The method of sampling cast products for spectrochemical and other methods of analysis shall be suitable for the form of material being analyzed and the type of analytical method used.

7.4 *Method of Analysis*—The determination of chemical composition shall be made in accordance with suitable chemical (Test Methods E 35), spectrochemical, or other methods. In case of dispute, the results secured by Test Methods E 35 shall be the basis of acceptance.

## 8. Mechanical Properties and Tests

8.1 Unless specified in the contract or purchase order or specifically guaranteed by the manufacturer, acceptance of die castings under these specifications shall not depend on mechanical properties determined by tension or impact tests. Tables X1.1 and X1.2 show typical mechanical properties and characteristics. When tension or impact tests are made, the tension test specimen shown in Fig. 13 of Methods B 557, and the impact test specimen shown in Fig. 6 of Test Methods E 23 shall be used.

8.2 When specified in the contract or purchase order, die castings shall withstand proof tests without failure as defined by agreement between the purchaser and the producer or supplier.

## 9. Permissible Variations in Dimensions

9.1 Permissible variations in dimensions shall be within the limits specified on the drawings or in the contract or purchase order.

9.1.1 Any dimensions for which a tolerance is not specified shall be in accord with ADCI Product Standard Series E1 to E16 inclusive.

9.2 Dimensional tolerance deviations waived by the purchaser shall be confirmed in writing to the producer or supplier.

## 10. General Quality

10.1 *Internal Soundness*—When specified, the soundness of die castings shall conform to standards or requirements agreed upon between the producer or supplier and the purchaser. The number and extent of imperfections shall not exceed those specified by the purchaser. The standards or requirements may consist of radiographs in accordance with Reference Radiographs E 505, photographs, or sectioned die castings.

10.2 Imperfections inherent in die castings shall not be cause for rejection provided it is demonstrated that the die castings are in accordance with the requirements and standards agreed upon.

10.3 *Workmanship*—Die castings shall be of uniform quality, free from injurious discontinuities that will adversely affect their serviceability.

10.4 *Finish*—When specified in the contract or purchase order the as-cast surface finish required shall conform to standards agreed upon between the purchaser and the producer or supplier, or as prescribed in ADCI Product Standard E 18.

10.5 *Pressure Tightness*—When specified in the contract or purchase order the pressure tightness of die castings shall conform to standards agreed upon between the purchaser and the producer or supplier, or as prescribed in ADCI Product Standard E 17.

## 11. Source Inspection

11.1 If the purchaser desires that his representative inspect or witness the inspection and testing of the product prior to shipment, such agreement shall be made by the purchaser and producer or supplier as part of the contract or purchase order.

11.2 When such inspection or witness of inspection and testing is agreed upon, the producer or supplier shall afford the purchaser's representative all reasonable facilities to satisfy him that the product meets the requirements of this specification. Inspection and tests shall be conducted so there is no unnecessary interference with the producer's operations.

## 12. Rejection and Retest

12.1 When one or more samples, depending on the approved sampling plan, fail to meet the requirements of this specification, the represented lot is subject to rejection except as otherwise provided in 12.2.

12.2 Lots rejected for failure to meet the requirements of this specification may be resubmitted for test provided:

12.2.1 The producer has removed the nonconforming material or the producer has reworked the rejected lot as necessary to correct the deficiencies.

12.3 Individual castings that show injurious imperfections during subsequent manufacturing operations may be rejected. The producer or supplier shall be responsible only for replacement of the rejected castings to the purchaser. As much of the rejected original material as possible shall be returned to the producer or supplier.

## 13. Certification

13.1 The producer or supplier shall, when called for in the contract or purchase order, furnish to the purchaser a certificate of inspection stating that each lot has been sampled, tested, and