



Standard Specification for Electric-Fusion-Welded Austenitic Chromium-Nickel Stainless Steel Pipe for High-Temperature Service and General Applications¹

This standard is issued under the fixed designation A 358/A 358M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers electric-fusion-welded austenitic chromium-nickel stainless steel pipe suitable for corrosive or high-temperature service, or both, or for general applications.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

1.2 This specification covers the grades of alloy and stainless steel listed in Table 1. The selection of the proper grade and requirements for heat treatment shall be at the discretion of the purchaser, dependent on the service conditions to be encountered.

1.3 Five classes of pipe are covered as follows:

1.3.1 *Class 1*—Pipe shall be double welded by processes employing filler metal in all passes and shall be completely radiographed.

1.3.2 *Class 2*—Pipe shall be double welded by processes employing filler metal in all passes. No radiography is required.

1.3.3 *Class 3*—Pipe shall be single welded by processes employing filler metal in all passes and shall be completely radiographed.

1.3.4 *Class 4*—Same as Class 3 except that the weld pass exposed to the inside pipe surface may be made without the addition of filler metal (see 6.2.2.1 and 6.2.2.2).

1.3.5 *Class 5*—Pipe shall be double welded by processes employing filler metal in all passes and shall be spot radiographed.

1.4 Supplementary requirements covering provisions ranging from additional testing to formalized procedures for manufacturing practice are provided. Supplementary Requirements S1 through S6 are included as options to be specified when desired.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

2. Referenced Documents

2.1 ASTM Standards:³

A 240/A 240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

A 262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

A 480/A 480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

A 941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

A 994 Guide for Editorial Procedures and Form of Product Specifications for Steel, Stainless Steel, and Related Alloys

A 999/A 999M Specification for General Requirements for Alloy and Stainless Steel Pipe

E 527 Practice for Numbering Metals and Alloys (UNS)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved March 1, 2004/2005. Published April 2004/2005. Originally approved in 1952. Last previous edition approved in 2004/2004 as A 358/A 358M – 04.

² For ASME Boiler and Pressure Vessel Code applications see related Specifications SA-358 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

2.2 ASME Boiler and Pressure Vessel Code:⁴

Section II, Materials

Section III, Rules for Construction of Nuclear Facility Components

Section VIII, Pressure Vessels

Section IX, Welding and Brazing Qualifications

2.3 AWS Specifications:⁵

A 5.22 Flux Cored Arc Welding

A 5.30 Consumable Weld Inserts for Gas Tungsten Arc Welding

A 5.4 Corrosion-Resisting Chromium and Chromium-Nickel Steel Covered Welding Electrodes

A 5.9 Corrosion-Resisting Chromium and Chromium-Nickel Steel Welding Rods and Bare Electrodes

A 5.11 Nickel and Nickel-Alloy Covered Welding Electrodes

A 5.14 Nickel and Nickel-Alloy Bare Welding Rods and Electrodes

2.4 Other Standard:⁶

SAE J1086 Practice for Numbering Metals and Alloys (UNS)

3. Terminology

3.1 Definitions:

3.1.1 The definitions in Specification A 999/A 999M and Terminology A 941 are applicable to this specification.

4. Ordering Information

4.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for product under this specification. Such requirements to be considered include, but are not limited to, the following:

4.1.1 Quantity (feet, metres, or number of lengths),

4.1.2 Name of material (electric-fusion-welded pipe),

4.1.3 Grade (Table 1),

4.1.4 Class (see 1.3),

4.1.5 Size (outside diameter and nominal wall thickness),

4.1.6 Length (specific or random),

4.1.7 End finish (Section on Ends of Specification A 999/A 999M),

4.1.8 Authorization for repair of plate defects by welding and subsequent heat treatment without prior approval if such is intended (see 9.3),

4.1.9 Specification designation,

4.1.10 Special requirements,

4.1.11 Statement invoking requirements of 16.4 if such is intended.

4.1.12 Circumferential weld permissibility (see Section 16),

4.1.13 Supplementary Requirements (S1 through S6),

4.1.14 Applicable ASME Code if known,

4.1.15 For ASME Code Section III applications, the service classification intended, and

4.1.16 Certification requirements (see Section on Certification of Specification A 999/A 999M).

5. General Requirements

5.1 Material furnished to this specification shall conform to the applicable requirements of the current edition of Specification A 999/A 999M unless otherwise provided herein.

6. Materials and Manufacture

6.1 Materials:

6.1.1 The steel plate material shall conform to the requirements of one of the grades of Specification A 240/A 240M, listed in Table 1, except as provided in 6.3.2.3.

6.2 Welding:

6.2.1 The joints shall be full penetration double-welded or single-welded butt joints employing fusion welding processes as defined under "Definitions," ASME Boiler and Pressure Vessel Code, Section IX. This specification makes no provision for any difference in weld quality requirements regardless of the weld joint type employed (single or double) in making the weld. Where backing rings or strips are employed, the ring or strip material shall be of the same P-Number (Table QW-422 of Section IX) as the plate being joined. Backing rings or strips shall be completely removed after welding, prior to any required radiography, and

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990.

⁵ Available from The American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126.

⁶ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.