



SLOVENSKI STANDARD
SIST ISO 175:1996

01-junij-1996

Polimerni materiali - Ugotavljanje učinkov tekočih kemikalij, vključno z vodo

Plastics -- Determination of the effects of liquid chemicals, including water

Plastiques -- Détermination de l'action des agents chimiques liquides, y compris l'eau

Ta slovenski standard je istoveten z: ISO 175:1981

[SIST ISO 175:1996](https://standards.iteh.ai/catalog/standards/sist/ddc58d14-ea7a-49d0-8082-7000e7832851/sist-iso-175-1996)

<https://standards.iteh.ai/catalog/standards/sist/ddc58d14-ea7a-49d0-8082-7000e7832851/sist-iso-175-1996>

ICS:

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	--------------------------------	---------------------

SIST ISO 175:1996

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 175:1996

<https://standards.iteh.ai/catalog/standards/sist/ddc58d14-ca7a-49d0-8082-7000e7832851/sist-iso-175-1996>

International Standard



175

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Plastics — Determination of the effects of liquid chemicals, including water

Plastiques — Détermination de l'action des agents chimiques liquides, y compris l'eau

First edition — 1981-07-01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 175:1996

<https://standards.iteh.ai/catalog/standards/sist/ddc58d14-ca7a-49d0-8082-7000e7832851/sist-iso-175-1996>

UDC 678.5/.8 : 678.019.32/.34

Ref. No. ISO 175-1981 (E)

Descriptors : plastics, chemical resistance, liquids, water, chemical products, absorption, tests, submerging tests, measurement, calculus of variations, test specimens.

Price based on 12 pages

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 175 was developed by Technical Committee ISO/TC 61, *Plastics*, and was circulated to the member bodies in March 1979.

It has been approved by the member bodies of the following countries :

Belgium	Hungary	Romania
Brazil	India	South Africa, Rep. of
Bulgaria	Israel	Spain
Canada	Italy	Sweden
China	Korea, Rep. of	Switzerland
Czechoslovakia	Japan	Turkey
Egypt, Arab Rep. of	Libyan Arab Jamahiriya	United Kingdom
Finland	Netherlands	USA
France	New Zealand	USSR
Germany, F.R.	Poland	

No member body expressed disapproval of the document.

This International Standard cancels and replaces ISO Recommendations R 175-1961 and R 462-1965, of which it constitutes a technical revision.

Plastics — Determination of the effects of liquid chemicals, including water

0 Introduction

Because of their varied applications, plastics are frequently brought into contact with liquids such as chemical products, motor fuels, lubricants, etc., and, possibly, with their vapours.

Under the action of a liquid, a plastic material may be subjected to several phenomena which may occur simultaneously. On the one hand absorption of liquid and extraction of constituents soluble in the liquid may occur. On the other hand, a chemical reaction, most often resulting in a significant change in the properties of the plastic, may occur.

The behaviour of plastics in the presence of chemicals can be determined only under arbitrarily fixed conditions aimed at making comparisons between different materials. The choice of test conditions (nature of the liquids, temperatures and durations), as well as of the properties in which changes are to be measured, depends on the eventual application of the plastic under test.

However, it is not possible to establish any direct correlation between the experimental results and the behaviour of the plastic in service. These tests do, nevertheless, permit a comparison to be made of the behaviour of different plastic materials under specified conditions, thus allowing an initial evaluation of their behaviour in relation to certain groups of substances.

NOTE — In view of its special importance, the particular case of the determination of the quantity of water absorbed is dealt with in ISO 62. The effects of water described in this International Standard are concerned only with changes in dimensions and in physical properties as a result of the action of the water.

1 Scope and field of application

1.1 This International Standard specifies a method of exposing test specimens of plastic materials, free from all external restraint, to liquid chemicals, and methods for determining the changes in properties resulting from such exposure.

1.2 It only considers, therefore, testing by immersion of the entire surface of the test specimen.¹⁾

1.3 It is applicable to all solid plastics that are available in the form of moulding or extrusion materials, plates, tubes, rods or sheets, having a thickness greater than 0,1 mm. It is not applicable to cellular materials.

1.4 Methods for determination of changes in properties are specified as follows :

a) changes in mass, dimensions and appearance immediately after immersion or after immersion and drying;

b) changes in physical properties (mechanical, thermal, optical, etc.) immediately after immersion or after immersion and drying.

1.4.1 The test immediately after immersion is used when it is required to ascertain the state of the material while still acted upon by the liquid.

1.4.2 The test after immersion and drying is used when it is required to ascertain the state of the material after the liquid, if it is volatile, has been eliminated. It can allow determination of the influence of a soluble constituent.

2 References

ISO 62, *Plastics — Determination of water absorption.*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing.*

ISO 293, *Plastics — Compression moulding test specimens of thermoplastic materials.*

ISO 294, *Plastics — Injection moulding test specimens of thermoplastic materials.*

ISO 295, *Plastics — Compression moulding test specimens of thermosetting materials.*

ISO 412, *Gum spirit of turpentine and wood turpentines for paints and varnishes.*

¹⁾ Although it is not within the scope of this International Standard, it may also be of interest, when dealing with volatile liquids or those which give off vapours, to submit the specimen to the effect of only the gaseous phase above the liquid. In this event, it is advisable to proceed exactly as indicated, but to suspend the test specimen above the liquid, seal the container and maintain it at the test temperature throughout.

ISO 175-1981 (E)

ISO 1817, *Vulcanized rubbers — Resistance to liquids — Methods of test.*

ISO 2818, *Plastics — Preparation of test specimens by machining.*

ISO 3126, *Plastics pipes — Measurement of dimensions.*

ISO 3205, *Preferred test temperatures.*

IEC Publication 296, *Specification for new insulating oils for transformers and switchgear.*

3 Principle

Complete immersion of test specimens in a test liquid for a specified time and at a specified temperature.

Determination of their properties before and after immersion and, if applicable, after drying; in the latter case, the determinations are made, if possible, one after the other on the same specimens.

NOTE — It is emphasized that the comparison of different plastics by means of this test is valid only if the specimens used are of the same shape, the same dimensions (in particular the same thickness) and in as nearly as possible the same state (of internal stresses, surface, etc.).

4 General requirements and procedure

4.1 Test liquids

4.1.1 Choice of test liquid

If information is required about the behaviour of a plastic in contact with a specific liquid, that liquid shall, as a rule, be used.

Industrial liquids are not generally of absolutely constant composition. Whenever possible, the test shall be carried out in defined chemical products used on their own or as a mixture, and which are as representative as possible of the effect of the products under consideration on the plastic material concerned.

NOTE — If making a series of tests in a liquid of doubtful composition, it is important to take all the samples of the liquid from the same container.

4.1.2 Test liquids

Types of test liquids are given in annex A.

4.2 Test temperatures

4.2.1 Immersion temperatures

The preferred test temperatures are :

- a) 23 ± 2 °C;
- b) 70 ± 2 °C.

If a different temperature has to be used in order to correspond to the temperature at which the plastic is used, it shall be selected from the preferred temperatures given in ISO 3205.¹⁾

NOTE — In the event that the test is to be carried out at a temperature above normal ambient conditions, it may be desirable to condition another series of specimens at this temperature for a period equal to that of the test, and to measure their properties after this conditioning in order to be able to distinguish the effect of temperature from that of the liquid.

In the case of long duration tests, specimens stored in air at 23 °C may undergo a change in properties. Preparation of an additional series of test specimens is recommended for comparison purposes.

4.2.2 Measurement temperature

The temperature for the determination of changes in mass, dimensions or physical properties is 23 ± 2 °C. If the immersion temperature is different, bring the specimen to 23 °C by the procedure described in 4.6.3.

4.3 Test durations

The preferred test durations are :

- a) 24 h for a short duration test;
- b) 1 week for a standard test (particularly at 23 °C);
- c) 16 weeks for a long duration test.

If it is essential to adopt other test durations, for example if it is desired to perform tests as a function of time or to plot the curve until equilibrium is reached, it is recommended that the durations be chosen from the following standard scale :

- a) 1 — 2 — 4 — 8 — 16 — 24 — 48 — 96 — 168 h;
- b) 2 — 4 — 8 — 16 — 26 — 52 — 78 weeks;
- c) 1,5 — 2 — 3 — 4 — 5 years.

1) In particular, the following temperatures should be used :

0 — 20 — 27 — 40 — 55 — 85 — 100 — 125 — 150 °C,

with a tolerance of ± 2 °C on temperatures up to and including 105 °C, and ± 3 °C on temperatures greater than 105 °C and up to and including 200 °C.

In the special case of testing plastic pipes, the temperature of 60 °C given in the annex to ISO 3205 may be used.

4.4 Test specimens

Depending upon the proposed test after exposure (mass, dimensions, physical properties) and the nature and form (sheet, film, rod, etc.) of the plastic material, the specimens will be of very diverse shapes and dimensions.

They may be obtained directly by moulding, or by machining. In the latter case, cut surfaces shall be machined to a fine finish and shall show no trace of carbonization that could be attributed to the method of preparation.

The number of specimens to be used will be specified in the International Standards relevant to the tests to be carried out after treatment. In the absence of specific International Standards, at least three specimens shall be tested.

4.5 Conditioning

Condition the specimens in accordance with ISO 291.

NOTE — For certain plastics which are known to approach rapidly, or, on the contrary, very slowly, equilibrium of temperature and especially of humidity, shorter or longer conditioning periods may be specified in the appropriate product specifications (see annex B).

4.6 Procedure

4.6.1 Quantity of test liquid

The quantity of test liquid used shall be at least 8 ml per square centimetre of the total surface area of the specimen in order to avoid a concentration of extracted product in the liquid during the course of the test. The test liquid shall cover the specimen completely.

NOTE — A different quantity of liquid may, however, be specified in particular International Standards; for example, for rigid PVC and polyolefin pipes, where the amount of extractable substances is known to be very small, a smaller quantity of liquid is specified in the relevant International Standards.

4.6.2 Positioning of specimens

As a rule, place each set of test specimens in a given container and completely immerse them in the test liquid (using a weight if necessary).

However, when several materials of the same composition are to be tested, it is permissible to put several sets of specimens into the same container.

In every case, no significant proportion of the surfaces of the specimens shall make contact with the surface of other specimens, with the walls of the container, or with any weight that is used.

During the test, stir the liquids, for example by rotating the containers, at least once per day.

If the test lasts longer than seven days, replace the liquid with an equal amount of the original liquid every seventh day.

If the liquid is unstable (for example sodium hypochlorite), replace the liquid more frequently.

If light is likely to have an influence on the action of the test liquid, it is recommended to operate either in darkness or in defined illumination conditions.

It may be necessary in certain cases (for example if there is a risk of oxidation) to specify the height of the liquid level above the specimens.

4.6.3 Rinsing and wiping

At the end of the period of immersion, bring the temperature of the specimens back to ambient temperature if necessary, by transferring them quickly into a fresh quantity of test liquid at room temperature, for a period of 15 to 30 min.

Remove the specimens from the test liquid and rinse them with a product which has no effect on the material under test and which is chosen to suit the nature of the test liquid.

Wipe the specimens dry with filter paper or a lint-free cloth.

NOTES

1 If requested, it may be necessary to examine the test liquid at the end of the test. This examination may be a simple visual examination or a more rigorous examination, including, for example, a titration.

This examination may not be practicable if the liquid has been replaced during the test.

2 In the case of specimens tested in solvents such as acetone or alcohol at ambient temperature, rinsing and wiping may not be necessary.

4.7 Expression of results

4.7.1 Numerical expression

In addition to the results of measurements before and after immersion, the results may be expressed (except in special cases of changes in mass) as a percentage of the value of the property after immersion (V_2) with respect to the value before immersion (V_1), i.e. as

$$(V_2/V_1) \times 100$$

4.7.2 Graphical expression

In every case where measurements are made as a function of time, it is recommended that corresponding graphs be plotted. The values obtained (including the original value), or the differences in value, shall be plotted as the ordinates, and the durations (t) as the abscissae. If it is necessary to shorten the duration scale, either a \sqrt{t} scale or a $\log t$ scale may be used.

5 Determination of changes in mass and (or) dimensions and (or) appearance

These determinations may, if necessary, be carried out on the same specimens.

At least three specimens shall be used.

ISO 175-1981 (E)

5.1 Apparatus

5.1.1 Beakers, of suitable dimensions and fitted with lids (airtight, if necessary, and fitted with condensers in the case of volatile liquids or those which give off vapours).

5.1.2 Enclosure, thermostatically controlled at the test temperature.

5.1.3 Thermometer, of suitable range and accuracy.

5.1.4 For determination of changes in mass :

5.1.4.1 Weighing bottle.

5.1.4.2 Balance, accurate to within 0,001 g in the case of specimens of mass equal to or greater than 1 g, or to within 0,000 1 g in the case of specimens of mass less than 1 g.

5.1.5 For determination of dimensional changes :

5.1.5.1 Dial micrometer, with flat anvils, accurate to 0,01 mm.

5.1.5.2 Caliper gauge, capable of measuring to an accuracy of 0,1 mm.

5.1.6 Ventilated oven, if required, capable of being controlled at the chosen drying temperature.

NOTE — In the absence of any special instructions, use an oven controlled at 50 ± 2 °C.

5.2 Test specimens (see also 4.4)

5.2.1 Moulding materials

Specimens shall have a diameter of 50 ± 1 mm and a thickness of $3 \pm 0,2$ mm. They shall be moulded to shape under the conditions specified in the appropriate product specification (or under the conditions prescribed by the supplier).

NOTES

1 The general principles for the preparation of moulded specimens are the subjects of ISO 293, ISO 294 and ISO 295.

2 In certain special cases, a square specimen, $50 \text{ mm} \times 50 \text{ mm} \times 4 \text{ mm}$, may be used by agreement between the interested parties.

5.2.2 Extrusion compounds

Specimens shall have a diameter of 50 ± 1 mm and a thickness of $3 \pm 0,2$ mm. They shall be cut from a sheet of this

thickness, prepared under the conditions prescribed in the appropriate product specification (or under the conditions prescribed by the supplier of the material).

NOTE — In certain special cases, a square specimen, $50 \text{ mm} \times 50 \text{ mm} \times 4 \text{ mm}$, may be used by agreement between the interested parties.

5.2.3 Sheets and plates

Specimens shall be 50 ± 1 mm square and shall be machined from the sheet or plate submitted for test.¹⁾

The thickness of the specimens shall be the same as that of the sheet or plate submitted for test, if its nominal thickness is less than or equal to 25 mm.

If the nominal thickness is greater than 25 mm, and in the absence of special provisions in the relevant specification, reduce the thickness of the specimen to 25 mm by machining one face only.

5.2.4 Tubes and rods

5.2.4.1 Tubes

If possible, reference shall be made to the relevant International Standards for the material under test.²⁾ In the absence of specific International Standards, the specimen shall be a piece of tube, of length 50 ± 1 mm, obtained by cutting it at right angles to its longitudinal axis.

For tubes of outside diameter greater than 50 mm, a length of 50 ± 1 mm shall be cut and the test specimen prepared from this length by making a cut along each of two planes containing the longitudinal axis of the tube, so as to give a developed width of 50 ± 1 mm when measured on the outer surface.

5.2.4.2 Rods

For rods of diameter less than or equal to 50 mm, the test specimen shall be a piece of the rod of length 50 ± 1 mm, obtained by cutting it at right angles to its longitudinal axis.

For rods of diameter greater than 50 mm, in the absence of any specification agreed between the interested parties, the test specimen shall be a 50 ± 1 mm length of the rod with its diameter reduced to 50 ± 1 mm by machining concentrically.

5.2.5 Profile sections

In the absence of specific International Standards, cut a 50 ± 1 mm long piece of the profile section and use as the test specimen either :

- a) this piece of the profile section;

1) For example, in accordance with ISO 2818.

2) The preparation of methods of test for plastics pipes is the responsibility of ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*. The general procedures described in this International Standard have been used as a basis for the appropriate methods of evaluating the effects of chemical products on plastics pipes. ISO 4433 will specify the method of test for polyolefin pipes; methods of test for PVC and ABS pipes will form the subjects of future International Standards.

b) this piece after machining in such a manner as to reduce one or several of the dimensions of the profile cross section so that the thickness, in particular, approximates as closely as possible to $3 \pm 0,2$ mm.

In this case, the dimensions to be achieved and the machining conditions shall be subject to agreement between the interested parties.

5.3 Determination of changes in mass¹⁾

5.3.1 Procedure

5.3.1.1 Conditioning

Condition the specimens and select the test conditions in accordance with clause 4.

5.3.1.2 Determination of initial mass

Determine the mass m_1 of each specimen to the nearest 0,001 g in the case of specimens of mass greater than or equal to 1 g, or to the nearest 0,000 1 g in the case of specimens of mass less than 1 g.

Immerse the specimens in the test liquid as specified in 4.6.2.

5.3.1.3 Measurement immediately after immersion

Place each rinsed and wiped specimen in a tared weighing bottle, stopper it and determine the mass m_2 to the nearest 0,001 g or 0,000 1 g as appropriate (see 5.3.1.2).

If the liquid used for the test is volatile at ambient temperature, the time during which the specimen is exposed to the air shall not exceed 30 s. If it is necessary to continue the test after weighing (test as a function of time), immediately replace the specimens in the test liquid and put the containers back in the thermostatically controlled enclosure.

5.3.1.4 Measurement after immersion and drying

Remove the specimens from the weighing bottles and dry them in the oven at the specified temperature (usually for 2 h at 50 ± 2 °C) to constant mass. Cool the specimens if necessary, recondition them in accordance with 5.3.1.1 and determine the mass m_3 of each specimen.

NOTE — In certain cases, the interested parties may agree that the plastics under test require no conditioning.

5.3.1.5 Measurement only after immersion and drying

After removal from the test liquid, rinse and wipe the specimens in accordance with 4.6.3, then immediately place the specimens in the oven and proceed in accordance with 5.3.1.4.

5.3.2 Calculation and expression of results

5.3.2.1 Report, for each specimen, the masses in milligrams, of

- the specimen before immersion, m_1 ;
- the specimen immediately after immersion, m_2 ;
- the specimen after immersion, drying and reconditioning, m_3 .

Calculate the values of

$$m_2 - m_1,$$

and

$$m_3 - m_1,$$

and report these values with the applicable signs.

5.3.2.2 It is permissible, subject to agreement between the interested parties, or on request, to express the results by the following methods:

5.3.2.2.1 Method I — Change in mass per unit area

For each specimen, calculate the increase or decrease in mass per unit area, expressed in milligrams per square centimetre, by means of one of the following formulae

$$(m_2 - m_1)/A$$

or

$$(m_3 - m_1)/A$$

where

m_1 , m_2 and m_3 have the same meanings as in 5.3.2.1;

A is the initial total surface area, in square centimetres, of the specimen.

5.3.2.2.2 Method II — Percentage change in mass

For each specimen, calculate the percentage increase or decrease in mass by means of one of the following formulae

$$100 (m_2 - m_1)/m_1$$

or

$$100 (m_3 - m_1)/m_1$$

where m_1 , m_2 and m_3 have the same meanings as in 5.3.2.1

1) In the case of water, see ISO 62.