

SLOVENSKI STANDARD

SIST EN ISO 384:2016

01-marec-2016

Nadomešča:
SIST ISO 384:1995

Laboratorijska steklena in plastična posoda - Načela za oblikovanje in konstruiranje volumetrijske steklovine (ISO 384:2015)

Laboratory glass and plastics ware - Principles of design and construction of volumetric instruments (ISO 384:2015)

Laborgeräte aus Glas oder Kunststoff - Grundlagen für Gestaltung und Bau von Volumenmessgeräten (ISO 384:2015)

Matériel de laboratoire en verre ou en plastique - Principes de conception et de construction d'instruments volumétriques (ISO 384:2015)

Ta slovenski standard je istoveten z: **EN ISO 384:2015**

ICS:

17.060	Merjenje prostornine, mase, gostote, viskoznosti	Measurement of volume, mass, density, viscosity
71.040.20	Laboratorijska posoda in aparati	Laboratory ware and related apparatus

SIST EN ISO 384:2016 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 384:2016

<https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016>

EUROPEAN STANDARD

EN ISO 384

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 17.060

English Version

Laboratory glass and plastics ware - Principles of design and construction of volumetric instruments (ISO 384:2015)

Matériel de laboratoire en verre ou en plastique -
Principes de conception et de construction
d'instruments volumétriques (ISO 384:2015)

Laborgeräte aus Glas oder Kunststoff - Grundlagen für
Gestaltung und Bau von Volumenmessgeräten (ISO
384:2015)

This European Standard was approved by CEN on 16 November 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

iTeh STANDARD PREVIEW

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 384:2016
<https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016>

European foreword

This document (EN ISO 384:2015) has been prepared by Technical Committee ISO/TC 48 "Laboratory equipment" in collaboration with Technical Committee CEN/TC 332 "Laboratory equipment" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by June 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW Endorsement notice (standards.iteh.ai)

The text of ISO 384:2015 has been approved by CEN as EN ISO 384:2015 without any modification.

[SIST EN ISO 384:2016](https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016)

<https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 384:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016>

INTERNATIONAL STANDARD

ISO 384

Second edition
2015-12-15

Laboratory glass and plastics ware — Principles of design and construction of volumetric instruments

*Matériel de laboratoire en verre ou en plastique — Principes de
conception et de construction d'instruments volumétriques*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 384:2016](https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016)

<https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016>



Reference number
ISO 384:2015(E)

© ISO 2015

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 384:2016

<https://standards.iteh.ai/catalog/standards/sist/408fd81f-0c58-4aab-8c70-cca0985c7896/sist-en-iso-384-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Unit of volume and reference temperature	1
4.1 Unit of volume.....	1
4.2 Reference temperature.....	1
5 Volumetric accuracy	1
6 Methods of calibration and use	2
7 Construction	3
7.1 Material.....	3
7.2 Wall thickness.....	3
7.3 Shape.....	3
7.4 Capacity.....	3
7.5 Stability.....	3
7.6 Delivery jets.....	3
7.7 Stoppers.....	4
7.8 Stopcocks or similar devices.....	4
8 Linear dimensions	4
9 Graduation lines	5
10 Scales	6
10.1 Spacing of graduation lines.....	6
10.2 Length of graduation lines (see Figure 2).....	6
10.2.1 General.....	6
10.2.2 Graduation pattern I.....	6
10.2.3 Graduation pattern II.....	6
10.2.4 Graduation pattern III.....	6
10.2.5 Special cases.....	7
10.3 Sequence of graduation lines (see Figure 1).....	7
10.4 Position of graduation lines (see Figure 2).....	8
11 Figuring of graduation lines	9
12 Marking	10
13 Visibility of graduation lines, figures and inscriptions	11
Annex A (normative) Maximum permissible error in relation to the inner diameter at the meniscus	12
Bibliography	15

ISO 384:2015(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 48, *Laboratory equipment*.

This second edition cancels and replaces the first edition (ISO 384:1978), which has been technically revised to incorporate the following modifications:

- a) Volumetric instruments made from plastics have been added to the scope.
- b) Volumetric instruments of class AS have been added.
- c) The thickness of graduation lines has been modified.
- d) The basic principles for construction have been modified such that they comply with the product standards ISO 1042, ISO 648, ISO 835, ISO 385, ISO 4788 and ISO 4787.
- e) The relation between maximum permissible error and the inner diameter has been specified by an equation.
- f) [Annex A](#), explaining that relation, has been reworded.

Laboratory glass and plastics ware — Principles of design and construction of volumetric instruments

1 Scope

This International Standard sets out principles for the design of volumetric instruments manufactured from glass or from plastics in order to facilitate the most reliable and convenient use to the intended degree of accuracy.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 383, *Laboratory glassware — Interchangeable conical ground joints*

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

ISO/IEC Guide 99, *International vocabulary of metrology — Basic and general concepts and associated terms (VIM)*

3 Terms and definitions

For the purposes of this document the terms and definitions given in ISO/IEC Guide 99 apply.

4 Unit of volume and reference temperature

4.1 Unit of volume

The unit of volume shall be the millilitre (ml), which is equivalent to one cubic centimetre (cm³).

4.2 Reference temperature

The standard reference temperature, i.e. the temperature at which the volumetric instrument is intended to contain or deliver its volume (capacity), shall be 20 °C.

When the volumetric instrument is required for use in a country which has adopted a standard reference temperature of 27 °C, this figure shall be substituted for 20 °C.

NOTE The capacity of volumetric instruments varies with change of temperature. A volumetric instrument which was adjusted at 20 °C, but used at 27 °C or vice versa, would show an extra error of only 0,007 % if it is made of borosilicate glass having a coefficient of cubic thermal expansion of $9,9 \times 10^{-6} \text{ °C}^{-1}$ and of 0,02 % if it is made of soda-lime glass having a coefficient of cubic thermal expansion of $27 \times 10^{-6} \text{ °C}^{-1}$. These errors are smaller than the limits of error for most volumetric instruments. It follows, therefore, that the reference temperature is of minor importance in practical use when dealing with glassware. However, when performing calibrations, it is important to refer to the reference temperature, especially when considering volumetric plastic ware.

5 Volumetric accuracy

5.1 There are two classes of accuracy: