



SLOVENSKI STANDARD

SIST EN 1013-4:2000

01-september-2000

Prosojna profilirana polimerna plošča za enoslojno strešno kritino - 4. del: Posebne zahteve, preskusne metode in lastnosti plošč iz polikarbonata (PC)

Light transmitting profiled plastic sheeting for single skin roofing - Part 4: Specific requirements, test methods and performance of polycarbonate (PC) sheets

Profilierte lichtdurchlässige Platten aus Kunststoff für einschalige Dacheindeckungen - Teil 4: Besondere Anforderungen, Prüfverfahren und -verhalten für Platten aus Polycarbonat (PC)

(standards.iteh.ai)

Plaques profilées éclairantes en matière plastique pour couverture en simple paroi - Partie 4: Exigences spécifiques, méthodes d'essai et performance pour plaques en polycarbonate (PC)

Ta slovenski standard je istoveten z: EN 1013-4:2000

ICS:

83.140.10	Filmi in folije	Films and sheets
91.060.20	Strehe	Roofs

SIST EN 1013-4:2000 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1013-4:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/2c6b60ae-3093-49eb-a2ea-07380e266119/sist-en-1013-4-2000>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1013-4

January 2000

ICS 83.140.10

English version

Light transmitting profiled plastic sheeting for single skin roofing
- Part 4: Specific requirements, test methods and performance
of polycarbonate (PC) sheets

Plaques profilées éclairantes en matière plastique pour
couverture en simple paroi - Partie 4: Exigences
spécifiques, méthodes d'essai et performance pour plaques
en polycarbonate (PC)

Profilierte lichtdurchlässige Platten aus Kunststoff für
einschalige Dacheindeckungen - Teil 4: Besondere
Anforderungen, Prüfverfahren und -verhalten für Platten
aus Polycarbonat (PC)

This European Standard was approved by CEN on 7 November 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword	2
1 Scope	2
2 Normative References	3
3 Materials	3
4 Classification	3
5 Dimensions	3
6 Visual characteristics	3
7 Longitudinal reversion and profile retention	3
8 <i>E</i> -modulus and tensile strength	4
9 Multi-axial impact resistance variation	4
10 Thermal ageing	4
11 Test methods	4

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 128 "Roof covering products for discontinuous laying and products for wall cladding", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2000, and conflicting national standards shall be withdrawn at the latest by July 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

(standards.iteh.ai)

This standard is one of a series dealing with profiled plastics sheeting for single skin roofing.

EN 1013-1:1997	Light transmitting profiled plastic sheeting for single skin roofing - Part 1: General requirements and test methods
EN 1013-2:1998	Light transmitting profiled plastic sheeting for single skin roofing - Part 2: Specific requirements and test methods for sheets of glass fibre reinforced polyester resin (GRP)
EN 1013-3:1997	Light transmitting profiled plastic sheeting for single skin roofing - Part 3: Specific requirements and test methods for sheets of polyvinyl chloride (PVC)
EN 1013-4:1999	Light transmitting profiled plastic sheeting for single skin roofing - Part 4: Specific requirements, test methods and performance of polycarbonate (PC) sheets
EN 1013-5:1999	Light transmitting profiled plastic sheeting for single skin roofing - Part 5: Specific requirements, test methods and performance of polymethylmethacrylate (PMMA) sheets

1 Scope

1.1 This part of EN 1013 specifies requirements for materials, methods of testing and performance of polycarbonate (PC) light transmitting profiled sheets produced to the desired profile by extrusion and/or forming for single skin applications. It is applicable in conjunction with the general requirements contained in EN 1013-1:1997.

1.2 Requirements are specified relative to:

- Sheet thickness
- Visual characteristics
- Longitudinal reversion
- Retention of profile
- Multi-axial impact resistance
- Thermal ageing

Test methods are indicated as appropriate.

2 Normative References

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 1013-1:1997	Light transmitting profiled plastic sheeting for single skin roofing - Part 1: General requirements and test methods
ISO 527-1:1993	Plastics - Determination of tensile properties - Part 1: General principles
ISO 527-2:1993	Plastics - Determination of tensile properties - Part 2: Test conditions for moulding and extrusion plastics
ISO 6603-1:1985	Plastics - Determination of multiaxial impact behaviour of rigid plastics - Part 1: Falling dart method
ISO 7391-1:1996	Plastics - Polycarbonate (PC) moulding and extrusion materials - Part 1: Designation system and basis for specifications

3 Materials

The sheets shall consist substantially of polycarbonate according to ISO 7391-1:1996. They can comprise both unmodified materials and materials containing lubricants, processing aids, UV absorbers, pigmented colorants, surface hard-coatings and flame retardants.

4 Classification

SIST EN 1013-4:2000

<https://standards.iteh.ai/catalog/standards/sist/2c6b60ae-3093-49eb-a2ea-038c20911988/en-1013-4-2000>

In addition to the requirements described in clauses 5 to 10, sheets shall be characterized according to EN 1013-1:1997 dealing with general requirements for each of the following:

- Light transmission;
- Ageing procedure;
- Impact resistance.

5 Dimensions

5.1 General

The dimensions of the sheet shall be quoted by the manufacturer and shall include those identified in Annex A of EN 1013-1:1997 together with a value for the nominal sheet thickness.

5.2 Tolerance for nominal sheet thickness (Quality control test)

When tested in accordance with 11.1 the values of sheet thickness obtained from crown, valley and flanks shall be the nominal thickness quoted $\pm 20\%$ respectively.

6 Visual characteristics

(Quality control test)

Both sides of the sheet shall be of regular appearance. Visual or tactile examination shall reveal no evidence of any hole, cracking, splitting or cluster of bubbles greater than 1mm in diameter, or inclusions that are likely to affect properties. The edges of the sheet shall be straight and clean.

Further requirements concerning the visual aspects of the sheets are to be agreed upon between the manufacturer and the customer.

7 Longitudinal reversion and profile retention

(Type test)

When the sheet is tested by the method described in 11.2 at a temperature of 100°C for 60 min, the average percentage change in dimensions shall not exceed the following:

- Longitudinal reversion : $\pm 2\%$
- Profile retention : $\pm 3\%$

Manufacturers' literature shall give guidance where conditions of use may lead to these figures being exceeded.

8 E-modulus and tensile strength

(Type test)

When the sheet is tested according to ISO 527-1:1993 and ISO 527-2:1993, the *E*-modulus has to be at least 2200 MPa and the tensile strength has to be at least 50 MPa.

9 Multi-axial impact resistance variation

(Type test)

When the sheet is tested by the method ISO 6603-1:1985 the minimum impact resistance levels are:

Table 1: Minimum impact resistance levels

Thickness mm.	Unaged samples E_{kin} J	Aged samples E_{kin} J
0,8	≥ 14	≥ 9
1,0	≥ 24	≥ 19

Ageing shall be carried out in accordance with 7.1 of EN 1013-1:1997 using a Xenon arc lamp.

The duration of the ageing shall be chosen as such that an exposure ≥ 18 GJ/m² according to class A₀ in EN 1013-1:1997 results.

10 Thermal ageing

(Type test)

When the sheet is exposed to dry heat for 3 000 h at 100 °C by the method described in 11.4, property levels, with respect to unexposed sheet, shall be maintained at:

- Light transmission $\geq 90\%$ of its original value
- Change in yellowness index ≤ 10 points

11 Test methods

11.1 Sheet thickness

The sheet thickness shall be determined by using a micrometer screw with hemispherical tips of 5 mm in diameter and with an accuracy of $\pm 0,01$ mm.

Sheet thickness is to be checked by nine measurements taken at random in the crowns, valleys and flanks across the total sheet width at a distance of 20 mm from the one end. First and last measurements are to be within 25 mm of the sheet edges.

11.2 Longitudinal reversion and profile retention

11.2.1 Principle

During a given period of time, the test pieces are submitted to a determined temperature. Next, the percentage changes in length and in the pitch of corrugations are determined.

11.2.2 Apparatus

- Air circulation oven capable of maintaining a temperature of (100 ± 2) °C.
- Suitable means of measuring test pieces to an accuracy of $\pm 0,25$ mm.
- Suitable means of applying a minimum load as necessary to the test pieces shall be provided to ensure that the horizontal underside of the valleys are in contact with the flat surface immediately prior to making measurements.

11.2.3 Test pieces

Five rectangular test pieces are required which shall be not less than 250 mm in length. The width of test pieces shall be such that one of the following conditions is satisfied (see also Figure 1):

- a) for pitches greater or equal to 200 mm: one pitch plus adjacent valleys on both sides.
- b) for pitches less than 200 mm: the minimum number of pitches which gives a distance greater or equal to 200 mm between outer crowns with adjacent valleys on both sides.
- c) complete width of the sheet if neither a) nor b) can be met.

11.2.4 Test procedure

Carry out the test in a room maintained at a temperature of (23 ± 2) °C and 50 % relative humidity.

Scribe two pairs of reference marks on each test piece as follows:

a) Longitudinal reversion

The line joining the two marks shall be parallel to the axis of the corrugations and the distance between the marks shall be not less than 200 mm.

b) Profile retention

The marks shall be on the crown of two corrugations. The line joining the two marks shall be at right angles to the direction of the corrugations and the distance between the marks shall be not less than 200 mm.

If the horizontal underside of the valleys are not in contact with the flat surface apply load(s) to the sheet just sufficient to obtain contact between the horizontal undersides of the valleys and the flat surface before conducting any measurements.

Measure the distances between the two marks of each set of reference marks.

Place the test pieces in the air circulation oven which is at (100 ± 2) °C in such a way that they are under no stress.

After a period of 60 min, which shall commence when the temperature of the oven regains (100 ± 2) °C, remove the test pieces and allow to cool on a flat surface for 10 min.

If the horizontal underside of the valleys are not in contact with the flat surface apply load(s) to the sheet just sufficient to obtain contact between the horizontal underside of the valleys and the flat surface before conducting measurements.

Repeat the measurement of the distances between the marks on each test piece and calculate the individual and average percentage changes in length and in the pitch of the corrugations.

11.3 Multi-axial impact resistance variation (Type test)

11.3.1 Principle

The energy required to fracture is determined by the kinetic energy extracted from a Falling Dart in the process of breaking the test pieces.

Tests are conducted on unaged and aged test pieces and the ratio of impact strength is determined using statistical techniques.

11.3.2 Apparatus

The apparatus is as described in ISO 6603-1:1985.

11.3.3 Test pieces

Test pieces from unaged and aged material shall have a minimum dimension of 60 mm x 60 mm.

The number of test specimens shall be in accordance with 6.3 of ISO 6603-1:1985.

Ageing shall be carried out in accordance with EN 1013-1:1997 using the Xenon Arc lamp. The duration of the ageing will refer to the class A₀ as mentioned in EN 1013-1:1997.

The unaged and aged test specimens shall be of the same shape and prepared by the same method.

11.3.4 Test procedure

Each test piece shall be visually examined to ensure that it is free from any defects.

Each test piece shall be tested in accordance with Method A of ISO 6603-1:1985 and the impact strength determined.

The impactor shall hit the face out surface of the lowest area of the valley, in the centre.

11.3.5 Expression of results

Using the procedures given in ISO 6603-1:1985 determine the 50 % impact failure energy for the unaged test pieces tested.

Using the procedures given in ISO 6603-1:1985 determine the 50 % impact failure energy for the aged test pieces tested.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

11.4 Thermal ageing

SIST EN 1013-4:2000

11.4.1 Principle

<https://standards.iteh.ai/catalog/standards/sist/2c6b60ae-3093-49eb-a2ea-07380e266119/sist-en-1013-4-2000>

Light transmission and yellowness index measurements are made on test pieces which have been subjected to dry heat in a ventilated oven at 100 °C. Changes in the values of these properties are determined by comparison with unexposed sheet.

11.4.2 Apparatus

- Air circulation oven capable of maintaining a temperature of (100 ± 2) °C.
- Apparatus for light transmission and yellowness index measurements as specified in 7.2.1 and 7.3.1 of EN 1013-1:1997.

11.4.3 Test pieces

Ten test pieces are required which shall be cut from the profiled sheet so as to yield approximately flat specimens of sufficient dimensions to enable the appropriate measurements to be made.

Five test pieces shall be retained as reference specimens and shall be stored in the dark at (23 ± 2) °C.

Test pieces which will be exposed to heat shall be supplied with a hole at one end to allow vertical suspension in the oven.

11.4.4 Test procedure

Suspend the test pieces in the oven so that they neither touch each other nor the walls of the oven.

Maintain the oven temperature (100 ± 2) °C for $(3\ 000 \begin{smallmatrix} +50 \\ 0 \end{smallmatrix})$ h.

When the specified period has been completed remove the test pieces from the oven and allow to cool. Cooling of the test pieces can be carried out between polished stainless steel plates, under a load, in order to preserve flatness.

If storage of test pieces is necessary, eg. if light transmission measuring equipment is not readily available, then this should be done in a similar manner to that for reference test pieces (see 11.4.3.)

Make light transmission and yellowness index measurements on all the test pieces in accordance with 7.2.3, and 7.3.3 of EN 1013-1:1997 respectively.

Determine changes in property levels for light transmission and yellowness index in accordance with 7.2.4 and 7.3.4 of EN 1013-1:1997 respectively.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[SIST EN 1013-4:2000](https://standards.iteh.ai/catalog/standards/sist/2c6b60ae-3093-49eb-a2ea-07380e266119/sist-en-1013-4-2000)

<https://standards.iteh.ai/catalog/standards/sist/2c6b60ae-3093-49eb-a2ea-07380e266119/sist-en-1013-4-2000>