
**Rubber hoses and hose assemblies for
water suction and discharge —
Specification**

*Tuyaux et flexibles en caoutchouc pour aspiration et refoulement
d'eau — Spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4641:2005](https://standards.iteh.ai/catalog/standards/sist/62819cd8-29c5-46fb-8634-82be426bfa56/iso-4641-2005)

<https://standards.iteh.ai/catalog/standards/sist/62819cd8-29c5-46fb-8634-82be426bfa56/iso-4641-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4641:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/62819cd8-29c5-46fb-8634-82be426bfa56/iso-4641-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Classification.....	2
5 Couplings and end fittings	2
6 Materials and construction	2
6.1 Lining	2
6.2 Reinforcement.....	2
6.3 Cover	3
7 Dimensions and tolerances	3
7.1 Bore	3
7.2 Enlarged ends	3
7.3 Unit lengths	3
7.4 Lining	3
7.5 Cover	3
8 Physical properties.....	3
8.1 Rubber compounds	3
8.2 Hoses and hose assemblies.....	4
9 Frequency of testing.....	6
10 Marking	6
11 Test report	7
12 Packaging and storage.....	7
Annex A (normative) Type approval and routine tests	8
Annex B (informative) Production acceptance tests	9
Annex C (informative) Couplings and end fittings.....	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4641 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This third edition cancels and replaces the second edition (ISO 4641:1991), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4641:2005
<https://standards.iteh.ai/catalog/standards/sist/62819cd8-29c5-46fb-8634-82be426bfa56/iso-4641-2005>

Rubber hoses and hose assemblies for water suction and discharge — Specification

1 Scope

This International Standard specifies the minimum requirements for textile-reinforced, smooth-bore rubber water-suction and discharge hoses and hose assemblies.

Three types of hoses and hose assemblies are specified according to their operating duty requirements, i.e. their ambient and water temperature ranges:

- ambient temperatures: -25 °C to $+70\text{ °C}$;
- water temperatures during operation: 0 °C to $+70\text{ °C}$.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1307:1992, *Rubber and plastics hoses for general-purpose industrial applications — Bore diameters and tolerances, and tolerances on length*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1746, *Rubber or plastics hoses and tubing — Bending tests*

ISO 2393, *Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of dimensions*

ISO 4672:1997, *Rubber and plastics hoses — Sub-ambient temperature flexibility tests*

ISO 7233:1991, *Rubber and plastics hoses and hose assemblies — Determination of suction resistance*

ISO 7326:1991, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8033, *Rubber and plastics hose — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 8331, *Rubber and plastics hoses and hose assemblies — Guide to selection, storage, use and maintenance*

ISO/TR 17784, *Rubber and plastics hoses and hose assemblies — Guide for use by purchasers, assemblers, installers and operating personnel*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

4 Classification

Hoses for this application are classified into three types according to their operating duty requirements:

- Type 1: Light-duty hoses for suction service to $-0,63$ bar (-63 kPa) and for discharge pressures up to 3 bar (0,3 MPa).
- Type 2: Medium-duty hoses for suction service to $-0,8$ bar (-80 kPa) and for discharge pressures up to 5 bar (0,5 MPa).
- Type 3: Heavy-duty hoses for suction service to $-0,97$ bar (-97 kPa) and for discharge pressures up to 10 bar (1,0 MPa).

Table 1 — Hose/hose assembly types
 iteh STANDARD PREVIEW
 (standards.iteh.ai)

Duty	Service range	Temperature range
Light	Suction to $-0,63$ bar	Ambient: -25 °C to $+70$ °C
	Discharge to max. 3 bar	Transferred water: 0 °C to $+70$ °C
Medium	Suction to $-0,8$ bar	Ambient: -25 °C to $+70$ °C
	Discharge to max. 5 bar	Transferred water: 0 °C to $+70$ °C
Heavy	Suction to $-0,97$ bar	Ambient: -25 °C to $+70$ °C
	Discharge to max. 10 bar	Transferred water: 0 °C to $+70$ °C

5 Couplings and end fittings

Hoses may be fitted with coupling types to form hose assemblies, as given in Annex C.

6 Materials and construction

6.1 Lining

The lining shall consist of suitably compounded water-resistant natural or synthetic rubber. Its internal surface shall be smooth and free from imperfections which could impair the expected use.

6.2 Reinforcement

The reinforcement shall consist of a suitable textile material and may contain a helix that can be metallic wire or of another suitable material.

6.3 Cover

The cover shall consist of suitably compounded natural or synthetic rubber. Its external surface may be corrugated or fluted. An external helix is optional and can be either metallic wire or of another suitable material.

7 Dimensions and tolerances

7.1 Bore (internal diameter)

The bore size range is 16 mm to 315 mm with bore diameters and tolerances in accordance with the requirements of ISO 1307:1992, Table 1.

7.2 Enlarged ends

Where enlarged ends are required, the dimensions and tolerances shall be specified by agreement between the purchaser and the manufacturer. The design of the enlarged end shall take into account the hose performance requirements.

7.3 Unit lengths

The unit lengths shall be determined according to the conditions of use. The tolerances, unless otherwise agreed between the purchaser and the manufacturer, shall be those specified in ISO 1307:1992, Table 2.

7.4 Lining

When measured in accordance with ISO 4671, the minimum thickness of the lining shall be 1,5 mm. See Table 5.

7.5 Cover

When measured in accordance with ISO 4671, the minimum thickness of the cover shall be 2 mm. If the cover is fluted, the depth of the flutes shall be not greater than 50 % of the cover thickness. See Table 5.

8 Physical properties

8.1 Rubber compounds

8.1.1 General

Wherever possible, all tests shall be carried out on test pieces cut from the finished hose. Otherwise, take samples from test sheets prepared in accordance with ISO 2393 and vulcanized to the same degree as the hose.

The physical properties of the rubber compounds used for the lining and cover shall conform to the values given in Table 2.

8.1.2 Tensile strength and elongation at break of rubber lining and cover

When tested in accordance with ISO 37, the lining and cover shall have a tensile strength and elongation at break of not less than the values given in Table 2.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4641:2005](https://standards.iteh.ai/catalog/standards/sist/62819cd8-29c5-46fb-8634-82be426bfa56/iso-4641-2005)

<https://standards.iteh.ai/catalog/standards/sist/62819cd8-29c5-46fb-8634-82be426bfa56/iso-4641-2005>

8.1.3 Resistance to ageing

After ageing as specified in ISO 188 for 3 days at a temperature of 100 °C ± 1 °C, the tensile strength and elongation at break of the lining and cover, as determined by ISO 37, shall not vary by more than ± 25 % and ± 50 %, respectively, from the initial values.

Table 2 — Physical properties of rubber compounds

Property	Unit	Requirements		Method of test
		Lining	Cover	
Tensile strength, min.	MPa	7	7	ISO 37 (dumb-bell test piece)
Elongation at break, min.	%	200	200	ISO 37 (dumb-bell test piece)
Resistance to ageing:				ISO 188 (3 days at 100 °C ± 1 °C); ISO 37 (dumb-bell test piece)
Change in tensile strength from original value (max.)	%	± 25	± 25	
Change in elongation at break from original value (max.)	%	± 50	± 50	

8.2 Hoses and hose assemblies

ITCA STANDARD PREVIEW
(standards.itech.ai)

8.2.1 Hydrostatic-pressure requirements (proof pressure test)

The proof pressure test shall be carried out on full lengths of finished hose and on hose assemblies. When tested in accordance with ISO 1402, the hose (and the hose assembly) shall meet the requirements of Table 3. The maximum variation in length and outside diameter at maximum working pressure shall be ± 7 %, and the hose/hose assembly shall not burst or fail by showing signs of leakage, cracking, abrupt distortion indicating irregularities in material or manufacture, or other signs of failure. See Table 5.

Table 3 — Hydrostatic-pressure requirements

Hose type	Maximum working pressure bar	Proof pressure bar	Minimum burst pressure bar
1	3	5	10
2	5	8	16
3	10	15	30

8.2.2 Burst test

When tested by the method specified in ISO 1402, hoses shall meet the requirements of Table 3.

8.2.3 Resistance to bending (minimum bend radius as a function of nominal bore)

When subjected to the minimum bend radii given in Table 4, in accordance with one of the methods specified in ISO 1746 (the method chosen to be the most appropriate one for the size of hose), hoses shall show no kinking, breaking or peeling under visual examination. The value of *T/D* shall not be lower than 0,95.

Table 4 — Minimum bend radii

Nominal bore	Minimum bend radius mm
16	50
20	60
25	75
31,5	95
40	120
50	150
63	250
80	320
100	500
125	750
150	960
160	
200	1 200
250	1 500
315	1 900

iTeh STANDARD PREVIEW
(standards.iteh.ai)

8.2.4 Resistance to suction flattening [ISO 4641:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/62819cd8-29c5-46fb-8634->

The test shall be carried out in accordance with [ISO 7233](#). The test conditions shall be as follows:

–0,63 bar (–63 kPa) for type 1;

–0,80 bar (–80 kPa) for type 2;

–0,97 bar (–97 kPa) for type 3.

Duration of test: 10 min.

For hoses of nominal internal diameter greater than 80 mm (ISO 7233:1991, method B), the measured collapse shall not exceed 5 % of the nominal internal diameter.

8.2.5 Low-temperature flexibility

When tested at –25 °C by method B of ISO 4672:1997, all types of hose shall show no cracks and shall pass the proof pressure test as specified in 8.2.1.

8.2.6 Adhesion

When determined in accordance with ISO 8033, the adhesion between the various components (except the helix, when included in the construction of the hose wall) shall be not less than 2 N/mm. See Table 5.

8.2.7 Ozone resistance of the cover

When tested in accordance with method 2 of ISO 7326:1991, all types of hose shall show no cracks. See Table 5.