

Designation: B 240 – 04^{€1}

Standard Specification for Zinc and Zinc-Aluminum (ZA) Alloys in Ingot Form for Foundry and Die Castings¹

This standard is issued under the fixed designation B 240; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

 ϵ^1 Note—Footnote A in paragraph 1.1 was corrected editorially in April 2005.

1. Scope*

1.1 This specification covers commercial zinc and zincaluminum (ZA) alloys in ingot form for remelting for the manufacture of pressure die castings, foundry castings and continuous cast bar stock as designated and specified in Table 1. Seven alloy compositions are specified, designated as follows:

UNS ^A	ASTM ^A	Common	Traditional
Z33521 Z35522 Z35530 Z35540 Z35635 Z35630 Z35840	AG 40A AG 40B AC 41A AC 43A	Alloy 3 Alloy 7 Alloy 5 Alloy 2	Zamak 3 Zamak 7 Zamak 5 Zamak 2 ZA-8 ZA-12 ZA-27
2000.0			

^ASee Table 1, footnote B.

1.2 Zinc alloys Z33521, Z33522, Z35530, and Z35540 are used primarily for remelting in the manufacture of pressure die castings. Zinc-aluminum alloys Z35635, Z35630, and Z35840 are used for remelting in the manufacture of both foundry and pressure die castings. Castings made from these ingots are specified in Specification B 86, Standard Specification for Zinc and Zinc-Aluminum Alloys for Foundry and Die Castings.

1.3 The values stated in inch-pound units are to be regarded as standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 The following documents of the issue in effect on data of order acceptance form a part of this specification to the extent referenced herein:

2.2 ASTM Standards: ²

- **B** 86 Specification for Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings
- B 275 Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought
- **B** 899 Terminology Relating to Non-ferrous Metals and Alloys
- B 908 Practice for the Use of Color Codes for Zinc Casting Alloy Ingot
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E 47 Test Methods for Chemical Analysis of Zinc Die-Casting Alloys³
- **E 88** Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition
- E 527 Practice for Numbering Metals and Alloys (UNS)
- E 536 Test Methods for Chemical Analysis of Zinc and Zinc Alloys
- E 634 Practice for Sampling of Zinc and Zinc Alloys for Optical Emission Spectrometric Analysis
- 2.3 Other ASTM Document:

Methods for Emission Spectrochemical Analysis⁴

3. Terminology

3.1 Terms shall be defined in accordance with Terminology **B 899**.

3.2 Definitions of Terms Specific to This Standard:

¹This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.04 on Zinc and Cadmium.

Current edition approved Oct. 1, 2004. Published October 2004. Originally approved in 1949. Last previous edition approved in 2003 as B 240 - 03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.

⁴ Methods for Emission Spectrochemical Analysis: General Practices, Nomenclature, Standard Methods, Proposed Methods, Suggested Methods, ASTM International, 1982.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.