
Road vehicles — Elastomeric cups and seals for cylinders for hydraulic braking systems using a non-petroleum base hydraulic brake fluid (Service temperature 120 °C max.)

iTeh STANDARD PREVIEW
Véhicules routiers — Coupelles et joints en caoutchouc pour cylindres de dispositifs de freinage hydrauliques utilisant un liquide de frein à base non pétrolière (Température maximale d'utilisation 120 °C)

[ISO 4928:2006](#)

<https://standards.iteh.ai/catalog/standards/sist/ad6667a9-a86a-44b8-a3bb-aaac3d81f5f8/iso-4928-2006>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4928:2006](https://standards.iteh.ai/catalog/standards/sist/ad6667a9-a86a-44b8-a3bb-aaac3d81f5f8/iso-4928-2006)

<https://standards.iteh.ai/catalog/standards/sist/ad6667a9-a86a-44b8-a3bb-aaac3d81f5f8/iso-4928-2006>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

| | |
|---|----------|
| Foreword..... | iv |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions..... | 1 |
| 4 General requirements..... | 2 |
| 4.1 Workmanship and finish | 2 |
| 4.2 Marking | 2 |
| 4.3 Packaging | 2 |
| 4.4 Sampling..... | 2 |
| 5 Test requirements..... | 2 |
| 5.1 Resistance to fluid at elevated temperature | 2 |
| 5.2 Precipitation | 2 |
| 5.3 Wheel cylinder seals heat pressure stroking | 2 |
| 5.4 Master cylinder seals heat pressure stroking | 3 |
| 5.5 Low-temperature performance | 4 |
| 5.6 Oven ageing | 4 |
| 5.7 Corrosion..... | 4 |
| 5.8 Storage corrosion test..... | 5 |
| 6 Test procedures | 5 |
| 6.1 Resistance to fluid at elevated temperature — Dimensional test..... | 5 |
| 6.2 Precipitation test..... | 7 |
| 6.3 Wheel cylinder seals heat pressure stroking | 8 |
| 6.4 Master cylinder seals heat pressure stroking | 9 |
| 6.5 Low-temperature performance | 11 |
| 6.6 Oven ageing | 12 |
| 6.7 Hardness determination..... | 12 |
| 6.8 Corrosion test | 13 |
| 6.9 Storage corrosion test..... | 14 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 40421 was prepared by Technical Committee ISO/TC 22, *Road vehicles*, Subcommittee SC 2, *Braking and systems equipment*.

This third edition cancels and replaces the second edition (ISO 4928:1980), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4928:2006
<https://standards.iteh.ai/catalog/standards/sist/ad6667a9-a86a-44b8-a3bb-aaac3d81f5f8/iso-4928-2006>

Road vehicles — Elastomeric cups and seals for cylinders for hydraulic braking systems using a non-petroleum base hydraulic brake fluid (Service temperature 120 °C max.)

1 Scope

This International Standard specifies performance tests of brake cups and seals for hydraulic braking systems for road vehicles; it does not include requirements relating to chemical composition, tensile strength and elongation of the rubber compound. Disc brake seals are not covered by this International Standard.

This International Standard is applicable to moulded seals (cups or double-lipped type gland seals), 60 mm in diameter and smaller, compounded from high temperature-resistant rubber, for use in hydraulic actuating cylinders using road vehicle non-petroleum base hydraulic brake fluid conforming to the requirements of ISO 4925.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 188:1998, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1250, *Mineral solvents for paints — White spirits and related hydrocarbon solvents*

ISO 4925, *Road vehicles — Specification of non-petroleum-base brake fluids for hydraulic systems*

ISO 4926, *Road vehicles — Hydraulic braking systems — Non-petroleum base reference fluids*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

sloughing

release of carbon black on the surface of the rubber

3.2

scoring

formation of grooves in the rubber parallel to the direction of travel of the piston or seal

3.3

scuffing

visible erosion of the outer surface of the rubber

4 General requirements

4.1 Workmanship and finish

Seals shall be free from blisters, pin-holes, cracks, protuberances, embedded foreign material or other physical defects which can be detected by thorough inspection, and shall conform to the dimensions specified on the drawings.

4.2 Marking

The identification mark of the manufacturer and other details as specified on drawings shall be moulded into each seal. Each seal in conformity with this International Standard may also have the following mark: "ISO 4928".

4.3 Packaging

Seals shall be packaged to meet requirements specified by the purchaser.

4.4 Sampling

The minimum lot on which complete specification tests shall be conducted for quality control testing, or the frequency of any specific type test used to control production, shall be agreed upon by the manufacturer and the purchaser.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5 Test requirements

5.1 Resistance to fluid at elevated temperature

<https://standards.iteh.ai/catalog/standards/sist/ad6667a9-a86a-44b8-a3bb-ade300a01102/iso-4928-2006>

After being subjected to the test for resistance to compatibility fluid at elevated temperature as prescribed in 6.1, the seals shall conform to the requirements specified in Table 1, and shall show no excessive disintegration as evidenced by blisters or sloughing.

Table 1 — Requirements for fluid resistance at elevated temperature (120 °C)

| Characteristics | Permitted change |
|------------------------|--------------------------|
| Volume | From 0,0 % to + 20,0 % |
| Outside diameter, lip | From 0,0 % to + 5,75 % |
| Outside diameter, base | From 0,0 % to + 5,75 % |
| Hardness | From – 15 IRHD to 0 IRHD |

5.2 Precipitation

Not more than 0,3 % sediment by volume shall be formed in the centrifuge tube after the seals have been tested as specified in 6.2.

5.3 Wheel cylinder seals heat pressure stroking

5.3.1 General

Wheel cylinder seals, when tested by the procedure specified in 6.3, shall meet the performance requirements specified in 5.3.2 to 5.3.6.

5.3.2 Lip diameter change

The minimum lip diameter of wheel cylinder seals after the stroking test shall be greater than the wheel cylinder bore by the minimum dimensions specified in Table 2.

Table 2 — Lip diameter change of wheel cylinder seals

Dimensions in millimetres

| Diameter of wheel cylinder bore | Minimum excess over bore |
|---------------------------------|--------------------------|
| ≤ 19,05 | 0,40 |
| > 19,05; ≤ 25,4 | 0,50 |
| > 25,4; ≤ 38,1 | 0,65 |
| > 38,1; ≤ 60 | 0,75 |

5.3.3 Leakage

No constant dampness past the seals or fluid discoloration of the filter paper on two or more inspections shall occur.

5.3.4 Corrosion

Pistons and cylinder bore shall not show corrosion as evidenced by pitting to an extent discernible to the naked eye, but staining or discoloration shall be permitted.

5.3.5 Change in hardness

Rubber seals shall not decrease in hardness by more than 15 IRHD when tested in accordance with the procedure as specified in 6.7.

5.3.6 Condition of test seals

Wheel cylinder seals shall not show excessive deterioration such as scoring, scuffing, blistering, cracking, chipping (heel abrasion) or change in shape from original appearance.

5.4 Master cylinder seals heat pressure stroking

5.4.1 General

Master cylinder seals, when tested by the procedure specified in 6.4, shall meet the performance requirements specified in 5.4.2 to 5.4.6.

5.4.2 Lip diameter change

The minimum lip diameter of master cylinder seals after the stroking test shall be greater than the master cylinder bore by the minimum dimensions specified in Table 3.

Table 3 — Lip diameter change of master cylinder seals

Dimensions in millimetres

| Diameter of master cylinder bore | Minimum excess over bore |
|----------------------------------|--------------------------|
| ≤ 19,05 | 0,30 |
| > 19,05; ≤ 25,4 | 0,40 |
| > 25,4; ≤ 38,1 | 0,50 |
| > 38,1; ≤ 60 | 0,65 |

5.4.3 Leakage

The same requirement as specified for wheel cylinder seals shall be applied (see 5.3.3).

5.4.4 Corrosion

The same requirement as specified for wheel cylinder seals shall be applied (see 5.3.4).

5.4.5 Change in hardness

The same requirement as specified for wheel cylinder seals shall be applied (see 5.3.5).

5.4.6 Condition of test seals

The same requirement as specified for wheel cylinder seals shall be applied (see 5.3.6).

5.5 Low-temperature performance

5.5.1 Leakage

No leakage of fluid shall occur when seals are tested according to the procedure specified in 6.5.1.

5.5.2 Bend test

The seal shall not crack and shall return to approximately its original shape within 1 min when tested according to the procedure specified in 6.5.2.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.6 Oven ageing

ISO 4928:2006

<https://standards.iteh.ai/catalog/standards/sist/ad6667a9-a86a-44b8-a3bb-aaac3d81f5f8/iso-4928-2006>

5.6.1 General

Seals, when tested according to the procedure specified in 6.6, shall meet the requirements specified in 5.6.2 and 5.6.3.

5.6.2 Change in hardness

The change in hardness shall be within the limits of ± 5 IRHD.

5.6.3 Condition of test seals

The seal shall show no evidence of deterioration, or change in shape from original appearance.

5.7 Corrosion

5.7.1 General

Seals, when tested according to the procedure specified in 6.8, shall meet the requirements specified in 5.7.2 and 5.7.3.

5.7.2 Corrosion of metal strips

The seals shall not cause corrosion exceeding the limits shown in Table 4. The metal strips outside of the area where the strips are in contact shall be neither pitted nor roughened to the extent discernible to the naked eye, but staining or discoloration is permitted.

Table 4 — Permissible change in mass of corrosion test strips

| Test strips | Permissible change in mass mg/cm ² of surface |
|-------------|---|
| Tinned iron | ± 0,2 |
| Steel | ± 0,2 |
| Aluminium | ± 0,1 |
| Cast iron | ± 0,2 |
| Brass | ± 0,4 |
| Copper | ± 0,4 |
| Zinc | ± 0,4 |

5.7.3 Fluid-water mixture characteristics

The fluid-water mixture at the end of the test shall show no jelling at 23 °C ± 5 °C. No crystalline type deposits shall form and adhere to either the glass wall or the surface of metal strips. The fluid-water mixture shall contain no more than 0,2 % sediment by volume.

5.8 Storage corrosion test

After twelve cycles in the humidity cabinet when operated according to the procedure specified 6.9, there shall be no evidence of corrosion adhering to or penetrating the wall of the cylinder bore that was in contact with the test seal.

Slight discoloration (staining) or any corrosion or spots away from the contact surface of the test seals may be permissible.

6 Test procedures

6.1 Resistance to fluid at elevated temperature — Dimensional test

6.1.1 Apparatus and material

- 6.1.1.1 **Micrometer, shadowgraph or other suitable apparatus**, to measure accurately to 0,02 mm.
- 6.1.1.2 **Glass container**, of capacity approximately 250 ml and diameter 50 mm, which can be tightly sealed.
- 6.1.1.3 **Chemical balance**, capable of weighing to 1 mg.
- 6.1.1.4 **Oven**, uniformly heated dry air type, conforming to the requirements for Method B of ISO 188:1998.
- 6.1.1.5 **Two glass-stoppered weighing bottles**, of adequate mouth size to hold the seals under test.
- 6.1.1.6 **Isopropyl or ethyl alcohol**, of 95 % (by volume) reagent grade for washing purpose.

6.1.2 Test specimens

Two seals shall be used for testing at 120 °C.

6.1.3 Procedure

Rinse the cups in the alcohol (6.1.1.6) and wipe dry with a clean, lint-free cloth to remove dirt and packing debris. Do not leave the seals in the alcohol for more than 30 s.

Measure the lip and base diameters to the nearest 0,02 mm, taking the average of two readings at right angles to one another. Take care when measuring the diameters before and after ageing that the measurements are made in the same manner and at the same locations.

Determine and record the initial hardness of the test seals. (See 6.7 and Figure 3.)

Determine the volume of each seal in the following manner: weigh the seals in air (m_1) to the nearest 0,001 g and then weigh the seals immersed in distilled water at room temperature (m_2). Quickly dip each specimen in alcohol and then blot dry with filter paper free of lint and foreign material.

Immerse two seals completely in 75 ml ± 1 ml of compatibility reference fluid as defined in ISO 4926, in the glass container (6.1.1.2) and seal the container to prevent vapour loss. Place the container in the oven (6.1.1.4) set at 120 °C ± 2 °C for a period of 70 h ± 2 h. At the end of the heating period, remove the container from the oven and allow the seals to cool in the container at 23 °C ± 5 °C for 60 min to 90 min. At the end of the cooling period, remove the seals from the container and rinse in the alcohol and wipe dry with a clean, lint-free cloth. Do not allow the seals to remain in the alcohol for more than 30 s.

After removal from the alcohol and drying, place each seal in a separate, tarred, stoppered weighing bottle (6.1.1.5) and weigh (m_3). Remove each seal from its weighing bottle and weigh immersed in distilled water (m_4) to determine water displacement after hot fluid immersion. Make all weighings to the nearest 0,001 g.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Determine the final volume, dimensions and hardness of each seal within 60 min of rinsing in the alcohol.

6.1.4 Expression of results

[ISO 4928:2006](#)

6.1.4.1 Volume change <https://standards.iteh.ai/catalog/standards/sist/ad6667a9-a86a-44b8-a3bb-aaac3d81f5f8/iso-4928-2006>

Volume change ΔV shall be reported as a percentage of the original volume. The change in volume is given by the equation:

$$\Delta V = \frac{(m_3 - m_4) - (m_1 - m_2)}{(m_1 - m_2)} \times 100$$

where

m_1 is the initial mass in air, in grams;

m_2 is the initial apparent mass in water, in grams;

m_3 is the mass in air after immersion in test fluid, in grams;

m_4 is the apparent mass in water after immersion test fluid, in grams.

6.1.4.2 Dimensional changes

The original measurements of the lip and base diameters shall be subtracted from measurements taken after the test and the difference reported in millimetres and as percentages of the original diameters.

6.1.4.3 Hardness

Change in hardness shall be determined and recorded.

6.1.4.4 Disintegration

The seals shall be examined for disintegration as evidenced by blisters or sloughing.

6.2 Precipitation test

6.2.1 Apparatus

6.2.1.1 Glass containers, of capacity approximately 250 ml and diameter 50 mm, which can be tightly sealed.

6.2.1.2 Cone-shaped centrifuge tube, of capacity 100 ml.

6.2.1.3 Oven, uniformly heated dry air type, conforming to the requirements for Method B of ISO 188:1998.

6.2.2 Test specimen

From two or more seals to be tested, obtain a sample of mass $4,0 \text{ g} \pm 0,5 \text{ g}$. Since sizes of seals vary, small pieces may be cut from the seal to reach the specified mass. Use the minimum number of pieces to obtain a mass of $4,0 \text{ g} \pm 0,5 \text{ g}$.

6.2.3 Procedure

To determine the precipitation compatibility characteristics of the test seals, place the sample (6.2.2) in one of the specified glass containers (6.2.1.1) containing 75 ml of compatibility fluid of ISO 4926. Seal the container to prevent vapour loss and place in the oven (6.2.1.3) at $120 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$ for $70 \text{ h} \pm 2 \text{ h}$.

As an optional test, a blank test may be run on the brake fluid prior to the real test and any sediment from the blank test may be subtracted from the sediment amount obtained from the real test.

At the end of the heating period, remove the container from the oven and allow to cool at room temperature for 24 h, after which remove the seals.

Agitate thoroughly the contents of the jar and transfer the fluid and suspended particles to a cone-shaped centrifuge tube (6.2.1.2) of 100 ml capacity and determine the sediment as follows.

- a) Measure a 10 ml sample of the fluid and suspended particles to be tested, into each of two clean, dry centrifuge tubes at room temperature. Fill each tube to the 100 ml mark with the naphtha (see caution below) and close tightly with a softened cork (not a rubber stopper). Then invert each tube at least twenty times, allowing the liquid to drain thoroughly from the tapered tip of the tube each time. Place the tubes in a water bath at $32 \text{ }^\circ\text{C}$ to $35 \text{ }^\circ\text{C}$ for 5 min. Momentarily remove the corks to relieve any pressure, and invert each tube again at least twenty times, exactly as before. The success of this method depends to a large degree upon having a thoroughly homogeneous mixture that will drain quickly and completely from the tapered tip when the tube is inverted.

CAUTION — Naphtha is an inflammable liquid. Handle in a well-ventilated area, away from naked flames or other sources of ignition. The use of protective gloves and suitable eye protection is recommended.

- b) Balance the two centrifuge tubes or pairs of tubes with their respective trunnion cups and place them on opposite sides of the centrifuge head. Then whirl them for 10 min at a rate sufficient to produce a relative centrifugal force (rcf) of between 600 and 700 at the tips of the whirling tubes. Repeat this operation until the volume of sediment in each tube remains constant for three consecutive readings. In general, not more than four whirlings will be required.
- c) Read the volume of the solid sediment at the bottom of each centrifuge tube, estimating to 0,1 ml or closer if possible. If the two readings differ by not more than 0,1 ml, report the mean of the two as the