



Designation: A481 – 05

Standard Specification for Chromium Metal¹

This standard is issued under the fixed designation A481; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers several grades of chromium metal.

1.2 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

[A1025 Specification for Ferroalloys and Other Alloying Materials, General Requirements](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

[E363 Test Methods for Chemical Analysis of Chromium and Ferrochromium](#)

3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification [A1025](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A1025](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A1025](#), this specification shall prevail.

4. Chemical Composition

4.1 The various grades shall conform to the requirements as to chemical composition specified in [Tables 1 and 2](#).

4.2 The manufacturer shall furnish an analysis of each shipment showing the elements specified in [Table 1](#).

4.3 The values shown in [Table 2](#) are expected maximums. Upon request of the purchaser, the manufacturer shall furnish an analysis for any of these elements on a cumulative basis over a period mutually agreed upon between the manufacturer and the purchaser.

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.18](#) on Castings.

Current edition approved May 1, 2005. Published May 2005. Originally approved in 1963. Last previous edition approved in 2004 as A481 – 94 (2004). DOI: 10.1520/A0481-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Chemical Requirements

Element	Composition, %	
	Grade A	Grade B
Chromium, min	99.0	99.4
Carbon, max	0.050	0.050
Silicon, max	0.15	0.10
Sulfur, max	0.030	0.010
Phosphorus, max	0.010	0.010

5. Size

5.1 The various grades are available in sizes as listed in [Table 3](#).

5.2 The sizes listed in [Table 3](#) are typical as shipped from the manufacturer's plant. These alloys exhibit varying degrees of friability; therefore, some attrition may be expected in transit, storage, and handling. A quantitative test is not available for rating relative friability of ferroalloys. A code system has been developed, therefore, for this purpose, and a number rating each product type is shown in the last column of [Table 3](#). Definitions applicable to these code numbers are given in Specification [A1025](#).

TABLE 2 Supplementary Chemical Requirements

Element	Composition, %	
	Grade A	Grade B
Nitrogen, max	0.050	0.020
Iron, max	0.35	0.35
Manganese, max	0.01	0.01
Hydrogen, max	0.01	0.003
Oxygen, max	0.50	0.10
Vanadium, max	0.050	0.050
Copper, max	0.01	0.01
Molybdenum, max	0.050	0.01
Columbium, max	0.050	0.050
Tantalum, max	0.050	0.003
Cobalt, max	0.003	0.001
Aluminum, max	0.30	0.10
Titanium, max	0.050	0.003
Zirconium, max	0.050	0.003
Arsenic, max	0.005	0.003
Lead, max	0.003	0.001
Tin, max	0.001	0.001
Zinc, max	0.005	0.003
Boron, max	0.005	0.003
Antimony, max	0.005	0.003
Silver, max	0.003	0.001
Bismuth, max	0.003	0.001

*A Summary of Changes section appears at the end of this standard.